

T, °C	UO ₂ + 2NF _{3(g)} = UF _{6(g)} + O _{2(g)} + N _{2(g)}			UO ₂ + 6HF _(g) = UF _{6(g)} + 2H ₂ O _(g) + H _{2(g)}		
	ΔH	ΔS	ΔG	ΔH	ΔS	ΔG
	kJ/mol F	J/K/mol F	kJ/mol F	kJ/mol F	J/K/mol F	kJ/mol F
100	-133.0	29.7	-144.1	15.5	-39.4	30.2
200	-133.0	29.7	-147.1	15.3	-39.8	34.1
300	-133.2	29.4	-150.1	15.2	-40.0	38.1
400	-133.4	29.0	-153.0	15.1	-40.1	42.1
500	-133.7	28.7	-155.9	15.1	-40.1	46.1
600	-134.0	28.3	-158.7	15.1	-40.0	50.1
700	-134.4	27.9	-161.5	15.2	-40.0	54.1
800	-134.7	27.6	-164.3	15.3	-39.9	58.1
900	-135.1	27.2	-167.0	15.4	-39.8	62.1
1000	-135.5	26.9	-169.7	15.4	-39.8	66.1