BLUE JEANS & COTTON LINTERS
Papermaking
ART 235
Spring 2025
Avery Schmeichel

Cooking Log
1 ¼ lbs of blue jeans (cut into 1 inch x 1 inch squares)
125 grams of soda ash
10 liters of water
5lb cooking pot
Total cooking time for blue jean squares: 37 ½ hours
3/11/2025- Drained and rinsed blue jeans

Hollander
Processed blue jean fiber
1lb cotton linter
3/11/2025
10:20 am - add blue jeans to the hollander and started beating
10:55 am- ½ turn down
11:20 am- ½ turn down
12:07 pm -stopped hollander and drained the pulp
3/13/2025
10:05 am- started hollander again with blue jeans
10:20 am- ½ turn down
10:25 am- ½ turn down
10:30 am- stopped hollander and drained and strained pulp from hollander and stored in plastic bags in the fridge
3/25/2025
10:15 am- started hollander with blue jeans
added 1 lb of pre soaked cotton linters
10:35 am- ½ turn down
10:40 am- ½ turn down
10:45 am- 1 whole turn down
10: 50 am- ½ turn down
10:57am- all fiber was broken down, stopped the hollander and drained the pulp
Mixed 2 scoops of formation aid and enough pulp into a tub of water
Started making paper.
3/27/25
Optional: added 5 tablespoons of mica to each tub for sparkles