



Issued to: QR Code Number: 100000843376	Report No.: ITLBIS20251205004 Letter Ref. No.: Nil & Dated: 04/12/2025 Date of Receipt: 05/12/2025 Period of Testing: 06/12/2025-24/12/2025 Date of Report: 24/12/2025
--	---

Particulars of Sample Submitted

- | | | |
|---|---|---|
| 1. Sample Code | : | GZBO/72541/20251204/SM/1 |
| 2. Reference Standard/ Specification | : | IS 733: 1983 up to Amd. No. 2 |
| 3. Sample Description | : | Wrought Aluminum and Aluminium Alloy
T- Section, Temper Condition- T6,
Designation: 63400, Thickness- 2 mm,
Width- 25 mm |
| 4. Sample Quantity | : | 2 pcs × 1 m + 5 pcs of 5 × 5 sq.cm |
| 5. Date of Manufacturing | : | 15/11/2025 |
| 6. Batch No. | : | 1002 |
| 7. Grade/Type/Variety/Size/Class/Rating | : | Temper Condition- T6, Designation: 63400 |
| 8. Declared value, if any | : | Thickness- 2 mm, Width- 25 mm |
| 9. Report No. | : | ITLBIS20251205004 |
| 10. Date of Start of analysis | : | 06/12/2025 |
| 11. Date of Completion of analysis | : | 24/12/2025 |
| 12. Nature of Packing | : | Wrapped in Shrinked |
| 13. Manner of Sealing | : | Waxed Sealed & Signed |
| 14. Additional Information, if any | : | - |



LR-1404
Page 2 of 3

Issued to: QR Code Number: 100000843376	Report No.: ITLBIS20251205004 Letter Ref. No.: Nil & Dated: 04/12/2025 Date of Receipt: 05/12/2025 Period of Testing: 06/12/2025-24/12/2025 Date of Report: 24/12/2025
--	---

S. No.	Tests	Clause No.	Test Methods	Results	Requirements IS 733: 1983 up to Amd. No. 2 Designation – 63400 Condition – T6
1.	Mechanical Testing				
A.	Dimensions, mm	Clause 7.1			
1.	Width, (A) mm		IS 3965: 1981	24.98	25 ± 0.30
2.	Width, (B) mm		IS 3965: 1981	24.79	25 ± 0.30
3.	Thickness, (A) mm		IS 3965: 1981	2.18	2.0 ± 0.20
4.	Tolerance for Straightness and Twist Test		IS 3965: 1981	0.84	2.1 (mm/m length)
5.	Angular tolerance		IS 3965: 1981	0.090°	$\pm 2^\circ$
6.	Concavity and Convexity				
(i)	Width, mm		IS 3965: 1981	0.027	± 0.18
B	Freedom from Defects	Clause 4.1	IS 733: 1983	Satisfactory	It shall be sound and free from harmful defects.
C	0.2 Percent Proof Stress, MPa	Clause 5.1	IS 1608(P-1): 2022	179.1	150 Min.
D	Tensile Strength, MPa		IS 1608(P-1): 2022	196.0	185 Min.
E	Elongation Percent on 50 mm, %		IS 1608(P-1): 2022	11.6	7 Min.
F	Marking	Clause 11.	IS 733: 1983	N/A	Shall be suitably marked for identification, with the 'name of the manufacturer, alloy designation and condition of the material.



Issued to: QR Code Number: 100000843376	Report No.: ITLBIS20251205004 Letter Ref. No.: Nil & Dated: 04/12/2025 Date of Receipt: 05/12/2025 Period of Testing: 06/12/2025-24/12/2025 Date of Report: 24/12/2025
--	---

S. No.	Tests	Clause No.	Test Methods	Results	Requirements IS 733: 1983 up to Amd. No. 2 Designation – 63400 Condition – T6
2.	Chemical Testing				
a)	Copper, % by mass	Clause 5.1	ITL/SOP/CHE/01	0.052	0.1 Max
b)	Magnesium, % by mass		IS: 504 – 1963	0.67	0.4 – 0.9
c)	Silicon, % by mass		IS: 504 – 1963	0.48	0.3 – 0.7
d)	Iron, % by mass		ITL/SOP/CHE/01	0.29	0.6 Max.
e)	Manganese, % by mass		ITL/SOP/CHE/01	0.13	0.3 Max.
f)	Zinc, % by mass		ITL/SOP/CHE/01	0.10	0.2 Max.
h)	Titanium and/or other Grain Refining Elements, % by mass		ITL/SOP/CHE/01	0.12	0.2 Max.
g)	Chromium, % by mass		ITL/SOP/CHE/01	0.062	0.1 Max.
h)	Aluminium, % by mass		IS: 504 – 1963	98.10	Remainder

Remark: The Sample conforms to IS 733: 1983 up to Amd No. 2 with respect to the above tests only.

*Any deviation from the Standard Test Method/Specification is nil.

*Scan the QR Code for authenticity of this report.

---End of the Report---