

Product Specification

Quality: NR Pearl Coat

Substance g/m ²	Caliper μ	Bulk cc/gm	Bending Resistance, mN (L&W)			
			MD	CD	GM	MD/CD
T410	T 411		T556			
230	334	1.45	183	91	129	2.0
250	362	1.45	233	120	167	1.9
270	400	1.48	288	148	206	1.9
285	422	1.48	337	175	243	1.9
300	450	1.50	386	203	280	1.9
320	480	1.50	459	242	333	1.9
350	525	1.50	589	319	433	1.8
380	570	1.50	715	397	533	1.8
400	600	1.50	832	451	613	1.8
Tol : ± 3%	±5%		± 15% on GM Value			

Properties	UOM	Value	Standard
Roughness 230-300 g/m ² PPS (Avg. Top) >301 g/m ²	μ	1.5 ± 0.2 1.6 ± 0.2	T 555
Surface Strength IGT Pick (MV) Top	m/s	1.2 Min	ISO 3782
ISO Brightness (L&W Elrepho) Top	%	90 ±1	ISO 2470
CIE Whiteness Top Back	%	110 Min	ISO 11475
Moisture Content <300 >301	%	6.0-7.5 7.0-8.5	T 412
Gloss at 75° Top	%	40 Min	T 480
Scott Ply Bond	J/m ²	>140	T 569
Cobb ₆₀ Top Back	g/m ²	35 ± 5 40 ± 5	T 441

Construction



Note:

1. Test Conditions -Temperature 23±1°C & Relative Humidity 50±2%. (Tappi 402)
2. All properties are according to NRAIL Unit 5, Sarigam measurements.
3. Tolerance are based upon 95% confidence limits of single mill measurement of conditioned random samples.
4. FSC Mix,coated virgin board is supplied on demand.
5. Regulatory: REACH,FDA, Heavy metal, ROHS

NR Pearl Coat is a premium-grade virgin fiber paperboard, meticulously engineered for high-performance printing, converting, and packaging applications. Manufactured from 100% virgin bleached pulp, it features a coated top and reverse side (C2S) delivering exceptional print quality, consistent visual appeal, and reliable structural integrity. Designed to meet the demands of premium brands and modern production lines, NR Pearl Coat offers the ideal combination of aesthetics and performance across a wide range of packaging formats and graphic applications.

Being a progressive organization,NR Agarwal Industries Ltd. continually evolves in response to customer requirements.The specification mentioned are therefore subject to change.

Date: 03.10.2025

Revision: 01