



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet

Product: NR Shine SS

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	54 - 120	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.30	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	21	TAPPI T441 om-98
	Bottom	gsm	Max	22	TAPPI T441 om-98
Breaking Length		Meters	Min	5500	TAPPI T404 om-92
		Meters	Min	2500	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	TAPPI T411 om-97
	CD	-	Min	55	TAPPI T411 om-97
ISO Brightness		%	Min	90	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	180	ISO 8791-2
	Bottom	ml/min	Max	220	ISO 8791-2
Wax Pick		No.	Min	14-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet

Product: NR Shine

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	50 - 52	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.30	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4500	TAPPI T404 om-92
		Meters	Min	2000	TAPPI T404 om-92
Tear Factor	MD	-	Min	45	TAPPI T411 om-97
	CD	-	Min	50	TAPPI T411 om-97
ISO Brightness		%	Min	90	ISO 2470
Opacity		%	Min	88	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	180	ISO 8791-2
	Bottom	ml/min	Max	240	ISO 8791-2
Wax Pick		No.	Min	10-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet

Product: NR Excel SS

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	54 - 120	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.25	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	21	TAPPI T441 om-98
	Bottom	gsm	Max	22	TAPPI T441 om-98
Breaking Length		Meters	Min	5000	TAPPI T404 om-92
		Meters	Min	2300	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	TAPPI T411 om-97
	CD	-	Min	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	88	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	180	ISO 8791-2
	Bottom	ml/min	Max	240	ISO 8791-2
Wax Pick		No.	Min	14-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet

Product: NR Excel

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	50 - 52	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.30	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4000	TAPPI T404 om-92
		Meters	Min	2000	TAPPI T404 om-92
Tear Factor	MD	-	Min	45	TAPPI T411 om-97
	CD	-	Min	50	TAPPI T411 om-97
ISO Brightness		%	± 2.0	88	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	180	ISO 8791-2
	Bottom	ml/min	Max	240	ISO 8791-2
Wax Pick		No.	Min	10-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet

Product: NR Excel SS (PS)

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	54 - 120	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.25	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	21	TAPPI T441 om-98
	Bottom	gsm	Max	22	TAPPI T441 om-98
Breaking Length		Meters	Min	5000	TAPPI T404 om-92
		Meters	Min	2300	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	TAPPI T411 om-97
	CD	-	Min	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	86	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	180	ISO 8791-2
	Bottom	ml/min	Max	240	ISO 8791-2
Wax Pick		No.	Min	14-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5



Technical Specification Sheet

Product: NR Maxima SS

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	54 - 120	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.25	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4500	TAPPI T404 om-92
		Meters	Min	2200	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	TAPPI T411 om-97
	CD	-	Min	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	84	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	200	ISO 8791-2
	Bottom	ml/min	Max	260	ISO 8791-2
Wax Pick		No.	Min	14-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5



Technical Specification Sheet

Product: NR Maxima

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	50 - 52	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.30	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4000	TAPPI T404 om-92
		Meters	Min	2000	TAPPI T404 om-92
Tear Factor	MD	-	Min	45	TAPPI T411 om-97
	CD	-	Min	50	TAPPI T411 om-97
ISO Brightness		%	± 2.0	84	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	220	ISO 8791-2
	Bottom	ml/min	Max	280	ISO 8791-2
Wax Pick		No.	Min	10-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5



Technical Specification Sheet

Product: NR Classic SS

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	54 - 120	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.25	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4500	TAPPI T404 om-92
		Meters	Min	2200	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	TAPPI T411 om-97
	CD	-	Min	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	80	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	200	ISO 8791-2
	Bottom	ml/min	Max	260	ISO 8791-2
Wax Pick		No.	Min	14-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5



Technical Specification Sheet

Product: NR Classic

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	54 - 120	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.30	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4000	TAPPI T404 om-92
		Meters	Min	2000	TAPPI T404 om-92
Tear Factor	MD	-	Min	45	TAPPI T411 om-97
	CD	-	Min	50	TAPPI T411 om-97
ISO Brightness		%	± 2.0	80	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	220	ISO 8791-2
	Bottom	ml/min	Max	280	ISO 8791-2
Wax Pick		No.	Min	10-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet


Product: NR Brilliance

Properties		UOM	Tolerance	Values	Values	Values	Standards
Substance		gsm	± 2.5%	70	75	80	TAPPI T410 om-98
Bulk		cm3/gm	± 5%	1.40	1.38	1.35	-
Moisture		%	± 0.5	4.5	4.5	4.5	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	25	25	25	TAPPI T441 om-98
	Bottom	gsm	Max	26	26	26	TAPPI T441 om-98
Breaking Length		Meters	Min	5500	5500	5500	TAPPI T404 om-92
		Meters	Min	2600	2600	2600	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	50	50	TAPPI T411 om-97
	CD	-	Min	55	55	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	88	88	88	ISO 2470
Opacity		%	Min	93	93	93	ISO 2471
Smoothness (Bendtsen)	Top	m l/m in	Max	250	250	250	ISO 8791-2
	Bottom	ml/min	Max	300	300	300	ISO 8791-2
Wax Pick		No.	Min	14-A	14-A	14-A	TAPPI T459 om-93

Features:

- NR BrillianceCopier is surface sized copy paper made from high bright chemical pulp.
- No Multifeeding
- High tensile strength and surface properties
- Jam free performance
- Ideal for Hi-Speed Copying
- Perfect Finish
- Multiple Usage -Laser Printer ,Ink Jet Printer, Copier Machine & Fax Machine

Construction



Surface Sized
High Bright Chemical Pulp
Surface Sized

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples



NR AGARWAL INDUSTRIES LTD.UNIT 5



Technical Specification Sheet


Product: NR Copier

Properties		UOM	Tolerance	Values	Values	Values	Standards
Substance		gsm	± 2.5%	70	75	80	TAPPI T410 om-98
Bulk		cm3/gm	± 5%	1.40	1.37	1.32	-
Moisture		%	± 0.5	4.5	4.5	4.5	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	25	25	25	TAPPI T441 om-98
	Bottom	gsm	Max	26	26	26	TAPPI T441 om-98
Breaking Length		Meters	Min	5500	5500	5500	TAPPI T404 om-92
		Meters	Min	2500	2500	2500	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	50	50	TAPPI T411 om-97
	CD	-	Min	55	55	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	84	84	84	ISO 2470
Opacity		%	Min	93	93	93	ISO 2471
Smoothness (Bendtsen)	Top	m l/m in	Max	250	250	250	ISO 8791-2
	Bottom	ml/min	Max	300	300	300	ISO 8791-2
Wax Pick		No.	Min	14-A	14-A	14-A	TAPPI T459 om-93

Features:

- NR BrillianceCopier is surface sized copy paper made from high bright chemical pulp.
- No Multifeeding
- High tensile strength and surface properties
- Jam free performance
- Ideal for Hi-Speed Copying
- Perfect Finish
- Multiple Usage -Laser Printer ,Ink Jet Printer, Copier Machine & Fax Machine

Construction



Surface Sized
High Bright Chemical Pulp
Surface Sized

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples