



NR AGARWAL INDUSTRIES LTD.UNIT 5

Technical Specification Sheet

Product: NR Excel

Properties		UOM	Tolerance	Values	Standards
Substance		gsm	± 2.5%	50 - 52	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.30	-
Moisture		%	± 0.5	5.0	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	24	TAPPI T441 om-98
	Bottom	gsm	Max	25	TAPPI T441 om-98
Breaking Length		Meters	Min	4000	TAPPI T404 om-92
		Meters	Min	2000	TAPPI T404 om-92
Tear Factor	MD	-	Min	45	TAPPI T411 om-97
	CD	-	Min	50	TAPPI T411 om-97
ISO Brightness		%	± 2.0	88	ISO 2470
Opacity		%	Min	90	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	180	ISO 8791-2
	Bottom	ml/min	Max	240	ISO 8791-2
Wax Pick		No.	Min	10-A	TAPPI T459 om-93

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23o C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples