



NR AGARWAL INDUSTRIES LTD.UNIT 5



Technical Specification Sheet

Product: NR Copier

Properties		UOM	Tolerance	Values	Values	Values	Standards
Substance		gsm	± 2.5%	70	75	80	TAPPI T410 om-98
Bulk		cm ³ /gm	± 5%	1.40	1.37	1.32	-
Moisture		%	± 0.5	4.5	4.5	4.5	TAPPI T412 om-94
Cobb ₆₀	Top	gsm	Max	25	25	25	TAPPI T441 om-98
	Bottom	gsm	Max	26	26	26	TAPPI T441 om-98
Breaking Length		Meters	Min	5500	5500	5500	TAPPI T404 om-92
		Meters	Min	2500	2500	2500	TAPPI T404 om-92
Tear Factor	MD	-	Min	50	50	50	TAPPI T411 om-97
	CD	-	Min	55	55	55	TAPPI T411 om-97
ISO Brightness		%	± 2.0	84	84	84	ISO 2470
Opacity		%	Min	93	93	93	ISO 2471
Smoothness (Bendtsen)	Top	ml/min	Max	250	250	250	ISO 8791-2
	Bottom	ml/min	Max	300	300	300	ISO 8791-2
Wax Pick		No.	Min	14-A	14-A	14-A	TAPPI T459 om-93

Features:

- NR Copier is surface sized copy paper made from chemical pulp.
- No Multifeeding
- High tensile strength and surface properties
- Jam free performance
- Ideal for Hi-Speed Copying
- Perfect Finish
- Multiple Usage -Laser Printer ,Ink Jet Printer, Copier Machine & Fax Machine

Construction

	Surface Sized
	Chemical Pulp
	Surface Sized

Note:

- All Properties are according to NR Agarwal Industries Ltd Unit-V Sarigam, Vapi measurements.
- All Properties climate 50% RH & 23° C (as per TAPPI T 402 sp-98).
- Tolerances are based upon 2 sigma level of random samples