



## NR AGARWAL INDUSTRIES LTD.UNIT 5 (PM2)

### Product Specification

#### Quality: NR Pearl Pac

| Substance<br>g/m <sup>2</sup> | Caliper<br>μ | Bulk<br>cc/gm | Bending Resistance, mN (L&W) |     |     |       | Properties                                                                 | UOM              | Value     | Standard  |
|-------------------------------|--------------|---------------|------------------------------|-----|-----|-------|----------------------------------------------------------------------------|------------------|-----------|-----------|
|                               |              |               | MD                           | CD  | GM  | MD/CD |                                                                            |                  |           |           |
| T410                          | T 411        |               | T556                         |     |     |       |                                                                            |                  |           |           |
| 230                           | 368          | 1.60          | 208                          | 112 | 153 | 1.9   | Roughness 230-300 g/m <sup>2</sup><br>PPS (Avg. Top) >301 g/m <sup>2</sup> | μ                | 1.5 ± 0.2 | T555      |
| 250                           | 400          | 1.60          | 280                          | 146 | 202 | 1.9   |                                                                            |                  | 1.6 ± 0.2 |           |
| 270                           | 432          | 1.60          | 362                          | 185 | 259 | 2.0   | Surface Strength<br>IGT Pick (MV) Top                                      | m/s              | 1.2 Min   | ISO 3782  |
| 285                           | 456          | 1.60          | 399                          | 195 | 279 | 2.0   |                                                                            |                  |           |           |
| 300                           | 480          | 1.60          | 484                          | 237 | 339 | 2.0   | ISO Brightness (L&W Elrepho) Top                                           | %                | 90 ±1     | ISO 2470  |
| 320                           | 512          | 1.60          | 590                          | 291 | 414 | 2.0   | CIE Whiteness Top                                                          | %                | 110 Min   | ISO 11475 |
| 350                           | 560          | 1.60          | 713                          | 352 | 501 | 2.0   | Moisture Content <300<br>>301                                              | %                | 6.0-7.5   | T 412     |
| 380                           | 608          | 1.60          | 900                          | 455 | 640 | 2.0   |                                                                            |                  | 7.0-8.5   |           |
| 400                           | 640          | 1.60          | 980                          | 482 | 687 | 2.0   | Gloss at 75° Top                                                           | %                | 40 Min    | T 480     |
| Tol : ± 3%                    | ±5%          |               | ± 15% on GM Value            |     |     |       | Scott Ply Bond                                                             | J/m <sup>2</sup> | >140      | T 569     |
| Construction                  |              |               |                              |     |     |       | Cobb <sub>60</sub> Top                                                     | g/m <sup>2</sup> | 35 ± 5    | T 441     |
|                               |              |               |                              |     |     |       | Back                                                                       |                  | 40 ± 5    |           |

### Construction



#### Note:

1. Test Conditions -Temperature 23±1°C & Relative Humidity 50±2%. (Tappi 402)
2. All properties are according to NRAIL Unit 5, Sarigam measurements.
3. Tolerance are based upon 95% confidence limits of single mill measurement of conditioned random samples.
4. FSC Mix,coated virgin board is supplied on demand.
5. Regulatory: REACH,FDA, Heavy metal, ROHS

NR Pearl Pac is a premium-grade virgin fiber paperboard, expertly engineered for high-performance printing, converting, and packaging applications. Made from 100% virgin bleached pulp, it features a coated top surface and a starch-coated reverse, ensuring outstanding print quality, consistent visual appeal, and dependable structural integrity. Developed to meet the rigorous demands of premium brands and modern production lines, NR Pearl Pac delivers the perfect balance of aesthetics and performance,making it ideal for a wide range of packaging formats and graphic applications.

Being a progressive organization,NR Agarwal Industries Ltd. continually evolves in response to customer requirements.The specification mentioned are therefore subject to change.

Date: 03.10.2025

Revision: 01