CL-206028

Matt WhitePET Film Label

EXTREME CHEMICAL-RESISTANT LABELLING

Matt white PET film with a chemically resistant thermal-transfer topcoat and a permanent solvent acrylic adhesive. Designed for automotive and industrial identification where aggressive chemical exposure is expected.

TECHNICAL SPECIFICATIONS

Product Code	CL-206028
Facestock	Matt white topcoated polyester (PET) film
Facestock Basis Weight	79 g/m² (ISO 536)
Facestock Caliper	56 µm (ISO 534)
Adhesive	High-strength permanent solvent acrylic adhesive
Adhesive Coat Weight	32 g/m² (FTM 12)
Release Liner	White supercalendered glassine release paper
Liner Basis Weight	63 g/m² (ISO 536)
Liner Caliper	56 µm (ISO 534)
Total Caliper	144 µm ±10%, including liner (ISO 534)
Initial Tack	25 N/25 mm; FTM 9, glass
90° Peel Adhesion	14 N/25 mm; FTM 2, stainless steel
Min. Application Temperature	+7 °C (+44.6 °F)
Service Temperature	-40 °C to +150 °C (-40 °F to +302 °F)
Shelf Life	1 year; see storage conditions below

MATERIAL CONSTRUCTION

56 µm matt white PET film

32 g/m² solvent acrylic adhesive

56 µm glassine release liner

Schematic only; layers are not to scale.

APPLICATIONS

- Automotive component identification
- Industrial equipment and durable goods
- Difficult plastics and coated surfaces
- Labels exposed to aggressive chemicals

PRINTING & CONVERTING

Thermal transfer printing with Ricoh B110CU, the ribbon used in the reported chemical-resistance tests. Other ribbons require validation. Flexographic, UV letterpress and screen printing require application-specific testing.

APPLICATION & STORAGE NOTES

Chemical performance depends on the label, ribbon and exposure conditions. Source rub tests showed fading with gasoline and MEK; no universal chemical-resistance claim is implied.

Validate adhesion and print durability in actual use. Avoid sharp die-cut corners. Store in protective packaging under the conditions below.

Shelf Life: To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25 °C; 40-50% RH). Prolonged storage outside these conditions may reduce the shelf life.

Warranty: © 2023, codeLINE

codeLINE products are sold on the understanding that the Buyer will test them under actual conditions of use and determine their suitability for the intended application.

codeLINE warrants to the Buyer that its products are free from defects in materials and workmanship. codeLINE's obligations under this warranty are limited to replacing products demonstrated to the satisfaction of codeLINE to have been defective, provided that the Buyer has complied with the handling, storage and shelf life requirements specified in the applicable codeLINE material specifications.

The above warranties extend solely to the Buyer, and all warranty claims must be made by the Buyer. Rework or replacement shall not alter the original warranty period. In all cases, the warranty period shall not exceed thirty (30) days from the date of the original shipment.

THE ABOVE WARRANTIES ARE EXCLUSIVE OF AND IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE. NO IMPLIED STATUTORY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. codeLINE SHALL NOT BE LIABLE, EITHER IN TORT OR IN CONTRACT, FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR INABILITY TO USE THE PRODUCT, OR FROM DELAY IN THE REPLACEMENT OR REPAIR OF PRODUCTS UNDER THE ABOVE WARRANTY.