CL-206051

White PET Film Label

HIGH-TACK ADHESIVE

Gloss white, topcoated PET label material with a high-tack adhesive for rough and low-surface-energy substrates. Suitable for barcode, serial-number and durable product identification using compatible resin ribbons.

TECHNICAL SPECIFICATIONS

Product Code	206051
Facestock	Topcoated gloss white polyester (PET) film
Facestock Basis Weight	76 g/m² (ISO 536)
Facestock Caliper	50 µm (ISO 534)
Adhesive	Rubber-hybridised acrylic adhesive
Adhesive Coat Weight	45 g/m² (FTM 12)
Release Liner	White glassine paper, siliconised on both sides
Liner Basis Weight	64 g/m² (ISO 536)
Liner Caliper	55 µm (ISO 534)
Total Caliper	150 µm ±10%, including liner (ISO 534)
Initial Tack	25 N/25 mm; FTM 9, glass
90° Peel Adhesion	25 N/25 mm; FTM 2, stainless steel, 24 h dwell
Min. Application Temperature	+5 °C (+41 °F)
Service Temperature	-40 °C to +150 °C (-40 °F to +302 °F)
Shelf Life	1 years from manufacture at 20-25 °C and 40-50% RH

MATERIAL CONSTRUCTION

50 µm gloss white PET film

45 g/m² high-tack adhesive

55 µm glassine release liner

Schematic only; layers are not to scale.

APPLICATIONS

- Low-surface-energy plastic components
- Rough, textured and painted surfaces
- Automotive, electronics and appliances
- Durable identification and warning labels

PRINTING & CONVERTING

Thermal transfer printing with compatible resin ribbons on flat-head or near-edge printers. Also suitable for flexographic, UV letterpress and screen printing. Compatibility with selected UV inkjet systems must be verified.

APPLICATION & STORAGE NOTES

Allow at least 24 hours after application before assessing adhesion. Verify chemical resistance and print durability with the intended substrate and ribbon.

The high adhesive coat weight requires care during die-cutting and winding to control adhesive ooze. Store rolls in their protective packaging and rewrap immediately after partial use.

Shelf Life: To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20–25 °C; 40–50% RH). Prolonged storage outside these conditions may reduce the shelf life.

Warranty: © 2023, codeLINE
codeLINE products are sold on the understanding that the Buyer will test them under actual conditions of use and determine their suitability for the intended application.

codeLINE warrants to the Buyer that its products are free from defects in materials and workmanship. codeLINE's obligations under this warranty are limited to replacing products demonstrated to the satisfaction of codeLINE to have been defective, provided that the Buyer has complied with the handling, storage and shelf life requirements specified in the applicable codeLINE material specifications.
The above warranties extend solely to the Buyer, and all warranty claims must be made by the Buyer. Rework or replacement shall not alter the original warranty period. In all cases, the warranty period shall not exceed thirty (30) days from the date of the original shipment.

THE ABOVE WARRANTIES ARE EXCLUSIVE OF AND IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE. NO IMPLIED STATUTORY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. codeLINE SHALL NOT BE LIABLE, EITHER IN TORT OR IN CONTRACT, FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR INABILITY TO USE THE PRODUCT, OR FROM DELAY IN THE REPLACEMENT OR REPAIR OF PRODUCTS UNDER THE ABOVE WARRANTY.

Rev. 02 | 10 Nov 2026