HIGH-TEMPERATURE POLYIMIDE LABEL

DURABLETAG

PML 6064

POLYIMIDE 25 TC WHITE SA88 WG



Product Code: PML 6064

Product Name: POLYIMIDE 25 TC WHITE SA88 WG

Facestock : A durable polyimide film with a high-temperature resistant, highly opaque, semi-matt white topcoat. The smooth surface is print treated to achieve good thermal tranfer ribbon printability and ink anchorage.

Basis Weight: 50 g/m² ISO 536

Caliper: 25 µm ISO 534

Adhesive: SA88 is a high temperature acrylic adhesive with excellent heat and chemical resistance.

Liner: White , a supercalendered glassine paper.

Basis Weight: 80 g/m² ISO 536

Caliper: 70 µm ISO 534

Total Caliper: 145 µm±10% ISO 534

Minimum Application Temperature: +10 °C (+50 °F)

Temperature Range, Including Short-Term Exposure: −4 °C to +220 °C (+24.8 °F to +428 °F)

Property	Unit	Value	Test Method
Polyimide Film Thickness	µm	25	ASTM D1000
Ink Thickness	µm	18	ASTM D1000
Adhesive Thickness	µm	23	ASTM D1000
Adhesion to Stainless Steel (20 min)	N/100 mm	42	ASTM D1000
Adhesion to Stainless Steel (24 min)	N/100 mm	55	ASTM D1000
Adhesion to Epoxy PC Board (20 min)	N/100 mm	32	ASTM D1000
Adhesion to Epoxy PC Board (24 min)	N/100 mm	43	ASTM D1000
Adhesive Coating Weight	g/m²	25	ASTM D1000
Initial Tack	No./Ball	≤3	ASTM D2979
180° Adhesive Strength	kgf/25 mm	≥0.6	ASTM D2979
Holding Strength	Hr/kg×25mm	≥45	ASTM D2979
Tensile Strength	kgf/25 mm	13	ASTM D2979
Extrusion Force	%	55	ASTM D2979
Voltage Resistance	kV	>9.5	ASTM D1000
Insulation Resistance	Ω	1.0×10^{10}	ASTM D2979

- 4 °C ~ + 220 °C

Designed for identification in selected reflow soldering processes. Suitability must be verified against the actual temperature profile, exposure duration, cleaning chemicals and printing system. Not recommended for bottom-side PCB applications exposed to wave soldering.

Shelf Life: To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20–25 °C; 40–50% RH). Prolonged storage outside these conditions may reduce the shelf life.

Warranty: © 2023, DURABLETAG

DURABLETAG products are sold on the understanding that the Buyer will test them under actual conditions of use and determine their suitability for the intended application.

DURABLETAG warrants to the Buyer that its products are free from defects in materials and workmanship. DURABLETAG's obligations under this warranty are limited to replacing products demonstrated to the satisfaction of DURABLETAG to have been defective, provided that the Buyer has complied with the handling, storage and shelf life requirements specified in the applicable DURABLETAG material specifications.
The above warranties extend solely to the Buyer, and all warranty claims must be made by the Buyer. Rework or replacement shall not alter the original warranty period. In all cases, the warranty period shall not exceed thirty (30) days from the date of the original shipment.

THE ABOVE WARRANTIES ARE EXCLUSIVE OF AND IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE. NO IMPLIED STATUTORY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. DURABLETAG SHALL NOT BE LIABLE, EITHER IN TORT OR IN CONTRACT, FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR INABILITY TO USE THE PRODUCT, OR FROM DELAY IN THE REPLACEMENT OR REPAIR OF PRODUCTS UNDER THE ABOVE WARRANTY.

Rev. 02 | 01 Nov 2026

www.durabletag.com