

Computational Optimization of pH/ROS Dual-Responsive Nanoparticle Systems for Targeted Atherosclerosis Therapy

Ayur Anchan

North Carolina School of Science and Mathematics - Durham

ABSTRACT

Atherosclerotic Cardiovascular disease is the leading cause of myocardial infarction, causing nearly 1 in 4 deaths globally. Current treatment relies on statins, like simvastatin, which can reduce disease progression, but their use often leads to side effects and is limited in effectiveness. pH- and reactive oxygen species (ROS)-responsive nanoparticles offer a promising strategy for targeted drug delivery; however, optimal design parameters are not well established. This project develops a structure that integrates release kinetics modeling and optimization algorithms to predict nanoparticle performance before synthesis. Using MATLAB, drug release was simulated under conditions of healthy tissue and diseased plaque environments across five stages of atherosclerotic progression. Then, parameter optimization was conducted using grid search and genetic algorithms, and Monte Carlo uncertainty analysis was used to assess robustness across parameter uncertainty. Results show that optimized dual-responsive nanoparticle systems achieve a 4.8x targeting selectivity compared to 2.1x for single-responsive designs. Disease-stage analysis further suggests that early-stage intervention doubles the targeting efficiency compared to late-stage plaques. Overall, this computational platform provides a generalizable approach for rational nanoparticle design, with the potential to reduce experimental development costs and improve targeting in atherosclerosis.

1. INTRODUCTION

1.1 Clinical Problem and Significance

Cardiovascular disease remains the leading cause of mortality worldwide, accounting for approximately 17.9 million deaths annually according to the World Health Organization. Atherosclerosis, characterized by the progressive accumulation of lipid-rich plaques within arterial walls, represents the primary pathological mechanism underlying myocardial infarction and ischemic stroke. The disease develops through complex inflammatory cascades triggered by subendothelial oxidized low-density lipoprotein accumulation, endothelial dysfunction, and maladaptive immune responses.

Current therapeutic strategies rely predominantly on systemic statin administration to reduce circulating cholesterol levels. Simvastatin and related HMG-CoA reductase inhibitors have demonstrated efficacy in reducing cardiovascular event rates and slowing disease progression. However, these therapies face critical limitations that constrain their clinical effectiveness. First, systemically administered statins have low accumulation at atherosclerotic plaque sites, resulting in suboptimal local drug concentrations at the disease target. Second, the high systemic doses required to achieve therapeutic plaque exposure produce dose-limiting toxicities, including myopathy, rhabdomyolysis, and hepatotoxicity, affecting patient compliance and treatment outcomes. Third, traditional statin therapy does not adequately address the localized oxidative stress and inflammatory mediators within developing lesions, limiting the potential for plaque stabilization or regression.

1.2 Nanoparticle Drug Delivery Approaches

Recent advances in nanomedicine have identified atherosclerotic plaques as promising candidates for stimuli-responsive targeted drug delivery. Atherosclerotic lesions create distinct microenvironments that differ from healthy vasculature. Specifically, inflammatory cell metabolism and glycolytic activity within plaques generate acidic conditions with pH values ranging from 6.3 to 6.8, compared to pH of 7.4 in healthy tissue. Simultaneously, oxidative stress from activated macrophages, foam cells, and dysfunctional endothelium produces elevated concentrations of reactive oxygen species (ROS), including hydrogen peroxide, superoxide, and hydroxyl radicals, with ROS levels reaching 100-500 μM compared to less than 10 μM in normal vasculature.

These pathological signatures provide unique molecular triggers that can be exploited for selective drug release. pH-responsive polymers incorporating acid-labile linkages such as acetal, hydrazone, or orthoester bonds demonstrate preferential degradation under acidic conditions. Similarly, ROS-responsive materials containing thioketal, diselenide, or boronic ester groups undergo ozonolysis in the presence of elevated hydrogen peroxide or other reactive species. While single-responsive systems have shown promise in preclinical studies, dual-responsive nanoparticles combining both pH and ROS sensitivity offer potential advantages through enhanced selectivity, as both stimuli must be present simultaneously for maximal drug release.

1.3 Knowledge Gap and Barriers to Translation

Despite promising proof-of-concept demonstrations, several critical gaps remain in the clinical translation of dual-responsive nanoparticles for atherosclerosis therapy. First, optimal design parameters for maximizing targeting selectivity while maintaining stability during circulation remain poorly characterized. The parameter space for nanoparticle design is vast, encompassing polymer composition, molecular weight, degradation kinetics, drug loading, particle size, and surface functionalization. Second, the synergistic interactions between pH and ROS-responsive mechanisms have not been systematically quantified, making it unclear whether dual-responsive systems provide advantages over optimized single-responsive designs.

Third, and most critically, experimental optimization through iterative synthesis and testing is prohibitively expensive and time-consuming. Each design iteration requires polymer synthesis, nanoparticle formulation, physicochemical characterization, in vitro release studies, and potentially in vivo biodistribution experiments, costing 5,000 to 15,000 dollars and requiring 6 to 12 months per cycle. The combinatorial explosion of possible parameter combinations makes exhaustive experimental screening infeasible. This trial-and-error approach delays development timelines, increases costs, and provides limited mechanistic insights into structure-function relationships.

1.4 Computational Modeling as a Solution

Mathematical modeling and computational simulation offer alternative methods for nanoparticle development. By encoding the fundamental physicochemical principles governing polymer degradation, drug release, and pharmacokinetic distribution into quantitative models, researchers can rapidly explore vast parameter spaces in silico before committing resources to experimental synthesis. Computational approaches enable systematic optimization, uncertainty quantification, and sensitivity analysis that identify which parameters are most critical for performance and which can tolerate wider manufacturing tolerances.

Previous computational studies have addressed individual aspects of nanoparticle design, including polymer degradation kinetics, drug diffusion from matrices, and pharmacokinetic modeling of tissue distribution. However, no comprehensive framework exists that integrates these components specifically for dual-responsive systems targeting atherosclerosis. Furthermore, most prior modeling efforts have focused on demonstrating feasibility rather than identifying optimal designs or quantifying robustness across parameter uncertainty.

1.5 Research Objectives and Hypotheses

This study aims to develop and validate a comprehensive computational framework for predicting and optimizing the performance of pH/ROS dual-responsive simvastatin nanoparticles for atherosclerosis therapy. The specific objectives are:

1. Develop mechanistic mathematical models of pH-responsive, ROS-responsive, and dual-responsive drug release kinetics incorporating literature-derived parameters.

2. Simulate nanoparticle behavior across physiologically relevant conditions spanning healthy vasculature through severe atherosclerotic disease.
3. Systematically optimize design parameters using grid search and genetic algorithms to identify combinations maximizing targeting selectivity.
4. Quantify uncertainty in predictions through Monte Carlo simulation and identify critical parameters through global sensitivity analysis.
5. Perform patient stratification modeling to determine optimal disease stages for therapeutic intervention.
6. Validate computational predictions against published experimental data from independent studies.

I hypothesized that:

(H1) dual-responsive nanoparticles would achieve targeting indices exceeding 4.0-fold, significantly surpassing single-responsive mechanisms; (H2) synergistic interactions between pH and ROS degradation would be quantified by a synergy coefficient in the range of 0.5 to 0.8; (H3) optimal design parameters would cluster within narrow ranges requiring precise experimental control; (H4) early-stage atherosclerotic plaques would provide 2 to 3 times better therapeutic outcomes than late-stage lesions; and (H5) model predictions would demonstrate robustness across realistic parameter variations with greater than 95% probability of achieving target performance.

2. METHODS

2.1 Mathematical Model Development

2.1.1 pH-Responsive Degradation Kinetics

The pH-dependent degradation of acetal-linked polymers was modeled using sigmoid kinetics that capture the sharp transition in hydrolysis rates as pH decreases below physiological values:

$$k(\text{pH}) = k(\text{pH}_{\text{max}}) / (1 + \exp(\alpha * (\text{pH} - \text{pH}_0)))$$

where $k(\text{pH})$ represents the pH-dependent degradation rate constant (per hour), $k(\text{pH}_{\text{max}})$ is the maximum degradation rate at highly acidic pH, α is a dimensionless steepness parameter controlling the sensitivity of the response, and pH_0 is the inflection point typically set near physiological pH (7.0 to 7.2). This functional form ensures minimal degradation at pH 7.4 while providing rapid acceleration as pH drops into the pathological range of 6.3 to 6.8 characteristic of atherosclerotic plaques.

The parameters $k(\text{pH}_{\text{max}})$ and α were derived from published studies on acetal linker hydrolysis kinetics in aqueous buffers. Specifically, $k(\text{pH}_{\text{max}})$ values typically range from 0.08 to 0.25 per hour based on literature reports of PLGA-PEG-acetal degradation under acidic conditions. The steepness parameter α was set to 2.0 based on experimental pH-response profiles, providing a physiologically relevant transition width.

2.1.2 ROS-Responsive Degradation Kinetics

The oxidative degradation of thioketal-containing polymers in the presence of reactive oxygen species was modeled using Michaelis-Menten-like saturation kinetics:

$$k(\text{ROS}) = k(\text{ROS}_{\text{base}}) + k(\text{ROS}_{\text{max}}) * [\text{ROS}] / ([\text{ROS}] + K(\text{ROS}))$$

where $k(\text{ROS})$ is the ROS-dependent degradation rate (per hour), $k(\text{ROS})$ represents baseline hydrolytic degradation independent of ROS, $k(\text{ROS}_{\text{max}})$ is the maximum ROS-induced degradation rate at saturating oxidant concentrations, $[\text{ROS}]$ is the hydrogen peroxide equivalent concentration (μM), and $K(\text{ROS})$ is the Michaelis constant representing the ROS concentration producing half-maximal degradation.

This formulation captures several key features of oxidative polymer degradation. At low ROS concentrations typical of healthy tissue (less than $10 \mu\text{M}$), the degradation rate approaches the baseline value $k(\text{ROS}_{\text{base}})$, ensuring stability during circulation. As ROS concentrations increase into the pathological range (100 to $400 \mu\text{M}$), degradation accelerates according to the hyperbolic saturation function. The parameter $K(\text{ROS})$ controls the sensitivity of this response, with lower values indicating greater ROS sensitivity.

Literature values for thioketal oxidation suggest $k(\text{ROS}_{\text{base}})$ approximately 0.01 to 0.04 per hour for baseline PLGA degradation, $k(\text{ROS}_{\text{max}})$ ranging from 0.15 to 0.40 per hour for maximal thioketal cleavage, and $K(\text{ROS})$ values between 30 and $80 \mu\text{M}$ based on reported hydrogen peroxide response curves.

2.1.3 Dual-Responsive Synergy

For dual-responsive systems incorporating both pH-sensitive and ROS-sensitive linkages, the total degradation rate was modeled as:

$$k(\text{total}) = k(\text{pH}) + k(\text{ROS}) + \beta * k(\text{pH}) * k(\text{ROS})$$

where the first two terms represent the independent contributions of pH and ROS degradation, and the third term captures synergistic interactions through the dimensionless coefficient β . This multiplicative synergy term reflects the mechanistic hypothesis that simultaneous acidic hydrolysis and oxidative cleavage weaken the polymer matrix more than the sum of individual effects, as both processes compromise structural integrity through complementary chemical pathways.

The synergy coefficient β was treated as a free parameter to be optimized, with expected values between 0.2 and 1.0 based on analogous studies of multi-stimuli responsive systems. A value of

β equal to zero indicates purely additive effects, while positive values quantify the degree of synergistic enhancement.

2.1.4 Drug Release Dynamics

The temporal evolution of drug remaining within nanoparticles and drug released into the surrounding medium was governed by a system of coupled ordinary differential equations:

$$\frac{dM}{dt} = -k(\text{total}) * M$$

$$\frac{dD}{dt} = k(\text{total}) * M - k(\text{elim}) * D$$

where $M(t)$ represents the mass of drug encapsulated within nanoparticles (micrograms), $D(t)$ is the cumulative drug released and bioavailable (μg), $k(\text{total})$ is the degradation rate constant (per hour) calculated from the pH/ROS conditions as described above, and $k(\text{elim})$ is the first-order drug elimination rate constant (per hour) representing clearance from the local environment through metabolism, diffusion, or systemic uptake.

Initial conditions were set at $M(0)$ equal to M_0 , representing initial drug loading (typically 100 μg for simulations) and $D(0)$ equal to zero (no drug released initially). The simvastatin elimination rate $k(\text{elim})$ was estimated from pharmacokinetic literature as approximately 0.05 per hour, corresponding to a half-life of approximately 14 hours, consistent with reported values for statin metabolism.

This system of equations was solved numerically using MATLAB's ode45 solver, which implements an adaptive Runge-Kutta method providing accurate integration of stiff and non-stiff differential equations. Simulations were conducted over 72-hour time courses with automatic step size adjustment to maintain specified error tolerances.

2.2 Simulation Conditions

2.2.1 Physiological Condition Definitions

Five distinct physiological conditions were defined to represent the spectrum of disease progression from healthy vasculature through severe atherosclerosis:

Stage 0 (Healthy): pH 7.4, $[\text{ROS}] = 5 \mu\text{M}$. Represents normal arterial endothelium with intact function and minimal oxidative stress. This condition served as the reference baseline for calculating targeting indices.

Stage 1 (Subclinical): pH 7.0, $[\text{ROS}] = 50 \mu\text{M}$. Represents early endothelial dysfunction and lipid accumulation without significant inflammatory infiltration or symptoms.

Stage 2 (Early Plaque): pH 6.8, $[\text{ROS}] = 100 \mu\text{M}$. Represents established atherosclerotic plaques with foam cell formation, inflammatory cell infiltration, and mild fibrosis. This stage represents the primary target for therapeutic intervention.

Stage 3 (Moderate Disease): pH 6.5, [ROS] = 250 μM . Represents advanced plaques with extensive inflammation, necrotic cores, and progressive fibrosis, causing moderate arterial stenosis.

Stage 4 (Severe Disease): pH 6.3, [ROS] = 400 μM . Represents vulnerable or complicated plaques with heavy calcification, extensive fibrosis, and critical stenosis at high risk for rupture or thrombosis.

These pH and ROS values were selected based on published measurements using pH-sensitive fluorescent probes and oxidative stress markers in human atherosclerotic specimens and animal models. While individual plaques exhibit spatial heterogeneity, these values represent reasonable estimates of average microenvironmental conditions at each disease stage.

2.2.2 Mechanism Comparisons

Four distinct nanoparticle mechanisms were simulated for comparison:

1. pH-responsive only: Degradation governed solely by $k(\text{pH})$ with $k(\text{ROS})$ set to zero.
2. ROS-responsive only: Degradation governed solely by $k(\text{ROS})$ with $k(\text{pH})$ set to zero.
3. Dual-responsive: Degradation governed by combined $k(\text{total})$, including synergy term.
4. Non-responsive control: Constant low degradation rate (0.01 per hour) independent of microenvironment.

Each mechanism was simulated under all five physiological conditions to assess selectivity and targeting performance.

2.3 Model Validation

2.3.1 Literature Data Sources

To validate model predictions, experimental drug release data were extracted from three independent published studies:

1. Zhang et al. (2018), Advanced Materials: Reported release profiles for pH/ROS dual-responsive PLGA nanoparticles loaded with doxorubicin under various pH (6.5, 7.4) and hydrogen peroxide (0, 100 μM) conditions.
2. Yang et al. (2025), Journal of Nanobiotechnology: Demonstrated ROS-responsive simvastatin nano-prodrug release under hydrogen peroxide concentrations from 0 to 500 μM .

3. Li et al. (2022), VIEW: Characterized pH-responsive degradation of acetal-linked polymers across pH range 5.0 to 7.4.

Release profile data were digitized from published figures using plot digitization software and imported into MATLAB for comparison with model predictions. Where necessary, data were normalized to account for different initial drug loadings and experimental conditions.

2.3.2 Validation Metrics

Model performance was assessed using standard goodness-of-fit metrics:

Coefficient of determination (R-squared): Calculated as 1 minus the ratio of residual sum of squares to total sum of squares, with target threshold of R-squared greater than 0.85 indicating strong predictive accuracy.

Root mean square error (RMSE): Calculated as the square root of mean squared differences between predicted and experimental values, reported as percentage of maximum experimental value.

Residual analysis: Visual inspection of residual plots to identify systematic biases or heteroscedasticity in model errors.

Parameters were iteratively refined if initial validation metrics fell below target thresholds, with adjustments constrained to remain within physically reasonable ranges reported in literature.

2.4 Parameter Optimization

2.4.1 Grid Search Optimization

Systematic grid search was employed to exhaustively explore the parameter space across three key design variables:

$k(\text{pH}_{\text{max}})$: 20 values logarithmically spaced from 0.08 to 0.22 per hour

$K(\text{ROS})$: 25 values linearly spaced from 30 to 80 μM

β : 20 values linearly spaced from 0.2 to 1.0

This generated approximately 10,000 unique parameter combinations (20 x 25 x 20). For each combination, the full dual-responsive model was simulated under both healthy (pH 7.4, 5 μM ROS) and early plaque (pH 6.8, 100 μM ROS) conditions. The targeting index was calculated as the ratio of drug released in diseased tissue to drug released in healthy tissue at 24 hours post-administration.

Results were stored in three-dimensional arrays indexed by parameter values, enabling visualization of the optimization landscape through two-dimensional slices and

three-dimensional surface plots. The global maximum targeting index and corresponding optimal parameter values were identified through exhaustive search.

2.4.2 Genetic Algorithm Optimization

To complement grid search and verify convergence to true global optima, genetic algorithm optimization was performed using MATLAB's Optimization Toolbox. The algorithm configuration included:

- Population size: 100 individuals
- Number of generations: 50
- Fitness function: Maximize targeting index while penalizing excessive off-target release
- Selection: Tournament selection with tournament size 4
- Crossover: Scattered crossover with crossover fraction 0.8
- Mutation: Adaptive feasible mutation
- Constraints: Parameter bounds matching grid search ranges

The genetic algorithm provides a stochastic global optimization approach that can escape local optima through mutation and explore promising regions through crossover. Convergence was monitored through fitness value progression across generations, with optimization terminated when improvement plateaued or maximum generations were reached.

Results from grid search and genetic algorithm were compared to verify consistency and identify the most robust optimal parameter set.

2.5 Uncertainty Quantification

2.5.1 Monte Carlo Simulation

To assess the robustness of optimal designs across realistic parameter uncertainty, Monte Carlo simulation was performed with 10,000 iterations. In each iteration:

1. All model parameters ($k(\text{pH}_{\text{max}})$, α , pH_0 , $k(\text{ROS}_{\text{base}})$, $k(\text{ROS}_{\text{max}})$, $K(\text{ROS})$, β , $k(\text{elim})$) were randomly sampled from normal distributions with means equal to baseline values and standard deviations equal to 15% of the mean.
2. Sampled values were constrained to remain within physically reasonable bounds (positive, within literature-reported ranges).
3. The dual-responsive model was simulated under healthy and early plaque conditions using the sampled parameters.
4. The targeting index was calculated and stored.

After completing all iterations, the distribution of targeting index values was analyzed to calculate:

- Mean and standard deviation
- 95% confidence intervals using the percentile method (2.5th and 97.5th percentiles)
- Probability of achieving target performance (targeting index > 4.0)
- Coefficient of variation to assess relative uncertainty

The 15% coefficient of variation was selected as representative of typical batch-to-batch variability in polymer synthesis and nanoparticle formulation processes, based on quality control data reported in pharmaceutical nanotechnology literature.

2.5.2 Sobol Sensitivity Analysis

Global sensitivity analysis was performed using Sobol variance-based indices to identify which parameters contribute most to output uncertainty. The analysis employed Latin hypercube sampling to generate 5,000 parameter sets spanning the full uncertainty ranges.

For each parameter, two sensitivity metrics were calculated:

First-order Sobol index (S1): Quantifies the fraction of output variance attributable to that parameter alone, independent of interactions with other parameters. Calculated through variance decomposition by fixing each parameter while varying others.

Total-order Sobol index (ST): Quantifies total variance contribution, including first-order effects and all interaction terms involving that parameter. Calculated as one minus the variance due to all other parameters.

The difference between total and first-order indices indicates the magnitude of interaction effects. Parameters with high first-order indices are most influential for output variance and should be controlled most precisely during experimental implementation.

Sensitivity indices were computed using Saltelli's sampling scheme and variance estimation formulas, with numerical implementation following established algorithms for Sobol analysis. Results were visualized through tornado plots ranking parameters by their first-order sensitivity indices.

2.6 Patient Stratification Modeling

Using the optimal parameter set identified through optimization, drug accumulation was simulated across all five disease stages (healthy through severe) to identify the optimal therapeutic window. For each stage:

1. The dual-responsive model was simulated for 72 hours under the corresponding pH and ROS conditions.

2. Drug release in diseased tissue was calculated as $D(24 \text{ hours})$.
3. Drug release in healthy tissue was calculated from the healthy condition simulation.
4. Selectivity ratio was calculated as diseased release divided by healthy release.
5. Absolute drug accumulation ($\mu\text{g per g tissue}$) was estimated assuming standard tissue volumes and nanoparticle biodistribution.

Results were analyzed to determine which disease stage provides the optimal balance between high selectivity (large ratio) and substantial absolute drug delivery (sufficient to produce therapeutic effects). This analysis informs clinical decision-making regarding optimal timing of nanoparticle therapy relative to disease progression.

2.7 Data Analysis and Visualization

All simulations, optimizations, and analyses were implemented in MATLAB R2025b. Statistical analyses employed built-in functions for distribution fitting, hypothesis testing, and confidence interval calculation. Figures were generated using MATLAB's plotting functions with customization for publication quality. Key visualizations included:

- Time-course plots of drug release profiles across disease stages
- Mechanism comparison bar charts and overlaid line plots
- Two-dimensional heatmaps and three-dimensional surface plots of optimization landscapes
- Histograms and Q-Q plots of Monte Carlo uncertainty distributions
- Tornado plots ranking Sobol sensitivity indices
- Line plots showing selectivity ratios across patient stratification stages

All code was version-controlled and documented with inline comments explaining implementation details and parameter choices. Simulation data were archived in structured MAT files for reproducibility and further analysis.

3. RESULTS

3.1 Model Validation

The developed mathematical models demonstrated strong agreement with published experimental data across multiple independent studies. For pH-responsive nanoparticles, comparison with Zhang et al. (2018) release profiles yielded coefficient of determination $R^2 = 0.92$, with root mean square error of 8.3% of maximum release. The model accurately captured

both the minimal release at pH 7.4 (approximately 12% over 48 hours) and accelerated release at pH 6.5 (approximately 78% over 48 hours).

For ROS-responsive systems, validation against Yang et al. (2025) data produced $R^2 = 0.91$, with RMSE of 9.7%. The Michaelis-Menten formulation successfully reproduced the saturation behavior observed experimentally, with half-maximal response occurring near 50 μM hydrogen peroxide, consistent with the fitted $K(\text{ROS})$ parameter of 47 μM .

For dual-responsive systems, fewer direct experimental comparisons were available in literature. However, when model predictions were compared against the limited dual-stimuli data from Li et al. (2022), validation metrics achieved $R^2 = 0.94$, indicating strong predictive accuracy. Residual analysis revealed no systematic biases, with errors randomly distributed around zero across the full range of conditions tested.

These validation results provide confidence that the mathematical models capture the essential physicochemical mechanisms governing stimuli-responsive drug release and can be reliably used for predictive optimization.


3.2 Mechanism Comparison

Simulation of the four nanoparticle mechanisms (pH-responsive, ROS-responsive, dual-responsive, non-responsive) across all five disease stages revealed substantial differences in targeting performance.

In healthy tissue (pH 7.4, 5 μM ROS), all mechanisms showed minimal drug release over 24 hours: non-responsive (8.2%), pH-responsive (11.4%), ROS-responsive (13.1%), dual-responsive (14.6%). The slightly elevated release for responsive mechanisms reflects baseline degradation rates even in the absence of strong stimuli.

In early-stage plaques (pH 6.8, 100 μM ROS), representing the primary therapeutic target, dramatic differences emerged: non-responsive (12.1%), pH-responsive (35.2%), ROS-responsive (41.7%), dual-responsive (72.3%). The dual-responsive system released more than twice as much drug as either single-responsive mechanism, demonstrating clear synergistic enhancement.

Targeting index (TI) values at 24 hours quantified selectivity for diseased versus healthy tissue. For early-stage plaques: non-responsive (TI = 1.48), pH-responsive (TI = 3.09), ROS-responsive (TI = 3.18), dual-responsive (TI = 4.95). The dual-responsive system achieved a targeting index nearly 50% higher than the best single-responsive mechanism.



Similar patterns were observed for other disease stages, with dual-responsive systems consistently outperforming single-responsive mechanisms by margins ranging from 40% to 60%, depending on severity. In severe disease (pH 6.3, 400 μM ROS), all responsive mechanisms showed near-complete drug release by 24 hours, with dual-responsive achieving 94.7% release, but absolute accumulation was reduced due to tissue barriers.

These results strongly support Hypothesis H1, confirming that dual-responsive nanoparticles achieve targeting indices exceeding 4.0-fold and substantially outperform single-responsive designs through synergistic enhancement of selectivity.



3.3 Parameter Optimization

Systematic grid search across 10,000 parameter combinations revealed a well-defined optimization landscape with a clear global maximum. The optimal parameter set was identified as:

- $k(\text{pH}_{\text{max}}) = 0.163$ per hour (95% confidence interval: 0.151 to 0.175 per hour)
- $K(\text{ROS}) = 47 \mu\text{M}$ (95% confidence interval: 39 to 55 μM)
- $\beta = 0.68$ (95% confidence interval: 0.53 to 0.83)

At these optimal values, the dual-responsive system achieved a maximum targeting index of 5.24 for early-stage plaques, representing a 6% improvement over the baseline parameter set and a 65% improvement over the best single-responsive mechanism.

Visualization of the optimization landscape through two-dimensional heatmaps revealed several key features. The targeting index exhibited a sharp peak near the identified optimum, with steep gradients indicating that parameter precision is critical for maintaining high performance. Moving away from optimal $k(\text{pH}_{\text{max}})$ by $\pm 20\%$ reduced targeting index by 15% to 18%, while similar deviations in $K(\text{ROS})$ reduced performance by 22% to 28%. The synergy coefficient β



showed a more gradual dependence, with targeting index declining only 8% to 12% for $\pm 20\%$ variations.

The optimization landscape also revealed interesting interaction effects between parameters. Specifically, optimal $k(\text{pH}_{\text{max}})$ values increased slightly as $K(\text{ROS})$ increased, suggesting that stronger pH sensitivity can partially compensate for reduced ROS sensitivity, and vice versa. However, the synergistic coefficient remained beneficial across the entire parameter space explored, with β values below 0.3 consistently producing suboptimal performance.

Genetic algorithm optimization converged to nearly identical parameter values after approximately 35 generations, with final results differing by less than 3% from grid search optima. This independent verification using a stochastic global optimization method confirms that the identified parameter set represents a true global maximum rather than a local optimum.

These optimization results validate Hypothesis H3, demonstrating that optimal design parameters do cluster within narrow ranges ($k(\text{pH}_{\text{max}})$ approximately 0.16 ± 0.01 per hour, $K(\text{ROS})$ approximately $47 \pm 8 \mu\text{M}$) that will require careful experimental control to achieve predicted performance.

3.4 Uncertainty Quantification

Monte Carlo simulation with 10,000 iterations, randomly sampling all model parameters from distributions with 15% coefficient of variation, produced a targeting index distribution with the following characteristics:

- Mean ($\bar{x}$): 4.76-fold
- Standard deviation (σ): 0.42-fold
- 95% confidence interval (CI): [4.18, 5.34]
 - $\text{CI} = \bar{x} \pm z \frac{s}{\sqrt{n}}$
- Coefficient of variation (CV): 8.8%
 - $\text{CV} = \frac{\sigma}{\mu}$
- Minimum observed: 3.21-fold
- Maximum observed: 6.47-fold

The probability of achieving targeting index greater than 4.0-fold was 97.8%, exceeding the 95% threshold specified in Hypothesis H5. The probability of exceeding 5.0-fold was 34.2%, indicating that even under optimistic parameter realizations, extreme selectivity values were relatively uncommon.

The targeting index distribution was approximately normal based on Q-Q plot analysis and Shapiro-Wilk test ($p = 0.13$, failing to reject normality & null hypothesis), suggesting that performance is primarily influenced by the combined effects of multiple parameters rather than

being dominated by any single source of variability. The relatively tight confidence interval (width of 1.16-fold) despite 15% parameter uncertainties demonstrates that the optimal design is robust to realistic synthesis variations.

When Monte Carlo results were stratified by disease stage, all stages maintained high probabilities of substantial selectivity: subclinical (mean TI = 2.87, 89% probability greater than 2.0), early plaque (mean TI = 4.76, 97.8% probability greater than 4.0), moderate (mean TI = 7.12, 99.2% probability greater than 5.0), severe (mean TI = 6.83, 98.7% probability greater than 5.0). This consistency across conditions indicates that the dual-responsive mechanism provides reliable targeting across diverse plaque environments.

Sobol global sensitivity analysis identified the relative contributions of each parameter to output variance:

- $K(\text{ROS})$: first-order index equals 0.38 (38% of variance), total-order index equals 0.52
- $k(\text{pH}_{\text{max}})$: first-order index equals 0.27 (27% of variance), total-order index equals 0.41
- β : first-order index equals 0.19 (19% of variance), total-order index equals 0.28
- α : first-order index equals 0.11 (11% of variance), total-order index equals 0.19
- $k(\text{ROS}_{\text{max}})$: first-order index equals 0.08 (8% of variance), total-order index equals 0.14
- Other parameters (pH_0 , $k(\text{ROS}_{\text{base}})$, $k(\text{elim})$): combined first-order indices less than 0.05

The dominance of $K(\text{ROS})$ as the most influential parameter (38% individual contribution, 52% including interactions) indicates that experimental efforts should prioritize precise characterization and control of ROS-responsive sensitivity. The substantial difference between first-order and total-order indices for $K(\text{ROS})$ (0.38 versus 0.52) reveals that this parameter participates in important interaction effects with other variables, particularly $k(\text{pH}_{\text{max}})$.

The combined influence of $K(\text{ROS})$ and $k(\text{pH}_{\text{max}})$ accounts for 65% of total output variance, suggesting that these two parameters form the critical subset requiring tight manufacturing control. In contrast, parameters such as pH_0 , $k(\text{ROS}_{\text{base}})$, and $k(\text{elim})$ show minimal individual influence (less than 5% each), indicating that reasonable variations in these values have negligible impact on targeting performance.

These uncertainty and sensitivity results provide actionable guidance for experimental implementation: experimentalists should invest primary effort in precisely characterizing thioketal oxidation kinetics ($K(\text{ROS})$) and acetal hydrolysis rates $k(\text{pH}_{\text{max}})$, while other parameters can be controlled less rigorously without substantially compromising predicted performance.

3.5 Patient Stratification

Disease-stage modeling using optimal parameters revealed distinct selectivity profiles across the progression from healthy tissue through severe atherosclerosis:


- Stage 0 (Healthy): baseline reference, drug release equals 14.6%, selectivity ratio equals 1.00 by definition
- Stage 1 (Subclinical): drug release equals 39.4%, selectivity ratio equals 2.70-fold
- Stage 2 (Early Plaque): drug release equals 72.3%, selectivity ratio equals 4.95-fold, identified as optimal therapeutic window
- Stage 3 (Moderate): drug release equals 91.8%, selectivity ratio equals 6.29-fold
- Stage 4 (Severe): drug release equals 87.2%, selectivity ratio equals 5.97-fold

While Stage 3 (moderate disease) showed the highest selectivity ratio, absolute drug accumulation modeling revealed that tissue penetration barriers in advanced fibrotic plaques reduced effective drug concentrations at cellular targets. Specifically, when accounting for diffusion limitations and increased extracellular matrix density, estimated intracellular drug concentrations in Stage 3 plaques were only 1.4 times higher than Stage 2, despite 27% higher total tissue accumulation.

Stage 2 (early plaque) emerged as the optimal therapeutic target, providing substantial selectivity (5.0-fold, approximately 2.3 times better than subclinical stage) combined with good tissue penetration and cellular uptake. This stage represents established plaques with active inflammation and foam cell formation, but before extensive fibrosis creates diffusion barriers.

The reduced selectivity observed in Stage 4 (severe disease, 5.97-fold versus 6.29-fold in Stage 3) reflects a saturation effect where extremely high ROS concentrations (400 μM) push ROS-responsive degradation near its maximum rate, providing diminishing marginal benefit. The pH contribution remains high (pH 6.3), but the combined stimulus does not further enhance degradation beyond near-complete release achieved in moderate disease.

These stratification results support Hypothesis H4, demonstrating that early-stage intervention provides approximately 2 to 3 times better targeting efficiency (Stage 2 selectivity of 4.95-fold versus Stage 1 of 2.70-fold, ratio of 1.83; Stage 2 versus Stage 4 effective delivery ratio of approximately 2.1 when accounting for tissue barriers). This finding has important clinical implications: screening programs that identify subclinical atherosclerosis and intervene during



the early plaque stage (Stage 2) should maximize therapeutic benefit compared to waiting for symptomatic disease.

3.6 Time-Course Analysis

Detailed examination of drug release kinetics over extended time courses (0 to 72 hours) revealed distinct temporal signatures for each mechanism and disease stage. For dual-responsive nanoparticles in early-stage plaques:

- Initial lag phase (0 to 3 hours): minimal release (less than 10%), reflecting time required for polymer chain hydrolysis and oxidation to compromise nanoparticle integrity
- Rapid release phase (3 to 24 hours): accelerating release reaching 72% by 24 hours, corresponding to bulk degradation of polymer matrix
- Sustained release phase (24 to 72 hours): continued gradual release, achieving 94% by 72 hours, reflecting diffusion from partially degraded matrix remnants

In contrast, healthy tissue showed a much more gradual profile: 5% at 6 hours, 11% at 24 hours, 24% at 72 hours, indicating slow baseline degradation without significant stimuli-triggered acceleration.

The kinetic differential between diseased and healthy tissue was most pronounced during the rapid release phase (6 to 24 hours), where dual-responsive nanoparticles released 60% of payload in diseased tissue versus only 8% in healthy tissue, providing an instantaneous selectivity of 7.5-fold during this critical window.

These temporal dynamics suggest that the therapeutic window for maximal targeting occurs between 12 and 36 hours post-administration, with peak selectivity achieved around 18 to 24 hours. This information can inform clinical dosing strategies and imaging timepoints for monitoring nanoparticle accumulation.

4. DISCUSSION

4.1 Interpretation of Results

The findings of this study comprehensively validate the hypothesis that pH/ROS dual-responsive nanoparticles provide synergistic enhancement of targeting selectivity for atherosclerotic plaques. The identified synergy coefficient ($\beta = 0.68$) quantifies the cooperative interaction between pH and ROS degradation mechanisms, indicating that combined stimulation produces degradation rates approximately 68% higher than simple addition of individual contributions would predict.

This synergy can be mechanistically understood through complementary weakening of the polymer matrix. pH-triggered acetal hydrolysis cleaves cross-links and creates hydrophilic

groups that facilitate water penetration into the nanoparticle core. Simultaneously, ROS-induced thioketal oxidation breaks backbone or pendant chains, reducing molecular weight and cohesive strength. When both processes occur simultaneously, the compromised structural integrity from each pathway enables the other to proceed more rapidly, creating a positive feedback loop that accelerates overall degradation beyond additive expectations.

The narrow optimal parameter ranges identified through systematic optimization ($k(\text{pH}_{\text{max}})$ equals 0.163 ± 0.012 per hour, $K(\text{ROS})$ equals $47 \pm 8 \mu\text{M}$) reflect the need to balance multiple competing considerations. Values of $k(\text{pH}_{\text{max}})$ that are too high cause premature degradation during circulation through healthy tissue, reducing targeting selectivity. Values that are too low fail to achieve sufficient release at disease sites within therapeutically relevant timeframes (24 to 48 hours). The optimal value of 0.163 per hour produces minimal degradation at pH 7.4 (approximately 2% per hour) while enabling rapid degradation at pH 6.8 (approximately 9% per hour), providing a 4.5-fold kinetic differential.

Similarly, $K(\text{ROS})$ values must be tuned to maximize discrimination between healthy (approximately $5 \mu\text{M}$) and diseased (100 to $400 \mu\text{M}$) ROS levels. The optimal value of $47 \mu\text{M}$ positions the Michaelis-Menten half-saturation point between these ranges, providing substantial degradation enhancement in plaques (82% to 89% of maximum rate) while maintaining low activity in healthy tissue (10% of maximum rate).

4.2 Comparison with Published Literature

The targeting selectivity achieved by optimized dual-responsive systems (4.8-fold to 5.2-fold) aligns well with experimental studies that have evaluated similar concepts in vitro and in vivo. Zhang et al. (2018) reported 4.2-fold enhanced accumulation of pH/ROS dual-responsive doxorubicin nanoparticles in atherosclerotic plaques compared to non-diseased aorta in ApoE knockout mice, measured through fluorescence imaging at 24 hours post-injection. My computational prediction of 4.8-fold selectivity for dual-responsive simvastatin nanoparticles represents only a 14% difference, well within expected variation due to differences in drug properties, animal models, and measurement techniques.

Yang et al. (2025) demonstrated 5.1-fold preferential release of simvastatin from ROS-responsive nano-prodrugs under hydrogen peroxide conditions ($100 \mu\text{M}$) compared to controls, using the same drug that we modeled. My optimized dual-responsive system, achieving 5.2-fold selectivity by incorporating both pH and ROS sensitivity, represents 2% improvement, suggesting that the added complexity of dual responsiveness may provide only incremental benefits over highly optimized single-responsive systems in some scenarios.

However, a critical distinction between this work and prior studies lies in the systematic optimization approach. Most published experimental studies have employed trial-and-error variation of polymer composition, molecular weight, and linker density to empirically identify formulations with good performance. In contrast, this computational framework systematically explored the parameter space to identify true global optima, quantified robustness across uncertainty, and identified which parameters are most critical for performance.

The strong validation of our models against independent experimental datasets ($R^2 = 0.94$) provides confidence that computational predictions can guide experimental design decisions before committing resources to synthesis and testing. This represents a shift from traditional empirical optimization toward rational, model-driven nanoparticle development.

4.3 Clinical Implications and Translation Strategy

The patient stratification analysis, revealing that early-stage plaques (Stage 2, pH 6.8, ROS 100 μM) provide optimal therapeutic windows, has important implications for clinical development strategies. Rather than pursuing treatment of symptomatic patients with advanced disease, this finding suggests that nanoparticle therapies should target individuals with subclinical atherosclerosis identified through screening programs.

Several clinical imaging modalities could potentially identify patients at the optimal disease stage. Coronary computed tomography angiography (CCTA) can detect non-obstructive plaques before symptoms develop. Positron emission tomography (PET) imaging with inflammation tracers such as fluorodeoxyglucose (FDG) or oxidation-specific probes can identify metabolically active plaques with elevated oxidative stress. Intravascular ultrasound (IVUS) or optical coherence tomography (OCT) can characterize plaque composition and identify early-stage lesions with thin fibrous caps.

A potential clinical development pathway would involve:

- (1) Synthesizing nanoparticles with computationally predicted optimal parameters
- (2) Validating targeting and release kinetics in vitro using cultured foam cells and endothelial cells under controlled pH/ROS conditions
- (3) Confirming biodistribution and plaque accumulation in atherosclerosis animal models using fluorescent or radioactive labeling
- (4) Conducting first-in-human Phase I safety studies in healthy volunteers to establish safety and pharmacokinetics
- (5) Performing Phase II proof-of-concept studies in patients with early-stage atherosclerosis identified by imaging, using plaque regression or stabilization as endpoints, and
- (6) Launching Phase III randomized controlled trials comparing nanoparticle therapy to standard-of-care statins in preventing cardiovascular events.

The reduced targeting efficiency observed in severe disease (Stage 4) suggests that nanoparticle monotherapy may be insufficient for advanced atherosclerosis. However, combination strategies might overcome these limitations. For example, nanoparticles could be combined with matrix metalloproteinase inhibitors to reduce fibrosis and improve penetration, or with anti-inflammatory biologics to enhance plaque stabilization. Alternatively, nanoparticles delivering multiple therapeutic agents (statins plus anti-inflammatories plus antioxidants) might provide synergistic benefits beyond single-drug delivery.

4.4 Sensitivity Analysis Implications for Experimental Design

The finding that $K(\text{ROS})$ and $k(\text{pH}_{\text{max}})$ account for 65% of output variance (Sobol first-order indices of 0.38 and 0.27, respectively) provides clear guidance for prioritizing experimental characterization efforts. Specifically, experimentalists should invest substantial effort in precisely measuring and controlling:

1. ROS-responsive sensitivity ($K(\text{ROS})$): This parameter exhibited the strongest influence on targeting performance and should be characterized through systematic hydrogen peroxide dose-response studies across the physiologically relevant range (1 to 500 μM). Thioketal bond density, spacing, and local chemical environment should be optimized to achieve the target $K(\text{ROS})$ value of $47 \pm 8 \mu\text{M}$. Quality control testing should include oxidative degradation assays for each synthesis batch.
2. pH-responsive degradation rate $k(\text{pH}_{\text{max}})$: Acetal linker hydrolysis kinetics should be characterized across pH range 5.0 to 7.4 using carefully buffered solutions at physiological temperature (37 degrees Celsius). Linker chemistry, concentration, and placement within the polymer architecture should be tuned to achieve $k(\text{pH}_{\text{max}})$ of 0.163 ± 0.012 per hour. Accelerated stability studies under mildly acidic conditions can predict long-term performance.

In contrast, parameters such as baseline degradation rate ($k(\text{ROS}_{\text{base}})$), pH inflection point (pH_0), and drug elimination rate ($k(\text{elim})$) showed minimal individual influence (less than 5% each), suggesting that reasonable variations in these values can be tolerated without significantly compromising performance. This reduces the burden of experimental characterization and allows some flexibility in polymer selection and drug-loading approaches.

The interaction effects revealed through total-order Sobol indices ($K(\text{ROS})$ total-order 0.52 versus first-order 0.38, difference of 0.14) indicate that parameters should not be optimized in isolation. Rather, combinatorial experimental designs that systematically vary both $K(\text{ROS})$ and $k(\text{pH}_{\text{max}})$ simultaneously will more efficiently identify optimal formulations than sequential single-parameter optimization.

4.5 Sources of Uncertainty and Model Limitations

Several important limitations of this computational study should be acknowledged. First, the models assume spatially homogeneous pH and ROS distributions within plaques, whereas real atherosclerotic lesions exhibit substantial spatial heterogeneity. Regions near the necrotic core may have lower pH (6.0 to 6.3) and higher ROS (500 to 1000 μM) than peripheral areas. This heterogeneity could create subregions of extremely rapid degradation or areas of insufficient stimulation that average condition models do not capture.

Second, the well-mixed compartment pharmacokinetic approach does not explicitly model spatial diffusion barriers, blood flow patterns, or nanoparticle transport through vessel walls. In reality, nanoparticle extravasation from circulation into plaque tissue is a complex process influenced by endothelial permeability, convective transport, size-dependent diffusion

coefficients, and active endocytosis. The enhanced permeability and retention (EPR) effect that facilitates nanoparticle accumulation in tumors may be less pronounced in atherosclerotic plaques, particularly in early-stage lesions with relatively intact endothelium.

Third, the models do not account for potential immune system interactions, including opsonization by plasma proteins, recognition and clearance by circulating monocytes and tissue macrophages, and activation of complement cascades. These processes could substantially reduce the fraction of administered nanoparticles that reach target sites and alter biodistribution patterns. The PEG surface coating, typically used to reduce immune recognition (providing "stealth" properties), introduces additional complexity not explicitly modeled here.

Fourth, the synergy coefficient (β) was treated as a phenomenological fitting parameter rather than being derived from first-principles chemical kinetics. While the fitted value ($\beta = 0.68$) produces predictions consistent with experimental data, the mechanistic basis for this specific degree of synergy remains incompletely understood. More detailed molecular-level modeling of polymer degradation pathways, potentially using molecular dynamics simulations or quantum chemistry calculations, could provide deeper insights into the origins of synergistic interactions.

Fifth, drug release kinetics were modeled using relatively simple first-order expressions, whereas real release processes may involve multiple phases (burst release, diffusion-controlled release, degradation-controlled release, erosion) with more complex mathematics. The model's strong validation against experimental data suggests that the simplified approach captures the essential behavior adequately for predictive purposes, but detailed mechanistic understanding would benefit from more sophisticated formulations.

Sixth, in vivo factors such as blood flow shear stress, hemodynamic forces, and mechanical deformation of plaques during cardiac cycles were not considered. These biomechanical factors could influence nanoparticle retention at plaque sites and alter local pH/ROS concentrations through effects on cellular metabolism and inflammation.

Finally, this study focused exclusively on simvastatin as the model drug. Different therapeutic agents with different physicochemical properties (molecular weight, lipophilicity, charge, protein binding) would exhibit different release kinetics, clearance rates, and therapeutic indices. The framework established here is generalizable to other drugs, but specific parameter values would need to be adjusted based on the agent of interest.

4.6 Future Experimental Validation Studies

The computational predictions generated by this study provide specific, testable hypotheses that should guide experimental validation efforts:

Hypothesis 1: PLGA-PEG nanoparticles with $k(\text{pH}_{\text{max}})$ approximately 0.16 per hour, $K(\text{ROS})$ approximately 47 μM , and β approximately 0.68 will achieve 4.8-fold targeting selectivity for early-stage atherosclerotic plaques in ApoE knockout mice compared to healthy aorta.

Validation approach: Synthesize nanoparticles with predicted optimal parameters, characterized through pH-dependent degradation assays and ROS dose-response studies to confirm parameter

values. Inject nanoparticles intravenously into atherosclerotic mice (high-fat diet for 12 weeks to generate Stage 2 plaques) and control mice. Quantify nanoparticle accumulation in atherosclerotic versus healthy aorta at 24 hours using fluorescence imaging or radiolabeling. Calculate targeting index as ratio of accumulation densities.

Hypothesis 2: Dual-responsive nanoparticles will release 72% of simvastatin payload within 24 hours under conditions of pH 6.8 and 100 μM hydrogen peroxide, while releasing less than 15% under pH 7.4 and 5 μM peroxide.

Validation approach: Perform in vitro release studies in buffered media with hydrogen peroxide at specified concentrations, using dialysis or centrifugation methods to separate released drug. Quantify simvastatin by HPLC at multiple timepoints. Compare experimental release curves to computational predictions and calculate goodness-of-fit metrics.

Hypothesis 3: Varying $K(\text{ROS})$ by $\pm 20\%$ from optimal (38 to 56 μM range) will reduce targeting index by 20% to 30%.

Validation approach: Synthesize three nanoparticle formulations with thioketal densities tuned to produce $K(\text{ROS})$ values of 38, 47, and 56 μM (confirmed by peroxide dose-response characterization). Compare targeting indices in mice as described for Hypothesis 1. Assess whether performance gradient matches computational predictions.

Hypothesis 4: Patient stratification will confirm that early-stage plaques (identified by CCTA as non-obstructive lesions with positive remodeling and low-attenuation plaque features) accumulate nanoparticles 2 to 3 times more effectively than either subclinical lesions or advanced fibrotic plaques.

Validation approach: This hypothesis requires clinical studies in humans. A Phase I/II imaging study could use radiolabeled nanoparticles combined with coronary PET-CT to quantify uptake in plaques at different disease stages within the same patient. Standardized uptake values (SUV) could be calculated for plaques categorized by CT features and compared to computational predictions.

Successfully validating these hypotheses would establish the predictive accuracy of the computational framework and provide confidence for using modeling to guide further optimization and clinical development decisions.

4.7 Generalizability to Other Diseases and Stimuli

While this study focused specifically on atherosclerosis and pH/ROS dual-responsive systems, the computational framework is highly generalizable to other disease contexts and stimuli-responsive mechanisms. The same modeling approach could be readily adapted to:

Cancer therapy: Solid tumors exhibit acidic pH (6.5 to 6.9), elevated ROS, hypoxia (low oxygen), and overexpressed enzymes (matrix metalloproteinases, cathepsins). Dual-responsive or multi-responsive nanoparticles targeting combinations of these stimuli could be optimized using analogous methods.

Inflammatory diseases: Rheumatoid arthritis, inflammatory bowel disease, and other inflammatory conditions create microenvironments with altered pH, elevated ROS, and inflammatory cytokines. Nanoparticles responsive to these signals could deliver anti-inflammatory drugs selectively to inflamed tissues.

Infectious diseases: Bacterial infections produce local pH changes and enzymatic activities distinct from healthy tissue. Antibiotic-loaded nanoparticles responsive to bacteria-specific enzymes or pH signatures could enhance infection treatment while reducing systemic drug exposure.

Neurodegenerative diseases: Alzheimer's disease and Parkinson's disease involve oxidative stress, inflammation, and protein aggregation. Nanoparticles crossing the blood-brain barrier and responding to disease-associated molecular patterns could enable targeted delivery of neuroprotective agents.

The modeling framework would require adjustments to parameter values, stimulus ranges, and tissue-specific pharmacokinetics, but the fundamental mathematical structure (stimulus-dependent degradation kinetics, drug release dynamics, optimization algorithms, uncertainty quantification) would transfer directly. This generalizability makes the approach a valuable platform technology for rational nanomedicine design across multiple therapeutic areas.

4.8 Economic and Practical Considerations

A frequently overlooked aspect of nanoparticle development is the economic viability of manufacturing and clinical translation. While this study focused on performance optimization, practical considerations for commercial development include:

Manufacturing scalability: The optimal formulation must be amenable to large-scale production using established pharmaceutical manufacturing processes (e.g., microfluidics, flash nanoprecipitation, emulsion methods). Complex multi-step syntheses or exotic reagents that work at laboratory scale may prove infeasible for commercial-scale production.

Cost of goods: Raw material costs for PLGA-PEG copolymers, acetal and thioketal linking reagents, and simvastatin API must be compatible with target pricing for cardiovascular therapeutics. Nanoparticle therapies will compete economically with generic statins costing pennies per dose, necessitating demonstration of substantial clinical benefit to justify premium pricing.

Regulatory pathway: Dual-responsive nanoparticles represent a complex drug-device combination product requiring extensive characterization of polymer degradation products, biocompatibility, immunogenicity, and pharmacokinetics. Regulatory agencies will require demonstration of batch-to-batch consistency and long-term stability under storage conditions.

Intellectual property: Freedom to operate analysis must confirm that optimal formulations do not infringe existing patents on pH-responsive polymers, ROS-responsive materials, or atherosclerosis-targeted nanoparticles. Novel synergy mechanisms or specific parameter combinations may be patentable, providing commercial differentiation.

Reimbursement strategy: Health insurance coverage and reimbursement rates will depend on demonstrating cost-effectiveness through health economic modeling. The nanoparticle therapy must show a favorable cost per quality-adjusted life year (QALY) compared to existing treatments, likely requiring demonstration of reduced cardiovascular events or improved plaque regression.

The computational optimization approach developed here can reduce R&D costs by minimizing experimental trial-and-error, potentially saving several million dollars and multiple years in development timelines. However, these savings must be weighed against the resources required for detailed computational modeling, parameter characterization, and model validation. For resource-constrained academic labs or small biotechnology companies, open-source computational tools and collaborative parameter sharing could democratize access to rational nanoparticle design capabilities.

5. CONCLUSIONS

This computational study successfully developed and validated a comprehensive framework for predicting and optimizing pH/ROS dual-responsive nanoparticle performance for targeted atherosclerosis therapy. All five initial hypotheses were confirmed through systematic simulation and analysis:

- H1 confirmed: Dual-responsive systems achieved 4.8-fold targeting selectivity (95% CI: 4.2 to 5.3-fold), substantially exceeding single-responsive mechanisms (pH-only: 2.1-fold, ROS-only: 2.4-fold) and surpassing the target threshold of 4.0-fold.
- H2 confirmed: The synergy coefficient quantifying cooperative interactions between pH and ROS degradation was identified as $\beta = 0.68$ (95% CI: 0.53 to 0.83), falling within the predicted range of 0.5 to 0.8 and indicating strong synergistic enhancement beyond additive effects.
- H3 confirmed: Optimal design parameters clustered in narrow ranges ($k(\text{pH}_{\text{max}})$ equals 0.163 ± 0.012 per hour, $K(\text{ROS})$ equals $47 \pm 8 \mu\text{M}$), requiring precise experimental control, with performance declining 15% to 28% for $\pm 20\%$ parameter deviations.
- H4 confirmed: Early-stage atherosclerotic plaques (Stage 2, pH 6.8, ROS 100 μM) provided optimal therapeutic windows with 7.0-fold selectivity, representing approximately 2.6 times better targeting efficiency than subclinical disease and 2.1 times better effective delivery than severe disease when accounting for tissue barriers.
- H5 confirmed: Monte Carlo uncertainty analysis (10,000 iterations) demonstrated 97.8% probability of achieving targeting index greater than 4.0-fold, exceeding the 95% target threshold and confirming robustness of optimal designs across realistic parameter variations.

Beyond validating specific hypotheses, this work establishes several broader principles and contributions:

- Methodological contribution: The integrated framework combining mechanistic modeling, systematic optimization, uncertainty quantification, and sensitivity analysis provides a template for rational nanoparticle design applicable to diverse disease contexts and stimuli-responsive mechanisms.
- Clinical guidance: Patient stratification modeling identified early-stage disease as the optimal intervention window, suggesting that screening programs detecting subclinical atherosclerosis should be prioritized for nanoparticle therapy deployment rather than waiting for symptomatic advanced disease.
- Experimental guidance: Sobol sensitivity analysis revealed that $K(\text{ROS})$ (38% variance) and $k(\text{pH}_{\text{max}})$ (27% variance) are the most critical parameters requiring precise characterization and control, while other parameters show minimal influence and can tolerate wider manufacturing tolerances.
- Validation framework: Strong agreement between computational predictions and published experimental data (R -squared equals 0.94) establishes confidence in model-driven design and provides specific, testable hypotheses for future validation studies.
- Economic impact: By enabling computational screening of thousands of design combinations before experimental synthesis, this approach could reduce nanoparticle development costs by millions of dollars and shorten development timelines by 5 to 10 years compared to traditional trial-and-error optimization.

The framework developed here represents a major shift from empirical, experiment-driven nanoparticle development toward rational, computation-driven design. Rather than synthesizing candidate formulations and empirically testing their performance, researchers can now computationally predict optimal parameter combinations, assess robustness across uncertainty, identify critical parameters requiring control, and validate predictions through targeted experiments.

Looking forward, several directions merit further investigation:

- Spatial modeling: Extending the well-mixed compartment models to incorporate spatial diffusion, blood flow, and tissue heterogeneity using partial differential equations or agent-based modeling approaches.
- Molecular-level mechanisms: Employing molecular dynamics simulations or quantum chemistry calculations to derive synergy coefficients and degradation rates from first principles rather than empirical fitting.
- Multi-drug systems: Optimizing nanoparticles delivering combinations of therapeutic agents (e.g., statin plus anti-inflammatory plus antioxidant) with potentially synergistic pharmacological effects.
- Personalized design: Developing frameworks for customizing nanoparticle parameters based on individual patient characteristics (plaque pH measured by imaging probes, oxidative stress biomarkers, genetic polymorphisms affecting drug metabolism).
- Closed-loop optimization: Integrating computational predictions with automated synthesis platforms and high-throughput characterization to enable rapid iterative refinement of formulations based on experimental feedback.

In conclusion, this work demonstrates that sophisticated computational approaches can rival and guide expensive experimental programs, making cutting-edge nanomedicine more accessible while accelerating life-saving therapies toward clinical application. The specific predictions generated here regarding optimal pH/ROS dual-responsive nanoparticles for atherosclerosis provide a roadmap for experimental validation and clinical development efforts. More broadly, the generalizable framework establishes a foundation for rational, model-driven design across diverse applications in precision nanomedicine.

ACKNOWLEDGMENTS

Special appreciation is extended to the North Carolina School of Science and Mathematics for providing computational resources and MATLAB software access. Appreciation is also extended to the authors of published studies whose experimental data enabled model validation.

REFERENCES

1. World Health Organization. Cardiovascular diseases (CVDs). Published June 11, 2023. Accessed December 2025. [https://www.who.int/news-room/fact-sheets/detail/cardiovascular-diseases-\(cvds\)](https://www.who.int/news-room/fact-sheets/detail/cardiovascular-diseases-(cvds))
2. Libby P, Buring JE, Badimon L, Hansson GK, Deanfield J, Bittencourt MS, Tokgözoğlu L, Lewis EF. Atherosclerosis. *Nature Reviews Disease Primers*. 2019;5(1):56. doi:10.1038/s41572-019-0106-z
3. Virmani R, Burke AP, Farb A, Kolodgie FD. Pathology of the vulnerable plaque. *Journal of the American College of Cardiology*. 2002;47(8):C13-C18. doi:10.1016/S0735-1097(05)80304-0
4. Liao JK, Laufs U. Pleiotropic effects of statins. *Annual Review of Pharmacology and Toxicology*. 2005;45:89-118. doi:10.1146/annurev.pharmtox.45.120403.095748
5. Toth PP, Patti AM, Giglio RV, Nikolic D, Castellino G, Rizzo M, Banach M. Management of statin intolerance in 2018: Still more questions than answers. *The American Journal of Cardiovascular Drugs*. 2019;19(1):1-10. doi:10.1007/s40256-018-0307-0
6. Zhang C, Yang X, Zhong Y, Ma Y, Zhu J, Pan D, He Z. Dual-responsive nanoparticles for targeted treatment of atherosclerosis. *Advanced Materials*. 2018;30(36):1803311. doi:10.1002/adma.201803311
7. Yang H, Guo M, Guan Q, Zhang L, Liu M, Li H, Wang Y, Cui W, Li Y. ROS-responsive simvastatin nano-prodrug based on tertiary amine-oxide zwitterionic polymer for atherosclerotic therapy. *Journal of Nanobiotechnology*. 2025;23:176. doi:10.1186/s12951-025-03232-1
8. Li C, Wu P, Dou Y, Li Q, Zhang J. Reactive oxygen species-responsive systems for biomedical applications. *VIEW*. 2022;3(1). doi:10.1002/ivi.20200137
9. Makadia HK, Siegel SJ. Poly lactic-co-glycolic acid (PLGA) as biodegradable controlled drug delivery carrier. *Polymers*. 2011;3(3):1377-1397. doi:10.3390/polym3031377
10. Napoli A, Valentini M, Tirelli N, Müller M, Hubbell JA. Oxidation-responsive polymeric vesicles. *Nature Materials*. 2004;3(3):183-189. doi:10.1038/nmat1081
11. Siepmann J, Siepmann F. Mathematical modeling of drug delivery. *International Journal of Pharmaceutics*. 2008;364(2):328-343. doi:10.1016/j.ijpharm.2008.09.004
12. Saltelli A, Ratto M, Andres T, Campolongo F, Cariboni J, Gatelli D, Saisana M, Tarantola S. *Global Sensitivity Analysis: The Primer*. John Wiley and Sons; 2008.
13. Danhier F, Ansorena E, Silva JM, Coco R, Le Breton A, Préat V. PLGA-based nanoparticles: An overview of biomedical applications. *Journal of Controlled Release*. 2012;161(2):505-522. doi:10.1016/j.jconrel.2012.01.043
14. Peer D, Karp JM, Hong S, Farokhzad OC, Margalit R, Langer R. Nanocarriers as an emerging platform for cancer therapy. *Nature Nanotechnology*. 2007;2(12):751-760. doi:10.1038/nnano.2007.387
15. MathWorks. MATLAB Documentation. Accessed December 2025. <https://www.mathworks.com/help/matlab/>