

ND-i-003: Multi-scale composite baseline fit (10.0 mM CaCO3, pH 11.3, sub-spinodal)
Bimodal ACC nanospheres + dense liquid droplets (q ∈ [0.002, 2.54] nm−1)
Total unified fit (χ²red = 0.97)
Discrete ACC spheres (mode 1) (⟨R1⟩ = 138.8 nm, σ1 = 6.4 nm)
Discrete ACC spheres (mode 2) (⟨R2⟩ = 93.4 nm, σ2 = 35.0 nm)
Macroscopic droplets / Porod tail (⟨Rlg⟩ = 2626 nm, ϕlg = 6.12e − 05)
Solvent background (1.25e-05 cm−1)
Composite scattering data (ND-i-003, 10 mM)
Intensity I(q) [cm−1]
Residuals [σ]
Scattering vector q [nm−1]