

ND-i-002: multi-scale composite baseline fit (20.0 mM CaCO3, pH 11.3, spinodal gelation)
Spinodal fractal network + bimodal macroscopic droplets + Tanaka PNC mesh (q ∈ [0.002, 2.54] nm−1)
Composite scattering data (ND-i-002, 20 mM)
Total unified fit (χ²red = 0.46)
Spinodal fractal network (R = 11.4 nm, Dm = 1.85, ξ = 355 nm)
Bimodal macroscopic droplets (⟨R1⟩ = 1460 nm, ⟨R2⟩ = 5034 nm)
Tanaka viscoelastic fluctuations (ξfluc = 7.6 nm, Afluc = 0.018 cm−1)
Solvent background (1.26e-04 cm−1)
Intensity I(q) [cm−1]
Residuals [σ]
Scattering vector q [nm−1]