

ND-i-003: Multiscale Composite Baseline Fit (10.0 mM CaCO3, pH 11.3, Sub-spinodal)
Bimodal ACC Nanospheres + Dense Liquid Droplets (q ∈ [0.002, 2.54] nm−1)
Total Unified Fit (χ2red = 0.97)
Discrete ACC Spheres (Mode 1) (⟨R1⟩ = 138.8 nm, σ1 = 6.4 nm)
Discrete ACC Spheres (Mode 2) (⟨R2⟩ = 93.4 nm, σ2 = 35.0 nm)
Macroscopic Droplets / Porod Tail (⟨Rlg⟩ = 2626 nm, ϕlg = 6.12e − 05)
Solvent Background (1.25e-05 cm−1)
Composite Scattering Data (ND-i-003, 10 mM)
Intensity I(q) [cm−1]
Res. [σ]
Scattering Vector q [nm−1]