

ND-i-009: Multi-scale composite baseline fit (40.0 mM CaCO3, pH 10.0, pure benchmark)
Tanaka VPS network + droplet inversion + viscoelastic mesh (q ∈ [0.002, 2.5] nm−1)
Composite scattering data (ND-i-009, 40 mM, pH 10.0)
Total unified fit (χ²red = 3.22)
Spinodal fractal network (R = 9.40 nm, Dm = 1.98, ξ = 248 nm)
Macroscopic droplets / Porod tail (⟨R⟩ = 3196 nm)
Tanaka PNC fluctuation mesh (ξfluc = 14.66 nm)
Solvent background (0.00e+00 cm−1)
Intensity I(q) [cm−1]
Residuals [σ]
Scattering vector q [nm−1]