

Quality Control Plan

STOCK-QP-015_A

Fe6-01 Spring Washer

Revision	Date	Author	Checked by	Amendments
A	18/12/2024	 2024.12.18 14:41:39 +11'00'	 Digitally signed by Andrew Franklin Date: 2024.12.18 14:51:16 +11'00'	Initial Issue

Project	STOCK	Part Number	Fe6-01
Specification	SPEC-ACC-FE6	Drawing Number	ACC-Fe6-01


Quality Control Plan

Sample [] Trial-production [] Mass production [✓]	Main contact/Tel:	Prepared Date: 18/12/2024	Revise Date:
Core Team:		Approved date about the project (if necessary):	
		Approved date about the quality (if necessary):	
Supplier: Sudelan	Supplier No.:	Approved date (if necessary):	Approved date about others (if necessary):

No.	Description	Characteristic				Method					FAT
		Item	Part Name	Content		Criteria/ Nominal Value / Tolerance	Relevant Standard / Document / Drawing	Measuring Equipment	Min Sample Frequency	Control Method	
1	Fe6 Spring Washer	1	Raw Material 38Si7	Chemical Composition Test	C	0.35-0.42%	Delkor Specification SPEC-ACC-FE6	Various	1 per batch	Test Report	Document Review Only
					Si	1.50-1.80%					
					Mn	0.50-0.80%					
					P	≤0.025%					
					S	≤0.025%					
				Tensile Strength		1180-1370Mpa		Universal Testing Machine			
				Yield Strength		≥1030Mpa					
				Elongation at break		≥6.0%					
				Reduction of area after break		≥20%					
				Impact energy at room temperature KU ₂		≥9J					

Quality Control Plan

Sample [] Trial-production [] Mass production [✓]	Main contact/Tel:	Prepared Date: 18/12/2024	Revise Date:
Core Team:		Approved date about the project (if necessary):	
		Approved date about the quality (if necessary):	
Supplier: Sudelan	Supplier No.:	Approved date (if necessary):	Approved date about others (if necessary):

		2	Finished Product	Springiness on Release Test	• Meet value on manufacturing drawing for relieving spring way • Overall height after test must be within limits of manufacturing drawing	PROC-SWVT	Various	Single Sampling Plan, Special Inspection Level S-I, AQL 2.5 (ISO 2859-1)	Test Report	Document Review Only
				Texture Test	Smooth broken section without trace of internal cracking	Delkor Specification SPEC-ACC-FE6	Visual			
				Torsion Test	No cracks after twisting					
				Vickers Hardness	430 – 515 HV30		Hardness Tester			
				Dimensional accuracy	Inspection dimensions shown in reference document as per example below 	ACC-FE6-01	Various	Single Sampling Plan, General Inspection Level I, AQL 2.5 (ISO 2859-1)		
				Appearance	Identification and Markings as per reference document	ACC-FE6-01	Visual Inspection			
				Coating Thickness	Minimum Average ≥ 53µm	ISO 1461	Thickness Gauge	Single Sampling Plan, Special Inspection Level S-I, AQL 2.5 (ISO 2859-1)		