

苏州苏德兰铁路配件有限公司尺寸检测报告

DIMENSIONAL TEST REPORT

品名 Product Name: 螺纹道钉 Screw Spike

合同编号 Contract NO : 9429

规格 Size: 24×165

检测日期 Inspection date: 2025.07.18

等级 Grade: Gr5.6 , GB/T3098.1

发货日期 Date of shipment: 2025.12.30

标记 Mark : DEL 165-1 SDL 25 Ss8

序号 No	检测项目 Test feature	技术要求 Specification	实测数值 Actual Size	结果 Result
1	圆盘直径 head diameter	$\varnothing 44 \pm 1$	$\varnothing 43.4 \sim 43.8$	OK
2	方头顶长度 top of head length	26 ± 0.5	$25.8 \sim 26.3$	OK
3	方头底长度 bottom of head length	28 ± 0.5	$27.7 \sim 28.1$	OK
4	方头顶宽度 top of head breadth	19 ± 0.5	$18.8 \sim 19.4$	OK
5	方头底宽度 bottom of head breadth	21 ± 0.5	$20.7 \sim 21.1$	OK
6	方头高度 square head length	28 ± 1	$27.7 \sim 28.3$	OK
7	头部尖厚度 the height of head	3	$2.7 \sim 3.3$	OK
8	头部总高 head total length	$35 +2/-1$	$34.7 \sim 35.6$	OK
9	圆台厚度 head cup height	4	$3.7 \sim 4.3$	OK
10	头部R radius of head	R32	R32	OK
11	杆部直径 shank diameter	$\varnothing 24 +0.7/-0.3$	$\varnothing 23.9 \sim 24.4$	OK
12	螺纹内径 ID	$\varnothing 16 \pm 0.5$	$\varnothing 15.7 \sim 16.2$	OK
13	螺纹外径 OD	$\varnothing 24 \pm 0.5$	$\varnothing 23.7 \sim 24.2$	OK
14	白杆长度 unthreaded shank length	37 ± 2	$35.5 \sim 38.7$	OK
15	杆部总长 shank length	$165 +1/-5$	$160.4 \sim 165.8$	OK
16	单牙距 Single screw pitch	12.5 ± 0.1	$12.4 \sim 12.6$	OK
17	5牙距 screw pitch	62.5 ± 0.5	$62.2 \sim 62.6$	OK
18	牙高 screw height	4	$3.9 \sim 4.1$	OK
19	螺纹底部R角 Thread R angle	R1.5	R1.5	OK
20	螺纹底部R角 Thread R angle	R3	R3	OK
21	表面处理 surface treatment	热镀锌 $\geq 55\mu\text{m}$ Hot-dip Galvanise	$62 \sim 98$	OK
数量 Quantity			3000件 (Pieces)	
检验 Inspector			张全恢 Zhang-QuanHui	
审核 In Charge			杨黎程 Yang-LiCheng	

苏州苏德兰铁路配件有限公司性能检测报告

PERFORMANCE TEST REPORT

品名 Product Name: 螺纹道钉 Screw Spike

规格 Size: 24×165

等级 Grade :Gr5.6 , GB/T3098.1

标记 Mark : DEL 165-1 SDL 25 Ss8

合同编号 Contract NO: 9429

检测日期 Inspection date:2025.07.18

发货日期 Date of shipment: 2025.12.30

数量 Quantity: 3000(件 Pieces)

规格 Size	材料 Material	炉批号 Raw material Heat No	化学成分 CHEMICAL COMPOSITION (%)					机械性能 MECHANICAL PROPERTIES			结果 Result
			C	Si	Mn	P	S	屈服强度 Yield Strength	抗拉强度 Tensile Strength	延伸率 Elongation δ 5	
24×165	35K	G532004793	0.35	0.15	0.74	0.014	0.003	≥300Mpa	≥500Mpa	Min20%	
								379	602	24	OK
								390	621	22	OK
								361	611	23	OK
								355	597	24	OK
								374	605	23	OK

检验 Inspector: 张全恢 Zhang-QuanHui

审核 In Charge: 杨黎程 Yang-LiCheng



高速线材质量证明书

High-speed Wire Rod Quality Certificate

江苏沙钢集团有限公司
Jiangsu Shagang Group Co., LTD.

SG03B-1914E
江苏省张家港市锦丰镇 邮编: 215625
Jinfeng, Zhangjiagang, Jiangsu, P. R. CHINA
TEL: (0512) 58568866, 58568829
FAX: (0512) 58550366, 58550818

订货单位CUSTOMER		用户代码CUSTOMER CODE		合同号CONTRACT NO.	X55A00640009
牌号STEEL GRADE	SWRCH35K	提货单号DELIVERY	250522266002	发货日期DATE OF DELIVERY	20250522
交货标准 SPECIFICATION	Q/320582 SGY303-2024	质证书号CERTIFICATE NO.	2505222660026325	签发日期DATE OF ISSUE	20250522
		用途USE		精炼方式REFINING METHOD	炉外精炼

序号 NO	炉号 HEAT NO.	直径 Dia. mm.	盘数 Coils	重量 kg	化学成分CHEMICAL COMPOSITION %										拉伸试验TENSILE TEST			顶锻 试验 H. T.	硬度 试验 HRB	脱碳层 D. of. D	晶粒度 Micro- Grade	索氏体 Sorbite %	备注 REMARKS		
					C	Si	Mn	P	S	Cr	Ni	Cu				Rm	Rel							A11.3	Z
					2	2	2	3	3	2	2	2				MPa								%	
1	G532004793	24.0	14	31421	1= $\times 10^{-1}$ 2= $\times 10^{-2}$ 3= $\times 10^{-3}$ 4= $\times 10^{-4}$ 5= $\times 10^{-5}$										590			39.0	0	81.00	0.01	8			
					35	15	74	14	3	3	1	2				590			39.0	1/3	81.00	0.01			
合计 Total					14	31421	说明 NOTES 1. 本质量证明书适用于合金线材; 本产品不含有任何辐射元素。It is guaranteed that the products don't contain radiochemical imparities. 3. We, SHAGANG, hereby certify that the products specified in the present certificate have been fully processed in china. (facility angd address information is stated above. *1. H. T.—Head-colding Test; *2 D. of D.—Depth of Decarburization;																		
综合判定 FINAL RESULT		合格 PASS		注意事项 ATTENTIVE ITEMS 1. 质量证明书复印件不作有效证明文件, 除非盖章: The copy of this Certificate is not valid except stamped. 2. 用户验货后使用如有异议应及时告知炉号、牌号, 并保留实物及标志。Please inform us the steel grade and the heat number of under quanlified material(s) found in inspection on time, and keep the material(s) and the marking card										质检印章 SEAL 签证人 VISA											

