

苏州苏德兰铁路配件有限公司尺寸检测报告

DIMENSIONAL TEST REPORT

品名 Product Name: 螺纹道钉 Screw Spike

规格 Size: $\varnothing 23 \times 154$

等级 Grade: Gr5.6 , UIC864-1

标记 Mark: PANDROL SDL 5.6 GS54-B6 25

合同编号 Contract NO: CA2501835

检测日期 Inspection date: 2025.04.19

发货日期 Date of shipment: 2025.04.25



序号 No	检测项目 Test feature	技术要求 Specification	实测数值 Actual Size	结果 Result
1	圆盘直径 head diameter	$\varnothing 44 +0/-1$	43.3~43.7	OK
2	圆盘直径 head diameter	$\varnothing 40 +0/-1$	39.4~39.7	OK
3	方头顶宽度 top of head breadth	$21 +0/-1$	20.2~20.6	OK
4	方头底宽度 bottom of head	$23 +0/-1$	22.2~22.7	OK
5	头部高度 head total length	$20 +2/-0$	20.7~21.5	OK
6	头部R radius of head	R50	R50	OK
7	头部R radius of head	R10	R10	OK
8	头部R radius of head	$R2.5 +0.5/-0$	R2.5	OK
9	头部总高 head total length	$32 +2/-0$	32.7~33.5	OK
10	杆部直径 shank diameter	$\varnothing 23 -0.5/-1.8$	21.3~21.6	OK
11	杆部总长 shank length	154 ± 3	151.2~156.1	OK
12	白杆长度 unthreaded shank	50 ± 5	46.2~50.8	OK
13	螺纹内径 Core diameter	$\varnothing 16 +0/-1$	15.2~15.7	OK
14	螺纹外径 Outside diameter	$\varnothing 22 +0/-1$	21.1~21.6	OK
15	单牙距 single screw pitch	12 ± 0.1	11.95~12.05	OK
16	5牙距 screw pitch	60 ± 0.5	59.7~60.2	OK
17	牙高 screw height	3	2.9~3.1	OK
18	牙尖宽度 Tooth width	3	2.9~3.1	OK
19	螺纹底部R角 Thread R angle	$R1 +1/-0.5$	R1	OK
20	螺纹底部R角 Thread R angle	$R0.5 +0.5/-0$	R1	OK
21	螺纹头部R角 Thread R angle	$R1 +1/-0.5$	R1	OK
22	螺纹头部R角 Thread R angle	$R0.5 +0.5/-0$	R1	OK
23	尖部深度 Point depth	≤ 8	3.2~5.3	OK
24	表面处理 surface treatment	电镀白锌 $\geq 12 \mu m$ White Zinc plating	盐雾试验200小时无红锈 Salt spray test 200 hours without red rust	OK
数量 Quantity			50000件 (Pieces)	
检验 Inspector			张全恢 Zhang-QuanHui	
审核 In Charge			杨黎程 Yang-LiCheng	

苏州苏德兰铁路配件有限公司性能检测报告

PERFORMANCE TEST REPORT

品名 Product Name: 螺纹道钉 Screw Spike
规格 Size: $\varnothing 23 \times 154$
等级 Grade: Gr5.6, UIC864-1
标记 Mark : PANDROL SDL 5.6 GS54-B6 25

合同编号 Contract NO: CA2501835
检测日期 Inspection date: 2025.04.19
发货日期 Date of shipment: 2025.04.25
数量 Quantity: 50000 (件 Pieces)



规格 Size	材料 Material	炉批号 Raw material Heat No	化学成分 Chemical composition (%)					机械性能 Mechanical properties				结果 Result
			C	S	Si	Mn	P	屈服强度 Yield strength	抗拉强度 Tensile Strength	延伸率 Elongation δ5"	冷弯 Bend Test	
$\varnothing 23 \times 154$	35K	G431012119	0.36	0.002	0.13	0.74	0.018	$\geq 300\text{Mpa}$	$\geq 500\text{Mpa}$	Min20%	15°	
								381	613	22	OK	OK
								376	621	22	OK	OK
								392	628	22	OK	OK
								395	605	23	OK	OK
								389	619	22	OK	OK

检验 Inspector: 张全恢 Zhang-QuanHui

审核 In Charge: 杨黎程 Yang-LiCheng



江苏沙钢集团有限公司
Jiangsu Shagang Group CO., LTD.
高速线材质量证明书

SG03B-1914E

江苏省张家港市锦丰镇 邮编: 215625
Jinfeng, Zhangjiagang, Jiangsu, P. R. CHINA
TEL: (0512) 58568866, 58568829
FAX: (0512) 58550366, 58550818

沙钢 High-speed Wire Rod Quality Certificate

订货单位CUSTOMER	宁波办事处	用户代码CUSTOMER CODE	合同号CONTRACT NO.	X51D00020007
牌号STEEL GRADE	SWRCH35K	提货单号DELIVERY	发货日期DATE OF DELIVERY	20250127
交货标准 SPECIFICATION	Q/320582 SGV303-2024	质证书号CERTIFICATE NO.	签发日期DATE OF ISSUE	20250127
		用途USE	精炼方式REFINING MATHOD	炉外精炼

序号 NO	炉号 HEAT NO.	直径 Dia. mm.	盘数 Coils	重量 kg	化学成分CHEMICAL COMPOSITION %										拉伸试验TENSILE TEST			顶锻 试验 H.T.	硬度 试验 HRB	脱碳层 D.of.D	晶粒度 Micro- Grade	索氏体 Sorbite %	备注 REMARKS
					C	Si	Mn	P	S	Cr	Ni	Cu			Rm	Rel	A11.3	Z					
					2	2	2	3	3	2	2	2											
1	G431012119	22.0	18	40469	1= $\times 10^{-1}$ 2= $\times 10^{-2}$ 3= $\times 10^{-3}$ 4= $\times 10^{-4}$ 5= $\times 10^{-5}$										589			47.0	0	80.00	0.01	8	
2	G431012119	22.0	22	49509	36	13	74	18	2	2	1	1			589			47.0	1/3	82.00	0.01	8	
3	G431012404	24.0	15	33314	36	13	74	18	2	2	1	1			589			47.0	0	80.00	0.01	8	
4	G433009201	24.0	18	39521	35	15	75	17	2	3	1	1			584			44.0	0	80.00	0.01	8	
					34	13	75	15	5	3	1	1			583			46.0	1/3	81.00	0.01	8	
															583			46.0	0	82.00	0.01	8	

综合判定 FINAL RESULT		合格 PASS		注意事项 ATTENTIVE ITEMS		说明 NOTES		1. 质量证明书适用于合金线材; 本产品不含有任何辐射元素。It is guaranteed that the products don't contain radiochemical imparities. 3. We, SHAGANG, hereby certify that the products specified in the present certificate have been fully processed in china. (facility and address information is stated above. *1. H. T. —Head-colding Test; *2 D. of D. —Depth of Decarburization;		签证人 VISA  	
合计 Total		73		162813							