



Quality Control Plan
STOCK-QP-012
FE15-01

Revision	Date	Author	Checked By	Amendments
A	12/08/2024	 2024.08.12 09:59:18 +10'00'	 Andrew Franklin 2024.08.12 10:19:05 +10'00'	Initial Issue

Project	STOCK	Part Number	FE15-01
Specification	SPEC-ACC-FE6	Drawing Number	ACC-Fe15-01


Quality Control Plan

Sample [] Trial-production [] Mass production [✓]			Main contact/Tel:		Prepared Date: 12/08/2024		Revise Date:	
Core Team:					Approved date about the project (if necessary):			
					Approved date about the quality (if necessary):			
Supplier: Sudelan		Supplier No.:		Approved date (if necessary):		Approved date about others (if necessary):		

No.	Description	Characteristic			Method					FAT		
		Item	Part Name	Content	Criteria/ Nominal Value / Tolerance	Relevant Standard / Document	Measuring Equipment	Min Sample Frequency	Control Method			
1	Material	1	Spring Washer 38Si7	Chemical Composition Test	C	0.35-0.42%	Delkor Specification SPEC-ACC-FE6	Various	1 per batch of raw material	Test report	Document review only	
					Si	1.50-1.80%						
					Mn	0.50-0.80%						
					P	≤0.025%						
					S	≤0.025%						
				Tensile Strength		1180-1370Mpa		Universal Testing Machine				
				Yield Strength		≥1030Mpa						
				Elongation at break		≥6.0%						
				Reduction of area after break		≥20%						
				Impact energy at room temperature KU ₂		≥9J						Impact Testing Machine

Quality Control Plan

Sample [] Trial-production [] Mass production [✓]			Main contact/Tel:		Prepared Date: 12/08/2024		Revise Date:	
Core Team:					Approved date about the project (if necessary):			
					Approved date about the quality (if necessary):			
Supplier: Sudelan			Supplier No.:		Approved date (if necessary):		Approved date about others (if necessary):	

2	Finished Product	1	Fe15 Spring Washer	Springiness on Release Test	• Meet value on manufacturing drawing for relieving spring way • Overall height after test must be within limits of manufacturing drawing	PROC-SWVT	Various	Single Sampling Plan, Special Inspection Level S-I, AQL 2.5 (ISO 2859-1)	Test report	Document review only
				Texture Test	Smooth broken section without trace of internal cracking	Delkor Specification SPEC-ACC-FE6	Visual			
				Torsion Test	No cracks after twisting					
				Vickers Hardness	430 – 515 HV30					
				Dimensional accuracy	Inspection dimensions shown in reference document as per example below 	ACC-FE15-01	Various	Single Sampling Plan, General Inspection Level I, AQL 2.5 (ISO 2859-1)		
				Appearance	Identification and Markings as per reference document	ACC-FE15-01	Visual Inspection			
Coating Thickness	Minimum Average $\geq 53\mu\text{m}$	ISO 1461	Thickness Gauge	Single Sampling Plan, Special Inspection Level S-I, AQL 2.5 (ISO 2859-1)						