

苏州苏德兰铁路配件有限公司尺寸检测报告

DIMENSIONAL TEST REPORT

品名 Product Name: 螺纹道钉 Screw Spike

合同编号 Contract NO: PC26-00563

规格 Size: $\Phi 25 \times 159$

检测日期 Inspection date: 2026.04.09

等级 Grade: Gr5.6, UIC864-1

发货日期 Date of shipment: 2026.04.11

标记 Mark: PANDROL 26 5.6 GS195-J7 SDL

序号 No	检测项目 Test feature	技术要求 Specification	实测数值 Actual Size	结果 Result
1	对边尺寸 opposite side	$27 +0/-1$	26.1~26.4	OK
2	头部厚度 head thickness	15.5 ± 0.5	15.3~15.8	OK
3	头部R radius of head	R2	R2	OK
4	头部R radius of head	$R2 \pm 0.5$	R2	OK
5	头部角度 Head Angle	15°	15°	OK
6	头部总高 head total length	$20 +1.5/-0$	20.4~20.9	OK
7	圆盘直径 head diameter	$\Phi 40 +0/-1$	39.5~39.8	OK
8	圆盘直径 head diameter	$\Phi 42 +3/-1$	41.4~41.7	OK
9	杆部直径 shank diameter	$\Phi 25 +0.7/-0.5$	24.6~25.1	OK
10	白杆长度 unthreaded shank length	55 ± 5	50.7~55.8	OK
11	杆部总长 shank length	159 ± 3	156.2~161.4	OK
12	螺纹内径 ID	$\Phi 19 +0/-1$	18.1~18.6	OK
13	螺纹外径 OD	$\Phi 25 +0/-1$	24.1~24.6	OK
14	5牙距 screw pitch	60 ± 0.5	59.7~60.3	OK
15	单牙距 single screw pitch	12 ± 0.1	11.95~12.05	OK
16	螺纹底部R角 Thread R angle	$R0.5 +0.5/-0$	R1	OK
17	螺纹底部R角 Thread R angle	$R1 +1/-0.5$	R1	OK
18	螺纹头部R角 Thread R angle	$R0.5 +0.5/-0$	R1	OK
19	螺纹头部R角 Thread R angle	$R1 +1/-0.5$	R1	OK
20	牙尖宽度 Tip width	3	2.9~3.1	OK
21	螺纹角度 Thread angle	30°	30°	OK
22	螺纹角度 Thread angle	30°	30°	OK
23	尖部深度 Point depth	≤ 8	4.3~5.8	OK
24	表面处理 surface treatment	热镀锌 $\geq 50 \mu m$ Hot-dip Galvanise	61~106	OK
数量 Quantity			7240件 (Pieces)	
检验 Inspector			张全恢 Zhang-QuanHui	
审核 In Charge			杨黎程 Yang-LiCheng	

苏州苏德兰铁路配件有限公司性能检测报告

PERFORMANCE TEST REPORT

品名 Product Name: 螺纹道钉 Screw Spike

规格 Size: $\Phi 25 \times 159$

等级 Grade: Gr5.6 , UIC864-1

标记 Mark : PANDROL 26 5.6 GS195-J7 SDL

合同编号 Contract NO : PC26-00563

检测日期 Inspection date: 2026.04.09

发货日期 Date of shipment: 2026.04.11

数量 Quantity: 7240 (件 Pieces)



规格 Size	材料 Material	炉批号 Raw material Heat No	化学成分 Chemical composition (%)					机械性能 Mechanical properties				结果 Result
			C	S	Si	Mn	P	屈服强度 Yield strength	抗拉强度 Tensile Strength	延伸率 Elongation δ5"	冷弯 Bend Test	
$\Phi 25 \times 159$	35K	G633100351	0.35	0.002	0.12	0.73	0.017	$\geq 300\text{Mpa}$	$\geq 500\text{Mpa}$	Min20%	15°	
								389	631	21	OK	OK
								381	606	23	OK	OK
								360	628	22	OK	OK
								374	611	22	OK	OK
								371	602	23	OK	OK

检验 Inspector: 张全恢 Zhang-QuanHui

审核 In Charge: 杨黎程 Yang-LiCheng



高速线材质量证明书

江苏沙钢钢铁有限公司
Jiangsu Shagang Steel CO., LTD.

SG03B-1914E

沙钢

High-speed Wire Rod Quality Certificate

江苏省张家港市锦丰镇 邮编: 215625
Jinfeng, Zhangjiagang, Jiangsu, P. R. CHINA
TEL: (0512) 58568866, 58568829
FAX: (0512) 58550366, 58550818

订货单位CUSTOMER		用户代码CUSTOMER CODE		合同号CONTRACT NO.	
牌号STEEL GRADE	SWRCH35K	提货单号DELIVERY	260120112001	发货日期DATE OF DELIVERY	20260121
交货标准 SPECIFICATION	Q/320582 SGY303-2024	质证书号CERTIFICATE NO.	2601201120 013716	签发日期DATE OF ISSUE	20260121
		用途USE		精炼方式REFINING METHOD	炉外精炼

序号 NO	炉号 HEAT NO.	直径 Dia. mm.	盘数 Coils	重量 kg	化学成分CHEMICAL COMPOSITION %										拉伸试验TENSILE TEST			顶锻 试验 H. T.	硬度 试验 HRB	脱碳层 D. of. D	晶粒度 Micro- Grade	索氏体 Sorbite %	备注 REMARKS		
					C	Si	Mn	P	S	Cr	Ni	Cu				Rm	Rel							A11.3	Z
					2	2	2	3	3	2	2	2				MPa								%	
1	G633100351	26.0	15	33670	1= $\times 10^{-1}$ 2= $\times 10^{-2}$ 3= $\times 10^{-3}$ 4= $\times 10^{-4}$ 5= $\times 10^{-5}$										571			47.0	0	79.00	0.01	9			
					35	12	73	17	2	0	0	1			571			47.0	1/3	80.00	0.01	9			
合计 Total					15	33670	说明 NOTES 1. 本质量证明书适用于合金线材;本产品不含有任何辐射元素。It is guaranteed that the products don't contain radiochemical impurities. 3. We, SHAGANG, hereby certify that the products specified in the present certificate have been fully processed in china. (facility and address information is stated above. *1. H. T.—Head-colding Test; *2 D. of D.—Depth of Decarburization;																		
综合判定 FINAL RESULT		合格 PASS		注意事项 ATTENTIVE ITEMS		1. 质量证明书复印件不作有效证明文件, 除非盖章; The copy of this Certificate is not valid except stamped. 2. 用户验货后使用如有异议应及时告知炉号、牌号, 并保留实物及标志。Please inform us the steel grade and the heat number of under quanlified material(s) found in inspection on time and keep the material(s) and the marking card 质检印章 SEAL 签证人 VISA																	签字 [Signature]		