



ARTROM STEEL TUBES S.A.

Draganesti Str. 30, Slatina, jud. OLT, Romania 230119
 Tel: +40 (249) 434640, 434641 Fax: +40 (249) 437288, 430055
 E-mail: office@artrom.com www.artrom.com
 EUID: ROONRC.J1991000009283; J1991000009283; VAT No. RO 151021
 Subscribed and Paid Share Capital: 291.587.538,34 lei



Digitally signed by ARTROM STEEL TUBES SA
 This document is certified to be electronically
 controlled and approved.
 Signature requested by Maria Carmen Iancu
 on 2025-09-09 07:48:37 +03:00
 The original electronic document can be retrieved
 by scanning the QR code in the left.

INSPECTION CERTIFICATE - EN 10204: 2004 / 3.1

No.: E16581 Date: 04.09.2025	Manufacturer's mark:	Customer order no.: 4100002125	PL: 14999
CUSTOMER: --			
Specifications: EN 10216-2:24 / ASTM A106:19 / ASME SA106:21		Dimensions: 60.3 x 3.2 x 12000 to 12100 mm Steel: P235GH TC1 / P265GH TC1 / Gr. B	
Description: Hot rolled seamless steel pipes with bevelled ends; oiled; marking by painting at one end: ARTROM, standard, steel grade, dimensions, 4.51 Kg/m, TEST PRESSURE 17.0 MPa, S, heat no., LOT, LENGTH (m), mill inspector no. 5, technical control sign.			
Heat no.: R65126		Lot no.: 597155	
Quantity	Pcs.	Length m	Weight kg
	44	528.00	2394

Ladle Chemical Analysis (%)

Heat no.	C	Mn	S	P	Si	Ni	Cr	Mo	Cu	Al	Nb	Ti	V
R65126	0.12	0.54	0.002	0.010	0.20	0.09	0.07	0.02	0.21	0.028	0.001	0.001	0.001
Nb+V: 0.002							V+Nb+Ti: 0.003						

Mechanical Properties

TENSILE TEST (1. EN ISO 6892-1 / 2. ASTM A370) - at room temperature - Test Specimen / Strip-longitudinal		Rp0.2 MPa	Rm MPa	Elongation %
Dimension - Specimen (mm): 1. 15.25 x 3.3 / 2. 19.25 x 3.45	1.	372	461	35
Section - Specimen (mm ²): 1. 50.93 / 2. 67.69	2.	369	467	36
Length - Specimen (Lo) (mm): 1. 40 / 2. 50.8				

Heat treatment: normalized with temperature between 880°C - 940°C, cooled in still air
 Hydraulic test pressure (ASTM A530): 17.0 MPa for 5 sec: OK
 Flattening test (EN ISO 8492): OK
 Drift expanding test (EN ISO 8493): OK
 Bending test (ASTM A106 point 11): OK

Melting process: electric arc furnace, fully killed
 Hardness HRB: 74 - 75
 Hardness HRC max. 22
 (acc. to NACE MR0175/ISO15156:2022 /
 NACE MR0103/ISO 17945:2015)

Visual inspection and dimensional check: OK

NO WELD REPAIR ON HEREBY CERTIFIED TUBES

The manufacturer of pipes is certified in acc. with ISO 9001: 2015, ISO 14001:2015 and ISO 45001:2018

The material "not contain intentional additions of elements such as lead, selenium, or sulphur to improve machinability"

Our tubes are rolled from steel with low carbon footprint, carefully melted in our own

Romanian facilities only by recycling the ferrous scrap using 100% certified green electricity.

Our products do not incorporate steel products originating in Russia and Belarus, fully complying with the Regulations (EU) No 833/2014 and 765/2006. Steel melt by ARTROM STEEL TUBES Resita, ROMANIA.

CHIEF OF QC & TESTING OF THE METALLURGICAL TUBES PRODUCTS

Dipl. Eng. Silviu Barbulescu



MILL INSPECTOR

Eng. Constantin Lupu



This IC is digitally signed and sealed by ARTROM STEEL TUBES S.A. IT system. To check its authenticity and integrity, please scan the QR code to download the original electronic document from our site. If you already received an electronic copy from your supplier, please make sure that the file is digitally signed by ARTROM STEEL TUBES S.A. Falsification of this document is punishable under the legal provisions and entitles us to claim damages.

THIS IS FOR CERTIFY THAT THE MATERIAL HEREIN DESCRIBED HAS BEEN MANUFACTURED WITH THE ORDERED SPECIFICATION AND THAT INFORMATION IS CORRECT, THEY MEET THE SPECIFICATION'S REQUIREMENTS AND ARE RECORDS IN OUR COMPANY DOCUMENTS.