MESCİER®
DEMİR ÇELİK SAN.VE TİC. A.Ş.

MILL TEST CERTIFICATE

THE INSPECTION CERTIFICATE AS PER EN 10204 CLAUSE 3.1 CONFORMING TO THE DEFINITION IN EN 10168

10.03.2026

CERTIFICATE NO	381-2026
COMMODITY	
STANDARD OF GRADE OF PRODUCT	EN 10025-1-2 / 2019
SIZE AND SHAPE TOLERANCES STANDARDS	EN 10056-2 FOR EQUAL, EN 10279 FOR U, EN 10024 FOR I, 10034 FOR İ-H, EN 10058 FOR FLAT,10059 FOR SQUARE, 10060 FOR ROUND SDANDARDS APPLY
TEST STANDARDS	EN ISO 6892 -1/ EN İSO 148-1
DELIVERY RECUIREMENTS STANDART FOR SURFA	EN 10163-3

SHIPPER	MESCİER D.Ç. SAN. TIC. AŞ. ŞTİ.		
CUSTOMER	**YAKUP YILMAZ BORU PROFİL YAPI MALZEMELERİ İNŞAAT MAKİNA DIŞ TİCARET SANAYİ VE TİCARET ANONİM ŞİRKETİ TURGUT ÖZAL 2 BLV. 06080 GÜLTEPE MAH. ALTINDAĞ/ ANKARA**		
VESSEL			
İRSALİYE NO:			
ORDER NO		PAGE	

							MECHANICAL PROPERTIES								CHEMICAL COMPOSITION																	
							TENSION TEST					CHARPY TEST			PRODUCT ANALYSIS																	
TEST PIECES NO	HEAT NO	SIZE (mm)	QUALITY	PCS (BNDL)	LENGHT (m)	WORK ORDER	ORIENTATION(3)	YIELD S. (Re)	TENSİLE S.(Rm)	Rm / Re	ELONGATİON	TEST PIECES WİDTH (mm)	AVERAJ VALUE (JOULE)	TEST TEMPRATURE(°C)	C	Si	Mn	P	S	Ti	Cu	Ni	Cr	Mo	V	Al	W	Nb	N	CARBON EQUIVALENT		
								N/mm2			%				%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	(CEV)		
	26M020183	50X50X5	S235JR					330,5	471,4	1,43	30,2				0,17	0,19	0,58	0,010	0,008	0,005	0,17	0,14	0,14	0,020	0,012	0,009	0,011	0,004	0,000	0,32		
	26M020179	50X50X5	S235JR					323,8	468,7	1,45	30,9				0,16	0,18	0,577	0,011	0,009	0,005	0,17	0,12	0,14	0,017	0,012	0,009	0,014	0,003	0,000	0,31		
	26M020189	50X50X5	S235JR					331,4	473,9	1,43	31,9				0,15	0,27	0,56	0,010	0,013	0,005	0,18	0,20	0,14	0,024	0,011	0,029	0,017	0,007	0,000	0,31		
	26M020211	50X50X5	S235JR					303,4	438,4	1,44	32,9				0,14	0,21	0,522	0,008	0,009	0,005	0,13	0,15	0,14	0,016	0,013	0,016	0,015	0,004	0,000	0,28		
	2501388	100X100X10	S235JR					304,5	432,1	1,42	28,0	8	98	23	0,14	0,22	0,624	0,010	0,028	0,000	0,30	0,15	0,09	0,029	0,0031	0,006	0,005	0,001	0,008	0,30		
	26M020126	120 NPU	S235JR					311,0	442,6	1,42	36,9	8	107		0,12	0,22	0,533	0,011	0,006	0,005	0,15	0,17	0,12	0,021	0,012	0,021	0,017	0,002	0,000	0,26		

SURVEYOR TO

NOTES:

WE HEREBY CERTIFY THAT THE MATERIAL HEREIN HAS BEEN MADE AND TESTED IN ACCORDANCE WITH ABOVE SPECIFICATION AND THE RESULTS OF ALL TEST ARE ACCEPTANCE

(1) VALUES ARE FOR KV300

(2) BEND AND REBEND TESTS ARE FOR ONLY RİBBED REINFORCING STEELS

(3) "L" MEANS "LOGITUDINAL" "T" MEANS "TRANSVERSE"

(4) (NUMBER OF CYCLES X 1000000)

QUALITY CONTROL DEPARTMENT

MESCİER®
KARABÜK V.D. 619 052 9911