

# Selective Laser Sintering for sustainable polymers

Giorgio De Trane

March 30, 2022



*Year 2021/2022*

# Contents

<b>1</b>	<b>Introduction</b>	<b>3</b>
1.1	Polymers in Additive Manufacturing . . . . .	3
1.2	Common AM techniques for polymers . . . . .	4
1.2.1	FDM (Fused Deposition Modeling) . . . . .	5
1.2.2	SLS (Selective Laser Sintering) . . . . .	6
<b>2</b>	<b>PHAs (Polyhydroxyalkanoates)</b>	<b>8</b>
2.1	PHA and Additive Manufacturing . . . . .	9
2.1.1	PHBH . . . . .	9
<b>3</b>	<b>PBS (Polybutylene Succinate)</b>	<b>10</b>
<b>4</b>	<b>PBAT (Polybutylene Adipate Terephthalate)</b>	<b>10</b>
<b>5</b>	<b>Powder production for SLS</b>	<b>10</b>
5.1	Powder requirements for SLS . . . . .	10
5.2	Mechanical milling . . . . .	12
5.3	Chemical precipitation . . . . .	12

# 1 Introduction

*Additive manufacturing* (AM) is a broad term that encompasses several manufacturing techniques, characterized by their additive nature, as the name suggests, in contrast with more traditional subtractive processes.

AM techniques are applied to a vast range of materials, including ceramics, polymers and metal alloys, some of which are specifically developed or optimized to these kinds of applications.

The main advantage of AM is the ability to produce complex shapes in a relatively short time. These geometries are either too hard or even impossible to reproduce with subtractive manufacturing techniques, which often require multiple steps, using different pieces of equipment, trained personnel, etc.

Given the same material, the complex shapes allowed by AM can replace components made of multiple assembled parts with a unique solid piece of comparable or even better mechanical properties.

The inherent flexibility of AM often allows product designers to simplify or even entirely bypass the very strict CAD workflow (which is intrinsically tied to traditional manufacturing processes) and make use of organic and/or generative modeling.

As a consequence of better design choices and minimal need of post-processing of AM objects, far less raw material is wasted, compared to subtractive manufacturing techniques, leading to long term lowering of costs, faster design-to-market pipelines and, last but not least, lower emissions and environmental impact [9].

## 1.1 Polymers in Additive Manufacturing

Polymers and their composite materials have been used in all sorts of fields, ranging from arts and crafts all the way to advanced biomedical and aerospace applications, thanks to their unique and varied extended range of properties.

The rapid advancement of AM, where polymers have been extensively used for prototyping, in the form of resins, filaments, powders and viscous inks, has increased the demand for high-performance polymers, in order to take advantage of their quicker printing times (compared to metals) as well as their lower cost, while still maintaining good mechanical properties for an end product, rather than just a prototype [9].

The urge for drastically reducing the environmental impact of human activities involves every production field, including AM, which can be inherently less impactful than traditional manufacturing processes, given the same material and final product to achieve.

A consequence of the concerns about climate change and its potentially catastrophic outcomes is the research in the field of eco-friendly materials, including polymers that could be used in AM.

A great example is *PLA* (PolyLactic Acid), a polymer widely used in 3D printing, whose monomer is obtained by fermenting starches, such as corn starch.

Many new eco-friendly polymers have been and are currently being studied for AM techniques, but this case study will focus mostly on materials that can be potentially turned into powders for *PBF* (Powder Bed Fusion) techniques or filaments for *ME* (Material Extrusion).

## 1.2 Common AM techniques for polymers

Polymers can be processed with several AM techniques, including, but not limited to:

- **VP** (Vat Photopolymerization), which make use of UV lights (or other radiations) to solidify photosensitive resins. This class of AM processes can produce parts with the highest resolution among all AM methods [9, 4];
- **MJ** (Material Jetting), which consist of a deposition of viscous fluids (either in droplets or in a continuous fashion), solidified by different agents (time interacting chemicals, heating, cooling, drying, photopolymerization, etc.). These processes include several patented methods, characterized by high speed printing [9];
- **PBF** (Powder Bed Fusion), where the object is printed by locally fusing a powder bed (with a pulsing energy source -such as lasers- or with a local deposition of chemicals), layed out in a layer-by-layer fashion [9, 4];
- **ME** (Material Extrusion), where each layer is printed by direct deposition of materials through a nozzle, that solidify as they cool down [9, 4];
- **BJ** (Binder Jetting), similarly to 2D inkjet printing utilizes a polymer in the form of a liquid binder, that gets deposited in droplets onto a powder bed (usually made of metallic or ceramic particles). This method can build large parts without support structures and the lack of a high power heat source cuts its cost down, but the structural properties of the final parts are poor compared to sinterized equivalents, making heat treatments necessary [9];
- **Sheet Lamination**, where thin sheets of material are stacked together and bonded with adhesives or heat. This class of techniques is not entirely additive, since subtractive processes are used to cut and refine the final part, creating substantial material waste [9].

### 1.2.1 FDM (Fused Deposition Modeling)

FDM is a ME technique and the most well known AM process, commonly named 3D printing in popular media.

The process consists of a direct layer-by-layer deposition of a thermoplastic filament, heated up to its melting point (or enough to soften it until it reaches an optimal flow) and extruded through a nozzle [9, 4].

The nozzle is generally moved in the x-y plane until a layer is completed with the desired infill, then either the extruder head or the growth plate are moved along the z axis, initiating the printing of the subsequent layer.

The planar infill and the resolution on the z axis will determine the quality of the final print for a given material and geometry, in terms of density and visual appeal.

For a given planar infill, the z axis resolution greatly influences the final look of the part, as well as printing times: modern slicing software can analyze the geometry and generate an adaptive resolution, reducing the number of layers where the local curvature of the object is within a certain threshold and increasing it when necessary.

This approach can produce good quality parts, while reducing printing times.

FDM has gained a lot of popularity in the last few years, given its general ease of use, relatively low cost of both materials and equipment and its growing community of enthusiasts.

A wide variety of materials can be used with this technique, including (but not limited to) *PLA*, *ABS*, *PET*, *PETG*, *HIPS*, *TPU*, *nylon*.

### 1.2.2 SLS (Selective Laser Sintering)

*SLS* is a manufacturing process in the PBF family.

A powder bed is layed out onto a platform and a focused heat source (a laser) locally sinters the powder, until a single layer is completed [9, 4].

A mechanism swipes out the remaining powder, which is recollected and automatically redistributed by a recoating system for each subsequent layer [1].

This process is similar to *SLM* (Selective Laser Melting), typically used with metal alloys: in *SLS* the energy input is not high enough to bring the powders to their melting point, but sufficient for sinterization of the powders.

Despite the slight difference, many sources use the terms interchangeably, often effectively referring to *SLM* in metal manufacturing.

When it comes to thermoplastic materials, the required laser power to sinter each layer is substantially lower than that needed for metals.

*SLS* printers can be considerably more expensive than *FDM* machines of similar printing volume, but the advantages they offer, in terms of customizability, superior consistency in print quality and accuracy, higher production rate, less need for support structures, makes them a more cost effective solution for larger scale industrial production, whereas *FDM* printers are still more established in the hobbyists and enthusiasts market [1].

Generally speaking, *SLS* is a three stage process, consisting of:

- warm up (A)
- building (B)
- cooling (C)




Figure 1: Phases of an *SLS* process [7, 1]

As seen in figure (1), the first phase is the time required to reach a specific powder bed temperature ( $T_b$ ), based on the chosen material.

Ideally this temperature should be maintained constant inside the printing chamber, during the entire printing phase, through infrared or electric heaters. The main goal is avoiding drastic temperature gradients in different areas of the printed part, since they can cause visual artefacts such as local or global deformation and, most importantly, uneven residual mechanical tension that can rapidly degrade the structural integrity of the final piece, especially in structural components that might be placed under static or dynamic loads.

Once the final piece is printed, the entire chamber is cooled down homogeneously and gradually, until the equilibrium is reached at room temperature ( $T_e$ ) [1].

Quality standards for *SLS* printed parts have increased dramatically over the last few years, to the point where the manufactured components are not exclusively used for prototyping or as sacrificial items for investment casting, but they are used as finalized industrial grade parts.

However, there is still room for substantial improvements in the consistency of print accuracy, overall quality, reliability and scalability of the entire process, compared to more traditional manufacturing techniques.

The variety of physical phenomena involved in SLS, the fact that they can be interdependent and their different temporal regimes are the main source of complexity that makes the process very hard to study and inconsistent.

The most predominant phenomena are the following [1]:

- Laser motion and irradiation
- Thermal diffusion
- Polymer viscous flow and particle coalescence
- Powder spreading
- Solidification/crystallization

Further improvements are required in order to reduce the amount of discarded parts (still comparatively higher than most consolidated manufacturing techniques), usually defective in terms of porosity or thermal distortion or warping [1].

The next chapters will focus on potential SLS materials for this case study and their powder production specifically.

## 2 PHAs (Polyhydroxyalkanoates)

*PHAs* are a family of thermoplastic polyesters, obtained by hydroxyalkanoic acids via bacterial fermentation, under nutrient depletion and carbon excess conditions [4, 3].

They are a sustainable alternative to petrochemical polymers commonly utilized in additive manufacturing and they are mostly used for prototyping in the medical field [4, 3].

Similarly to other sustainable plastics, *PHA* can be produced using industrial byproducts as substrates (corn, soy, coffee, oil wastes, etc.) [4].

The monomer composition of *PHA* can be very diverse, depending on the microorganisms involved and the fermentation medium.

This variety impacts the overall mechanical, thermal and chemical properties of the final plastic, which depend on the concentration of different monomers in polymers and copolymers.

*PHAs* can be classified by the chain-length of their monomers [3]:

- *scl-PHA* (short-chain-length *PHA*) with 3 to 5 carbon atoms
- *mcl-PHA* (medium-chain-length *PHA*) with 6 to 14 carbon atoms
- *lcl-PHA* (long-chain-length *PHA*) with more than 14 carbon atoms

Estimating the exact meaningful measures of these properties is not always a straight-forward process, since manufacturers are not transparent about the exact composition of their products, which may be improved by additives, whose percentage is not often fully disclosed [4].

The market for bioderived *PHA* has gradually increased over the years and the growth is estimated to keep its pace, given that not only are they more sustainable to competing petrochemical polymers, but they offer additional valuable properties, such as piezoelectricity and protection against gases and UV lights [4].

Their bio-origin, non-toxicity, renewability, biodegradability and biocompatibility make *PHAs* a very compelling product in the ever growing market of sustainable materials.

However, these desirable qualities are a contributing factor to their higher price, which is still not competitive with more established polymers of similar properties [4].

The increasing demand and the improvements on their biosynthesis will make their price more accessible in the future, for all sorts of applications, including additive manufacturing, where *PHAs* can be printed successfully either with FDM or SLS techniques.



## 2.1 PHA and Additive Manufacturing

PHAs can be used in different AM techniques, including Stereolithography, which is part of VP processes (1.2), Fused Deposition Modeling (1.2.1), where the filaments are made of a mixture of PHA and PLA, (which increases thermal stability and cuts down cost), and Selective Laser Sintering (1.2.2) [4].

This case study will focus on its usage in SLS.

PHAs have been successfully printed via SLS and utilized in the medical field as scaffolds for tissues engineering applications.

These scaffolds can be printed with a porous structure (controlled by the laser energy density), which could carry biomolecules and release drugs, for instance. Unlike with FDM applications, where PHA can not be used as a standalone filament, but needs PLA addition in order to stabilize its melting phase, PHA powders in SLS maintain a good stability and their chemical composition does not get altered as easily.

This is a clear advantage, since the overall properties of the final products do not change drastically from its starting powder, and, in addition to this, the remaining powder is not thermally altered close to the melting pool, meaning that it can be reused for additional printing [4].

### 2.1.1 PHBH

Can't find anything RN

### 3 PBS (Polybutylene Succinate)

### 4 PBAT (Polybutylene Adipate Terephthalate)

### 5 Powder production for SLS

Manufacturing raw materials for FDM is a relatively easy process, since the plastics need to be mass produced into filaments or pellets [1.2.1](#).

Producing powders from plastics is a much harder process.

Two radically different approaches are possible, each with its own critical issues:

- Mechanical milling
- Chemical precipitation

#### 5.1 Powder requirements for SLS

The success rate of SLS prints is highly dependent on the characteristics of the powders involved.

The key factors in powder quality are particle size distribution, morphology, as well as thermal, flow and optical properties.

Ideally, a gaussian distribution, with most particles close to the average size is desirable, with a typical range of  $(20 \div 80) \mu m$  [\[8\]](#).

The average particle size directly influences the layer thickness in the SLS process.

Particle morphology is crucial in the sintering mechanism, where regular, smooth and non-hollow spherical geometries are preferable [\[8\]](#).

The powder's density is another parameter that should be considered, as it directly correlates with the final part's global density and it allows calculation of the Hausner ratio  $H_r$ , which is a direct predictor of powder flowability.

Ideally, this coefficient should be lower than 1.4, otherwise the powder could result in issues with fluidization [\[8\]](#).

$$H_r = \frac{\rho_{tap}}{\rho_{bulk}} \quad (1)$$

where  $\rho_{tap}$  is the tap density and  $\rho_{bulk}$  is the bulk density of the powder.




Figure 2: Two spherical powder particles forming a sintering neck [7]

Understanding the thermal properties of the powder is essential during the SLS process. SLS is characterized by an optimal sintering window, with a temperature range between crystallization ( $T_c$ ) and melting ( $T_m$ ). For any given heat flow within that range, the material is in a metastable phase, where full coalescence of the top powder layer, as well as adhesion with previously sintered layers are most likely guaranteed [8].

Therefore, creating a tailor-made powder feedstock involves using materials with a wide enough sintering window [2, 8].

Furthermore, optical properties of the powder bed need to be taken into account, since highly reflective materials (for a given laser wavelength) can waste most of the energy input, instead of absorbing a significant amount of radiation needed to effectively melt the powder [8].

This issue is prevalent in metal SLM 1.2.2, especially with aluminum.

However, when it comes to SLS and plastics powders, the required energy is substantially lower than that needed to melt metal alloys, meaning that any potential problem with poor radiation absorption can be compensated by increasing the laser power output [8].

Viscosity and surface tension of the melt pool are more relevant factors when choosing powders for SLS. High viscosity and surface tension can hinder the coalescence of polymer powders and the adhesion with previously sintered layers, resulting in residual shear stress, high porosity and thus poor quality of the 3D printed part in general.

In SLS, unlike other processes like investment casting or injection molding, there is no well distributed force (e.g. built up pressure against the mold) that can increase particle coalescence and layer adhesion, the only force acting on the printed part is gravity, along the vertical axis [8].

## 5.2 Mechanical milling

Grinding plastics into fine and homogeneous powders can be a challenge, since the high speed milling devices can easily overheat the plastics above their softening point, creating lumps of material, far from the desired result.

A solution to this problem is using so called *cryogenic grinding* devices, which utilize cooling agents such as dry ice, liquid carbon dioxide or liquid nitrogen, in order to keep the plastics below the glass transition point, where polymers become intrinsically brittle, similarly to a ceramic material, making it possible to turn the original mass into a powder [6, 5].

The heterogeneous powders can later be sieved and separated, based on their different granulometry.

Despite being an effective process for powder production, the morphology obtained with cryogenic milling is extremely irregular and unpredictable, which makes this method generally unsuitable for high quality SLS parts [8].

## 5.3 Chemical precipitation

There is little variety in the market of SLS ready polymer powders, with polyamide-12 (PA12) being the most optimized for this application and being produced by precipitation in ethanol [2].

Many other powders are produced using the precipitation method, but the developments of such powders are currently very limited and in early-stage, especially with thermoplastics, which are not as optimized as PA12.

## References

- [1] Federico Lupone; Elisa Padovano; Francesco Casamento; Claudio Badini. “Process Phenomena and Material Properties in Selective Laser Sintering of Polymers: A Review”. In: *Materials* (2021).
- [2] Maximilian A Dechet and Jochen Schmidt. “On the Development of Polymer Particles for Laser Powder Bed Fusion via Precipitation”. eng. In: *Procedia CIRP* 94 (2020), pp. 95–99. ISSN: 2212-8271.
- [3] Alberto Giubilini et al. “Advantages of Additive Manufacturing for Biomedical Applications of Polyhydroxyalkanoates”. In: *Bioengineering* 8.2 (2021). ISSN: 2306-5354. DOI: [10.3390/bioengineering8020029](https://doi.org/10.3390/bioengineering8020029). URL: <https://www.mdpi.com/2306-5354/8/2/29>.
- [4] Adriana Kovalcik. “Recent Advances in 3D Printing of Polyhydroxyalkanoates: A Review”. In: *The EuroBiotech Journal* 5 (2021).
- [5] Hemantkumar Junghare\*; Mayur Hamjade; C.K.Patil; S.B.Girase; Mandar M.Lele. “A Review on Cryogenic Grinding”. In: *International Journal of Current Engineering and Technology* (2017).
- [6] FRITSCH Milling and Sizing. *Cryogenic Grinding with the Variable Speed Rotor Mill PULVERISETTE 14 line*. <https://www.youtube.com/watch?v=3KUGXICL3Is>. 2021.
- [7] The Inkscape Project. *Inkscape*. <https://inkscape.org/>.
- [8] Manfred Schmid, Antonio Amado, and Konrad Wegener. “Polymer powders for selective laser sintering (SLS)”. In: *AIP Conference Proceedings* 1664.1 (2015), p. 160009. DOI: [10.1063/1.4918516](https://doi.org/10.1063/1.4918516). eprint: <https://aip.scitation.org/doi/pdf/10.1063/1.4918516>. URL: <https://aip.scitation.org/doi/abs/10.1063/1.4918516>.
- [9] Lisa Jiaying Tan; Wei Zhu; Kun Zhou. “Recent Progress on Polymer Materials for Additive Manufacturing”. In: *Advanced Functional Materials* (2020).