




Mix and dissolve




Drip chloroform solution




400 ml  
0.25 %w PVA



stir for 7.5 hrs  
@700-900 RPM




Fritted glass filter






Venturi vacuum ejector

sieving  
( $< 100 \mu\text{m}$ )



wet powder

drying  
@40-60 °C



Powder analysis