

The Iron Age of Grid Storage: Iron–Air Batteries as a World-Scale Solution for Multi-Day Energy Storage

Bartosz Osiej*

August 17, 2026

ABSTRACT

Renewable electricity is now cheaper than any fossil generation in most of the world, yet every grid that deploys it encounters the same wall: beyond roughly 50–70% variable renewable penetration, wind and solar must be either curtailed or backed by multi-day storage. This paper presents a comprehensive review and an original quantitative feasibility analysis of the iron–air battery as the world-scale answer to that wall. Iron–air cells oxidize metallic iron with atmospheric oxygen on discharge and electrochemically reduce the resulting rust back to iron on charge, delivering a theoretical energy density of $\sim 1200 \text{ Wh kg}^{-1}$ on the iron alone at a thermodynamic cell potential of 1.28 V. Because the active materials are iron, oxygen from air, and an alkaline electrolyte, the technology targets installed costs of $20 \$ \text{ kW}^{-1} \text{ h}$ – $40 \$ \text{ kW}^{-1} \text{ h}$ of storage capacity—four to six times below 2025 turnkey lithium-ion battery systems—at durations of 100 hours, precisely the regime that lithium-ion chemistry cannot serve economically.

We quantify the case with a worked design: a 100 MW / 10 GW h (100-hour) plant requires $\sim 17\,000 \text{ t}$ of iron (a few million dollars of commodity metal), occupies $\sim 15 \text{ ha}$ to 25 ha , and costs $\sim 200 \text{ million \$}$ to $400 \text{ million \$}$ versus $\sim 2.9 \text{ billion \$}$ for the equivalent lithium-ion stack—before considering the supply-chain and safety advantages of a chemistry built from the cheapest metal on Earth. We address the four honest engineering obstacles (round-trip efficiency near 50%, parasitic hydrogen evolution, the bifunctional air electrode, and carbon dioxide and water management), present a transparent levelized-cost-of-storage model, and place the technology in the context of the Long Duration Energy Storage Council’s projection of an 8 TW, $\$4 \text{ trillion}$ market by 2040 that could avoid 1.5–2.3 Gt of CO_2 per year. We conclude that iron–air storage is one of the few “boring” technologies—cheap, abundant, and unglamorous—that can actually carry the energy transition across the storage wall.

Keywords: iron–air battery, long-duration energy storage, grid storage, metal–air battery, renewable integration, curtailment, levelized cost of storage, iron anode, bifunctional air cathode

PACS: 82.47.Uv, 88.80.fh, 88.05.-t, 84.60.Ve, 82.45.Fk

1 Introduction: The Storage Wall

The energy transition has a specific, quantifiable bottleneck. Solar and wind are no longer expensive: 2024–2025 auctions cleared utility-scale solar below $20 \$ \text{ MW}^{-1} \text{ h}$ and onshore wind near $30 \$ \text{ MW}^{-1} \text{ h}$ in favorable markets, and lithium-ion battery packs fell to an average of $108 \$ \text{ kW}^{-1} \text{ h}$ in 2025—a 93% decline since 2010 [5]. The problem is not generation cost; it

*Independent Researcher, Szczecin, Poland. E-mail: mmc29213@gmail.com

is *time*. Wind and solar are variable, and beyond roughly 50–70% of annual generation, every grid must either throw energy away (curtailment), keep fossil plants spinning as backup, or store energy across gaps of days—not hours.

The gap between what lithium-ion can do and what the grid needs is now well quantified:

- **Curtailment is growing super-linearly.** Grids at high renewable penetration are already discarding meaningful fractions of zero-cost energy—tens of terawatt-hours per year globally, concentrated in California, Texas, Germany, and China—and every study of the phenomenon shows the discard rate accelerating as penetration rises [7].
- **Four-hour batteries cannot close multi-day gaps.** A “dunkelflaute” (dark, windless period) lasting three to five days is a normal feature of European weather, and winter lulls can last weeks. Meeting such events with 4-hour lithium-ion systems requires overbuilding energy capacity by a factor of 20–30, at a cost that is economically prohibitive [3].
- **The market is enormous and quantified.** The Long Duration Energy Storage (LDES) Council estimates that long-duration storage (8 hours to seasonal) is a \$3.6 trillion industry opportunity with 4–6 TW of installed potential by 2030, scaling to 8 TW and \$4 trillion by 2040, and avoiding 1.5–2.3 Gt of CO₂ per year—up to 6% of global energy-related emissions [3, 4].

This paper examines the most promising chemistry for that gap: the *iron–air battery*. It is deliberately unglamorous. Its active anode material is the cheapest metal on Earth (iron ore trades near 100 \$ t^{−1}); its cathode “fuel” is the oxygen in the air we breathe; its electrolyte is potassium hydroxide, a commodity chemical. There is no lithium, no cobalt, no nickel, no thermal-runaway risk, and no rare-earth supply chain. The question this paper answers is whether this boring chemistry is real—and whether it is the world-scale breakthrough that the storage wall demands.

1.1 Historical Development

Metal–air chemistry predates lithium-ion by a century. The zinc–air cell was patented by Maiche in 1878 and powered railway signaling for decades; iron–air was investigated as early as the 1960s–70s oil crisis, when Westinghouse and others built experimental cells for utility storage [8]. Two properties stalled the field for fifty years: the bifunctional air electrode had no cheap catalyst, and the iron electrode passivated after a few cycles. The modern revival has three roots:


- **2012–2014:** systematic materials work—sulfide additives, porous iron composites—demonstrated thousands of cycles at laboratory scale [9, 8].
- **2017:** Form Energy was founded by a team including former Tesla and MIT researchers with an explicit mission of multi-day storage [1].
- **2021–2026:** the chemistry was unveiled (2021); the first utility projects were contracted (Ballynahone in Northern Ireland, Great River in Minnesota); the first independent safety benchmark was published (2024); and Google’s 30 GWh order (2026) brought the technology to billion-dollar scale [2, 15].

The pattern is instructive: no single breakthrough, but fifteen years of incremental engineering: exactly what commodity-chemistry storage requires.

2 Electrochemistry of the Iron–Air Cell

2.1 Half-Reactions and Thermodynamics

In alkaline electrolyte (typically 30–45% KOH), the iron anode discharges through two oxidation steps [8, 9]:



while the air cathode reduces atmospheric oxygen:



The overall discharge is the controlled “rusting” of iron:



On charge, the reactions reverse: the hydroxide is electrochemically reduced back to metallic iron, and oxygen is evolved at the cathode. The open-circuit voltage of 1.28 V is confirmed by measurements of practical cells [12].

2.2 Specific Capacity and Energy Density

The theoretical specific capacity follows from the two electrons transferred per iron atom:

$$C_{\text{theor}} = \frac{2F}{M_{\text{Fe}}} = \frac{2 \times 96\,485\text{ C mol}^{-1}}{55.85\text{ g mol}^{-1}} \approx 960\text{ mA h g}^{-1} \quad (5)$$

giving a theoretical energy density on the iron alone of

$$\rho_E^{\text{theor}} = C_{\text{theor}} \times V_{\text{cell}} \approx 0.96 \times 1.28 = 1229\text{ W h kg}^{-1} \approx 1200\text{ W h kg}^{-1} \quad (6)$$

compared with $\sim 460\text{ W h kg}^{-1}$ for the best practical lithium-ion cells [11]. This is the key inversion of the betavoltaic problem analyzed by the author in a companion study: here the *energy* is cheap and abundant (a kilogram of iron stores as much energy as \$300 of lithium-ion capacity, at a metal cost of cents), and the challenge is power, efficiency, and lifetime—all of which are engineering problems, not physics limits.

2.3 Why Iron and Why Air

Iron is chosen for three reasons that no other metal matches:

1. **Abundance and price:** iron is the fourth most abundant element in the Earth’s crust and the second most abundant metal; ore costs $100\text{ \$ t}^{-1}$ to $150\text{ \$ t}^{-1}$ and scrap $250\text{ \$ t}^{-1}$ to $400\text{ \$ t}^{-1}$ (2025). The active material cost of a 10 GWh plant is a few million dollars—negligible against the \$200–400 M system price.
2. **Multi-electron chemistry in water:** iron oxidizes through two (and partially three) electrons per atom in aqueous alkaline electrolyte, unlike monovalent lithium, giving high specific energy without exotic electrolytes.
3. **Air as the cathode reactant:** the positive electrode draws oxygen from the atmosphere, so half the cell’s active mass is free. The air electrode is the price paid for this: it is the hardest component to engineer (Section 4.3).

2.4 Passivation, Self-Discharge, and Additives

The iron electrode’s original fatal flaw is passivation: the discharge product $\text{Fe}(\text{OH})_2$ is electronically insulating, so a dense electrode shuts itself down after a shallow discharge. Three engineering responses are now standard [9, 8]:

- **Porosity engineering:** sintered or pressed iron–carbon composites with 40–60% porosity accommodate the volume change of oxidation and maintain electronic pathways; utilization of the theoretical capacity rises from $< 20\%$ (flat plates) to 50–60%.
- **Sulfide additives** (Na_2S , Bi_2S_3): adsorb on the iron surface, suppress hydrogen evolution (Section 4.2), and promote the reversible $\text{Fe}/\text{Fe}(\text{OH})_2$ couple, roughly doubling cycle life in laboratory studies.
- **Electrolyte circulation:** pumping the electrolyte removes dissolved species and manages heat and concentration, at the cost of parasitic pump power.

Self-discharge is the slow corrosion of charged iron in alkaline media ($\text{Fe} + 2\text{H}_2\text{O} \rightarrow \text{Fe}(\text{OH})_2 + \text{H}_2$): the same hydrogen-evolution reaction as on charge (Section 4.2), proceeding spontaneously. Reported standing losses are a few percent per month—negligible against the multi-day mission, and far better than the self-discharge of many flow chemistries.

Temperature behavior: aqueous KOH freezes near -30°C at 45% concentration, so iron–air plants require thermal management (insulation or heating) in cold climates, and low temperature slows the oxygen electrode. Conversely, the cell tolerates heat without thermal-runaway risk (Section 11), giving a wide operating envelope that is a logistics question, not a chemistry one.

3 Cell and System Architecture

A practical iron–air cell (Fig. 1) consists of four functional components:

- **Iron anode:** a porous iron or iron–carbon composite electrode. Porosity is essential: the discharge product ($\text{Fe}(\text{OH})_2/\text{Fe}_3\text{O}_4$) occupies more volume than the metal, and a dense electrode passivates and dies after a few cycles. Binders (e.g., polyvinyl alcohol), additives (sulfide ions suppress hydrogen evolution), and carbon additives improve utilization and reversibility [8].
- **Bifunctional air cathode:** a gas-diffusion electrode catalyzing both oxygen reduction (discharge) and oxygen evolution (charge). This is the cell’s most expensive component per unit area and the focus of most material research (Section 4.3).
- **Alkaline electrolyte:** 30–45% aqueous KOH, which conducts OH^- and provides the redox medium. Potassium rather than sodium carbonate issues make KOH the standard, despite higher cost.
- **Air and CO_2 management:** the cell breathes. Ambient air must be filtered of CO_2 (which poisons the electrolyte as K_2CO_3) and humidified to avoid drying out; water management is a system-level discipline (Section 4.4).




Figure 1: Schematic of a rechargeable iron–air cell. On discharge the iron anode is oxidized ($\text{Fe} \rightarrow \text{Fe}(\text{OH})_2$, Eq. 1) while the air cathode reduces O_2 (Eq. 3); on charge both reactions reverse. The separator prevents shorting while conducting OH^- .

3.1 From Cell to Plant

Cells are assembled into bipolar stacks, stacks into modules, and modules into container-scale units. Form Energy—the field’s leading commercializer—describes its product as a turnkey 100-hour system scalable from 10 MW/1 GWh to 500 MW/50 GWh, deployable at any grid node [1]. Its first commercial project is the 100 MW/10 GWh Ballynahone plant in Northern Ireland, with a second at the Great River Energy project in Minnesota, and in 2026 Google contracted a 300 MW/30 GWh installation for data-center load firming—a 1 billion \$-scale order that marks the technology’s arrival at utility scale [2].

3.2 Power Electronics and Battery Management

Grid-scale aqueous stacks pose simpler power-electronics problems than lithium-ion systems, but they are not trivial:

- **Converter topology:** a 100 MW plant uses a modular multilevel or multiple parallel PCS (power conversion system) units; the low cell voltage (~ 1 V) is handled at the stack level by bipolar series connections, with DC–DC conversion to a ~ 1 kV DC bus.
- **Cell monitoring:** voltage, temperature, and electrolyte-level sensing per module; the slow duty cycle (hours to days) makes sampling cheap and reliability high.
- **Hydrogen monitoring:** the one gas of concern; sensors and recombiners are standard industrial components (Section 11).
- **State-of-charge estimation:** SOC follows coulomb counting plus electrolyte chemistry indicators; the 100-hour timescale makes drift easy to correct with periodic full charges.

Compared with the micro-watt power conditioning of betavoltaic systems analyzed by the author in a companion study, the engineering here is conventional—another sign that iron–air’s obstacles are industrial, not fundamental.

4 The Four Engineering Killers

Any honest assessment must name the obstacles. Iron–air has no exotic failure mode; it has four well-understood, addressable engineering problems.

4.1 1. Round-Trip Efficiency Near 50%

The thermodynamic potential is 1.28 V, but practical cells discharge at 0.8–1.0 V and charge at 1.4–1.6 V. Reported efficiencies decompose into a high coulombic efficiency ($\sim 96\%$) and a low voltage efficiency ($\sim 40\text{--}50\%$), giving overall round-trip efficiencies of 35–50% [8, 10]. Form Energy states a system round-trip efficiency near 50%.

This is the single most cited objection—and it is mostly a non-issue for the target application. Multi-day storage is charged from *curtailed* renewable energy whose marginal cost approaches zero; a 50%-efficient store of free energy is economically fine. What matters is the cost per kilowatt-hour *delivered* over the asset life, which we quantify in Section 6. Efficiency does matter at lower renewable penetrations, which is why iron–air’s sweet spot is the multi-day, high-penetration regime, not daily cycling.

4.2 2. Parasitic Hydrogen Evolution

On charge, iron deposition competes with water reduction:




only 49 mV above the iron deposition potential (Eq. 1). Hydrogen evolution wastes charge, pressurizes the cell, and must be managed safely (catalytic recombiners, venting, or containment). The standard mitigation is the addition of sulfide ions (e.g., Na_2S) or Bi_2S_3 , which suppress the hydrogen reaction and are now routine in the literature [9]. This is a solved problem in the sense that the mechanism is fully understood; it is an optimization problem in the sense that every percent of coulombic efficiency recovered matters at 100-hour scale.

4.3 3. The Bifunctional Air Electrode

The air cathode must catalyze oxygen *reduction* on discharge and oxygen *evolution* on charge—two reactions with opposite kinetics, at the same electrode, for tens of thousands of hours. Noble-metal catalysts (Pt for ORR, $\text{IrO}_2/\text{RuO}_2$ for OER) work but are unaffordable at grid scale. The field’s progress has been the development of cheap bifunctional catalysts: perovskite oxides ($\text{La}_{0.6}\text{Ca}_{0.4}\text{CoO}_3$ -class), MnO_2 , and doped carbon architectures that deliver adequate activity at fractions of a percent of the noble-metal cost [9, 10]. The air electrode is also a gas-diffusion structure that must reject electrolyte (wetting) while admitting oxygen, and it must survive thousands of wet/dry and charge/discharge cycles. It remains the dominant cost and lifetime risk in the cell.

4.4 4. Carbon Dioxide and Water Management

Ambient CO_2 reacts with KOH:



gradually carbonating the electrolyte and degrading performance, while water is consumed by evaporation and by the reactions themselves. A grid-scale plant therefore includes an air-handling system that scrubs CO_2 (a packed-bed or membrane contactor) and conditions humidity. This adds system cost and parasitic power—reported system-level penalties of a few percent—but is standard chemical-engineering infrastructure, not fundamental physics [14].

5 Quantitative Feasibility Model

We now size a concrete plant: **100 MW rated power, 100 hours duration, 10 GWh of storage**—the Form Energy class unit and the “dunkelflaute”-killing specification.

5.1 Iron Requirement

At an assumed usable energy density of 600 W h kg^{-1} of iron (50% of the 1200 W h kg^{-1} theoretical value, consistent with reported iron utilization of $\sim 50\text{--}60\%$ and cell-level voltages near 1 V), the iron mass is:

$$m_{\text{Fe}} = \frac{E_{\text{store}}}{E_{\text{usable}}} = \frac{10 \times 10^9}{600} \approx 1.7 \times 10^7 \text{ kg} \approx 17\,000 \text{ t} \quad (9)$$

At 2025 ore prices ($100 \$\text{t}^{-1}$ to $150 \$\text{t}^{-1}$ of contained iron), the active-material cost is 2 million\$ to 3 million\$—under 1% of the system price. Even the full cell stack (anode composite, electrolyte, cathode, structure), at a conservative system-level energy density of 150 W h kg^{-1} , weighs $\sim 67\,000 \text{ t}$ and its *materials* cost remains dominated by steel structures, not active chemistry.

5.2 Footprint

At a volumetric energy density of order 80 W h L^{-1} (aqueous systems are voluminous), 10 GWh occupies $\sim 1.3 \times 10^5 \text{ m}^3$ of cell volume; allowing for air-handling, aisles, and power-conversion equipment, a 10 GWh plant fits on 15 ha to 25 ha—comparable to a large solar farm substation, far smaller than a pumped-hydro reservoir, and sited anywhere a transformer yard fits.

5.3 Capital Cost

Table 1: Capital cost of a 100 MW / 100 h (10 GWh) storage plant, 2025–2026 estimates. Lithium-ion turnkey price of $117 \$\text{kW}^{-1} \text{ h}$ from [5]; scaling to 100 h multiplies energy capacity by 25. Other rows are representative published ranges.

Technology	Energy capex (\$/kWh)	Plant capex (10 GWh) (\$B)	Round-trip efficiency
Li-ion BESS (4 h, scaled 25 $\times$)	117	~ 2.9	85–90%
Pumped hydro	60–200	0.6–2.0	75–85%
Compressed-air (CAES)	100–150	1.0–1.5	50–60%
Iron–air	20–40	0.2–0.4	$\sim 50\%$

The headline result (Table 1) is that the energy-capacity capital cost of iron–air is four to six times below 2025 turnkey lithium-ion, and *its advantage grows with duration*: lithium-ion’s \$117/kWh buys four hours, while iron–air’s \$20–40/kWh buys one hundred. For the 100-hour mission, the lithium-ion stack costs 2.5 billion\$ to 3.5 billion\$; the iron–air plant costs 0.2 billion\$ to 0.4 billion\$. Figure 2 renders this comparison.




Figure 2: Estimated capital cost of a 100 MW / 100 h (10 GWh) storage plant by technology (midpoints of Table 1). The lithium-ion entry assumes scaling 4-hour systems to 100 hours of energy, which is precisely the application where its per-kWh price cannot compete.

6 Economics: Levelized Cost of Storage

Capital cost alone is insufficient; the honest metric is the levelized cost of storage (LCOS), the price per megawatt-hour delivered that recovers capital, operating, and charging costs:

$$\text{LCOS} = \frac{C_{\text{cap}} \cdot \text{CRF} + C_{\text{O\&M}}}{E_{\text{annual,out}}} + \frac{C_{\text{charge}}}{\eta_{\text{RT}}} \quad (10)$$

where C_{cap} is the installed cost, CRF the capital-recovery factor (e.g., 0.08 for 20 years at 7% interest), $C_{\text{O\&M}}$ annual operating cost, $E_{\text{annual,out}}$ the annual discharged energy, C_{charge} the charging cost per MWh, and η_{RT} the round-trip efficiency.

6.1 Worked Example

For the 10 GWh iron-air plant (\$300 M installed midpoint, CRF = 0.08, O&M \$3/kW-year = \$0.3 M/year), cycled 200 times per year (multi-day duty, 18 full discharges per month):

$$\text{Capex component} = \frac{0.08 \times 300 \times 10^6 + 0.3 \times 10^6}{200 \times 10 \times 10^3} = 12 \text{ \$ MW}^{-1} \text{ h} \quad (11)$$

$$\text{Charging component} = \frac{10}{0.50} = 20 \text{ \$ MW}^{-1} \text{ h} \quad (\text{at } \$10/\text{MWh} \text{ curtailed energy}) \quad (12)$$

giving **LCOS** $\approx 32 \text{ \$ MW}^{-1} \text{ h}$ —for *100-hour* reliability. The comparison is stark (Table 2):

- Lithium-ion 4-hour LCOS: \$65–78/MWh (2025) falling toward \$58/MWh [5, 6]—but only for four hours.
- Gas peaker marginal cost: \$100–200/MWh (fuel + variable O&M) [7].
- Iron-air, 100 hours: **\$30–40/MWh** in this model.

Table 2: Levelized cost of delivered energy for the multi-day mission. Lithium-ion and gas-peaker figures are 2025 published values; the iron–air value is the model of Eq. 10.

Technology	Duration	LCOS (\$/MWh)	Notes
Li-ion BESS	4 h	58–78	Energy-limited; cannot span multi-day gaps
Gas peaker	unlimited	100–200	Marginal (fuel) cost
Iron–air	100 h	30–40	Model of Eq. 10
Pumped hydro	8–24 h	40–100	Site-limited geography

6.2 Sensitivity

The model is transparent about its assumptions; the sensitivities matter:

- **Round-trip efficiency** 40% vs. 60%: charging component moves from \$25 to \$17/MWh—a \$8/MWh swing, smaller than the capex advantage over alternatives.
- **Cycles per year** 100 vs. 300: capex component \$24 vs. \$8/MWh. Iron–air is a *capacity* play: its economics favor few, deep, long discharges: the multi-day mission, where lithium-ion is structurally weakest.
- **Charging cost** \$0 vs. \$30/MWh: **the decisive variable**. If multi-day storage is charged from curtailed or surplus renewables (near-zero marginal cost), LCOS collapses below \$15/MWh. This is why the technology co-evolves with overbuilt renewables: overbuild + iron–air is the cheapest reliable system the literature has identified for high-penetration grids [3].

7 The Iron Family and the LDES Landscape

7.1 The Iron Family

Iron is not a single chemistry but a family (Table 3):

- **Aqueous iron–air** (this paper): 24–100 h at 20 \$kW^{−1} h to 40 \$kW^{−1} h target.
- **Iron flow batteries** (ESS Inc.): iron–chloride redox flow, 6–12 h, power and energy decoupled, targeting comparable cost; first systems deployed at MW scale [16].
- **High-temperature solid-state iron–air**: ceramic- electrolyte cells operating near 550 °C, demonstrating 1188 Wh/kg of iron and 55.6% round-trip efficiency in recent research—superior volumetric utilization than aqueous cells, at the cost of thermal management and materials complexity [21].
- **Iron–chromium flow** (NASA-era, revived in China): chromium is cheaper than vanadium but has slower kinetics.

The family shares one virtue—iron is abundant and cheap—and differs in power, duration, and engineering complexity. Aqueous iron–air is the current leader for the 24–100 h, capital-dominated mission.

Table 3: The iron battery family.

Chemistry	Duration	Energy capex	RT efficiency	Maturity
Aqueous iron–air	24–100 h	20–40 \$/kWh (target)	40–50%	Commercial (2024–)
Iron flow (ESS Inc.)	6–12 h	25–50 \$/kWh (target)	70–80%	Early commercial
HT solid-state iron–air	10–100 h	n/a (R&D)	55% (demo)	Laboratory
Iron–chromium flow	4–12 h	30–60 \$/kWh	70–80%	Pilot (CN)

7.2 The Competing Landscape

Iron–air is not the only horse in the multi-day race (Table 4). The honest picture, with 2025–2026 published figures:

- **Pumped hydro:** ~95% of installed storage worldwide, 8–24 h typical, LCOS \$40–100/MWh—but geography-limited and decade-scale to build.
- **Compressed air and CO₂** (adiabatic CAES, Energy Dome): 4–24 h, capex \$60–150/kWh, 50–60% RT; requires geology or tanks.
- **Vanadium flow:** \$300+/kWh, electrolyte cost-dominated; superb cycle life, poor economics for energy-dominated roles.
- **Zinc–air and zinc hybrid** (Eos, Zinc8): the same air-cathode economics as iron–air, 3–12 h, \$35–60/kWh targets; zinc is more expensive than iron and dendrite-prone.
- **Gravity** (Energy Vault et al.): \$60–100/kWh claims, low technology risk, but low energy density and unproven at scale.
- **Thermal storage** (particle, molten salt, Brayton): best for heat and industrial roles; \$20–50/kWh thermal; electricity round-trip through a turbine.
- **Green hydrogen** (electrolyzer + cavern + turbine or fuel cell): the only true seasonal store; \$60–150/kWh-equivalent at 30–40% RT—the natural complement, not competitor, to iron–air.

Alternative LDES ventures have raised more than \$6 billion over the past decade [18], and the US DOE Long Duration Storage Shot targets a 90% cost reduction for >10-h systems by 2030 [17]. The market research firm IDTechEx values the LDES market at \$223 billion by 2044 across all technologies [23]. Iron–air’s defensible position is the \$20–40/kWh, 100-h, aqueous-safe niche that no other technology occupies at comparable maturity.

Table 4: Long-duration storage landscape (2025–2026 estimates).

Technology	Duration	Energy capex (\$/kWh)	RT eff.	Cycles/yr	TRL	Notes
Pumped hydro	8–24 h	60–200	75–85%	200–400	9	Site-limited
CAES / CO ₂	4–24 h	60–150	50–60%	100–300	7–8	Geology/tanks
Vanadium flow	4–12 h	300+	70–80%	200–500	8	Electrolyte cost
Zinc–air	3–12 h	35–60	50–60%	100–300	6–7	Dendrites
Gravity	4–24 h	60–100	75–85%	200–400	5–6	Unproven at scale
Green H ₂	seasonal	60–150	30–40%	1–10	6–7	Seasonal only
Iron–air	24–100 h	20–40	40–50%	40–200	7–8	Multi-day niche

8 Grid Integration and Market Design

8.1 The Value Stack of Multi-Day Storage

Multi-day storage earns revenue across several products simultaneously—the *value stack*:

1. **Energy arbitrage**: buying surplus renewable energy at \$0–20/MWh and selling during the multi-day lull at \$50–200/MWh.
2. **Reliability and capacity**: displacing gas peakers and avoiding scarcity prices (\$1,000–9,000/MWh during events in ERCOT and elsewhere).
3. **Transmission deferral**: storing behind congested interconnects avoids \$100M+/km transmission builds.
4. **Firming contracts**: selling 24/7 firm power to data centers (the Google precedent [2]) or municipal utilities.

Lithium-ion captures (1) and part of (2), but cannot capture (4) beyond hours, and its capital cost makes (3) uneconomic.

8.2 What Market Design Must Provide

Storage is as much a *capacity* product as an energy product, and most energy-only markets underpay capacity:

- **Capacity mechanisms**: the EU Electricity Market Design Reform (2024) and US capacity markets (PJM, ISO-NE) must remunerate multi-day availability, not just daily cycling.
- **Scarcity pricing**: allowing prices to reach scarcity levels during multi-day lulls signals the value of 100-hour storage; price caps that truncate scarcity pricing suppress the very revenue that justifies the asset.
- **Transmission co-planning**: storage siting should be co-optimized with renewables in interconnection queues.
- **Long-term contracting**: multi-day assets need 10–20-year contracts (PPAs, capacity agreements) to be bankable at \$200–400M per plant.

8.3 A Simple Sizing Methodology

How much multi-day storage does a grid need? A defensible first-order model uses the residual-load time series:

$$R(t) = L(t) - [W(t) + S(t)] \quad (13)$$

where $L(t)$ is demand and $W(t) + S(t)$ is the wind-plus-solar generation available after transmission constraints. The storage requirement follows from the statistics of $R(t)$:

- **Power requirement** P_{st} : the largest deficit after firming (e.g., the 99.9th percentile of the deficit).
- **Energy requirement** E_{st} : the integral of the worst multi-day deficit (the worst “dunkelflaute”).

For a grid at 80% renewable penetration with a 30 GW winter peak, the worst multi-day lull of the last decade typically corresponds to 10–25 GWh of energy per 1 GW of deficit—i.e., 10–25 hours at rated power—with rare 3–5-day events demanding the 100-hour class. This is exactly the duration band where iron–air’s capital advantage is decisive, and where adding duration costs *only* \$20–40/kWh instead of lithium-ion’s \$117/kWh.

8.4 A Week in the Life: The Dunkelflaute Duty Cycle

Figure 3 illustrates the mission. During days 1–2 wind and solar meet the load; on day 3 a large weather system settles in and generation collapses for four days—the dunkelflaute. The iron–air plant discharges at rated power for ~90 hours, drawing SOC from 100% toward a reserve floor, then recharges from the surplus of days 7–8. No lithium-ion plant of any size participates in this sequence economically, because the energy to span days 3–6 is 20–30 full batteries, not one.




Figure 3: Illustrative 10-day operation of a 100 MW / 10 GWh iron–air plant during a wind-and-solar lull (shaded). The plant discharges ~90 h at rated power, then recharges from the subsequent surplus.

8.5 Overbuild Plus Storage: The Reference Architecture

The consensus that emerges from grid models and the LDES Council is that the cheapest reliable high-renewable system is not “exactly enough generation plus huge storage” but *overbuilt generation plus modest multi-day storage plus minimal firm backup* [3]. Overbuilding wind and solar by 20–40% costs \$10–30/MWh of surplus; storing that surplus in iron–air at \$20–40/kWh and discharging it over 100 hours costs less than keeping a gas peaker warm.

The synergy is structural: iron–air’s low efficiency matters least exactly when the surplus is cheapest, and its low capital cost matters most exactly when the duration is longest.

9 The World-Scale Case

The quantitative case assembled above supports an ambitious but honest conclusion: iron–air storage is the cheapest way found to date to make a high-renewable grid *reliable across days*. The world-scale arithmetic:

- **The market:** 8 TW of long-duration storage by 2040 is the LDES Council’s central scenario—a \$4 trillion capital program, the largest infrastructure build of the century after transmission itself [3, 4].
- **The emissions prize:** avoiding 1.5–2.3 Gt CO₂/yr (up to 6% of global energy emissions) is not the whole climate solution, but it is the piece that unlocks the rest: without multi-day storage, grids stall at ~50–70% renewable penetration and the remaining decarbonization simply does not happen [13].
- **The supply-chain argument:** lithium, cobalt, and nickel are geographically concentrated and price-volatile; iron is produced on every continent. A 10 GWh iron–air plant consumes ~17 kt of iron—less than a single week of global steel production (1.9 Gt yr^{−1}). There is no resource constraint at 8 TW of storage: the required iron inventory (~170 Mt at 600 Wh/kg) is months of global steel output.
- **The safety argument:** aqueous, non-flammable, no thermal runaway, no toxic electrolyte fire products. Iron–air is a technology that can be sited next to neighborhoods without controversy—a regulatory and social license advantage that cannot be priced into Table 1 but may matter more.

9.1 Regional Case Studies

Texas (ERCOT): Winter Storm Uri (February 2021) left millions without power for up to a week; the joint FERC–NERC inquiry documented a multi-day failure of gas, wind, and grid infrastructure, and the economic cost is estimated at \$80–200 billion [20]. ERCOT’s subsequent build-out of wind, solar, and 4-hour batteries reduced the frequency of emergency events but cannot close the multi-day gap—the canonical iron–air market, and one where scarcity pricing already rewards 100-hour availability.

California: spring-afternoon solar overproduction already drives midday prices to zero or negative and forces curtailment; the state’s 100% clean-electricity target for 2045 requires 8+ hour storage at scale [13]. Multi-day storage converts the state’s structural oversupply into winter-evening reliability.

Germany and Europe: the winter 2021/22 “dunkelflaute” pushed day-ahead prices above EUR 600/MWh for sustained periods, and ENTSO-E decarbonization scenarios include multi-day storage in every pathway [3]. European grids, with their deep wind reliance, are the clearest continental market for 100-hour assets.

Poland (detailed below): the last coal to retire is the coal that must back the weather gap—and that is precisely the coal iron–air can replace.

9.2 The Polish Angle

Poland’s grid is among the most coal-dependent in Europe (coal $\sim 60\text{--}70\%$ of generation) and is now deploying wind and solar at pace. Its coal phase-out faces exactly the storage wall: the last 30–40% of coal cannot retire until multi-day backup exists, and the national transmission operator already curtails renewables on sunny, windy weekends. Iron–air plants, manufacturable from Polish steel and sited on former coal-mining and power-station land (which has grid connections and trained workforces), offer a domestic, commodity-based path through the wall—and a manufacturing opportunity (the cell stack is essentially steel, KOH, and catalyst-coated electrodes) that Poland’s steel and chemical industry could serve.

10 Manufacturing and Supply Chain

10.1 Gigafactory Economics

Iron–air cells are unusually manufacturable: the anode is pressed or sintered iron–carbon, the cathode a coated gas-diffusion layer, the stack bipolar hardware—all familiar to the steel, powder-metallurgy, and battery industries. There are no dry rooms (the chemistry is aqueous), no flammable electrolyte fill lines, and no exotic materials. The capital cost per GWh of annual manufacturing capacity is therefore expected to be far below lithium-ion’s, and the bottleneck is the air electrode’s coating line and catalyst supply.

Applying a lithium-ion-like learning curve (pack costs fell $\sim 19\%$ per doubling of cumulative volume [5]) to iron–air from a \$40/kWh first-commercial price reaches \$20/kWh after roughly four doublings—a few tens of GWh of cumulative production. This is the standard cost-scaling argument, and it is the strongest reason to treat the \$20/kWh target as engineering, not marketing.

10.2 Materials Bill of a 10 GWh Plant

- **Iron:** ~ 17 kt, \$2–3 M. No supply constraint (global steel ~ 1.9 Gt/yr).
- **KOH:** $\sim 10\text{--}20$ kt of commodity chemical at $\sim \$1/\text{kg}$.
- **Catalysts:** MnO_2 , perovskite oxides, doped carbon—no platinum-group metals. PGM-free operation is what makes the cost curve achievable; PGM loading would add \$10–50/kWh.
- **Steel structure:** the largest mass and cost item after the cells themselves—and a domestic industry in almost every country, Poland included.

10.3 Supply-Chain Security

The geopolitical argument is blunt: lithium refining is concentrated in China ($\sim 60\%+$), cobalt in the DRC, nickel in Indonesia and Russia; a multi-terawatt storage build-out built on those metals is a strategic dependency. Iron is produced on every continent, and KOH is made from globally distributed potassium chloride. For the 8 TW scenario the iron requirement (~ 170 Mt) is months of steel output; there is no material bottleneck at any scale discussed in this paper.

11 Safety, Lifecycle, and Environment

11.1 Safety

The safety case is structural, not procedural:

- **No thermal runaway:** aqueous electrolyte, no flammable solvent, no oxygen release from a cathode lattice. Form Energy’s independent 2024 safety benchmark reported no uncontrolled heating, no thermal runaway, no dendrite formation, and no fire across abuse scenarios [15].
- **Hydrogen:** the one process risk; managed by catalytic recombiners, controlled venting, and plant-level zoning. Hydrogen is a well-understood industrial gas.
- **Regulatory familiarity:** aqueous alkaline batteries avoid the hazardous-cargo classification of lithium-ion under UN 38.3 and ADR, simplifying NFPA 855 compliance and permitting.

11.2 Standards and Certification

Iron–air systems are being certified under the same framework as other stationary storage: IEC 62933 (electrical energy storage systems), UL 9540 (safety) and NFPA 855 (installation) in North America, and CE/ENEL-equivalent routes in Europe. Two properties simplify the process: the chemistry is not classified as hazardous goods (no UN 38.3 lithium-battery transport regime), and the failure mode analysis is simpler without thermal runaway. Form Energy published its abuse-test benchmark in December 2024 precisely to shorten the permitting path [15].

11.3 Lifecycle Assessment

The embodied-energy story is favorable: iron ore is not refined to battery grade (no high-purity cathode synthesis), KOH is a bulk chemical, and the plant is mostly steel. Published assessments place the cradle-to-gate footprint of iron–air storage roughly an order of magnitude below NMC lithium-ion per kWh delivered, before counting recycling [22]. Water use is modest (electrolyte makeup) compared with pumped hydro.

11.4 End of Life

At end of life the iron—the bulk of the mass—is scrap steel; the KOH is recyclable or neutralizable; the cathode carbon can be reprocessed. Unlike lithium-ion, whose recycling is chemistry-intensive, an iron–air plant’s end of life is a steel-recycling event: the materials are worth more at 30 years than the chemistry premium paid to lithium.

12 Technology Roadmap

Table 5: Technology roadmap for iron–air grid storage.

Phase	Milestone	Significance
2024–2027	First commercial 10 MW/1 GWh units (Form Energy, Ballynahone, Great River)	Technology leaves the pilot phase; first utility revenue data
2027–2030	100–500 MW plants; second-generation air cathodes; $\geq 60\%$ round-trip targets	LCOS below \$30/MWh; capacity displaces gas peakers at scale
2030–2035	8 TW market build-out begins; iron–air as a default choice for 24–100 h storage; EU/PL first gigafactories	Multi-day reliability becomes standard; overbuild + iron–air the reference grid architecture
2035–2040	Seasonal-scale storage; integration with hydrogen production for industry	The storage wall is effectively removed; renewable penetration ceilings rise toward 90–100%

Figure 4 renders the phases on a timeline.




Figure 4: Timeline of the roadmap phases of Table 5.

12.1 Applications Beyond Bulk Grid Storage

- **Data centers:** 24/7 clean firming (the Google 30 GWh order [2]); multi-day backup displacing diesel generators for critical loads.
- **Island and off-grid systems:** solar plus iron–air replaces diesel at avoided fuel cost of \$0.30+ /kWh—the economics close first where diesel is expensive.
- **EV charging buffers:** buffering fast-charging hubs to flatten demand charges and defer grid upgrades.
- **Industrial microgrids:** firming for aluminum, steel, and ammonia plants with multi-day batch processes.
- **Transmission support:** multi-day storage as a non-wires alternative to interconnector reinforcement.

13 Risks and Honest Assessment

A review that names no risks is a sales brochure. The honest list:

1. **Lithium-ion is falling faster than expected.** BNEF’s 2025 data show stationary packs at \$70/kWh and turnkey systems at \$117/kWh—numbers that looked impossible in 2021. Iron–air’s \$20–40/kWh target must be *achieved at scale*, not assumed; a 10× cost miss would erase the advantage. However, the 100-hour mission protects iron–air: lithium-ion cannot follow it below ~\$2,000/kWh-equivalent, because its cost is linear in energy capacity.
2. **Round-trip efficiency is lower than the marketing.** Independent due-diligence documents place Form Energy’s system efficiency near 36–40% rather than the claimed 50–60%, and multi-day duty may yield only ~40–100 cycles per year [19]. The LCOS model of Section 6 is robust to this (the charging component moves from \$20 to \$25–28/MWh at 40%), but it narrows the margin and reinforces that iron–air is a capacity product, not a trading product: its economics assume cheap charging energy and few, deep cycles.
3. **Cycle life is not yet demonstrated at grid scale.** Fraunhofer’s early target was 500 cycles; Form Energy claims thousands, but independent multi-year field data do not yet exist (as of 2026). Iron–air’s economics tolerate deep cycles, but a passivation-driven capacity fade at 1000 cycles would change the LCOS calculation materially.
4. **The air electrode is the lifetime bottleneck.** Bifunctional catalysts degrade via carbon corrosion (OER side), catalyst dissolution, and gas-diffusion-layer flooding. Ten-year electrode lifetime is an assumption, not yet a demonstrated fact.
5. **Efficiency drags at low penetration.** At 40–60% renewable penetration, where charging energy has real value, a 50% round-trip store loses to other options; iron–air is a high-penetration technology, and its market timing depends on the renewable build-out it complements.
6. **Competition is real.** Iron–*flow* batteries (ESS Inc.), zinc-based systems, compressed CO₂, and gravity storage all target the same niche; the winner will be decided by delivered LCOS and bankability, not by chemistry elegance.

13.1 Common Misconceptions, Answered

- **“50% round-trip efficiency means it wastes half the energy.”** Only if the charging energy has market value. Multi-day storage is charged from surplus energy that would otherwise be curtailed at \$0–20/MWh; wasting half of a near-free input is the right trade for a 5× capital saving.
- **“Iron–air is just a lab curiosity that will never scale.”** Form Energy has contracted 100 MW / 10 GWh-class plants (Ballynahone, Great River) and a 300 MW / 30 GWh Google order [2]. Scaling is underway, not hypothetical.
- **“It is a battery, so it must cycle daily.”** The asset is designed for ~40–200 deep cycles per year—the opposite duty cycle of a daily-cycling lithium plant, and the reason its calendar life, not cycle life, is the binding constraint.
- **“Duration is solved by hydrogen.”** Hydrogen is the seasonal complement, but at 30–40% round-trip and \$60–150/kWh-equivalent it is not the 24–100-h answer; the two technologies partition the duration axis (Section 7).

14 Conclusions

This paper has presented a comprehensive review and an original quantitative feasibility analysis of iron–air batteries for long-duration grid storage. The principal findings:

1. **Iron–air is the chemistry of the storage wall.** Its theoretical 1200 W h kg^{-1} on a commodity metal, with air as the cathode reactant, is the only aqueous, non-flammable, non-toxic chemistry that can deliver 100-hour duration at \$20–40/kWh—four to six times below 2025 turnkey lithium-ion, with an advantage that *grows* with duration.
2. **The physics is sound; the engineering is known.** The four obstacles (50% round-trip efficiency, hydrogen evolution, the bifunctional air electrode, CO₂/water management) are all understood mechanisms with active, funded solutions—not unknown unknowns. This is the opposite of the betavoltaic case analyzed by the author in a companion paper, where the physics itself set the ceiling.
3. **The economics close for the mission that matters.** A worked 100 MW/10 GWh model gives LCOS of \$30–40/MWh for 100-hour reliability—below gas peakers (\$100–200/MWh) and below lithium-ion at any duration it can physically serve.
4. **The world-scale prize is real and quantified.** The LDES Council’s 8 TW/\$4 trillion-by-2040 scenario, avoiding 1.5–2.3 Gt CO₂/yr, is not a fantasy: it is the arithmetic of grids that must bridge multi-day weather gaps, and iron–air is the cheapest identified way to do so. There is no resource constraint: the iron for 8 TW of storage is months of global steel output.
5. **The honest verdict.** Iron–air will not be the only storage technology, and its success is not guaranteed—cycle-life validation, air-electrode lifetime, and manufacturing scale are real open questions. But it is the rare candidate that is simultaneously world-scale in ambition, commodity-based in materials, physically sound, and already shipping in 2024–2026 at utility scale. The “iron age” of grid storage is not a metaphor; it is a construction schedule.

The energy transition does not need another exotic battery that doubles capacity in a laboratory. It needs 8 terawatts of storage that costs twenty dollars a kilowatt-hour, lasts a century in calendar terms, and is made of the same metal as the grid’s own steel. That technology exists, it is being built, and its name is boring on purpose: iron–air.

Table 6: The argument in one page: iron–air vs. the alternatives for the multi-day mission.

Criterion	Iron–air	Li-ion (4 h)	Gas peaker
Duration served	100 h	4 h	unlimited
Energy capex	\$20–40/kWh	\$117/kWh (turnkey)	n/a (fuel)
Plant capex, 10 GWh	\$0.2–0.4 B	\$2.9 B (scaled)	n/a
LCOS (multi-day)	\$30–40/MWh	58–78/MWh (4 h only)	\$100–200/MWh
Round-trip efficiency	40–50%	85–90%	35–45% (thermal)
Materials	Fe, KOH, air, steel	Li, Co, Ni, graphite	natural gas
Thermal runaway	No	Yes (mitigated)	n/a
Supply-chain risk	None	Concentrated	Geopolitical
Recycling	Steel stream	Chemistry-intensive	n/a

Glossary of Acronyms

BESS battery energy storage system

CAES compressed-air energy storage

CRF capital-recovery factor

DOD depth of discharge

Gt gigatonne (1×10^9 t)

KOH potassium hydroxide

LCOS levelized cost of storage

LDES long-duration energy storage

MWh megawatt-hour

OER oxygen evolution reaction

ORR oxygen reduction reaction

PHS pumped hydro storage

RT round-trip (efficiency)

TW terawatt

VRE variable renewable energy

Acknowledgements

The author thanks the open-source community and public data from BloombergNEF, the LDES Council, Fraunhofer UMSICHT, and Form Energy for accessible literature and figures. No external funding was received for this work.

References

- [1] Form Energy, “Battery technology: 100-hour iron–air storage,” (2021–2026). Available: <https://formenergy.com/technology/battery-technology/>
- [2] Form Energy and Google, “300 MW / 30 GWh multi-day storage agreement,” (2026); widely reported, e.g. <https://formenergy.com>
- [3] Long Duration Energy Storage Council, “Long-duration energy storage must scale 50× faster to achieve decarbonisation goals,” Report, November 2024. Available: <https://ldescouncil.com>
- [4] Long Duration Energy Storage Council, “LDES: a \$3.6 trillion industry with 4–6 TW potential by 2030,” (2025). Available: <https://ldescouncil.com>
- [5] BloombergNEF, “Lithium-ion battery pack prices fall to \$108/kWh; stationary storage reaches \$70/kWh,” December 2025. Available: <https://about.bnef.com>
- [6] Ember, “Battery storage system costs: turnkey BESS \$117/kWh; 4-hour LCOS \$65–78/MWh,” Energy Storage Cost Survey (2025).
- [7] International Energy Agency, “Renewables 2024: analysis and forecast to 2030,” IEA, Paris (2024). Available: <https://www.iea.org>
- [8] H. A. Figueredo-Rodríguez, R. D. McKerracher, M. Insausti, A. G. Garcia, C. Ponce de León, M. Walsh, and F. C. Walsh, “A review of the iron–air secondary battery for energy storage,” *ChemPlusChem* **79**, 811–822 (2014).
- [9] S. R. Narayanan, G. K. S. Prakash, A. Manohar, B. Yang, S. Malkhandi, and A. Kindler, “Materials challenges and technical approaches for realizing inexpensive and robust iron–air batteries for large-scale energy storage,” *Solid State Ionics* **216**, 105–109 (2012).
- [10] Fraunhofer UMSICHT, “Iron–air battery project,” project description (targets: 250 Wh/kg, $\geq 60\%$ round-trip efficiency, 500 cycles). Available: <https://www.umsicht.fraunhofer.de/en/projects/iron-air-battery.html>
- [11] Electronics For You, “Energy storage solution enters the iron age,” August 2024 (theoretical energy densities: iron–air ~ 1200 Wh/kg vs. Li-ion ~ 460 Wh/kg).
- [12] PatSnap, “Measuring iron–air battery open-circuit voltage performance,” 2025 (OCV ≈ 1.28 V).
- [13] CRES Forum, “Issue brief: long-duration energy storage,” September 2022 (LDES avoids 1.5–2.3 Gt CO₂e/yr by 2040, up to 6% of global energy emissions).
- [14] Energy Solutions, “Iron–air batteries 2026: 100-hour grid storage at under \$20/kWh,” 2026 (round-trip efficiency 40–50%).
- [15] Form Energy, “Iron–air battery technology sets a new benchmark for safety in energy storage systems,” December 2024. Available: <https://formenergy.com>
- [16] ESS Inc., “Iron flow battery technology: long-duration storage without lithium,” white papers and product documentation, 2021–2026. Available: <https://essinc.com>

- [17] US Department of Energy, “Long Duration Storage Shot: 90% cost reduction for systems over 10 hours within one decade,” Energy Storage Grand Challenge (2021). Available: <https://www.energy.gov/eere/long-duration-storage-shot>
- [18] Modo Energy, “Billions raised, early stages on delivery: can alternative LDES technologies scale?” February 2026. Available: <https://modoenergy.com/research/en/lides-alternative-long-duration>
- [19] S. Fleming, “There are only 2 kinds of battery,” Clean Energy Review, May 2024 (analysis of Form Energy due-diligence round-trip efficiency).
- [20] FERC and NERC, “The February 2021 cold weather outages,” Joint Inquiry Staff Report, November 2021. Available: <https://www.ferc.gov>
- [21] “Sustainable development of iron–air batteries as long-duration energy storage,” *Adv. Sustain. Syst.* (2026): high-temperature solid-state iron–air cell with 1188 Wh/kg iron and 55.6% round-trip efficiency.
- [22] “Will iron forge the future of metal–air batteries in grid-scale energy storage?” *ChemSusChem* (2025), Perspective on sustainability and lifecycle aspects of iron–air chemistry.
- [23] IDTechEx, “Long Duration Energy Storage Market 2024–2044,” market report (LDES market valued at \$223 billion by 2044). Available: <https://www.idtechex.com>