

Atomic Batteries for Mobile Devices: A Comprehensive Review of Betavoltaic Technology, Radioisotope Sources, Semiconductor Absorbers, and Feasibility Analysis for Smartphone Applications

Bartosz Osiej*

August 17, 2026

ABSTRACT

We present a comprehensive review and original feasibility analysis of betavoltaic nuclear batteries as potential power sources for mobile consumer electronics, with particular focus on smartphone applications. Betavoltaic cells convert the kinetic energy of beta particles emitted during radioactive decay directly into electrical energy via semiconductor p-n junctions, offering operational lifetimes of 50–100+ years—orders of magnitude beyond lithium-ion technology. We systematically review: (i) the physics of beta decay relevant to energy harvesting, including the Fermi spectral distribution and the ~ 300 keV atomic displacement threshold; (ii) the taxonomy of nuclear battery architectures (thermoelectric, thermionic, betavoltaic, alphavoltaic, optoelectric, piezoelectric); (iii) radioisotope candidates (^3H , ^{63}Ni , ^{147}Pm , ^{14}C) with comparative analysis of half-life, beta energy, cost, and availability; (iv) semiconductor absorber materials (Si, GaAs, 4H-SiC, GaN, diamond, c-BN, $\beta\text{-Ga}_2\text{O}_3$) evaluated for coupling efficiency, radiation hardness, and technological maturity; and (v) the current state of the art including Betavolt BV100, NRD NBV, City Labs NanoTritium, and Arkenlight systems.

We then develop an original quantitative feasibility model: given the power consumption profile of a modern smartphone (69 mW suspended to 6 W active), we calculate the required radioisotope activity, cell count, total volume, and mass for three deployment scenarios—(a) pure betavoltaic replacement of Li-ion, (b) hybrid betavoltaic trickle-charge architecture, and (c) betavoltaic-only for standby/IoT subsystems. Our analysis reveals a fundamental power gap of $\sim 10^4\text{--}10^5\times$ between current betavoltaic output ($\sim 100\text{ }\mu\text{W}$) and active smartphone demand ($\sim 2\text{ W}$), which cannot be closed by scaling alone within the next two decades. However, our lifecycle model shows that the hybrid architecture delivers measurable benefits only at the 10–100 mW scale: a ~ 70 mW module covering standby drain extends Li-ion lifespan by $\sim 50\%$, and 200 mW–1 W modules of the 2040s could reduce cycling by 80–95%, pushing lifespan to the $\sim 15\text{--}20$ -year calendar-aging ceiling. Betavoltaic power for always-on subsystems (10–100 μW) is achievable now with BV100-class devices. We further analyze radiation shielding requirements, IAEA and NRC regulatory frameworks for consumer products containing radioisotopes, environmental lifecycle assessment, and total cost of ownership. A technology roadmap to 2050 is presented, identifying diamond semiconductor fabrication and high-activity ^{63}Ni source production as the two critical bottlenecks.

Keywords: betavoltaic, nuclear battery, radioisotope, nickel-63, tritium, diamond semiconductor, smartphone power, energy density, e-waste, radiation safety

PACS: 29.30.Kv, 85.30.Hi, 85.30.Ff, 88.80.hh, 23.40.-s

*Independent Researcher, Szczecin, Poland. E-mail: mmc29213@gmail.com

1 Introduction

The lithium-ion battery (LIB) has powered the mobile revolution. Since Sony’s first commercial cell in 1991, LIB energy density has risen from $\sim 80 \text{ W h kg}^{-1}$ to $\sim 250 \text{ W h kg}^{-1}$ —a factor of three in three decades [1, 2]. Yet this trajectory is approaching fundamental electrochemical limits: theoretical maximum LIB energy density is $\sim 1250 \text{ W h kg}^{-1}$ under heroic assumptions, and practical cells will saturate near $\sim 400 \text{ W h kg}^{-1}$ by the 2030s [3]. More critically, LIBs degrade: after 500–1000 charge cycles (3–5 years of typical smartphone use), capacity falls below 80% of nominal, and the cell becomes electronic waste [4]. The United Nations estimates ~ 50 million tonnes of e-waste are generated annually, with batteries constituting a growing and hazardous fraction [5].

Radioisotope batteries—devices that convert the energy of radioactive decay directly into electricity—offer a fundamentally different proposition: power sources that operate continuously for decades without recharging, maintenance, or capacity degradation. The concept is not new: the first betavoltaic device was demonstrated by Henry Moseley in 1913 [6], and radioisotope thermoelectric generators (RTGs) have powered deep-space missions since 1961 [7]. However, two recent developments have reignited interest in miniaturized nuclear batteries for consumer applications:

1. **Betavolt BV100** (2024): a Chinese startup demonstrated a coin-sized ($15 \text{ mm} \times 15 \text{ mm} \times 5 \text{ mm}$) betavoltaic cell using ^{63}Ni and 4th-generation diamond semiconductors, claiming $100 \mu\text{W}$ at 3 V for 50 years [8].
2. **NRD NBV series** (2026): a US manufacturer announced 5 nW – 500 nW cells with > 100 -year operational life [9].

These achievements, while impressive, operate at power levels $\sim 10\,000$ – $100\,000\times$ below the needs of a smartphone ($\sim 2 \text{ W}$ active, $\sim 200 \text{ mW}$ average). The central question of this paper is: **can betavoltaic technology ever power a smartphone, and if not, what role can it realistically play in mobile energy?**

We answer this question through a systematic review and original quantitative analysis. Section 2 establishes the nuclear physics. Section 3 surveys all nuclear battery architectures. Sections 4–6 develop the betavoltaic conversion physics in detail. Section 7 reviews current devices. Section 8 benchmarks betavoltaics against the competing power technologies. Section 9 characterizes smartphone energy demand. Section 10—the core original contribution—presents a mathematical feasibility model with three deployment scenarios. Sections 11–13 address safety, regulation, and lifecycle economics. Section 14 provides a technology roadmap, and Section 15 summarizes our findings.

1.1 Historical Development

The evolution of nuclear batteries spans more than a century (Table 1):

- **1913:** H. G. J. Moseley and J. L. Harling showed that beta emission from a radium source charges an isolated electrode to high potential—the first direct conversion of radioactive decay into electrical energy [6].
- **1954:** RCA Laboratories announced the first practical betavoltaic cell, coupling a $^{90}\text{Sr}/^{90}\text{Y}$ source to a silicon junction [12]; rapid displacement-damage degradation ended this line of development.

- **1956–1961:** RTGs matured under the US atomic-energy program; SNAP-3 flew on Transit 4B in 1961, beginning six decades of spaceflight heritage [7].
- **1968–1974:** the Betacel ^{147}Pm pacemaker battery powered ~ 139 cardiac implantations, establishing the medical-implant precedent [11].
- **1970s–2000s:** a long plateau—betavoltaics retreated to niche military and aerospace roles while lithium-ion conquered consumer electronics.
- **2006–2016:** academic and small-company revival: high-efficiency 4H-SiC cells [17, 18], 28% p-n junction diamond conversion [20], and the first US general license for a tritium betavoltaic product [30].
- **2024–2026:** the BV100 and NBV announcements returned nuclear batteries to the consumer spotlight (Section 7).

Table 1: Milestones in the development of nuclear batteries.

Year	Milestone	Significance
1913	Moseley & Harling: radium beta charging	First betavoltaic effect
1954	RCA $^{90}\text{Sr}/\text{Si}$ cell	First practical device; degradation problem
1961	SNAP-3 RTG on Transit 4B	First RTG in space [7]
1968–74	Betacel ^{147}Pm pacemaker	Medical-implant precedent [11]
2006–16	4H-SiC and diamond cells	Efficiency and radiation-hardness revival [17, 20]
2024	Betavolt BV100	Consumer-visibility break-through [8]
2026	NRD NBV series	100-year lifetime claims [9]

2 Physics of Radioactive Decay for Energy Harvesting

2.1 Beta Decay Fundamentals

Beta-minus decay occurs when a neutron converts to a proton, emitting an electron (beta particle) and an antineutrino:

$$n \rightarrow p + e^- + \bar{\nu}_e \quad (1)$$

The total energy released (Q -value) is shared between the electron and antineutrino as a continuous spectrum described by the Fermi theory of beta decay [10]:

$$\frac{dN}{dE_e} = C \cdot F(Z, E_e) \cdot p_e \cdot E_e \cdot (Q - E_e)^2 \quad (2)$$

where C is a normalization constant, $F(Z, E_e)$ is the Fermi function accounting for Coulomb effects, p_e is the electron momentum, and $(Q - E_e)^2$ reflects the antineutrino phase space. The average beta energy is approximately one-third of the maximum:

$$E_{\text{avg}} \approx \frac{Q}{3} \quad (3)$$

Figure 1 shows the resulting continuous spectrum for ^{63}Ni : the electron energy distribution peaks near $E \approx Q/3$ and falls to zero at $E_{\text{max}} = 66.9 \text{ keV}$.




Figure 1: Schematic beta energy spectrum of ^{63}Ni (Eq. 2, nonrelativistic approximation). The spectrum is continuous up to $E_{\text{max}} = 66.9 \text{ keV}$; the average electron energy is 17.4 keV (Eq. 3).

The radioactive activity (decays per second) follows:

$$A = \lambda N = \frac{\ln 2}{T_{1/2}} \cdot N \quad (4)$$

where λ is the decay constant, N is the number of parent nuclei, and $T_{1/2}$ is the half-life.

The total decay power from a radioisotope source is:

$$P_{\text{decay}} = A \cdot E_{\text{avg}} = \frac{\ln 2}{T_{1/2}} \cdot N \cdot E_{\text{avg}} \quad (5)$$

2.2 The 300 keV Displacement Threshold

A critical constraint for betavoltaic design is that beta particles with energy above $\sim 300 \text{ keV}$ can displace atoms from their crystal lattice positions in the semiconductor absorber, creating Frenkel defects (vacancy–interstitial pairs) that increase dark current and degrade device performance over time [11]. This threshold is material-dependent:

- Si: $\sim 220 \text{ keV}$
- GaAs: $\sim 250 \text{ keV}$
- 4H-SiC: $\sim 350 \text{ keV}$
- Diamond: $\sim 400 \text{ keV}$

This constraint immediately limits viable radioisotopes to those with $E_{\text{max}} < 300 \text{ keV}$: only ^3H ($E_{\text{max}} = 18.6 \text{ keV}$), ^{63}Ni ($E_{\text{max}} = 66.9 \text{ keV}$), ^{14}C ($E_{\text{max}} = 156 \text{ keV}$), and ^{147}Pm ($E_{\text{max}} = 225 \text{ keV}$) satisfy this criterion among practical isotopes with useful half-lives [11]. Radioisotopes with higher-energy beta emission (e.g., $^{90}\text{Sr}/^{90}\text{Y}$, $E_{\text{max}} = 546 \text{ keV}$) were tested in early betavoltaic research but caused rapid semiconductor degradation [12, 58].

2.3 Energy Density of Radioisotope Sources

The gravimetric energy density of radioisotope sources far exceeds chemical batteries. The total decay energy per unit mass follows directly from the average beta energy and the molar mass M :

$$\rho_E = \frac{E_{\text{total}}}{m} = \frac{N_A \cdot E_{\text{avg}}}{M} = \frac{6.022 \times 10^{23} \times 17.4 \times 10^3 \times 1.6 \times 10^{-19}}{63} \approx 7.4 \text{ kW h g}^{-1} \quad (6)$$

for ^{63}Ni ($E_{\text{avg}} = 17.4 \text{ keV}$, $M = 63$). This is approximately **4–5 orders of magnitude** ($\sim 30\,000$ – $50\,000\times$) the energy density of commercial Li-ion cells ($\sim 150 \text{ W h kg}^{-1}$ to $250 \text{ W h kg}^{-1} = \sim 0.15 \text{ W h g}^{-1}$ to 0.25 W h g^{-1}) [49]. However, this energy is released over a mean lifetime of ~ 144 years, corresponding to a specific power of only $\sim 5.9 \text{ mW g}^{-1}$ — the fundamental tradeoff of betavoltaic technology: enormous stored energy, delivered at a trickle.

3 Taxonomy of Nuclear Batteries

Nuclear batteries are classified by their energy conversion mechanism. We distinguish six principal architectures, summarized in Table 2.

Table 2: Taxonomy of nuclear battery architectures.

Architecture	Principle	Efficiency	Power range	Typical isotopes
RTG (thermoelectric)	Seebeck effect: $\Delta T \rightarrow V$ via thermocouples	3–8%	1 W–100 W	^{238}Pu , ^{241}Am
Thermionic	Electron emission from hot cathode to cool anode	5–20%	10 W–1 kW	^{238}Pu , ^{90}Sr
Betavoltaic	p-n junction collecting beta-generated e-h pairs	1–28%	1 nW–1 mW	^3H , ^{63}Ni , ^{147}Pm
Alphavoltaic	p-n junction collecting alpha-generated e-h pairs	1–10%	10 μW –1 mW	^{241}Am , ^{238}Pu
Optoelectric	Radioisotope $\rightarrow$ phosphor $\rightarrow$ photocell	0.5–3%	1 μW –100 μW	^{99}Tc , ^{147}Pm
Piezoelectric	Charge buildup $\rightarrow$ mechanical oscillation $\rightarrow$ piezo	0.01–1%	1 μW –100 μW	^{63}Ni , ^3H

3.1 Radioisotope Thermoelectric Generators

RTGs convert the heat generated by radioactive decay into electricity via the Seebeck effect in thermocouples. They are the most mature nuclear battery technology, with continuous

spaceflight heritage since 1961 (SNAP-3 on Transit 4B) [7]. The Multi-Mission RTG (MM-RTG) used on the Mars Curiosity rover produces ~ 110 W from ~ 4.8 kg of $^{238}\text{PuO}_2$ [15]. RTG efficiency is limited to 3–8% by Carnot constraints at the relatively low source temperatures (~ 1000 K). Their mass and power output are far beyond mobile consumer scale.

3.2 Betavoltaic Cells

Betavoltaic cells are the focus of this review. Unlike RTGs, they do not depend on a thermal intermediate: beta particles directly generate electron–hole pairs in a semiconductor junction, analogous to photovoltaic cells but with beta particles replacing photons [11]. This non-thermal mechanism eliminates Carnot limitations and enables miniaturization to sub-millimeter scales. The tradeoff is much lower power output: current devices produce 100 nW–100 μ W.

The comparison with photovoltaics is instructive. A solar cell converts photons of energy E_γ above the bandgap E_g into electron–hole pairs. A betavoltaic cell does the same with beta particles, but with critical differences: (i) beta particles deposit energy along a track (via ionization and scattering), not at a single point; (ii) the energy spectrum is continuous (Eq. 2), not monochromatic; (iii) backscattering from the semiconductor surface wastes a fraction of incident beta flux [13].

3.3 Other Architectures

Alphavoltaic cells use the same semiconductor junction principle but with alpha particles. Alphas have higher energy (~ 5 MeV) and shorter range (~ 20 μ m), enabling higher local power density but greater radiation damage [38].

Optoelectric nuclear batteries use a radioisotope to excite a phosphor, which then illuminates a photovoltaic cell. This two-stage conversion suffers from compounding inefficiencies but avoids direct radiation damage to the semiconductor [21].

Piezoelectric generators exploit the buildup of charge between plates to create mechanical oscillation, converting it to electricity via the piezoelectric effect. These produce pulsed output at ~ 35 Hz with milliwatt-level peak power [14].

4 Betavoltaic Conversion: Physics and Engineering

4.1 Operating Principle

A betavoltaic cell consists of three layers: (1) a beta-emitting radioisotope source, (2) a semiconductor absorber with a rectifying junction (p-n, p-i-n, or Schottky barrier), and (3) an electrical contact. The operating cycle is:

1. Beta particles are emitted isotropically from the source.
2. A fraction of emitted betas enter the semiconductor, losing energy via ionization (creating electron–hole pairs) and elastic scattering.
3. The built-in electric field of the p-n junction separates the generated carriers before they recombine.
4. The separated carriers flow through the external circuit as current.

The key performance parameters are:

- **Short-circuit current** (I_{sc}): proportional to the generation rate G of electron–hole pairs.
- **Open-circuit voltage** (V_{oc}): determined by the semiconductor bandgap and dark current.
- **Fill factor** (FF): ratio of maximum power to the product $I_{sc} \times V_{oc}$.
- **Conversion efficiency** (η): fraction of incident beta energy converted to electrical power.

4.2 Electron–Hole Pair Generation

The number of electron–hole pairs generated per beta particle is:

$$n_{e-h} = \frac{E_{dep}}{E_{pair}} \quad (7)$$

where E_{dep} is the energy deposited in the active region of the semiconductor and E_{pair} is the ionization energy (approximately $3 \times E_g$ for most semiconductors, where E_g is the bandgap). Typical values:

- Si ($E_g = 1.12$ eV): $E_{pair} \approx 3.6$ eV, so a 10 keV beta creates ~ 2800 pairs.
- 4H-SiC ($E_g = 3.26$ eV): $E_{pair} \approx 9.8$ eV, ~ 1020 pairs per 10 keV.
- Diamond ($E_g = 5.47$ eV): $E_{pair} \approx 16.4$ eV, ~ 610 pairs per 10 keV.

While wider-bandgap semiconductors generate fewer pairs per unit energy, they compensate with higher V_{oc} and superior radiation hardness, as analyzed in Section 6.

4.3 Coupling Efficiency

Not all emitted beta particles reach the semiconductor. The coupling efficiency η_{couple} accounts for: (i) geometric solid angle (4π emission, only forward-directed particles enter the absorber); (ii) self-absorption in the source; (iii) backscattering from the semiconductor surface; (iv) energy deposition in non-active layers (dead layers, contacts).

For a planar geometry with source on one side:

$$\eta_{couple} = \frac{1}{2} \cdot (1 - \eta_{backscatter}) \cdot (1 - \eta_{self-abs}) \cdot \eta_{dep} \quad (8)$$

The factor $\frac{1}{2}$ accounts for isotropic emission (half the betas travel away from the semiconductor). Backscattering fractions depend on the semiconductor’s effective atomic number Z_{eff} : diamond ($Z_{eff} \approx 6$) has $\eta_{backscatter} \approx 0.05$, while GaAs ($Z_{eff} \approx 32$) reaches $\eta_{backscatter} \approx 0.25$ [13].

4.4 Cell Architectures: Planar, Multilayer, and 3D

The coupling efficiency (Eq. 8) is dominated by geometry. Three architecture families exist (Fig. 2):

- **Planar (single-sided)**: the source sits on one side of the junction. Half the betas are lost by geometry (the $\frac{1}{2}$ factor of Eq. 8), limiting coupling to $\lesssim 25$ –30%. Simple to fabricate.

- **Multilayer (sandwich):** alternating ultra-thin source and absorber layers recover most of the 4π emission and raise coupling to 50–70% (e.g., ~ 300 nm tritide over ~ 10 μm absorbers). The BV100 uses this architecture with multiple 2 μm ^{63}Ni layers [8, 11].
- **3D/microstructured:** trenched, porous, or vertical-junction geometries enlarge the junction area per footprint, trading fabrication complexity for a $2\text{--}5\times$ higher output per unit area, at the cost of increased recombination at the surfaces [44].

The choice interacts with self-absorption. For low-energy emitters such as tritium (range ~ 1 μm in metal tritides), the source layer must stay thinner than the beta range, which forces multilayer architectures. For ^{63}Ni (beta range in nickel ~ 50 μm), single foils of 2–10 μm lose little activity to self-absorption, so planar stacks are viable.

Geometry optimization is today performed with Monte Carlo radiation transport codes (MCNP, Geant4, PENELOPE): coupling efficiency, energy-deposition profiles, and radiation dose are simulated for candidate layouts before fabrication [23, 44].




Figure 2: Schematic cross-section of a multilayer ^{63}Ni /diamond betavoltaic cell. Beta particles emitted into the semiconductor generate electron–hole pairs; the depletion-region field separates the carriers (Fig. 2 geometry follows [8]).

4.5 Conversion Efficiency Limit

The semiconductor conversion efficiency is bounded by the Shockley–Queisser-like limit adapted for betavoltaics:

$$\eta_S = \frac{V_{\text{oc}} \cdot J_{\text{sc}} \cdot FF}{\int_0^{E_{\text{max}}} E \cdot \frac{dN}{dE} dE} \quad (9)$$

where the denominator is the total incident beta power. For an ideal p-n junction ($Q = 1$, full collection), η_S increases with bandgap, reaching $\sim 30\%$ for the widest-bandgap materials (diamond, c-BN) [13]. In practice, non-radiative recombination, finite diffusion lengths, and contact losses reduce this to 1–10% for most demonstrated devices, with 28% achieved for p-n junction diamond under electron beam irradiation [20].

4.6 Power Output of a Single Betavoltaic Cell

The electrical power from a single cell is:

$$P_{\text{cell}} = \eta_{\text{total}} \cdot P_{\text{decay}} = \eta_{\text{couple}} \cdot \eta_S \cdot A \cdot E_{\text{avg}} \quad (10)$$

For the Betavolt BV100 (^{63}Ni , $\eta_{\text{total}} \approx 10\%$ consistent with demonstrated diamond conversion efficiencies):

$$A = \frac{P_{\text{cell}}}{\eta_{\text{total}} \cdot E_{\text{avg}}} = \frac{10^{-4}}{0.10 \times 17.4 \times 10^3 \times 1.6 \times 10^{-19}} \approx 3.6 \times 10^{11} \text{ Bq} \approx 9.7 \text{ Ci} \quad (11)$$

This is consistent with a stacked multilayer ^{63}Ni source: with $\sim 37 \text{ mCi/cm}^2$ per electroplated foil [37] and a $\sim 2.25 \text{ cm}^2$ footprint, ~ 120 ultra-thin layers are required—plausible within the 5 mm BV100 envelope.

4.7 Power Conditioning and System Integration

The raw output of a betavoltaic cell is a low-voltage, low-current DC source whose open-circuit voltage tracks the absorber bandgap ($V_{oc} \approx 0.5 \text{ V} - 2 \text{ V}$). Delivering useful power at the micro-watt level is itself an engineering problem:

- **DC–DC upconversion:** switched-capacitor or inductive converters with sub-micro-watt quiescent current (nanopower boost converters draw $\sim 100\text{--}300 \text{ nA}$) raise 0.5–2 V to 3.3 V at 70–90% efficiency. At these power levels the converter overhead is a significant fraction of the cell output, so efficiency and sleep modes matter as much as the cell itself.
- **Energy buffering:** an integrated capacitor or microbattery decouples the load from the cell, enabling burst operation (e.g., a periodic BLE transmission) at power levels far above the cell’s continuous average.
- **Array design:** cells are connected in series for voltage and in parallel for current. Mismatch, leakage, and per-cell degradation must be managed; a single degraded cell can limit an entire series string.
- **Temperature behavior:** V_{oc} decreases with temperature ($\sim -2 \text{ mV K}^{-1}$ for Si-class junctions), while I_{sc} is set by activity; the BV100’s rated -60°C to 120°C operating range is representative [8].

For the 10–100 μW always-on niche of Scenario C, a complete power train (cell + upconverter + storage + supervisor) adds $\sim 0.1\text{--}0.5 \text{ cm}^3$ and costs $\sim 20\text{--}40\%$ of the cell’s output—an acceptable price for 50-year autonomy. For the $\sim 70 \text{ mW}$ hybrid module of Scenario B, converter efficiency and array matching become first-order design drivers.

5 Radioisotope Source Candidates

Table 3 provides a comprehensive comparison of the four principal beta-emitting radioisotopes for betavoltaic applications.

Table 3: Radioisotope candidates for betavoltaic power sources. Data from [11, 13, 16].

Isotope	$T_{1/2}$ (yr)	E_{avg} (keV)	E_{max} (keV)	W_{spec} (W/g)	Cost/Ci (USD)	Availability
^3H (tritium)	12.3	5.7	18.6	3.3×10^{-1}	~ 3.50	Good (CANDU)
^{63}Ni	100.1	17.4	66.9	5.9×10^{-3}	~ 4000	Limited (reactor)
^{147}Pm	2.62	62	225	3.4×10^{-1}	N/A	Unavailable (US)
^{14}C	5730	49	156	1.3×10^{-3}	~ 30	Waste product

5.1 Tritium (^3H)

Tritium decays to stable ^3He via pure beta emission with $E_{\text{max}} = 18.6\text{ keV}$ —the lowest energy of any practical isotope. This makes it radiation-safe (betas cannot penetrate paper) and eliminates semiconductor displacement damage. However, the low energy means self-absorption in the source is severe: betas are absorbed within $\sim 1\text{ }\mu\text{m}$ of a metal tritide surface, requiring multilayer sandwich architectures (alternating $\sim 300\text{ nm}$ tritide and semiconductor layers) to utilize the full beta flux [11].

Tritium is the isotope of choice for most commercial betavoltaic products (City Labs NanoTritium) due to: (i) the lowest regulatory burden (general license in the US since 2010); (ii) wide availability from CANDU reactor moderator; (iii) low cost ($\sim \$3.50/\text{Ci}$). The power density limitation is the fundamental constraint: a tritium gas betavoltaic of 1 cm^3 at 3 atm produces only $\sim 8.4\text{ }\mu\text{W}$ at 10% efficiency [11]. Metal tritide layered designs reach $\sim 20\text{ }\mu\text{W}/\text{cm}^3$.

5.2 Nickel-63 (^{63}Ni)

^{63}Ni decays to stable ^{63}Cu with $E_{\text{max}} = 66.9\text{ keV}$ and a half-life of 100.1 years—making it the “conservative” choice for long-life applications, retaining $>50\%$ activity after a century [39]. Its higher average energy (17.4 keV vs. 5.7 keV for tritium) yields $\sim 10\%$ better coupling efficiency with all semiconductor absorbers [13].

The critical limitation is cost: enriched ^{63}Ni costs $\sim \$4000/\text{Ci}$, approximately $1000\times$ more than tritium. Production requires neutron irradiation of ^{62}Ni targets in nuclear reactors, followed by chemical purification and electroplating onto nickel foils [36]. Annual global production is limited to a few Ci.

5.3 Promethium-147 (^{147}Pm)

^{147}Pm offers the highest power density of the four viable isotopes ($\sim 0.34\text{ W g}^{-1}$, marginally above tritium) due to its relatively high average beta energy and short half-life. The Betacel pacemaker battery (1968–1974) used ^{147}Pm , achieving 4% efficiency and 400 μW output in a cardiac implant [11]. However, **^{147}Pm is currently unavailable for purchase in the United States** and only available in limited quantities from Chinese and Russian reactor programs. Additionally, the ^{146}Pm contaminant emits gammas requiring heavy shielding, increasing device volume [11].

5.4 Carbon-14 (^{14}C)

^{14}C has emerged as an intriguing candidate following a 2025 ACS presentation by Su-II In demonstrating a dye-sensitized betavoltaic cell with ^{14}C at both anode and cathode, achieving 2.86% efficiency—a $6\times$ improvement over the previous 0.48% [24]. The dual-placement “electron avalanche” design and the enormous availability of the UK’s $\sim 55\,000$ tonnes of irradiated AGR reactor graphite—containing the largest share of the $\sim 17.8\text{ PBq}$ ^{14}C inventory in UK wastes scheduled for transport to a geological disposal facility [25, 26]—make this a potentially transformative isotope for cost reduction, though the half-life (5730 years) complicates end-of-life management.

6 Semiconductor Absorber Materials

The semiconductor absorber determines the conversion efficiency, voltage, radiation hardness, and operational lifetime of the betavoltaic cell. We evaluate seven candidate materials.

Table 4: Semiconductor materials for betavoltaic absorbers. Data compiled from [13, 22, 11, 23].

Material	E_g (eV)	Z_{eff}	η_{max} (experimental)	Radiation hardness	Maturity
Si	1.12	14	2–4%	Low	Production
GaAs	1.42	32	2–3%	Low	Production
4H-SiC	3.26	10	1–5%	High	Production
GaN	3.40	16	0.5–1.1%	High	Maturing
Diamond	5.47	6	5–28%	Very high	R&D
c-BN	6.40	5	~30% (theo.)	Very high	Early R&D
β -Ga ₂ O ₃	4.80	18	TBD	High	Early R&D

6.1 Silicon and Gallium Arsenide

Silicon was the first betavoltaic absorber (RCA, 1954) [12] and remains the most mature semiconductor technology. However, its narrow bandgap (1.12 eV) yields low V_{oc} (~ 0.5 V) and poor radiation hardness—beta particles above ~ 220 keV cause measurable lattice damage. GaAs offers a modestly wider bandgap but suffers from high Z_{eff} (~ 32), causing 20–25% backscattering losses [13]. Neither material is competitive for high-efficiency betavoltaics.

6.2 4H-Silicon Carbide

4H-SiC ($E_g = 3.26$ eV) is the current “workhorse” of high-performance betavoltaics. Its advantages:

- Bandgap $3\times$ wider than Si, yielding $V_{\text{oc}} \approx 1.0$ V—twice that of Si.
- Excellent radiation hardness: the higher displacement energy (~ 350 keV) extends operational life.
- Mature fabrication: 4H-SiC substrates up to 150 mm are commercially available, with well-characterized n- and p-type doping.
- Long minority carrier diffusion lengths: $L \approx 100$ μm enables efficient collection of carriers generated deep in the absorber.

The p-n junction 4H-SiC betavoltaic by Chandrashekhar et al. (2006) demonstrated power density 50% higher than Schottky barrier designs for the same ^{63}Ni activity [17]. Thomas et al. (2016) achieved record efficiency with tritium sources [18]. Widetronix Inc. offers the first commercial 4H-SiC betavoltaic products [19]. More recent work quantifies trap-assisted losses and long-term radiation degradation in 4H-SiC cells [59, 46].

6.3 Diamond

Diamond ($E_g = 5.47$ eV) is the theoretically optimal betavoltaic absorber: the combination of ultra-wide bandgap, lowest effective atomic number ($Z_{\text{eff}} = 6$, minimizing backscattering), and self-repairing crystal structure (interstitial displacement recovery under irradiation) gives diamond a potential 34% power density advantage over 4H-SiC for tritium sources [13].

The Betavolt BV100 uses “4th-generation diamond semiconductor” technology. Shimaoka et al. demonstrated 28% semiconductor conversion efficiency for p-n junction diamond under electron beam irradiation [20]—the highest efficiency reported for any betavoltaic material. However, n-type diamond doping remains problematic, and substrate sizes are limited to a few mm².

6.4 Cubic Boron Nitride

c-BN ($E_g = 6.40$ eV) is an emerging ultra-wide-bandgap material with the highest theoretical conversion efficiency among all semiconductors ($\sim 30\%$ at $Q = 1$) [13]. It can be doped both n- and p-type and has excellent coupling efficiency with both ³H and ⁶³Ni sources. The technology is in its earliest stages—no experimental betavoltaic device has been demonstrated.

7 State of the Art (2024–2026)

7.1 Betavolt BV100

Announced January 2024, the BV100 is the most publicized betavoltaic device of the current era. Key specifications [8, 40]:

- Dimensions: 15 mm × 15 mm × 5 mm (~ 1.1 cm³)
- Output: 100 μ W at 3 V
- Radioisotope: ⁶³Ni (multiple 2 μ m layers)
- Semiconductor: 4th-generation diamond (multiple 10 μ m layers)
- Lifespan: 50 years
- Operating temperature: -60°C to 120°C

Betavolt claims the BV100 can be connected in series (higher voltage) or parallel (higher current). The company’s roadmap targets 1 W by 2025 and consumer smartphone integration pending regulatory approval (applications in drones and wearables are also promoted [55]). The device received unusually broad but largely uncritical press coverage [53, 57, 56, 54]; as of mid-2026, independent verification of the BV100’s performance has not been published.

7.2 NRD NBV Series

NRD (Nuclear Research & Development) announced the NBV series in June 2026, using ⁶³Ni with a solid-state betavoltaic design [9, 41]. Specifications:

- Dimensions: 20 mm × 20 mm × 12 mm
- Output: 5 nW–500 nW

- Lifespan: > 100 years

The NBV demonstrates the state of the art in longevity but its power output is insufficient for even the most power-frugal smartphone subsystems.

7.3 City Labs NanoTritium

City Labs (Miami) holds the only general license for manufacturing and distribution of betavoltaic products (awarded 2010, US NRC) [30]. Their NanoTritium battery uses tritium metal tritide with a semiconductor absorber, producing ~ 20 nW per cell. NASA has funded development for unattended sensor applications [31].

7.4 Market Context

The global betavoltaic cell market was valued at $\sim \$380$ M in 2026, growing at 6.4% CAGR, dominated by medical implant and aerospace applications [42]. The radioisotope battery market is projected to reach $\$760$ M by 2030 [43]. Consumer applications remain speculative. Independent analyses of the Betavolt claims are broadly skeptical about near-term phone integration [50, 51, 52], and recent academic reviews survey the full field [44].

8 Alternative and Competing Technologies

Betavoltaic cells do not compete in a vacuum. Claims of viability for mobile devices must be weighed against the alternatives summarized in Table 5.

8.1 Solid-State Batteries

All-solid-state lithium batteries replace the flammable organic electrolyte with a ceramic or polymer electrolyte, enabling lithium-metal anodes and projected cell-level energy densities of 400 W h kg^{-1} to 500 W h kg^{-1} (versus 250 W h kg^{-1} to 350 W h kg^{-1} for the best 2026 NMC cells). They are rechargeable, contain no radioactive material, and carry no nuclear regulatory burden. They attack the same weakness of conventional Li-ion (energy density) without betavoltaic drawbacks, but they cannot address the longevity gap: their calendar life remains limited by electrolyte/ electrode interfacial degradation to a decade or less.

8.2 Micro Fuel Cells

Direct methanol fuel cells (DMFCs) convert liquid methanol directly into electricity, offering system-level energy densities of 300 W h kg^{-1} to 1000 W h kg^{-1} —competitive with the “stored energy” of a betavoltaic over short horizons—and rapid refueling from a liquid cartridge. The obstacles are the same ones that defeated portable fuel cells in the 2000s: methanol logistics, catalyst cost, water management, and consumer safety. DMFCs remain confined to backup-power niches.

8.3 Energy Harvesting

Energy harvesting directly competes with betavoltaics in the always-on *micropower* niche:[11, 13]

- **Photovoltaic:** $10 \mu\text{W cm}^{-2}$ to $100 \mu\text{W cm}^{-2}$ under indoor lighting, 10mW cm^{-2} or more in sunlight—but intermittent and placement-dependent.
- **Thermoelectric:** $10 \mu\text{W}$ to $100 \mu\text{W}$ from body heat across a 5 K gradient, continuous while worn.
- **RF harvesting:** nano- to micro-watt from ambient radio signals, but strongly dependent on transmitter proximity.
- **Kinetic:** micro- to milli-watt bursts from motion, but mechanically complex and usage-dependent.

The decisive betavoltaic advantage is **determinism**: a sealed radioisotope source delivers a constant, environment-independent output for decades, with no moving parts and no dependence on light, heat gradients, or ambient signals. The decisive disadvantage is regulatory burden and public perception.

8.4 Supercapacitors

Supercapacitors offer 5Wh kg^{-1} to 10Wh kg^{-1} and cycle lifetimes beyond 1 000 000, but their energy density is two orders of magnitude below batteries; they complement rather than compete with any of the above as short-term power buffers.

Table 5: Betavoltaics versus competing power technologies.

Technology	Energy density	Typical output	Autonomy	Refuel/recharge	Radio-active	Maturity
Li-ion (NMC 2026)	250–350 Wh/kg	0.1–10 W	1–3 days	Yes	No	Mature
Solid-state (R&D)	400–500 Wh/kg (proj.)	mW–W	days–weeks	Yes	No	Emerging
DMFC	300–1000 Wh/kg (sys.)	1–20 W	hours–days	Methanol	No	Niche
PV (indoor)	—	10–100 $\mu\text{W/cm}^2$	daylight only	No	No	Mature
TEG (body heat)	—	10–100 μW	while worn	No	No	Mature
RF harvesting	—	nW– μW	varies	No	No	Emerging
Betavoltaic (^{63}Ni)	$\sim 7400 \text{Wh/g}$ (decay)	100 nW–100 μW	50–100 yr	Never	Yes	R&D

8.5 Comparative Assessment

Betavoltaics win only where the requirements are simultaneously **decades of autonomy**, **micropower output**, and **environmental independence**. They lose decisively on cost, power density, regulatory burden, and public acceptance. For the smartphone applications analyzed in Section 10, the honest ranking is: solid-state batteries and improved Li-ion address the energy-density shortfall; harvesting and betavoltaics compete for the always-on subsystem niche; and none of the alternatives removes the fundamental tradeoff that betavoltaic power is small but eternal.

9 Smartphone Power Budget Analysis

To assess betavoltaic feasibility, we must first characterize the target: the power consumption of a modern smartphone.

9.1 Power Consumption by Operating State

Table 6 summarizes power consumption across operating states, compiled from Carroll and Heiser [27] (Nexus One), Pathak et al. [28], and manufacturer datasheets.

Table 6: Smartphone power consumption by operating state. Data from [27, 28, 29].

State	Power (mW)	Duration per day
Suspended (deep sleep)	69	14–16 h
Idle (awake, screen off)	269	2–4 h
Audio playback (screen off)	320	1–2 h
Web browsing	500–1000	1–3 h
Video playback	450–700	1–2 h
Voice call	1050	0.5–1 h
Active gaming	2000–6000	0.5–1 h
Camera (video recording)	1500–3000	0–0.5 h
Typical daily average	200–500	
Peak (gaming)	6000	

9.2 Daily Energy Budget

A typical smartphone with a 5000 mA h battery at 3.8 V stores:

$$E_{\text{Li-ion}} = 5000 \times 3.8 = 19\,000 \text{ mW h} = 19 \text{ W h} = 68\,400 \text{ J} \quad (12)$$

At a daily consumption of $\sim 5 \text{ W h}$ (a reasonable average), the battery lasts ~ 3.8 days per charge—consistent with real-world experience. The annual energy demand is:

$$E_{\text{annual}} = 5 \text{ W h d}^{-1} \times 365 = 1825 \text{ W h yr}^{-1} \approx 1.83 \text{ kW h} \quad (13)$$

9.3 Component Breakdown

The dominant power consumers in a smartphone are [27]:

- **Display** (LCD/OLED): 300–600 mW (30–40% of active power)
- **Application processor (SoC)**: 200–2000 mW (20–35%)
- **Cellular radio (GSM/LTE/5G)**: 100–800 mW (10–25%)
- **Wi-Fi/Bluetooth**: 50–300 mW (5–10%)
- **Other** (sensors, audio, memory): 50–200 mW

During deep sleep (the dominant state), the cellular modem maintains network connectivity at $\sim 45 \text{ mW}$, accounting for 45–65% of the suspended-state draw [27].

10 Feasibility Analysis: Can Betavoltaics Power a Phone?

This section presents the core original contribution of this paper: a rigorous mathematical model for scaling betavoltaic cells to smartphone power levels.

10.1 Model Parameters

We define the following variables:

$$P_{\text{req}} = \text{required electrical power (W)} \quad (14)$$

$$\eta_{\text{total}} = \text{overall conversion efficiency} \quad (15)$$

$$E_{\text{avg}} = \text{average beta energy (J)} \quad (16)$$

$$A_{\text{total}} = \text{total radioisotope activity (Bq)} \quad (17)$$

$$V_{\text{cell}} = \text{volume of a single betavoltaic cell (cm}^3\text{)} \quad (18)$$

The power output of a betavoltaic array is:

$$P_{\text{out}} = \eta_{\text{total}} \cdot A_{\text{total}} \cdot E_{\text{avg}} \quad (19)$$

The required activity for a given power target is:

$$A_{\text{total}} = \frac{P_{\text{req}}}{\eta_{\text{total}} \cdot E_{\text{avg}}} \quad (20)$$

10.2 Scenario A: Pure Betavoltaic Replacement

Target: Replace the Li-ion battery entirely. $P_{\text{req}} = 2 \text{ W}$ (active smartphone average).

Using ^{63}Ni with $E_{\text{avg}} = 17.4 \text{ keV}$ and $\eta_{\text{total}} = 10\%$ (optimistic near-future efficiency):

$$A_{\text{total}} = \frac{2}{0.10 \times 17.4 \times 10^3 \times 1.6 \times 10^{-19}} = 7.2 \times 10^{15} \text{ Bq} = 194 \text{ kCi} \quad (21)$$

The required mass of ^{63}Ni :

$$m_{\text{Ni-63}} = \frac{A_{\text{total}} \cdot M_{\text{Ni}}}{N_A \cdot \lambda} = \frac{7.2 \times 10^{15} \times 63}{6.022 \times 10^{23} \times \frac{\ln 2}{3.16 \times 10^9}} \approx 3.4 \text{ kg} \quad (22)$$

The ^{63}Ni source alone occupies $\sim 380 \text{ cm}^3$ (nickel density 8.9 g cm^{-3}); including the semiconductor absorbers, encapsulation, and shielding, the total module mass would be $\sim 5 \text{ kg}$ —**approximately 10× heavier than a typical smartphone**—and its volume $\sim 500 \text{ cm}^3$ to 800 cm^3 , versus $\sim 20 \text{ cm}^3$ for a Li-ion cell.

Verdict: Pure betavoltaic replacement for active smartphone use is **physically possible but impractical** due to mass, volume, and isotope availability. The fundamental issue is the power gap: at $\eta_{\text{total}} = 10\%$, every watt of output requires $\sim 97 \text{ kCi}$ of ^{63}Ni . At current experimental efficiencies of 1–3%, the required activity increases to $\sim 320 \text{ kCi}$ to 970 kCi —four to six orders of magnitude above global annual ^{63}Ni production (a few Ci), making the module prohibitively large and expensive.

10.3 Scenario B: Hybrid Betavoltaic Trickle-Charge

Target: A betavoltaic module augments the Li-ion battery, reducing cycle stress and extending lifespan.

The first question is quantitative: how much betavoltaic power is actually needed to offset standby drain? During the ~ 16 hours/day of suspended state, the phone consumes:

$$E_{\text{suspend}} = 69 \times 10^{-3} \times 16 = 1.104 \text{ W h} \quad (23)$$

so a module that fully covers the suspended state must deliver an average of $\sim 69 \text{ mW}$ (1.104 Wh spread over 16 h). The activity required for a continuous output P at efficiency η_{total} is:

$$A_{\text{hybrid}} = \frac{P}{\eta_{\text{total}} \cdot E_{\text{avg}}} \quad (24)$$

For $P = 1 \text{ mW}$ (the level of near-term BV100-class devices) at $\eta_{\text{total}} = 10\%$:

$$A_{1 \text{ mW}} = \frac{10^{-3}}{0.10 \times 17.4 \times 10^3 \times 1.6 \times 10^{-19}} = 3.6 \times 10^{12} \text{ Bq} = 97 \text{ Ci} \quad (25)$$

i.e. only $\sim 1.7 \text{ g}$ of ^{63}Ni . But this 1 mW delivers just 24 mWh per day— $\sim 2\%$ of the suspended-state drain and $\sim 0.5\%$ of the $\sim 5 \text{ Wh}$ daily budget. A 1 mW module therefore **cannot meaningfully reduce Li-ion cycling**; its practical value is confined to the always-on subsystems of Scenario C above.

To cover the suspended state in full (69 mW average):

$$A_{\text{suspend}} = \frac{69 \times 10^{-3}}{0.10 \times 17.4 \times 10^3 \times 1.6 \times 10^{-19}} = 2.5 \times 10^{14} \text{ Bq} = 6.7 \text{ kCi} \quad (26)$$

requiring $\sim 120 \text{ g}$ of ^{63}Ni and a module of $\sim 200 \text{ g}$ to 300 g with absorber, encapsulation, and shielding—far beyond what a smartphone can accommodate, and 6.7 kCi exceeds global annual ^{63}Ni production by three orders of magnitude.

Impact on battery lifecycle. Li-ion degradation has two components: cycle aging (scales with the energy throughput drawn from the cell) and calendar aging (proceeds even at rest, accelerated by high temperature and high state of charge). A betavoltaic module reduces only the former, and only in proportion to the fraction of the daily budget it supplies:

- No hybrid: $\sim 5 \text{ Wh/day}$ drawn from Li-ion (0.26 full-equivalent cycles/day of a 19 Wh cell) $\rightarrow 500$ cycles in ~ 5 years
- With a 70 mW module covering suspend: throughput falls to $\sim 3.3 \text{ Wh/day}$ $\rightarrow$ lifespan extends to ~ 8 years
- With a 200 mW module (suspend + idle, 2040s): throughput $\sim 0.2 \text{ Wh/day}$ $\rightarrow$ cycle aging becomes negligible and lifespan is capped by calendar aging at ~ 15 – 20 years
- 1 mW modules: throughput reduction $< 1\%$ $\rightarrow$ no measurable cycle-life benefit

Verdict: The hybrid architecture is **realistic only in the mid-to-long term**. Meaningful cycle-life extension requires ~ 10 – 100 mW modules that are 15 – 30 years away, and a genuine “ 15 – 20 -year smartphone battery” requires $\sim 200 \text{ mW}$ – 1 W modules. Near-term 1 mW hybrids are indistinguishable from Scenario C in practice—their value is always-on functionality, not battery longevity.

10.4 Scenario C: Betavoltaic for Always-On Subsystems

Target: Power only the ultra-low-power subsystems: secure element (TPM), real-time clock (RTC), ambient sensor hub, “find my phone” BLE beacon.

Typical power budget for these subsystems: 10–100 μW . This falls within the output range of current betavoltaic devices ($\sim 100 \mu\text{W}$ for BV100-class).

A single BV100-class module (100 μW , 3 V, 1.1 cm^3 , $\sim 10 \text{ Ci}$ of ^{63}Ni at $\eta_{\text{total}} = 10\%$) could power:

- An always-on BLE beacon for device tracking
- A low-power RTC maintaining time without main battery
- A security coprocessor for biometric authentication
- Environmental sensors (temperature, humidity, pressure)

These features would remain functional for 50+ years even if the main Li-ion battery is completely discharged or removed.

Verdict: This is the **most immediately achievable** use case, requiring no improvements beyond current BV100-class technology.

Figure 3 summarizes the power landscape: the gap between current betavoltaic output and smartphone demand spans two to four orders of magnitude, and the three scenarios occupy very different positions on this axis.




Figure 3: Logarithmic comparison of the power required by the three deployment scenarios (Section 10) and of current BV100-class output, against typical smartphone demand. The one-to-four-orders-of-magnitude gap between $\sim 100 \mu\text{W}$ cells and the 2 W active phone is the central quantitative result of this paper.

10.5 Summary of Feasibility

Table 7: Feasibility summary for three betavoltaic deployment scenarios.

Scenario	P_{req} (W)	Isotope	Activity (Ci)	Module mass (g)	Timeline (yr)	Verdict
A: Pure replacement	2.0	^{63}Ni	194,000	5000	>30	Impractical
B: Hybrid trickle	0.07	^{63}Ni	6,700	250	15–20	Viable mid-term
C: Always-on subsys.	0.0001	^{63}Ni	9.7	3	5–10	Achievable now

11 Radiation Shielding Requirements

11.1 Beta Particle Penetration

The maximum range of beta particles in matter determines shielding requirements. For ^{63}Ni ($E_{\text{max}} = 66.9 \text{ keV}$), the CSDA (Continuous Slowing Down Approximation) range in silicon is $\sim 50 \mu\text{m}$, and in tungsten $\sim 10 \mu\text{m}$ [45]. These low energies are easily contained: a 0.1 mm tungsten foil attenuates $>99\%$ of ^{63}Ni betas.

For tritium ($E_{\text{max}} = 18.6 \text{ keV}$), the range is even shorter: $\sim 6 \mu\text{m}$ in silicon, stopped by a single sheet of paper.

11.2 Bremsstrahlung Radiation

When beta particles decelerate in high- Z materials, they produce Bremsstrahlung X-rays. The maximum Bremsstrahlung energy equals E_{max} of the beta particle. For ^{63}Ni , this is $\sim 67 \text{ keV}$ —below the threshold for significant biological harm at the activities involved.

The Bremsstrahlung dose rate from a planar ^{63}Ni source at 1 Ci behind 1 mm tungsten shielding is estimated at $\sim 0.01 \mu\text{Sv h}^{-1}$ [32]—well below the ICRP public dose limit of 1 mSv yr^{-1} .

11.3 Shielding Mass Budget

For a BV100-class device (9.7 Ci of ^{63}Ni):

- Beta shielding: 0.1 mm tungsten ($\sim 0.4 \text{ g}$)
- Bremsstrahlung shielding: 1 mm tungsten ($\sim 4 \text{ g}$)
- Total shielding mass: $\sim 5 \text{ g}$ (negligible)

Shielding is not a significant constraint for ^{63}Ni betavoltaics. The situation differs for higher-energy isotopes (^{147}Pm , ^{90}Sr) which require centimeter-scale lead shielding.

11.4 Dosimetry and Exemption Levels

For consumer products, the governing quantity is the effective dose to a member of the public, limited to 1 mSv yr^{-1} by ICRP and IAEA recommendations (Section 12). Two regulatory thresholds are decisive for betavoltaics:

- **Exempt activity and concentration** (IAEA GSR Part 3): ^{63}Ni is exempt below $\sim 1 \times 10^5 \text{ Bq g}^{-1}$ and $\sim 1 \times 10^7 \text{ Bq}$ total; tritium is exempt at $\sim 1 \times 10^6 \text{ Bq g}^{-1}$ and $\sim 1 \times 10^9 \text{ Bq}$ total [32]. A BV100-class ^{63}Ni module at $\sim 10 \text{ Ci}$ ($\sim 4 \times 10^{11} \text{ Bq}$) exceeds the exempt total by four orders of magnitude, so it requires specific licensing; low-activity tritium self-luminous products fall under general license. This asymmetry is why tritium dominates commercially available betavoltaics (Section 5).
- **Contact dose**: international guidance for consumer products requires the contact dose rate to be indistinguishable from background (or $\lesssim 1 \mu\text{Sv h}^{-1}$). With 1 mm tungsten encapsulation, a ^{63}Ni module satisfies this by a wide margin (Section 11).

12 Regulatory Framework

12.1 IAEA Safety Standards

The IAEA Safety Guide SSG-36 [32] establishes the framework for radiation safety of consumer products containing radioactive material. Key requirements:

- **Justification:** the product must provide a benefit commensurate with the radiation risk.
- **Dose limitation:** individual doses must not exceed 1 mSv yr^{-1} for members of the public.
- **Shielding and containment:** the product must be designed to prevent radiation exposure in normal and reasonably foreseeable adverse conditions (including fire, crushing, and submersion).
- **Disposal:** arrangements for safe disposal or recycling at end of life.

12.2 US NRC Regulations

Under 10 CFR 30–40, radioactive materials for consumer products fall into two categories [33]:

- **General license:** available for products containing tritium in self-luminous devices (exit signs, watch dials). City Labs’ NanoTritium holds the only general license for betavoltaic products (2010).
- **Specific license:** required for products containing ^{63}Ni , ^{147}Pm , or other non-exempted isotopes. Betavolt’s BV100 would require a specific NRC license for US distribution.

12.3 European Union

France prohibits intentional addition of radionuclides to consumer products [35], while the UK and Germany permit tritium-containing products under EURATOM Directive 2013/59 [34]. A harmonized EU pathway for betavoltaic consumer products does not yet exist.

12.4 Transport and Product Qualification

Beyond in-use licensing, consumer devices must survive transport and qualification testing:

- **Transport:** shipping radioactive consumer products falls under the IAEA Regulations for the Safe Transport of Radioactive Material (SSR-6) and, in Europe, ADR (road) and IMDG (sea). A $\sim 10 \text{ Ci}$ ^{63}Ni module (0.37 TBq) sits just below the A_2 limit for ^{63}Ni ($\sim 4 \times 10^{11} \text{ Bq}$), so it is a **Type A** package: certified packaging must survive the 9 m drop, 1 m puncture, and a 30-minute fire test at 800°C without releasing activity. The kilo-curie quantities of Scenario B would demand Type B certification, a step change in cost and logistics.
- **Environmental qualification:** consumer-electronics standards (IEC 60068; MIL-STD-810 for ruggedized products) add thermal cycling, vibration, humidity, and mechanical-shock requirements. The BV100’s claimed operating range of -60°C to 120°C already spans typical qualification limits [8].
- **Crush, fire, and leach testing:** hermetic encapsulation must prevent radionuclide release under crushing, submersion, and fire (SSG-36 requirements, Section 12).

12.5 Implications for Smartphone Integration

Any betavoltaic smartphone battery would require:

1. Specific nuclear regulatory approval in every target market.
2. Demonstration that crushing, fire, and immersion tests do not release radioactive material.
3. A take-back program for end-of-life disposal.
4. Public education to overcome “nuclear” stigma.

The regulatory pathway is achievable for tritium-based devices (precedent exists) but significantly more challenging for ^{63}Ni , which is not currently covered by any general license.

13 Environmental and Economic Assessment

13.1 Lifecycle Comparison

Table 8: Lifecycle comparison: Li-ion vs. betavoltaic battery for smartphone application.

Parameter	Li-ion (NMC)	Betavoltaic (^{63}Ni)
Operational lifetime	3–5 yr (500–1000 cycles)	50–100 yr
Capacity degradation	20% at 500 cycles	<1% at 50 yr
Recharging required	Every 1–3 days	Never
E-waste per device	1 cell every 3–5 yr	1 cell per device lifetime
Toxic materials	Cobalt, lithium, electrolyte	Stable copper (end product)
Recycling complexity	High (mixed chemistry)	Low (metallic copper)
Embodied energy	~50–100 kWh/kg	~1000 kWh/kg (isotope production)

13.2 Total Cost of Ownership

For a smartphone with a ~\$15 Li-ion battery replaced every 3 years:

$$\text{TCO}_{\text{Li-ion}}(30 \text{ yr}) = 10 \times \$15 = \$150 \quad (27)$$

The betavoltaic comparison must scale with activity. A 1 mW always-on module (~10 Ci of ^{63}Ni at $\eta_{\text{total}} = 10\%$) costs ~\$40,000 at current prices of ~\$4000/Ci—already ~270× the 30-year Li-ion TCO and the price of a high-end phone itself. A 70 mW standby module requires ~6.7 kCi, i.e. ~\$27M at today’s prices; even at the aspirational ~\$500/Ci of scaled 2040s production this remains ~\$3.4M. Cost competitiveness for hybrid phone batteries therefore does not follow from isotope price reductions alone.

The economics of betavoltaics are attractive only where replacement is expensive and reliability is paramount: medical implants (the Betacel precedent of 1968–1974), unattended remote sensors, and space systems. For these, a module that eliminates a surgical replacement or a maintenance visit is already cost-effective, and tritium-based devices (~\$3.50/Ci) such as City Labs’ NanoTritium reduce module cost by orders of magnitude at the price of a 12.3-year half-life.

13.3 Environmental Impact

If betavoltaic modules reduce Li-ion replacement frequency by 80–100%, the cumulative e-waste reduction is significant:

$$\Delta_{\text{waste}} = N_{\text{devices}} \times \Delta m_{\text{Li-ion}} \times \Delta_{\text{replacement}} \quad (28)$$

With 1.5 billion smartphones sold annually and a typical Li-ion cell mass of $\sim 50\text{--}80$ g, eliminating 80% of battery replacements would prevent $\sim 60\text{ kt yr}^{-1}$ to 70 kt yr^{-1} of Li-ion waste—a meaningful contribution to the 50 Mt/yr e-waste problem (though the dominant smartphone e-waste mass remains the device itself, not the battery).

14 Technology Roadmap

14.1 Critical Bottlenecks

Two technology bottlenecks must be overcome for betavoltaics to reach the ~ 100 mW level needed for meaningful hybrid benefits:

1. **Diamond semiconductor fabrication:** current CVD diamond substrates are limited to a few mm^2 with high defect density. Scaling to 150 mm wafers (matching SiC) requires 15–20 years of materials development.
2. **^{63}Ni source production:** global annual production is a few Ci. Scaling to the ~ 10 Ci required per 1 mW module—let alone the kilo-Ci quantities needed to offset standby drain—requires dedicated reactor irradiation capacity and isotope separation infrastructure.

14.2 Roadmap Phases

Table 9: Technology roadmap for betavoltaic mobile applications.

Phase	Milestone	Impact
2024–2027	BV100 mass production; NRD NBV commercialization	IoT sensors, medical implants, military
2027–2030	10 mW ^{63}Ni module demonstrated	Ultra-low-power wearables, hearing aids
2030–2035	150 mm CVD diamond wafers; 50 mW hybrid modules	Smartphone standby subsystems
2035–2040	200 mW modules; ^{14}C commercial sources	Hybrid standby coverage viable
2040–2050	500 mW–1 W modules; full regulatory harmonization	15–20 yr consumer battery life

Figure 4 plots the same phases on a timeline.




Figure 4: Timeline of the roadmap phases of Table 9. Labels give the continuous electrical output of a single module; the 2035–2040 phase marks the point at which hybrid standby coverage (Scenario B) becomes technically and economically viable.

14.3 Emerging Opportunities

Beyond smartphones, betavoltaic technology addresses several high-value niches where low power but extreme longevity is critical [47]:

- **Medical implants:** pacemakers, cochlear implants, neural interfaces—replacing Li-ion with 50-year betavoltaic eliminates replacement surgeries.
- **Structural health monitoring:** sensors embedded in bridges, dams, and buildings that operate for decades without maintenance.
- **Space:** CubeSat and deep-space missions where solar power is insufficient.
- **IoT:** remote environmental sensors, agricultural monitors, wildlife trackers.

Longer-horizon visions extend this logic to self-powered nanoscale machinery [48].

15 Conclusions

This paper has presented a comprehensive review and original feasibility analysis of betavoltaic nuclear batteries for mobile consumer electronics. Our principal findings are:

1. **Pure betavoltaic replacement of Li-ion for smartphones is not feasible within the next 20 years.** The power gap between current betavoltaic output ($\sim 100 \mu\text{W}$) and active smartphone demand ($\sim 2 \text{ W}$) is a factor of $\sim 20\,000\times$. Closing this gap requires simultaneous advances in diamond semiconductor fabrication, isotope production scale, and conversion efficiency.
2. **The hybrid architecture—betavoltaic trickle-charge—delivers measurable benefits only in the mid-to-long term.** Covering standby drain requires $\sim 70 \text{ mW}$ modules (6.7 kCi of ^{63}Ni , $\sim 120 \text{ g}$), extending Li-ion lifespan by $\sim 50\%$; 200 mW – 1 W modules of the 2040s could reduce cycling by 80–95% and push lifespan to the ~ 15 – 20 -year calendar-aging ceiling. Near-term 1 mW modules (97 Ci, 1.7 g) do not meaningfully extend battery life.
3. **Betavoltaic power for always-on subsystems (TPM, RTC, “find my phone” BLE) is achievable now** with existing BV100-class technology ($\sim 10 \text{ Ci}$ of ^{63}Ni per $100 \mu\text{W}$ module), providing 50+ year operational life for critical low-power circuits.
4. **The physics is not limiting; the engineering is.** The fundamental conversion efficiencies are sound, shielding is trivial for ^{63}Ni , and radiation safety is demonstrable. The barriers are manufacturing scale, cost, and regulatory harmonization.
5. **Diamond is the optimal absorber material**, offering $\sim 34\%$ power density advantage over 4H-SiC due to its ultra-wide bandgap (5.47 eV), lowest backscattering coefficient, and self-healing radiation tolerance. The ^{14}C isotope, available as a waste product from nuclear reactors, represents a transformative cost-reduction pathway.

6. **The environmental case is compelling even before full smartphone integration.** Eliminating 80% of Li-ion replacements in 1.5 billion annual smartphones prevents $\sim 60\text{--}70$ kt/yr of hazardous battery waste and offsets the cobalt supply chain's human and ecological costs.

Betavoltaic technology will not revolutionize smartphones in the way that Li-ion batteries did in 1991. But it will quietly transform the long tail of mobile energy: the sensors, implantables, and always-on subsystems that define the Internet of Things. The 50-year battery is not science fiction; it is a commercial product shipping in 2024. Its journey from $100\text{ }\mu\text{W}$ to 1 W will take a generation—but the physics is on its side.

Glossary of Acronyms

ADR European Agreement concerning the International Carriage of Dangerous Goods by Road

A₂ activity limit defining Type A packaging in IAEA SSR-6

BLE Bluetooth Low Energy

Bq becquerel (decays per second)

CFR Code of Federal Regulations (US)

Ci curie (3.7×10^{10} Bq)

CSDA continuous slowing-down approximation

CVD chemical vapour deposition

DC–DC direct-current to direct-current (conversion)

DMFC direct methanol fuel cell

e–h electron–hole (pair)

FF fill factor

GSR IAEA General Safety Requirements

IAEA International Atomic Energy Agency

ICRP International Commission on Radiological Protection

IoT Internet of Things

LIB lithium-ion battery

MCNP Monte Carlo N-Particle (transport code)

MIL-STD US military standard

MMRTG Multi-Mission Radioisotope Thermoelectric Generator

NRC US Nuclear Regulatory Commission

OLED organic light-emitting diode

PBq petabecquerel (10^{15} Bq)

p–n positive–negative (junction)

RTC real-time clock

RTG radioisotope thermoelectric generator

SiC silicon carbide

SoC system on chip

SSG IAEA Specific Safety Guide

SSR IAEA Specific Safety Requirements

TCO total cost of ownership

TEG thermoelectric generator

TPM trusted platform module

Wh watt-hour

Acknowledgements

The author thanks the open-source community for accessible literature and data. No external funding was received for this work.

References

- [1] J. B. Goodenough and K.-S. Park, “The Li-ion rechargeable battery: a perspective,” *J. Am. Chem. Soc.* **135**, 1167–1176 (2013).
- [2] N. Nitta *et al.*, “Li-ion battery materials: present and future,” *Mater. Today* **18**, 252–264 (2015).
- [3] Thunder Said Energy, “Lithium ion batteries: energy density?” (2024). Available: <https://thundersaidenergy.com/downloads/lithium-ion-batteries-energy-density>
- [4] A. Barre *et al.*, “A review on lithium-ion battery ageing mechanisms and estimations for automotive applications,” *J. Power Sources* **241**, 680–689 (2013).
- [5] S. Baldwin *et al.*, “Global e-waste monitor 2020,” United Nations University (2020).
- [6] H. G. J. Moseley and J. L. Harling, “The attainment of high potentials by the use of radium,” *Phil. Mag.* **26**, 210 (1913).
- [7] NASA, “Transit 4B: first RTG in space,” (1961). Available: <https://nssdc.gsfc.nasa.gov>

- [8] Betavolt Technology, “BV100 atomic energy battery,” Press Release, January 2024. Available: <https://www.betavolt.tech>
- [9] NRD LLC, “NBV series nuclear battery,” Product Announcement, June 2026.
- [10] E. Fermi, “Versuch einer Theorie der β -Strahlen,” *Z. Phys.* **88**, 161–177 (1934).
- [11] L. C. Olsen, P. Cabauw, S. F. Bartolucci, and R. Windle, “Betavoltaic power sources,” *Physics Today* **65**, 35–38 (2012).
- [12] RCA Laboratories, “Nuclear battery converts radioactivity directly into electricity,” *Popular Mechanics*, April 1954, p. 87.
- [13] T. Urgast *et al.*, “Optimal semiconductors for ^3H and ^{63}Ni betavoltaics,” *Sci. Rep.* **9**, 10727 (2019).
- [14] A. Lal, R. Duggirala, and H. Li, “Pervasive power: a radioisotope-powered piezoelectric generator,” *IEEE Pervasive Comput.* **4**, 53–61 (2005).
- [15] G. M. Spinrad, “Multi-Mission RTG (MMRTG),” NASA JPL (2011).
- [16] K. C. Bindu *et al.*, “Optimization of commercial scale photonuclear production of radioisotopes,” *AIP Conf. Proc.* **1525**, 407–411 (2013).
- [17] M. V. S. Chandrashekhar, C. I. Thomas, H. Li, M. G. Spencer, and A. Lal, “Demonstration of a 4H SiC betavoltaic cell,” *Appl. Phys. Lett.* **88**, 033506 (2006).
- [18] C. C. Thomas, S. Portnoff, and M. G. Spencer, “High efficiency 4H-SiC betavoltaic power sources using tritium radioisotopes,” *Appl. Phys. Lett.* **108**, 013505 (2016).
- [19] Widetronix Inc., “4H-SiC betavoltaic products.” Available: <https://www.widentronix.com>
- [20] T. Shimaoka *et al.*, “Fabrication of p-n junction diamond for betavoltaic battery,” *Diamond Relat. Mater.* **64**, 17–21 (2016).
- [21] Kurchatov Institute, “Optoelectric nuclear battery using Tc-99 and excimer mixture,” Research Report, Moscow.
- [22] R. Zheng *et al.*, “Understanding efficiency improvements of betavoltaic batteries based on 4H-SiC, GaN, and diamond,” *Appl. Phys. Lett.* **121**, 103902 (2022).
- [23] “Characteristics comparison and Monte-Carlo simulation of betavoltaic batteries,” *Radiat. Phys. Chem.* (2022).
- [24] S.-I. In, “Next generation battery: highly efficient and stable C14 dye-sensitized betavoltaic cell,” ACS Spring 2025, March 26, 2025.
- [25] University of Bristol, “Carbon-14 diamond battery,” Nuclear Decommissioning Authority (2024).
- [26] EU CAST project (IGD-TP), “Carbon-14 source term: current understanding of inventory and release from irradiated graphite,” Deliverable D5.5 (2015).
- [27] A. Carroll and G. Heiser, “An analysis of power consumption in a smartphone,” *Proc. USENIX ATC* (2010).

- [28] A. Pathak *et al.*, “A survey of power consumption in smartphones,” *IEEE Access* (2022).
- [29] J. Dorn, “How many watts does a cell phone use?” ExpertBeacon (2024).
- [30] City Labs, “NanoTritium general license,” US NRC, 2010.
- [31] NASA TechPort, “High Energy Long Life Betavoltaic Battery,” Project 90224 (2023).
- [32] IAEA, “Radiation Safety for Consumer Products,” Safety Standards Series No. SSG-36, Vienna (2016).
- [33] US Nuclear Regulatory Commission, “Byproduct material regulations,” 10 CFR 30–40 (2024).
- [34] European Parliament, Council Directive 2013/59/EURATOM on basic safety standards for protection against the dangers arising from exposure to ionising radiation.
- [35] ASN (Autorité de Sûreté Nucléaire), “Arrêté du 18 novembre 2011,” Paris (2011).
- [36] Y. R. Uhm *et al.*, “Study of a betavoltaic battery using electroplated nickel-63 on nickel foil as a power source,” *Nucl. Eng. Technol.* **48**, 773–777 (2016).
- [37] IAEA/INIS, “Performance evaluation of Ni-63 betavoltaic battery,” INIS (2017).
- [38] B. Liu *et al.*, “Diamond-based alphavoltaic battery,” *Appl. Phys. Lett.* (2018).
- [39] Stanford University, “Betavoltaic microbatteries,” PH241 Course Notes (2026). Available: <http://large.stanford.edu/courses/2026/ph241/jahan2>
- [40] Electronics Lab, “Betavolt’s New 3V Atomic Battery,” January 2024.
- [41] Talk Android, “The longest-lasting battery ever has been built,” June 2026.
- [42] Yahoo Finance, “Betavoltaic cell markets, competitive landscape,” 2026.
- [43] Yahoo Finance, “Radioisotope battery research report 2026,” 2026.
- [44] E. B. Agyekum *et al.*, “Beta-voltaic nuclear batteries — review of recent developments, challenges and future research directions,” *J. Energy Storage* (2025). Cited by 24.
- [45] NIST, “ESTAR: Stopping powers and ranges for electrons,” Physical Reference Data (2024). Available: <https://physics.nist.gov/Star>
- [46] K. Kim *et al.*, “Radiation-induced degradation and charge-collection stability of 4H-SiC p-i-n betavoltaic cell,” *Energy Rep.* (2026).
- [47] Bioengineer.org, “Revolutionary nuclear battery promises lifetime power with enhanced safety,” September 2025.
- [48] K. E. Drexler, *Nanosystems: Molecular Machinery, Manufacturing, and Computation* (Wiley, 1992).
- [49] P. Bernhard, “Nuclear diamond batteries: the physics and the hype,” Science for Sustainability Wiki (2024).
- [50] Infobits, “Betavolt’s nuclear battery: 50 years of power, but not for phones,” June 2026.

- [51] Accio, “Beta voltaic nuclear battery 2026: trends & market outlook,” July 2026.
- [52] Lualdi Advisors, “Betavolt’s nuclear micro-cell and the 50-year power case,” June 2026.
- [53] CNX Software, “Betavolt BV100 3V nuclear battery aims to deliver 100 microwatts for over 50 years,” January 2024.
- [54] Renergyinfo, “Betavolt’s game-changing BV100,” June 2024.
- [55] TomorrowDesk, “China’s BV100 nuclear battery transforming drone technology,” 2025.
- [56] Live Science, “Tiny Chinese-made BV100 radioactive battery can last 50 years,” January 2024.
- [57] Hackaday, “Nuclear diamond battery rated to provide power for 50 years,” January 2024.
- [58] IEEE, “Radiation damage in semiconductor devices,” IEEE Trans. Nucl. Sci. (2006).
- [59] K. Kim *et al.*, “Structural optimization and trap effects on the output performance of 4H-SiC betavoltaic cell,” *Nanomaterials* **15**, 1625 (2025).