MECHANICAL PROPERTIES

Product Denomination	ZZ300T-DT195N-42			
Weaving Style	TWILL			
Yarn Type	ZYLON HM			
F.A.W. (g/m^2)	300			
Nominal Fiber Volume Fraction	54%			
Cure Conditions vs. Mechanical Data	Autoclave cure: Cured 90 min @ 135°C / 6 bar			
Average Density of Cured Sample (g/cm^3)	0,78			
Nominal CPT (mm)	0,38			
Test Conditions	Room Temp.			
TEST ID	CM14-52			
TENSILE 0°	ASTM D3039			
Actual CPT (mm)	0,39			
Tensile strength (MPa)	988			
Tensile modulus (GPa)	51,9			
Calculated Ultimate Elongation (%)	1,91			
Tensile Poisson ratio (-)	0,06			
TENSILE 90°	ASTM D3039			
Actual CPT (mm)	0,39			
Tensile strength (MPa)	966			
Tensile modulus (GPa)	52,3			
Calculated Ultimate Elongation (%)	1,85			
COMPRESSION 0°	ASTM D6641			
Actual CPT (mm)	0,38			
Compression strength (MPa)	143			
Compression modulus (GPa)	34,4			
COMPRESSION 90°	ASTM D6641			
Actual CPT (mm)	0,38			
Compression strength (MPa)	146			
Compression modulus (GPa)	34,5			
IN-PLAIN SHEAR	EN 6031			
Shear strength of 5% Strain (MPa)	-			
Maximun Shear strength (MPa)	64,9			
Shear modulus (GPa)	1,30			
ILSS	ASTM D2344			
ILSS (MPa)	23,87			

All data are normalised to Nominal fibre volume fraction (except for ILSS and In-Plane Shear).

The technical specifications, data and measures supplied in this datasheet are provided on an as-is basis by Delta-Tech S.p.A. which gives no warranty, express or implied, as to the completeness, accuracy, reliability or fitness for any specific or particular use, field of use, application, performance, result or purpose.Therefore, any specific or particular use, application, performance, result or purpose of the technical specifications, data and measures supplied in this datasheet shall be at the users sole risk and liability. Consequently, any user should conduct its own searches, verifications and tests taking into consideration the peculiar nature and function of the products (including parts, components or accessories) which will be manufactured using prepregs.

The technical data and measures supplied in this datasheet are confidential and property of Delta-Tech S.p.A. but Delta-Tech S.p.A. does not give any warranty of non infringement of third parties' property rights.