

Type	Code	Nd	vd	NF-NC	Ne	ve	Nt	Nr	NC	ND	NF	Ng
------	------	----	----	-------	----	----	----	----	----	----	----	----

FC	1	471-673	1.47069	67.31	0.006993	1.47236	67.11	1.46237	1.46728	1.46853	1.47063	1.47552	1.47925
	3	465-658	1.46450	65.77	0.007063	1.46619	65.49	1.45613	1.46111	1.46235	1.46444	1.46941	1.47319
	5	487-704	1.48749	70.44	0.006921	1.48914	70.24	1.47913	1.48411	1.48535	1.48743	1.49227	1.49594
PC	1	504-669	1.50378	66.89	0.007532	1.50558	66.71	1.49480	1.50010	1.50145	1.50371	1.50898	1.51299
	2	518-652	1.51821	65.16	0.007953	1.52011	64.96	1.50880	1.51435	1.51576	1.51814	1.52371	1.52796
	3	525-646	1.52542	64.62	0.008131	1.52736	64.40	1.51584	1.52148	1.52292	1.52535	1.53105	1.53540
PCS	1	517-697	1.51728	69.68	0.007424	1.51906	69.48	1.50855	1.51366	1.51499	1.51722	1.52241	1.52636

nh	ni	Specific Gravity	Color	Bubble Group	Chemical Properties			Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					Dw	DA	Tg	Ts	α	Hk	FA			

	1.48231	1.48748	2.30	32/29	1	6	5	405	475	87	415(4)	120	P	FK	1
	1.47628	1.48150	2.27	34/29	1	5	4	385	475	87	395(4)	120	P		3
	1.49896	1.50405	2.45	32/28	1	5	5	475	555	85	525(5)	110	P		5
	1.51629	1.52185	2.45	32/29	1	2	1	575	640	66	605(6)	100	P	PK	1
	1.53145	1.53737	2.53	33/29	1	2	1	570	620	81	590(6)	90			2
	1.53898	1.54505	2.62	35/30	1	2	1	575	630	83	570(6)	90			3
	1.52960	1.53503	2.58	36/32	1-2	4	2	525	555	110	415(4)	310	P	PKS	1

FC
PC
PCS
PCD
BSC

BaCL
C
ZnC
BaC

BaCD

BaCED

LaCL

LaC

TaC

CF

BaF
BaFL
BaFL

Type	Code	nd	vd	nF-nc	ne	ve	nt	nr	nc	nd	nF	ng
------	------	----	----	-------	----	----	----	----	----	----	----	----

PCD 2	569-631	1.56873	63.10	0.009013	1.57088	62.90	1.55825	1.56436	1.56596	1.56865	1.57497	1.57980
3	552-634	1.55232	63.42	0.008708	1.55440	63.19	1.54223	1.54812	1.54965	1.55224	1.55836	1.56305
BSC 1	510-634	1.51009	63.43	0.008041	1.51201	63.21	1.50074	1.50620	1.50762	1.51002	1.51566	1.51998
3	498-651	1.49831	65.13	0.007651	1.50014	64.97	1.48911	1.49457	1.49594	1.49824	1.50359	1.50764
6	531-621	1.53113	62.07	0.008556	1.53317	61.83	1.52131	1.52701	1.52851	1.53105	1.53707	1.54167
7	517-642	1.51680	64.20	0.008050	1.51872	64.00	1.50733	1.51289	1.51432	1.51673	1.52237	1.52667

nh	ni	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					Dw	DA	Tg	Ts	α	Hk	FA		

1.58380	1.59058	3.05	36/31	1-2	5	5	600	650	71	595(6)	110		PSK 2
1.56692	1.57346	2.91	35/30	1-2	5	4	600	650	73	605(6)	100		3
1.52355	1.52961	2.47	33/29	1	3	1	550	615	90	570(6)	110		BK 1
1.51096	1.51657	2.37	33/28	1	3	1	550	605	59	590(6)	80		3
1.54548	1.55196	2.70	34/29	1-2	3	1	535	585	92	565(6)	120		6
1.53022	1.53622	2.51	34/30	1	4	1	555	615	87	595(6)	100		7

Type	Code	n_d	ν_d	$n_F - n_C$	n_e	ν_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	---------	-------------	-------	---------	-------	-------	-------	-------	-------	-------

BaCL I	526-601	1.52642	60.11	0.008757	1.52850	59.84	1.51655	1.52223	1.52375	1.52634	1.53251	1.53728
3	518-604	1.51835	60.40	0.008583	1.52040	60.15	1.50868	1.51423	1.51573	1.51827	1.52431	1.52896
C	3 518-590	1.51823	58.96	0.008790	1.52033	58.67	1.50834	1.51405	1.51557	1.51816	1.52436	1.52915
5	522-595	1.52249	59.45	0.008789	1.52458	59.17	1.51261	1.51830	1.51982	1.52241	1.52861	1.53339
7	511-605	1.51112	60.49	0.008450	1.51314	60.25	1.50154	1.50707	1.50854	1.51105	1.51699	1.52155
10	501-563	1.50137	56.30	0.008906	1.50349	56.00	1.49138	1.49716	1.49868	1.50129	1.50759	1.51249
12	523-586	1.52307	58.64	0.008920	1.52520	58.36	1.51305	1.51883	1.52037	1.52299	1.52929	1.53415

n_h	n_i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					D _w	D _A	T _g	T _s	α	H _k	F _A		

1.54125	1.54800	2.69	33/29	I	4	I	505	560	109	515(5)	130	BaLK I	
1.53282	1.53936	2.62	33/29	I	4	I	505	550	106	510(5)	120	3	
1.53314	1.53996	2.54	33/30	I-2	4	I	505	560	103	530(5)	110	K	3
1.53736	1.54408	2.57	33/30	I	2	I	545	600	86	535(5)	110	5	
1.52532	1.53174	2.53	33/29	I	3	I	525	585	93	520(5)	110	7	
1.51659	1.52366	2.53	32/30	I-2	4	2	435	495	89	490(5)	110	10	
1.53820	1.54510	2.57	33/30	I	2	I	530	585	94	530(5)	110	12	

BaLK K

BaCL C

ZnCL BaC

BaCD

BaCED

LaCL

LaC

TaC

CP

BaFL

Type	Code	n_d	ν_d	$n_F - n_C$	n_e	ν_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	---------	-------------	-------	---------	-------	-------	-------	-------	-------	-------

ZnC	1 533-581	1.53315	58.06	0.009182	1.53534	57.80	1.52284	1.52878	1.53036	1.53307	1.53954	1.54453
5	534-554	1.53375	55.38	0.009638	1.53604	55.10	1.52317	1.52918	1.53083	1.53366	1.54047	1.54577
7	508-613	1.50847	61.27	0.008300	1.51045	61.07	1.49878	1.50445	1.50592	1.50840	1.51422	1.51867
BaC	1 573-575	1.57250	57.49	0.009959	1.57487	57.20	1.56148	1.56777	1.56948	1.57241	1.57944	1.58491
2	540-597	1.53996	59.72	0.009041	1.54212	59.45	1.52980	1.53565	1.53721	1.53988	1.54625	1.55118
4	569-560	1.56883	56.04	0.010150	1.57125	55.78	1.55755	1.56400	1.56575	1.56874	1.57590	1.58147
5	557-586	1.55671	58.56	0.009506	1.55898	58.29	1.54612	1.55219	1.55382	1.55662	1.56333	1.56848
6	574-564	1.57444	56.36	0.010193	1.57687	56.07	1.56314	1.56961	1.57136	1.57435	1.58155	1.58715

n_h	n_i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Customary Type
					D_w	D_A	T_g	T_s	α	H_k	F_A		

1.54866	1.55572	2.72	33/29	1-2	2	2	560	625	91	510(5)	120		ZK 1
1.55020	1.55779	2.75	33/29	2	2	1	520	560	102	505(5)	120		5
1.52235	1.52858	2.50	35/31	3	2	1	535	605	49	530(5)	100		7
1.58947	1.59726	3.19	35/30	2	3	2	590	640	79	530(5)	150		BaK 1
1.55527	1.56225	2.86	33/28	2	3	1	555	610	90	540(5)	130		2
1.58612	1.59410	3.11	35/31	1-2	3	3	560	610	77	560(6)	130		4
1.57276	1.58015	3.02	33/29	1-2	2	1	575	625	92	570(6)	120		5
1.59183	1.59988	3.10	36/32	2	3	1	575	630	78	555(6)	130		6

Type	Code	n_D	n_D	$n_F - n_C$	n_e	n_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	-------	-------------	-------	-------	-------	-------	-------	-------	-------	-------

BaCDI	564-608	1.56384	60.83	0.009269	1.56605	60.58	1.55334	1.55940	1.56101	1.56376	1.57028	1.57529
12	583-595	1.58313	59.46	0.009807	1.58547	59.19	1.57209	1.57846	1.58015	1.58304	1.58996	1.59526
13	592-583	1.59181	58.31	0.010150	1.59423	58.03	1.58053	1.58698	1.58873	1.59172	1.59888	1.60442
14	603-607	1.60311	60.69	0.009937	1.60548	60.43	1.59182	1.59836	1.60009	1.60302	1.61002	1.61540
15	623-581	1.62299	58.12	0.010719	1.62555	57.87	1.61104	1.61787	1.61973	1.62290	1.63045	1.63628
16	620-603	1.62041	60.32	0.010285	1.62286	60.08	1.60869	1.61547	1.61727	1.62032	1.62755	1.63312
18	639-555	1.63854	55.46	0.011514	1.64129	55.18	1.62586	1.63309	1.63506	1.63844	1.64657	1.65290

n_h	n_i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					D_w	D_A	T_g	T_s	α	H_k	F_A		

1.57945	1.58655	3.07	35/30	1-2	3	2	600	650	75	605(6)	120		SK 11
1.59965	1.60718	3.27	37/31	1-2	3	3	630	660	69	585(6)	120		12
1.60903	1.61690	3.38	36/31	1	3	3	630	675	70	560(6)	110		13
1.61984	1.62742	3.43	36/30	1	4	5	645	680	72	585(6)	130		14
1.64115	1.64946	3.67	37/32	1	4	4	640	680	78	550(6)	150		15
1.63773	1.64558	3.58	37/32	1	5	5	640	680	77	570(6)	140		16
1.65818	1.66728	3.71	37/32	1	3	4	620	670	78	550(6)	160		18

FEL	BaF	FL F	BaFD	FD	FDS FF	BaCED	LaCL	LaC	TaC	CF	BaF	BaFL
-----	-----	---------	------	----	-----------	-------	------	-----	-----	----	-----	------

Type	Code	N _d	ν_d	N _F -N _C	N _e	ν_e	n _t	n _r	N _C	N _D	N _F	N _G
------	------	----------------	---------	--------------------------------	----------------	---------	----------------	----------------	----------------	----------------	----------------	----------------

BaCED	1 617-539	1.61720	53.94	0.011441	1.61993	53.66	1.60477	1.61180	1.61375	1.61710	1.62519	1.63151
2	622-531	1.62230	53.11	0.011717	1.62509	52.84	1.60958	1.61676	1.61876	1.62220	1.63048	1.63696
3	615-512	1.61484	51.15	0.012020	1.61770	50.85	1.60198	1.60921	1.61123	1.61473	1.62325	1.62994
4	618-552	1.61765	55.16	0.011198	1.62032	54.87	1.60540	1.61236	1.61427	1.61755	1.62547	1.63162
5	658-509	1.65844	50.85	0.012949	1.66152	50.56	1.64452	1.65235	1.65454	1.65832	1.66749	1.67471
9	620-498	1.62012	49.82	0.012447	1.62308	49.52	1.60675	1.61430	1.61639	1.62001	1.62884	1.63581
20	649-530	1.64850	53.03	0.012229	1.65141	52.74	1.63526	1.64274	1.64481	1.64839	1.65704	1.66382

N _h	N _i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					D _w	D _A	T _g	T _s	α	H _k	F _A		

1.63679	1.64579	3.63	36/32	1	3	3	635	685	72	565(6)	140		SSK 1
1.64241	1.65182	3.68	37/32	1	3	3	640	690	74	555(6)	140		2
1.63557	1.64536	3.60	37/32	1	2	3	625	670	77	540(5)	150		3
1.63675	1.64555	3.62	37/32	1	3	3	645	695	71	575(6)	130		4
1.68080	1.69143	3.78	39/34	1	4	3	640	680	78	560(6)	170		5
1.64171	1.65207	3.27	39/34	1	4	4	580	625	92	555(6)	180		9
1.66950	1.67930	3.74	38/34	1	3	3	635	665	88	550(6)	200		20

SSK

BaCED

LaCL

LaC

TaC

CF

BaF BaFL

Type	Code	n_d	ν_d	$n_F - n_C$	n_e	ν_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	---------	-------------	-------	---------	-------	-------	-------	-------	-------	-------

Lac	6	643-580	1.64250	57.96	0.011085	1.64514	57.72	1.62991	1.63720	1.63912	1.64240	1.65021	1.65620
	7	652-584	1.65160	58.40	0.011157	1.65426	58.15	1.63899	1.64628	1.64821	1.65150	1.65936	1.66538
	8	713-539	1.71300	53.94	0.013219	1.71615	53.72	1.69813	1.70669	1.70898	1.71288	1.72220	1.72939
	9	691-547	1.69100	54.70	0.012633	1.69401	54.48	1.67674	1.68496	1.68715	1.69088	1.69978	1.70663
	10	720-503	1.72000	50.34	0.014302	1.72341	50.10	1.70442	1.71324	1.71568	1.71987	1.72998	1.73785
	11	658-573	1.65830	57.26	0.011496	1.66104	57.03	1.64531	1.65279	1.65479	1.65819	1.66629	1.67251
	12	678-555	1.67790	55.52	0.012211	1.68081	55.26	1.66439	1.67210	1.67420	1.67779	1.68641	1.69306
	13	694-533	1.69350	53.30	0.013011	1.69660	53.02	1.67945	1.68737	1.68958	1.69338	1.70259	1.70975
	14	697-555	1.69680	55.46	0.012564	1.69980	55.25	1.68250	1.69078	1.69297	1.69669	1.70553	1.71235
	15	697-561	1.69680	56.11	0.012418	1.69976	55.89	1.68268	1.69085	1.69301	1.69668	1.70543	1.71216

n_h	n_i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					D _w	D _A	T _g	T _s	α	H _k	F _A		

	1.66117	1.66967	3.57	36/30	1	5	5	630	660	73	625(6)	120		Lak	6
	1.67035	1.67884	3.62	38/31	1	5	5	645	665	90	580(6)	150			7
	1.73537	1.74559	3.83	39/31	1-2	2	4	625	645	73	750(7)	70			8
	1.71231	1.72209	3.65	38/31	1	3	4	625	650	78	695(7)	70			9
	1.74443	1.75579	3.87	38/31	1	2	3	620	645	93	650(7)	110			10
	1.67768	1.68649	3.63	38/31	1	3	4	630	665	84	615(6)	130			11
	1.69860	1.70808	3.80	38/32	1	3	5	635	670	92	590(6)	150			12
	1.71573	1.72599	4.23	37/32	1	4	5	640	670	95	550(6)	200			13
	1.71801	1.72765	3.65	39/32	1-2	3	4	635	665	75	745(7)	70			14
	1.71774	1.72721	3.95	39/31	1-2	3	4	655	680	94	670(7)	80			15

