

Type	Code	n_d	ν_d	$n_F - n_C$	n_e	ν_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	---------	-------------	-------	---------	-------	-------	-------	-------	-------	-------

FDS	2	728-287	1.72830	28.67	0.025399	1.73430	28.45	1.70372	1.71696	1.72096	1.72808	1.74636	1.76163
	3	785-261	1.78470	26.06	0.030115	1.79180	25.86	1.75603	1.77133	1.77604	1.78444	1.80615	1.82453
	5	762-269	1.76180	26.91	0.028305	1.76849	26.71	1.73475	1.74924	1.75366	1.76156	1.78196	1.79912
	9	847-238	1.84666	23.83	0.035535	1.85504	23.64	1.81339	1.83104	1.83651	1.84635	1.87204	1.89390
FF	1	511-510	1.51118	51.03	0.010018	1.51356	50.71	1.50023	1.50649	1.50818	1.51109	1.51820	1.52384
	2	533-459	1.53256	45.94	0.011592	1.53531	45.63	1.52016	1.52717	1.52911	1.53246	1.54070	1.54737
	5	593-355	1.59270	35.45	0.016722	1.59666	35.17	1.57579	1.58513	1.58782	1.59256	1.60454	1.61445

I _h	I _i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					D _w	D _A	T _g	T _s	α	H _k	F _A		

	1.77519	1.80052	4.45	42/37	1-2	2	2	425	475	88	385(4)	210		SFS 2
	1.84099	—	4.91	43/37	1-2	3	2	435	485	86	385(4)	250	L(42/37)	3
	1.81447	—	4.73	43/37	1-2	3	3	420	460	84	385(4)	230	L(42/37)	5
	1.91361	—	5.39	44/37	2-3	3	3	430	470	95	360(4)	310		9
	1.52866	1.53723	2.46	38/34	1	2	1	450	520	87	520(5)	130	P	TIF (K.F.H.)
	1.55316	1.56369	2.51	38/35	1	1	1	455	520	89	520(5)	140	P	(L.F.H.) ²
	1.62320	1.63952	2.64	38/35	1	2	1	515	570	89	500(5)	180	P	(P.16) ⁵

Type	Code	n_d	ν_d	$n_F - n_C$	n_e	ν_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	---------	-------------	-------	---------	-------	-------	-------	-------	-------	-------

NbFD 1	789-428	1.78900	42.76	0.018453	1.79339	42.51	1.76954	1.78042	1.78350	1.78884	1.80195	1.81236
2	797-411	1.79720	41.14	0.019376	1.80180	40.89	1.77698	1.78824	1.79144	1.79703	1.81082	1.82184
3	805-396	1.80450	39.64	0.020298	1.80932	39.39	1.78348	1.79514	1.79849	1.80433	1.81879	1.83038
4	831-365	1.83060	36.54	0.022728	1.83599	36.31	1.80743	1.82016	1.82388	1.83040	1.84661	1.85976
5	762-403	1.76200	40.26	0.018926	1.76649	39.98	1.74268	1.75333	1.75642	1.76184	1.77534	1.78623
6	757-363	1.75670	36.34	0.020820	1.76164	36.08	1.73594	1.74723	1.75059	1.75652	1.77141	1.78358
7	783-361	1.78300	36.07	0.021710	1.78814	35.80	1.76082	1.77311	1.77663	1.78281	1.79834	1.81104
8	807-355	1.80740	35.54	0.022717	1.81279	35.27	1.78450	1.79711	1.80076	1.80720	1.82348	1.83676
9	757-318	1.75690	31.80	0.023803	1.76253	31.57	1.73333	1.74615	1.74996	1.75669	1.77376	1.78783
10	834-373	1.83400	37.34	0.022333	1.83930	37.09	1.81116	1.82378	1.82742	1.83381	1.84975	1.86268

n_h	n_i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Customary Type
					D_w	D_A	T_g	T_s	α	H_k	F_A		

1.82120	1.83677	4.37	41/34	1	1	4	605	630	72	670(7)	80		NbSF 1
1.83123	1.84779	4.32	40/34	1	1	4	615	645	67	705(7)	70		2
1.84030	1.85788	4.39	42/35	1	1	5	585	615	72	615(6)	80		3
1.87116	1.89181	4.47	44/35	1	1	5	595	615	71	695(7)	80		4
1.79558	1.81228	4.33	41/35	1	1	3	670	725	88	570(6)	150		5
1.79416	1.81330	4.75	43/35	1	1	4	560	610	90	485(5)	220		6
1.82212	1.84248	3.94	44/36	1	1	5	585	610	84	600(6)	100		7
1.84831	1.86946	4.30	44/36	1	2	4	570	595	73	625(6)	100		8
1.80017	—	4.22	44/38	1	1	4	530	575	72	510(6)	170		9
1.87385	1.89393	4.57	44/35	1	1	4	585	610	78	695(7)	70		10

Type	Code	n_d	ν_d	$n_F - n_C$	n_e	ν_e	n_t	n_r	n_C	n_D	n_F	n_g
------	------	-------	---------	-------------	-------	---------	-------	-------	-------	-------	-------	-------

TaFD 1	815-442	1.81470	44.24	0.018417	1.81908	44.01	1.79506	1.80605	1.80916	1.81454	1.82758	1.83791
2	838-420	1.83770	41.97	0.019958	1.84244	41.73	1.81672	1.82843	1.83175	1.83752	1.85171	1.86300
5	835-430	1.83500	42.98	0.019426	1.83962	42.75	1.81445	1.82594	1.82919	1.83483	1.84862	1.85955
9	850-322	1.85030	32.18	0.026423	1.85655	31.94	1.82402	1.83837	1.84260	1.85007	1.86902	1.88470
10	816-445	1.81550	44.53	0.018314	1.81986	44.29	1.79594	1.80694	1.81002	1.81534	1.82833	1.83859
13	855-366	1.85540	36.56	0.023399	1.86095	36.31	1.83153	1.84471	1.84851	1.85519	1.87191	1.88544

n_h	n_i	Specific Gravity	Color	Bubble Group	Chemical Properties		Thermal Properties			Mechanical Properties		Remarks	Custom-ary Type
					D_w	D_A	T_g	T_s	α	H_k	F_A		

1.84666	1.86184	4.99	40/33	1	1	4	670	690	78	740(7)	60		TaSF 1
1.87258	1.88927	4.97	42/34	1	1	4	660	680	77	735(7)	60		2
1.86881	1.88494	5.02	43/34	1-2	1	3	660	680	74	740(7)	60		5
1.89852	—	4.61	46/37	1-2	1	5	585	610	81	585(6)	130		9
1.84726	1.86226	4.87	41/32	1-2	1	4	665	695	78	805(7)	60		10
1.89712	1.91832	4.59	46/35	1-2	1	4	640	670	75	700(7)	70		13

PRINTED IN JAPAN 1975.9.

HOYA OPTICAL GLASS

Catalog No. 7509

