
SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.4mm x100 UD+LD+MD 10/24/2024 500µm



Clariant SU7000 5.00kV 7.3mm x100 UD+LD+MD 10/24/2024 500µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x100 UD+LD+MD 10/24/2024 500µm




Clariant SU7000 5.00kV 7.3mm x100 UD+LD+MD 10/24/2024 500µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.4mm x200 UD+LD+MD 10/24/2024 200µm



Clariant SU7000 5.00kV 7.3mm x200 UD+LD+MD 10/24/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x200 UD+LD+MD 10/24/2024 200µm



Clariant SU7000 5.00kV 7.3mm x200 UD+LD+MD 10/24/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x500 UD+LD+MD 10/24/2024 100µm



Clariant SU7000 5.00kV 7.3mm x500 UD+LD+MD 10/24/2024 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x500 UD+LD+MD 10/24/2024 100µm



Clariant SU7000 5.00kV 7.3mm x500 UD+LD+MD 10/24/2024 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x1.00k UD+LD+MD 10/24/2024 50.0µm



Clariant SU7000 5.00kV 7.3mm x1.00k UD+LD+MD 10/24/2024 50.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x1.00k UD+LD+MD 10/24/2024 50.0µm



Clariant SU7000 5.00kV 7.3mm x1.00k UD+LD+MD 10/24/2024 50.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x2.00k UD+LD+MD 10/24/2024 20.0µm




Clariant SU7000 5.00kV 7.3mm x2.00k UD+LD+MD 10/24/2024 20.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.1mm x2.00k UD+LD+MD 10/24/2024 20.0µm



Clariant SU7000 5.00kV 7.3mm x2.00k UD+LD+MD 10/24/2024 20.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x5.00k UD+LD+MD 10/24/2024 10.0µm




Clariant SU7000 5.00kV 7.3mm x5.00k UD+LD+MD 10/24/2024 10.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.1mm x5.00k UD+LD+MD 10/24/2024 10.0µm



Clariant SU7000 5.00kV 7.3mm x5.00k UD+LD+MD 10/24/2024 10.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x10.0k UD+LD+MD 10/24/2024 5.00µm




Clariant SU7000 5.00kV 7.3mm x10.0k UD+LD+MD 10/24/2024 5.00µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x10.0k UD+LD+MD 10/24/2024 5.00µm




Clariant SU7000 5.00kV 7.3mm x10.0k UD+LD+MD 10/24/2024 5.00µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x25.0k UD+LD+MD 10/24/2024 2.00µm



Clariant SU7000 5.00kV 7.3mm x25.0k UD+LD+MD 10/24/2024 2.00µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1147 2/3 4m 800C 3C/m 1h B 1.4/1.3P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048359-4

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x25.0k UD+LD+MD 10/24/2024 2.00µm



Clariant SU7000 5.00kV 7.3mm x25.0k UD+LD+MD 10/24/2024 2.00µm