Dr. Torsten Busch
Tel.: +49 (0) 69/257203 012
Fax: +49 (0) 69/257203 999
Email: torsten.busch@curiaglobal.com

Curia Germany GmbH
Process Research & Development
Industriepark Hoechst, D569
D-65926 Frankfurt am Main

June 18th 2024

Graphene synthesis project update

1. Biochar synthesis

- Overall seven syntheses finished with hemp fibers from BAFA neu GmbH
    - three syntheses done with 0.02M sulfuric acid
        - first product not representative, not used further
        - second and third batch converted (see below)
    - four syntheses done with 0.10M sulfuric acid
        - very similar observations and outputs
        - products of these have been combined/homogenized
        - part of the combined lots has been converted

- Canadian Rockies Hemp arrived and cleared customs
    - eleven synthesis batches finished (18.0 g product in total), seven of these (11.2 g) were combined and homogenized

- (Re)-Activation of larger vessel in progress

2. Biochar analysis

- Sample of combined biochar (milled, MB2946X_gem) analyzed by SEM and Raman for reference

3. Graphene synthesis

- two experiments finished with steep heating ramp (20-30 °C/min)
    - biochar ground manually for first experiment (TB1131)
    - laboratory mill used for second experiment (TB1132)
    - products not yet characterized
    - no serious handling issues

- two experiments performed with much gentler heating ramp (3 °C/min, TB1133/1134)
    - better handling but no other apparent difference
- one experiment performed at 5 °C/min (MB2946)

- 2 g of combined biochar milled with 2 g of KOH and used for several batches on 0.25 g scale
    - 800 °C, 1 h: minimal yield (MB2947A)
    - 800 °C, 2 h: minimal yield (MB2947B)
    - 800 °C, 3 h: no output (MB2947C)

➔ Inertion apparently insufficient and material likely incinerated
- 800 °C, 3 h repeat, much higher Ar stream: 38 mg output obtained (MB2947D)
- 800 °C, 1 h, nitrogen inertion: 60 mg output (TB1135-1)
- 800 °C, 1 h, increased nitrogen inertion: 70 mg output (TB1135-2)

- 2 g of combined biochar milled with 2 g of KOH and used for several batches on 0.25 g scale
    - 800 °C, 2 h, inertion equivalent to TB1135-2: output tbd (MB2952B)
    - 800 °C, 3 h, inertion equivalent to TB1135-2: in progress (MB2952C)

- Installation of oxygen sensor pending

4. Graphene analysis

- SEM (and Raman) results available for
    - TB1133, MB2946A, MB2947D, TB1135-1 (step 2 products)
    - 900561-500MG (Sigma-Aldrich reference)
    - 924458-500MG (Sigma-Aldrich reference "Single-layer graphene sheets for battery, Bio-sourced")

- Discussion with potential service provider (TEM, BET) in progress

5. Currently open questions

Experiment overview

Experiment	Reactor	Raw material		Acid				T	t	pressure			Wash		Output	
MB2928	AV1	6.0 g	BAFA neu Hemp Fibre VF	100.0 g	0.19%	0.02 M	Sulfuric acid	180 °C	22.5 h	8.7 bar	->	10.4 bar	742 g	Water	2.6 g	->
Comment	Fibres not completely covered by liquid															
MB2933	AV1	6.1 g	BAFA neu Hemp Fibre VF	174.0 g	0.19%	0.02 M	Sulfuric acid	180 °C	24 h	8.7 bar	->	9.5 bar	647 g	Water	1.2 g	->
Comment	dark crusts on glassware, metal and liquid surface removed before filtration															
MB2935	AV1	6.0 g	BAFA neu Hemp Fibre VF	172.9 g	0.19%	0.02 M	Sulfuric acid	180 °C	23 h	8.8 bar	->	9.5 bar	500 g	Water	1.3 g	->
Comment	dark crusts on glassware, metal and liquid surface removed before filtration															
MB2936	AV1	6.0 g	BAFA neu Hemp Fibre VF	172.4 g	0.96%	0.10 M	Sulfuric acid	180 °C	23 h	8.8 bar	->	10.6 bar	589 g	Water	0.8 g	
Comment	dark crusts on glassware, metal and liquid surface removed before filtration															
MRa225	AV1	6.0 g	BAFA neu Hemp Fibre VF	153.8 g	0.96%	0.10 M	Sulfuric acid	180 °C	24 h	?	->	10.5 bar	500 g	Water	0.9 g	
Comment	dark crusts on glassware, metal and liquid surface removed before filtration															->
MRa228	AV1	6.3 g	BAFA neu Hemp Fibre VF	154.0 g	0.96%	0.10 M	Sulfuric acid	180 °C	22.5 h	8.7 bar	->	11.0 bar	500 g	Water	0.9 g	
Comment	dark crusts on glassware, metal and liquid surface removed before filtration															
MRa231	AV1	6.1 g	BAFA neu Hemp Fibre VF	168.8 g	0.96%	0.10 M	Sulfuric acid	180 °C	23.5 h	8.0 bar	->	10.5 bar	500 g	Water	0.8 g	
Comment	dark crusts on glassware, metal and liquid surface removed before filtration															

Experiment	Qty	Base			grinding	Gas	T (rate)	T (max)	t	Wash		Drying	Output
TB1131	1.2 g	1.2 g	KOH	(90%)	manual	Ar	20-27 °C/min	790 °C	1 h	20 g	10% HCl	100 °C N2 stream	0.16 g
Comment	ground biochar: brown powder, strong electrostatic charge									(+ water)		(atm. Pressure)	
TB1132	1.3 g	1.3 g	KOH	(90%)	mill (2 min)	Ar	20-29 °C/min	792 °C	1 h	20 g	10% HCl	100 °C N2 stream	0.3 g
Comment	ground biochar: brown powder									(+ water)		(atm. Pressure)	
TB1133	1.0 g	1.0 g	KOH	(90%)	mill (1 min)	Ar	3 °C/min	785 °C	1 h	20 g	10% HCl	100 °C N2 stream	0.3 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	
TB1134	1.0 g	1.0 g	KOH	(90%)	mill (2 min)	Ar	3 °C/min	771 °C	1 h	20 g	10% HCl	100 °C N2 stream	0.3 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	

Experiment	Reactor	Raw material		Acid				T	t	pressure			Wash		Output	
MB2937	AV1	9.4 g	Canadian Rockies Hemp	179.3 g	0.96%	0.10 M	Sulfuric acid	180 °C	24 h	8.6 bar	->	10.9 bar	569 g	Water	1.6 g	
Comment	very low amount of foreign material observed and removed during filtration															
MB2938	AV1	8.9 g	Canadian Rockies Hemp	175.0 g	0.96%	0.10 M	Sulfuric acid	180 °C	23.5 h	9.2 bar	->	13.2 bar	577 g	Water	1.4 g	
Comment	very low amount of foreign material observed and removed during filtration															
MB2940	AV1	9.2 g	Canadian Rockies Hemp	177.1 g	0.96%	0.10 M	Sulfuric acid	180 °C	22.5 h	8.7 bar	->	10.6 bar	555 g	Water	1.5 g	
Comment	very low amount of foreign material observed and removed during filtration															
MB2942	AV1	8.9 g	Canadian Rockies Hemp	177.6 g	0.96%	0.10 M	Sulfuric acid	180 °C	23 h	8.3 bar	->	13.5 bar	578 g	Water	1.6 g	
Comment	low amount of foreign material observed and removed during filtration															
MB2943	AV1	9.8 g	Canadian Rockies Hemp	178.2 g	0.96%	0.10 M	Sulfuric acid	180 °C	24 h	8.3 bar	->	12.7 bar	611 g	Water	1.7 g	
Comment	low amount of foreign material observed and removed during filtration															->
MB2944	AV1	9.0 g	Canadian Rockies Hemp	178.4 g	0.96%	0.10 M	Sulfuric acid	180 °C	24 h	8.4 bar	->	9.7 bar	593 g	Water	1.8 g	
Comment	low amount of foreign material observed and removed during filtration															
MB2945	AV1	9.1 g	Canadian Rockies Hemp	177.7 g	0.96%	0.10 M	Sulfuric acid	180 °C	24 h	8.7 bar	->	9.8 bar	6 g	Water	1.6 g	
Comment	low amount of foreign material observed and removed during filtration															

Experiment	Qty	Base			grinding	Gas	T (rate)	T (max)	t	Wash		Drying	Output
MB2946	1.0 g	1.0 g	KOH	(90%)	mill (1 min)	Ar	5 °C/min	770 °C	1 h	22 g	10% HCl	100 °C N2 stream	0.3 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	
MB2947A	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	Ar	3 °C/min	803 °C	1 h	10 g	10% HCl	40 °C N2 stream	<0.01 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		210 mbar	
MB2947B	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	Ar	3 °C/min	804 °C	2 h	10 g	10% HCl	40 °C N2 stream	<0.01 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		210 mbar	
MB2947C	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	Ar	3 °C/min	806 °C	3 h	Batch discarded			
Comment	ground biochar: brown powder; see temperature trend												
MB2947D	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	Ar	3 °C/min	810 °C	3 h	10 g	10% HCl	100 °C N2 stream	38 mg
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	
TB1135-1	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	N2	3 °C/min	800 °C	1 h	14 g	10% HCl	100 °C N2 stream	0.06 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	
TB1135-2	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	N2	3 °C/min	800 °C	1 h	14 g	10% HCl	100 °C N2 stream	0.07 g
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	
MB2952B	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	N2	3 °C/min	800 °C	2 h	10 g	10% HCl	100 °C N2 stream	
Comment	ground biochar: brown powder; see temperature trend									(+ water)		(atm. Pressure)	
MB2952C	0.25 g	0.25 g	KOH	(90%)	mill (1 min)	N2	3 °C/min	800 °C	3 h				
Comment	ground biochar: brown powder; see temperature trend												

Experiment	Reactor	Raw material		Acid				T	t	pressure			Wash		Output
MB2948	AV1	9.4 g	Canadian Rockies Hemp	175.1 g	0.96%	0.10 M	Sulfuric acid	180 °C	25 h	9.0 bar	->	12.6 bar	475 g	Water	1.7 g
Comment	low amount of foreign material observed and removed during filtration														
MB2949	AV1	9.2 g	Canadian Rockies Hemp	174.3 g	0.96%	0.10 M	Sulfuric acid	180 °C	23.5 h	8.4 bar	->	10.2 bar	538 g	Water	1.8 g
Comment	low amount of foreign material observed and removed during filtration														
MB2950	AV1	9.1 g	Canadian Rockies Hemp	170.5 g	0.96%	0.10 M	Sulfuric acid	180 °C	23 h		->	11.1 bar	534 g	Water	1.6 g
Comment	low amount of foreign material observed and removed during filtration														
MB2951	AV1	9.3 g	Canadian Rockies Hemp	178.5 g	0.96%	0.10 M	Sulfuric acid	180 °C	24 h	9.1 bar	->	11.2 bar		Water	
Comment	low amount of foreign material observed and removed during filtration														
MRa255	AV1	9.2 g	Canadian Rockies Hemp	170.8 g	0.96%	0.10 M	Sulfuric acid	180 °C	23.5 h	8.1 bar	->	12.8 bar	488 g	Water	1.7 g
Comment	some foreign material observed and removed during filtration														

Experiment	Qty	Base	grinding	Gas	T (rate)	T (max)	t	Wash	Drying	Output