



SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x100 UD+LD+MD 10/18/2024 500µm




Clariant SU7000 5.00kV 7.3mm x100 UD+LD+MD 10/18/2024 500µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x100 UD+LD+MD 10/18/2024 500µm



Clariant SU7000 5.00kV 7.4mm x100 UD+LD+MD 10/18/2024 500µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x200 UD+LD+MD 10/18/2024 200µm



Clariant SU7000 5.00kV 7.3mm x200 UD+LD+MD 10/18/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x200 UD+LD+MD 10/18/2024 200µm




Clariant SU7000 5.00kV 7.1mm x200 UD+LD+MD 10/18/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3


Sample treatment: The sample was subjected to platinum sputter coating and then measured.




SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x500 UD+LD+MD 10/18/2024 100µm



Clariant SU7000 5.00kV 7.2mm x500 UD+LD+MD 10/18/2024 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x1.00k UD+LD+MD 10/18/2024 50.0µm




Clariant SU7000 5.00kV 7.4mm x1.00k UD+LD+MD 10/18/2024 50.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.2mm x1.00k UD+LD+MD 10/18/2024 50.0µm




Clariant SU7000 5.00kV 7.2mm x1.00k UD+LD+MD 10/18/2024 50.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x2.00k UD+LD+MD 10/18/2024 20.0µm




Clariant SU7000 5.00kV 7.4mm x2.00k UD+LD+MD 10/18/2024 20.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x2.00k UD+LD+MD 10/18/2024 20.0µm



Clariant SU7000 5.00kV 7.4mm x2.00k UD+LD+MD 10/18/2024 20.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x5.00k UD+LD+MD 10/18/2024 10.0µm




Clariant SU7000 5.00kV 7.5mm x5.00k UD+LD+MD 10/18/2024 10.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x5.00k UD+LD+MD 10/18/2024 10.0µm




Clariant SU7000 5.00kV 7.3mm x5.00k UD+LD+MD 10/18/2024 10.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x10.0k UD+LD+MD 10/18/2024 5.00µm



Clariant SU7000 5.00kV 7.5mm x10.0k UD+LD+MD 10/18/2024 5.00µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x10.0k UD+LD+MD 10/18/2024 5.00µm




Clariant SU7000 5.00kV 7.4mm x10.0k UD+LD+MD 10/18/2024 5.00µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x25.0k UD+LD+MD 10/18/2024 2.00µm



Clariant SU7000 5.00kV 7.5mm x25.0k UD+LD+MD 10/18/2024 2.00µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB2997A 2/3 5m 800C 3C/m 1h A 2x1.6P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048326-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 7.3mm x25.0k UD+LD+MD 10/18/2024 2.00µm



Clariant SU7000 5.00kV 7.4mm x25.0k UD+LD+MD 10/18/2024 2.00µm