

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x100 UD+LD+MD 09/26/2024 500µm



Clariant SU7000 5.00kV 6.5mm x100 UD+LD+MD 09/26/2024 500µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x100 UD+LD+MD 09/26/2024 500µm



Clariant SU7000 5.00kV 6.5mm x100 UD+LD+MD 09/26/2024 500µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x200 UD+LD+MD 09/26/2024 200µm



Clariant SU7000 5.00kV 6.3mm x200 UD+LD+MD 09/26/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x200 UD+LD+MD 09/26/2024 200µm



Clariant SU7000 5.00kV 6.2mm x200 UD+LD+MD 09/26/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x500 UD+LD+MD 09/26/2024 100µm



Clariant SU7000 5.00kV 6.4mm x500 UD+LD+MD 09/26/2024 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x500 UD+LD+MD 09/26/2024 100µm



Clariant SU7000 5.00kV 6.5mm x500 UD+LD+MD 09/26/2024 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x1.00k UD+LD+MD 09/26/2024 50.0µm



Clariant SU7000 5.00kV 6.4mm x1.00k UD+LD+MD 09/26/2024 50.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.3mm x1.00k UD+LD+MD 09/26/2024 50.0µm



Clariant SU7000 5.00kV 6.5mm x1.00k UD+LD+MD 09/26/2024 50.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x2.00k UD+LD+MD 09/26/2024 20.0µm



Clariant SU7000 5.00kV 6.4mm x2.00k UD+LD+MD 09/26/2024 20.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x2.00k UD+LD+MD 09/26/2024 20.0µm



Clariant SU7000 5.00kV 6.5mm x2.00k UD+LD+MD 09/26/2024 20.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x5.00k UD+LD+MD 09/26/2024 10.0µm



Clariant SU7000 5.00kV 6.4mm x5.00k UD+LD+MD 09/26/2024 10.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x5.00k UD+LD+MD 09/26/2024 10.0µm



Clariant SU7000 5.00kV 6.5mm x5.00k UD+LD+MD 09/26/2024 10.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x10.0k UD+LD+MD 09/26/2024 5.00µm



Clariant SU7000 5.00kV 6.4mm x10.0k UD+LD+MD 09/26/2024 5.00µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x10.0k UD+LD+MD 09/26/2024 5.00µm



Clariant SU7000 5.00kV 6.5mm x10.0k UD+LD+MD 09/26/2024 5.00µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.5mm x25.0k UD+LD+MD 09/26/2024 2.00µm



Clariant SU7000 5.00kV 6.4mm x25.0k UD+LD+MD 09/26/2024 2.00µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: TB1139 2/3 5m 800C 3C/m 1h A 2x1.7P

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 24-048142-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 6.4mm x25.0k UD+LD+MD 09/26/2024 2.00µm



Clariant SU7000 5.00kV 6.5mm x25.0k UD+LD+MD 09/26/2024 2.00µm