



SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x100 UD+LD+MD 07/05/2024 500µm




Clariant SU7000 5.00kV 4.0mm x100 UD+LD+MD 07/05/2024 500µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x100 UD+LD+MD 07/05/2024 500µm




Clariant SU7000 5.00kV 4.3mm x100 UD+LD+MD 07/05/2024 500µm

SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1


Sample treatment: The sample was subjected to platinum sputter coating and then measured.




SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x200 UD+LD+MD 07/05/2024 200µm




Clariant SU7000 5.00kV 4.3mm x200 UD+LD+MD 07/05/2024 200µm

SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1


Sample treatment: The sample was subjected to platinum sputter coating and then measured.




SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x500 UD+LD+MD 07/05/2024 100µm




Clariant SU7000 5.00kV 4.2mm x500 UD+LD+MD 07/05/2024 100µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x1.00k UD+LD+MD 07/05/2024 50.0µm




Clariant SU7000 5.00kV 4.2mm x1.00k UD+LD+MD 07/05/2024 50.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.2mm x1.00k UD+LD+MD 07/05/2024 50.0µm




Clariant SU7000 5.00kV 4.8mm x1.00k UD+LD+MD 06/28/2024 50.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x2.00k UD+LD+MD 07/05/2024 20.0μm




Clariant SU7000 5.00kV 4.3mm x2.00k UD+LD+MD 07/05/2024 20.0μm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.3mm x2.00k UD+LD+MD 07/05/2024 20.0µm




Clariant SU7000 5.00kV 4.2mm x2.00k UD+LD+MD 07/05/2024 20.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x5.00k UD+LD+MD 07/05/2024 10.0µm




Clariant SU7000 5.00kV 4.3mm x5.00k UD+LD+MD 07/05/2024 10.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.3mm x5.00k UD+LD+MD 07/05/2024 10.0μm




Clariant SU7000 5.00kV 4.3mm x5.00k UD+LD+MD 07/05/2024 10.0μm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x10.0k UD+LD+MD 07/05/2024 5.00µm




Clariant SU7000 5.00kV 4.3mm x10.0k UD+LD+MD 07/05/2024 5.00µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.3mm x10.0k UD+LD+MD 07/05/2024 5.00µm




Clariant SU7000 5.00kV 4.2mm x10.0k UD+LD+MD 07/05/2024 5.00µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x25.0k UD+LD+MD 07/05/2024 2.00µm




Clariant SU7000 5.00kV 4.3mm x25.0k UD+LD+MD 07/05/2024 2.00µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB2955A2
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 24-047491-1

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.3mm x25.0k UD+LD+MD 07/05/2024 2.00µm



Clariant SU7000 5.00kV 4.2mm x25.0k UD+LD+MD 07/05/2024 2.00µm