



SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.2mm x100 UD+LD+MD 03/17/2025 500µm




Clariant SU7000 5.00kV 4.0mm x100 UD+LD+MD 03/17/2025 500µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x100 UD+LD+MD 03/17/2025 500µm




Clariant SU7000 5.00kV 4.1mm x100 UD+LD+MD 03/17/2025 500µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.2mm x200 UD+LD+MD 03/17/2025 200µm




Clariant SU7000 5.00kV 4.0mm x200 UD+LD+MD 03/17/2025 200µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.0mm x200 UD+LD+MD 03/17/2025 200µm



Clariant SU7000 5.00kV 4.1mm x200 UD+LD+MD 03/17/2025 200µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x500 UD+LD+MD 03/17/2025 100µm



Clariant SU7000 5.00kV 4.0mm x500 UD+LD+MD 03/17/2025 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 3.9mm x500 UD+LD+MD 03/17/2025 100µm



Clariant SU7000 5.00kV 4.1mm x500 UD+LD+MD 03/17/2025 100µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x1.00k UD+LD+MD 03/17/2025 50.0µm



Clariant SU7000 5.00kV 4.0mm x1.00k UD+LD+MD 03/17/2025 50.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 3.9mm x1.00k UD+LD+MD 03/17/2025 50.0µm



Clariant SU7000 5.00kV 4.1mm x1.00k UD+LD+MD 03/17/2025 50.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x2.00k UD+LD+MD 03/17/2025 20.0µm




Clariant SU7000 5.00kV 4.0mm x2.00k UD+LD+MD 03/17/2025 20.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 3.9mm x2.00k UD+LD+MD 03/17/2025 20.0µm




Clariant SU7000 5.00kV 4.1mm x2.00k UD+LD+MD 03/17/2025 20.0µm


SCANNING ELECTRON MICROSCOPE (SEM)

Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot
Ordering customer: Dr. Torsten Busch
Dept./Plant: Curia Germany GmbH
Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 4.1mm x5.00k MD 03/17/2025 10.0µm



Clariant SU7000 5.00kV 4.0mm x5.00k UD+LD+MD 03/17/2025 10.0µm

SCANNING ELECTRON MICROSCOPE (SEM)


Sample name: MB3056 2/3 3x30sec 800C 3C/m 1h Rot

Ordering customer: Dr. Torsten Busch


Dept./Plant: Curia Germany GmbH

Order number: 25-049538-3

Sample treatment: The sample was subjected to platinum sputter coating and then measured.



Clariant SU7000 5.00kV 3.9mm x5.00k MD 03/17/2025 10.0µm



Clariant SU7000 5.00kV 4.2mm x5.00k UD 03/17/2025 10.0µm