Applicant	:	Jiaxing Mingzhi Textile Co., LTD
Address	:	Room 1707, Building 1, Xingguang Hui Mall, Haizhou Street, Haining, Jiaxing, Zhejiang,China
Manufacturer	:	Jiaxing Mingzhi Textile Co., LTD
Address	:	Room 1707, Building 1, Xingguang Hui Mall, Haizhou Street, Haining, Jiaxing, Zhejiang,China
Trade marks	:	--

The following sample(s) was /were submitted and identified on behalf of the clients as ：

Sample Name	：	Cotton socks
Model No.	：	MZ-D-001
Labeled Age Grading	：	Over 3 years old
Test Age Grading	：	Over 3 years old
Sample Received Date	：	Sep.24,2024
Testing Period	：	Sep.24,2024 To Sep.27, 2024
Test Method	：	Please refer to next page(s).
Test Result	：	Please refer to next page(s).
CPSC Lab ID	：	1779

Signed for and on behalf of

Andy

Dongguan True Safety Testing Co., Ltd. Approve

Andy Zheng
Technical Director

This report shall not be altered,increased or deleted.The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Result Summary:

	Test Requested	Conclusion
1	Color Fastness to Rubbing ,with reference to ISO105-X12:2016	PASS
2	Color Fastness to Washing ,with reference to ISO 105-C06:2010	PASS
3	Fiber Identification and Content ,with reference to ISO 1833:2020	--
4	pH Value ,with reference to ISO 3071:2020	PASS
5	Formaldehyde ,with reference to ISO 14184-1:2011	PASS
6	AZO Colorants ,with reference to EN 14362-1&3-2012	PASS
7	Colour Fastness To Perspiration(Grade),ISO 105-E04:2007	PASS

Sample Description:

No.	Description
1.	Cotton socks (Finished product)
2.	Red fabric
3.	White fabric

This report shall not be altered,increased or deleted.The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel:+86-0769-85088050 Fax:+86-0769-81221086 E-mail:tst@tst-test.com Http:www.tst-test.com

Test items (units of measurement) (Sample identification)	Test method (Parameter Description)	Technical requirement (Remarks)	Test results (red fabric)
Colour Fastness To Perspiration(Grade)	ISO 105-E04:2007	Acid: discoloration, Acid: stained , Alkaline: discoloration , Alkaline: Stained (According to customer requirements)	(Acid) (Alkaline) discoloration 4-5 4-5 staining -Acetate fiber 4-5 4-5 -cotton 4-5 4-5 -polyamide 4-5 4-5 -terylene 4-5 4-5 -Acrylic fibe 4-5 4-5 -wool 4-5 4-5
Color Fastness to Rubbing（Grade）	ISO105-X12:2016	Dry friction (According to customer requirements)	4-5
Color Fastness to Washing（Grade）	ISO 105-C06:2010	Discoloration, Stained (According to customer requirements)	Discoloration 4-5 staining -Acetate fiber 4-5 -cotton 4-5 -polyamide 4-5 -terylene 4-5 -Acrylic fibe 4-5 -wool 4-5
pH Value	ISO 3071:2020 (Extraction medium: potassium chloride solution）	(According to customer requirements)	5.5

This report shall not be altered,increased or deleted.The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Test items (units of measurement) (Sample identification)	Test method (Parameter Description)	Technical requirement (Remarks)	Test results (red fabric)
Formaldehyde（mg/kg）	ISO 14184-1:2011 UV-Vis Detection limit：20mg/kg	(According to customer requirements)	Not detected
AZO Colorants（mg/kg）	EN 14362-1-2012 EN 14362-3-2012 GC-MS Detection limit：5mg/kg	forbidden（≤20）	Not detected
	Remark：1）Undetected = Less than the method detection limit 2）A list of banned aromatic amines is attached		
Fiber Identification and Content（%）	Combined with the common moisture regain rate AATCC TM20-2021 AATCC TM20A-2021 ISO 1833:2020	--	Cotton:78.0% Polyester fibre:20.1% Spandex:1.9%

Remark ：

（1）N/A Is not applicable or not required

（2）-= unitless

This report shall not be altered,increased or deleted.The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel:+86-0769-85088050 Fax:+86-0769-81221086 E-mail:tst@tst-test.com Http:www.tst-test.com

Attached page: List of banned aromatic amines

ID	Test item	CAS No.	ID	Test item	CAS No.
1	4-aminobenzene	92-67-1	13	2-methoxy-5-methylaniline	120-71-8
2	benzidine	92-87-5	14	4,4'-methylene-bis	101-14-4
3	4-chloro-o-toluidine	95-69-2	15	4,4′-Diaminodiphenyl ether	101-80-4
4	2-naphthylamine	91-59-8	16	4,4′-Diaminodiphenyl sulfide	139-65-1
5*	o-aminoazotoluene	97-56-3	17	o-toluidine	95-53-4
6	p-chloroaniline	106-47-8	18	2,4-diaminotoluene	95-80-7
7	2, 4-dihydroanisole	615-05-4	19	2,4,5-trimethylaniline	137-17-7
8	4,4' -diaminodiphenylmethane	101-77-9	20	o-aminoanisole	90-04-0
9	3.3 7-dichlorobenzidine	91-94-1	21	2,4-dimethylaniline	95-68-1
10	3,3' -dimethoxybenzidine	119-90-4	22	2,6-dimethylaniline	87-62-7
11	3,3' -dimethylbenzidine	119-93-7	23*	5-Nitro-o-toluidine	99-55-8
12	3,3'-dimethyl-4,4' -diaminodiphenylmethane	838-88-0	24**	4-Aminoazobenzene	60-09-3

Remark： 1. ”*” = O-aminoazotoluene (CAS No. 97-56-3), 5-nitro-o-toluidine (CAS No.99-55-8)After treatment with this method, the samples were decomposed into o-toluidine and 2, 4-diamino-toluene

2. ”**” = 4-aminoazabenzene was quantitatively tested with reference to EN 14362-1&3-2012。

This report shall not be altered,increased or deleted.The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel:+86-0769-85088050 Fax:+86-0769-81221086 E-mail:tst@tst-test.com Http:www.tst-test.com

Sample pictures:





*** End of Report ***

This report shall not be altered,increased or deleted.The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel:+86-0769-85088050 Fax:+86-0769-81221086 E-mail:tst@tst-test.com Http:www.tst-test.com