



TIGA WARNA PRIMER

Menciptakan Warna, mendefinisikan Kualitas

Pewarna Disperse **Disperse Dyestuffs**



KONSULTASI SEKARANG!

TENTANG KAMI

Kami merupakan perusahaan manufaktur terkemuka di Indonesia yang berfokus pada penyediaan pewarna Bubuk berkualitas.

Didukung oleh pengalaman industri yang kuat, teknologi produksi modern, serta penerapan standar internasional, kami menghadirkan solusi pewarnaan yang andal untuk memenuhi berbagai kebutuhan industri.

Komitmen terhadap kualitas, konsistensi, dan inovasi berkelanjutan menjadi fondasi utama dalam membangun kemitraan jangka panjang yang tepercaya, sekaligus mendukung proses produksi pelanggan secara optimal dan efisien.



ABOUT US

We are a leading manufacturing company in Indonesia specializing in the supply of high-quality powder dyes.

Backed by strong industry experience, modern production technology, and the implementation of international standards, we deliver reliable coloring solutions to meet the diverse needs of the industry.

Our commitment to quality, consistency, and continuous innovation forms the foundation for building long-term, trusted partnerships while optimally supporting our customers' production processes.

TABEL ISI

CONTENT

- **Prosedur Pencelupan**
Dyeing Procedure
- **Seri Umum**
General Series
- **Seri Pencelupan Kain Mikro**
Micro Fabrics Dyeing Series
- **Seri Pencelupan Cepat (HRD)**
Rapid Dyeing (HRD) Series
- **Seri Ketahanan Luntur Cuci Tinggi (HXF)**
High Washing Fastness (HXF) Series
- **Seri Disperse HXW**
Disperse HXW Series
- **Seri Ketahanan Luntur Cahaya Tinggi (HLF)**
High Light Fastness HLF Series
- **Seri Pencetakan Langsung**
High Light Fastness HLF Series

Dispersed dye general series

Product Colour	Number	Product Name		Product Colour	Number	Product Name
Yellow	TDY1001D	Disperse Yellow TE-RGFL		Orange	TD01101D	Disperse Orange TE-RL
	TDY1002D	Disperse Yellow TE-HGFL			TD01102D	Disperse Orange TE-HRL
	TDY1003D	Disperse Yellow TSE-FL			TD01103D	Disperse Orange TSE-3GL
	TDY1005D	Disperse Yellow TE-3G			TD01104D	Disperse Orange TSE-H3GL
	TDY1006D	Disperse Yellow TE-H3G			TD01105D	Disperse Orange TS-4RLS
	TDY1007D	Disperse Yellow TSE-4RL			TD01106D	Disperse Orange TS-4RL
	TDY1008D	Disperse Yellow TSE-H4RL			TD01107D	Disperse Orange TS-4RL
	TDY1009D	Disperse Yellow TSE-4RLN			TD01109D	Disperse Orange TSE-2R
	TDY1010D	Disperse Yellow TSE-3GL			TD01110D	Disperse Orange TS-3RFL
	TDY1012D	Disperse Yellow TS-G			TD01112D	Disperse Orange TS-2RL
	TDY1013D	Disperse Yellow TS-G			TD01113D	Disperse Orange TS-H2RL
	TDY1014D	Disperse Fluorescent Yellow T-8GFF			TD01115D	Disperse Orange TS-SF
	TDY1015D	Disperse Fluorescent Yellow T-8GFF			TD01116D	Disperse Orange TSE-3RLS
	TDY1016D	Disperse Fluorescent Yellow T-H8GFF			TD01117D	Disperse Orange TSE-3RL
	TDY1017D	Disperse Yellow TS-6GSL			TD01118D	Disperse Orange TSE-RFL
	TDY1018D	Disperse Yellow TS-H6GSL			TD01119D	Disperse Fluorescent Orange T-2GFL
	TDY1022D	Disperse Yellow TSE-5GL			TD01120D	Disperse Orange TSE-4RL
	TDY1027D	Disperse Fluorescent Yellow T-10GN		Red	TDR1301D	Disperse Red TT-B
	TDY1028D	Disperse Fluorescent Yellow T-H10GN			TDR1302D	Disperse Red TT-HB
	TDY1029D	Disperse Fluorescent Yellow T-10GN			TDR1303D	Disperse Red TT-BD
	TDY1030D	Disperse Yellow TSE-4G			TDR1304D	Disperse Red TT-HBD
	TDY1031D	Disperse Yellow TSE-H4G			TDR1305D	Disperse Red TT-2GH
	TDY1032D	Disperse Yellow TSE-5GR			TDR1306D	Disperse Red TS-3GL
	TDY1035D	Disperse Light Yellow TSE-4GL			TDR1308D	Disperse Red TE-FB
	TDY1036D	Disperse Light Yellow TSE-4GL			TDR1309D	Disperse Red TE-HFB
	TDY1037D	Disperse Golden Yellow TSE-3R			TDR1310D	Disperse Red TSE-GFL
	TDY1038D	Disperse Golden Yellow TE-RGN			TDR1311D	Disperse Red TSE-HGFL
	TDY1042D	Disperse Golden Yellow TE-GL			TDR1312D	Disperse Red TS-BGL

Dispersed dye general series

Product Colour	Number	Product Name		Product Colour	Number	Product Name
Red	TDR1313D	Disperse Red TS-BGL		Red	TDR1352D	Disperse Red TSE-H2GF
	TDR1314D	Disperse Red TSE-BBL			TDR1353D	Disperse Fluorescent Red T-GG
	TDR1317D	Disperse Red TS-BEL			TDR1357D	Disperse Red TE-3B
	TDR1319D	Disperse Red TT-2BL		Violet	TDV1501D	Disperse Violet T-2R
	TDR1320D	Disperse Red TT-2BL			TDV1502D	Disperse Violet T-2R
	TDR1321D	Disperse Red TT-BL			TDV1503D	Disperse Violet TT-FBL
	TDR1322D	Disperse Red TT-BS			TDV1504D	Disperse Violet TT-FBL
	TDR1323D	Disperse Red TT-HBS			TDV1505D	Disperse Violet TT-HFBL
	TDR1324D	Disperse Red TT-GS			TDV1507D	Disperse Violet TT-CB
	TDR1325D	Disperse Red TT-GS			TDV1508D	Disperse Violet TT-HCB
	TDR1326D	Disperse Red TT-HGS			TDV1509D	Disperse Violet TT-3RL
	TDR1327D	Disperse Red TSE-4GFL			TDV1510D	Disperse Violet TT-H3RL
	TDR1328D	Disperse Red TS-2GFL			TDV1512D	Disperse Violet TT-5R
	TDR1329D	Disperse Red TT-FRL			TDV1513D	Disperse Violet TT-5RN
	TDR1331D	Disperse Red TT-2B		Blue	TDB1601D	Disperse Blue TT-FFR
	TDR1332D	Disperse Fluorescent Red T-G (Y)			TDB1602D	Disperse Blue TT-GTP
	TDR1333D	Disperse Fluorescent Red T-HG (Y)			TDB1603D	Disperse Bright Blue TE-2BLN
	TDR1334D	Disperse Fluorescent Red T-G (B)			TDB1604D	Disperse Bright Blue TE-2BLN
	TDR1335D	Disperse Fluorescent Red T-HG (B)			TDB1605D	Disperse Bright Blue TE-4R
	TDR1337D	Disperse Red TSE-3B			TDB1606D	Disperse Turquoise Blue TS-GL
	TDR1338D	Disperse Red TSE-3BN			TDB1607D	Disperse Turquoise Blue TS-HGL
	TDR1342D	Disperse Fluorescent Red T-FBS			TDB1608D	Disperse Turquoise Blue TS-GLN
	TDR1343D	Disperse Fluorescent Red T-HFBS			TDB1614D	Disperse Blue TS-HGL
	TDR1344D	Disperse Fluorescent Red T-BG (Y)			TDB1615D	Disperse Blue TS-HGL
	TDR1345D	Disperse Fluorescent Red T-HBG (Y)			TDB1617D	Disperse Blue TS-HGLN
	TDR1346D	Disperse Fluorescent Red T-BG (B)			TDB1620D	Disperse Blue THA-GF
	TDR1347D	Disperse Fluorescent Red T-HBG (B)			TDB1621D	Disperse Blue TT-3RT
	TDR1351D	Disperse Red TSE-2GF			TDB1622D	Disperse Blue TT-BBLS

Dispersed dye general series

Product Colour	Number	Product Name		Product Colour	Number	Product Name
Blue	TDB1623D	Disperse Blue TT-HBBL5		Blue	TDB1647D	Disperse Blue TT-3RN
	TDB1624D	Disperse Blue TT-BGLS			TDB1649D	Disperse Navy Blue T-ECO
	TDB1625D	Disperse Blue TSE-2R		Green	TDG1801D	Disperse Green TT-6B
	TDB1626D	Disperse Blue TSE-2R			TDG1802D	Disperse Green TT-H6B
	TDB1627D	Disperse Blue TSE-H2R			TDG1803D	Disperse Fluorescent Green T-5G
	TDB1631D	Disperse Blue TT-3G		Grey	TDE1833D	Disperse Grey TT-N
	TDB1632D	Disperse Blue TT-3GN		Black	TDK1851D	Disperse Black TT-ECT
	TDB1633D	Disperse Blue TT-3GR			TDK1852D	Disperse Black TT-HECT
	TDB1634D	Disperse Blue TS-3G			TDK1853D	Disperse Black TT-XNT
	TDB1635D	Disperse Blue TS-R			TDK1854D	Disperse Black TT-XNT
	TDB1636D	Disperse Blue TS-R			TDK1855D	Disperse Black TT-HXNT
	TDB1637D	Disperse Blue TT-CRE			TDK1856D	Disperse Black TT-XSF
	TDB1638D	Disperse Blue TT-CRE			TDK1857D	Disperse Black TT-XSF
	TDB1641D	Disperse Blue TT-2BLM			TDK1858D	Disperse Black TT-HXSF
	TDB1643D	Disperse Navy Blue TT-SF			TDK1863D	Disperse Black TT-XNR
	TDB1644D	Disperse Navy Blue TT-HSF			TDK1864D	Disperse Black T-ECO

Disperse Dye Paste Series

Strength	Strength	Strength	This product is suitable		Strength	Strength	Strength	This product is suitable
	TD2001D	Disperse Light Yellow HAP-6GL	Printing Dyes			TD2022D	Disperse Brilliant Red HLD-3BS	Dip Dyes
	TD2002D	Disperse Orange HAP-4RL	Printing Dyes			TD2023D	Disperse Violet HLD-HFRL	Dip Dyes
	TD2003D	Disperse Ruby Red HAP-5BL	Printing Dyes			TD2024D	Disperse Turquoise Blue HLD-GL	Dip Dyes
	TD2004D	Disperse Ruby Red HAP-PB	Printing Dyes			TD2025D	Disperse Vivid Blue HLD-SR	Dip Dyes
	TD2005D	Disperse Scarlet HAP-GS	Printing Dyes			TD2026D	Disperse Bright Blue HLD-CRE	Dip Dyes
	TD2006D	Disperse Brilliant Red HAP-3B	Printing Dyes			TD2027D	Disperse Bright Blue HLD-2BLM	Dip Dyes
	TD2007D	Disperse Brilliant Red HAP-3BS	Printing Dyes			TD2028D	Disperse Bright Blue HLD-5R	Dip Dyes
	TD2008D	Disperse Violet HAP-HFRL	Printing Dyes			TD2029D	Disperse Navy Blue HLD-3BG	Dip Dyes
	TD2009D	Disperse Turquoise Blue HAP-GL	Printing Dyes			TD2030D	Disperse Black HLD	Dip Dyes
	TD2010D	Disperse Vivid Blue HAP-SR	Printing Dyes			TD2031D	Arabian Black DB	Dip Dyes
	TD2011D	Disperse Bright Blue HAP-5R	Printing Dyes			TD2032D	Disperse Light Yellow LPD-6GL	Pad Dyes
	TD2012D	Disperse Navy Blue HAP-3BG	Printing Dyes			TD2033D	Disperse Orange LPD-4RL	Pad Dyes
	TD2013D	Disperse Black HAP-HFP	Printing Dyes			TD2034D	Disperse Ruby Red LPD-5BL	Pad Dyes
	TD2014D	Disperse Black HAP-HLP	Printing Dyes			TD2035D	Disperse Scarlet LPD-GS	Pad Dyes
	TD2015D	Disperse Light Yellow HLD-6GL	Dip Dyes			TD2036D	Disperse Brilliant Red LPD-3BS	Pad Dyes
	TD2016D	Disperse Orange HLD-4RL	Dip Dyes			TD2037D	Disperse Violet LPD-HFRL	Pad Dyes
	TD2017D	Disperse Orange HLD-3RL	Dip Dyes			TD2038D	Disperse Turquoise Blue LPD-GL	Pad Dyes
	TD2018D	Disperse Ruby Red HLD-5BL	Dip Dyes			TD2039D	Disperse Bright Blue LPD-5R	Pad Dyes
	TD2019D	Disperse Ruby Red HLD-PB	Dip Dyes			TD2040D	Disperse Navy Blue LPD-3BG	Pad Dyes
	TD2020D	Disperse Scarlet HLD-GS	Dip Dyes			TD2041D	Disperse Black LPD	Pad Dyes
	TD2021D	Disperse Brilliant Red HLD-3B	Dip Dyes					

Ink Dye Series

Product Colour	Number	Product Name			Product Colour	Number	Product Name	
	TD9001D	Reactive Ink Cyan ATE	Digital Printing Ink			TD9101D	Disperse Ink Cyan WTK	Sublimation Ink
	TD9002D	Reactive Ink Magenta ATE	Digital Printing Ink			TD9102D	Disperse Ink Red WTK	Sublimation Ink
	TD9003D	Reactive Ink Yellow ATE	Digital Printing Ink			TD9103D	Disperse Ink Yellow WTK	Sublimation Ink
	TD9004D	Reactive Ink Royal Blue ATE	Digital Printing Ink			TD9104D	Disperse Ink Black WTK	Sublimation Ink
	TD9005D	Reactive Ink Black ATE	Digital Printing Ink					

Disperse dye printng series

Product Colour	Number	Product Name		Product Colour	Number	Product Name
Yellow	TDY1019D	Disperse Yellow TPP-6G		Blue	TDB1609D	Disperse Blue TPP-GL
	TDY1025D	Disperse Yellow TPP-BRL			TDB1611D	Disperse Blue TPP-BGL
	TDY1034D	Disperse Yellow TPP-3R			TDB1616D	Disperse Blue TPP-HGL
Orange	TD01108D	Disperse Orange TPP-4RL			TDB1618D	Disperse Blue TPP-HGLN
	TD01111D	Disperse Orange TPP-3RFL		Brown	TDN1832D	Disperse Brown TPP-2BL
	TD01114D	Disperse Orang TPP-3RL		Grey	TDE1834D	Disperse Grey TPP-HBL
Red	TDR1307D	Disperse Red TPP-3GL		Black	TDK1859D	Disperse Black TPP-2BL
	TDR1318D	Disperse Red TPP-BEL			TDK1860D	Disperse Black TPP-4BL
	TDR1330D	Disperse Red TPP-FRL			TDK1862D	Disperse Black TPP-GI
Violet	TDV1511D	Disperse Violet TPP-3RL				

Disperse dye high hydroxide series

Disperse dye high-fastness series

Product Colour	Number	Product Name		Product Colour	Number	Product Name
Yellow	TDY1020D	Disperse Yellow THW-6G		Red	TDR1336D	Disperse Red THS-XF
	TDY1021D	Disperse Yellow THW-GL			TDR1348D	Disperse Red THS-SF
	TDY1024D	Disperse Yellow THW-7G		Blue	TDB1628D	Disperse Blue THS-3RF
	TDY1033D	Disperse Yellow THW-3R			TDB1629D	Disperse Blue THS-AR
Orange	TD01122D	Disperse Orange THW-BGS			TDB1630D	Disperse Blue THS-XF
Red	TDR1339D	Disperse Red THW-CBN			TDB1639D	Disperse Blue THS-2GS
	TDR1340D	Disperse Red THW-HCBN			TDB1640D	Disperse Blue THS-2GSN
	TDR1341D	Disperse Red THW-BWF		Brown	TDN1831D	Disperse Brown THS-XF
	TDR1349D	Disperse Red THW-4BS				
	TDR1350D	Disperse Red THW-4BSN				
	TDR1355D	Disperse Scarlet THW-GBN				
	TDR1356D	Disperse Rose Red THW-BWFS				
Blue	TDB1648D	Disperse Bright Blue THW-RF				

Disperse dye high sun exposure series			Disperse dye microfibre series		
Product Colour	Number	Product Name	Product Colour	Number	Product Name
Yellow	TDY1004D	Disperse Yellow THL-FL	Yellow	TDY1039D	Disperse Golden Yellow TCC
	TDY1011D	Disperse Yellow THL-5G		TDY1040D	Disperse Yellow TCC
	TDY1023D	Disperse Yellow THL-2GL		TDY1041D	Disperse Yellow TAC
	TDY1026D	Disperse Yellow THL-BRLN	Orange	TD01123D	Disperse Orange TCC
Orange	TD01121D	Disperse Orange THL-AUL	Red	TDR1354D	Disperse Red TAC
Red	TDR1315D	Disperse Red THL-5GL		TDR1358D	Disperse Scarlet TCC
	TDR1316D	Disperse Red THL-REL		TDR1359D	Disperse Red TCC
Violet	TDV1506D	Disperse Violet THL-2RL		TDR1360D	Disperse Rubine TCC
Blue	TDB1610D	Disperse Blue THL-BGL	Blue	TDB1642D	Disperse Blue TAC
	TDB1612D	Disperse Blue THL-BFL		TDB1645D	Disperse Blue TCC
	TDB1613D	Disperse Blue THL-BFL		TDB1646D	Disperse Navy Blue TCC
	TDB1619D	Disperse Bright Blue THL-BGF	Black	TDK1861D	Disperse Black TCC

Dyeing Procedure of Disperse dyes

一. High temperature high pressure dyeing:

1. High temperature high pressure dyeing is carried out using a closed type dyeing machine such as cheese, beam, jet, jig or liquor flow type according to the form of the material.
2. General dyeing conditions are as follows: About 1-2g/L dispersing agent is added to dyeing liquor, and then PH value of the liquor is adjusted to 5-6 with acetic acid or buffer solution (acetic acid and sodium acetate). The dyeing liquor is then gradually raised from 40-60°C to 125-135°C, and at this temperature the dyeing is continued for 30-90 min.
3. When dyeing in pale color, sometimes no need to add Dispersing agent, but deep colour dyeing, must add suitable Dispersing agent to keep liquid dispersing.
4. And also dyeing temperature and dyeing time differ with the form of the material, the dye concentration and dyeing apparatus. Therefore, it is important to select the suitable dyeing condition. After dyeing by various methods, reduction cleaning is carried out generally, unfixed dye on the fiber surface is removed by this treatment. Colour of the dye itself as well as good rubbing and wet fastness are obtained.
5. The condition of reduction cleaning is generally as follows: 2g/L Hydrosulphite, 3ml/L Caustic soda 38° Bc, Temperature: 80°C Time: 10-15min

二. Carrier dyeing

1. Carrier dyeing is carried out under atmosphere pressure by an addition of carrier to the dyeing liquor. Methyl naphthalene or chlorobenzene type carrier is used generally, which is added in concentration of 2-7g/L to the dyeing liquor. Other conditions of the dyeing liquor are the same as those for high temperature dyeing. The temperature is raised gradually from 40-60°C and continued for 90-120min at 100°C.
2. In carrier dyeing, in some case the troubles such as staining of dye or carrier spot are taken from the non stability of emulsifier in the carrier under high temperature or some other conditions, Therefore, it is necessary to select the carrier so as to prevent the troubles.
3. Reduction cleaning as stated in high temperature high pressure dyeing.

三. Thermosol dyeing

1. Thermosol dyeing is a continuous dyeing method which is applied mainly for the polyester/cotton blended material. General dyeing condition is as follows.
2. Dye and 0.5-2g/L of migration inhibitor (for example, sodium alginate) and also wetting agent if necessary are added to the padding liquor.
3. Squeezing is carried out 1 dip 1 nip at room temperature, pick up 65-70%. After padding and intermediate drying, thermosol fixation is carried out by dry heating for 60-120sec. at 180-210°C, depending on the form of the material and type of disperse dyes.

E Type: 180-190°C x 60-120sec.

SE Type: 190-200°C x 60-120sec.

S Type: 200-210°C x 60-120sec.

5. Thermosol dyeing Reduction cleaning as stated in high temperature high pressure dyeing.

四. Printing

By printing style

- 1. Direct printing
- 2. Discharge printing
- 3. Resist printing

By printing apparatus

- 1. Hand printing
- 2. Screen printing
- 3. Roller printing

1. Direct Printing

(1) High pressure steaming method (HP steaming)

Recipe of color paste:

Disperse dye	x g
water (50-60°C)	y g
Thickening paste	500-600g
Tartaric acid	3g
Sodium chlorate	5g
Total	1000g

After printing and drying, steamed for 30 min, at 130°C, then washed with cold and warm water, and reduction cleaning.

(2) High temperature steaming method (HT steaming)

Recipe of color paste: x g

water (50-60°C)	y g
Thickening paste	500-600g
Dyeing accelerant	20-40g
Tartaric acid	3g
Sodium chlorate	5g
Total	1000g

After printing and drying, steamed with super heat steam for 6-8 min, at 180-185°C, then washed with cold and warm water, and reduction cleaning

2. Discharge Printing

The material dyed with dischargeable disperse dye by carrier or high temperature dyeing methods is discharged by following methods: By use of stannous chloride as a discharging agent

(1) White discharge

Stannous chloride	80-120g
Tartaric acid	5-25g
Urea	25g

Water 115-165g

Thickening paste 750-665g

Water Yg

After printing and drying, steamed for 20-30 min, at 120-130°C then washed with cold and warm water, and reduction cleaning.

(2) Colored discharge

Undischargeable disperse dye	x g
Stannous chloride	50-80g
Urea	80 g

Auxiliaries for discharge 50g
800-700g

Fluorescent brightening agent DT 15g

(3) Resist printing

Recipe of resist paste:

Undischargeable disperse dye	Xg
Thickning paste	500-600g
Wetting agent	0-20g
Warm water	Yg
Tartaric acid	3-5g
Stannous chloride	40-60g
Total	1000g

Recipe of over paste:

Dischargeable disperse dye	Xg
Thickning Past	500-600g
Wetting agent	0-20g
Warm water	Yg
Stannous chloride	40-60g
Sodium chlorate	2g
Total	1000g

After printing of resist paste, moreover printed a over paste, instantaneously or after drying, and dried, then steamed for 20-30 mins, at 120-130°C, and washed with cold and warm water, finally reduction cleaning.

五、Light fastness (xenon)GB/ 8427-1998 (EOV. ISO 105-B02:1994)

Washing fastness GB/T3921-2008 (EOV. ISO 105-C10:2006)

Rubbing fastness GB/T3920-1998 (EOV. ISO 105-X12:2001)

Sublimation fastness GB/ 5718-1997 (EOV. ISO 105 P01:1993)

六、△Very suitable ▲Suitable ▲not suitable