


HOLDFAST EXTRA-STICKY BODY GLITTER

A soft film that holds PET glitter on skin and wool, then comes off in cold water.

Chemistry from Scout MOL design d702c83f. Claims stop where that design stops. No wear-hour number was measured.



PCDI crosslinker · N=C=N in blue · Scout SMILES

On the body. On the wool.

01 Holds through movement

Once the film has set, glitter is meant to stay on skin and on wool instead of migrating. Wear hours were not measured. Do not read a timed all-night claim into that.

02 Flexes. Does not flake by design.

Soft anionic aliphatic polyester PUD, minimum film-forming temperature under 15 °C. Wool can drape. A rigid bondline was rejected because it cracks and sheds.

03 Leaves when you wash it out

Cold hand-wash after three days is the expected removal. Perchloroethylene sheds the flake. Machine or hot water is out — wool felts, and this film is not built for that.

04 Sets at room temperature

Twenty-four hours at room temp. Optional 40 °C for twenty minutes. No 60 °C oven. Full carbodiimide crosslink takes 3–7 days.

How it works Plain language from BP-PUD-1. Not a different chemistry.

Print a thin coat of a soft waterborne polyurethane. Drop the flake onto the wet film. A polycarbodiimide (Picassian XL-732 or Carbodilite E-02, 4 % on polymer) ties the film to carboxyl groups on wool. A small dose of pre-hydrolyzed GPTMS helps the same film wet PET glitter at carboxyl and hydroxyl ends, and wool amine. Acrylic-lacquered glitter needs no extra flake primer. CPO is for polypropylene, not PET. APTES only if aluminum is exposed. The film stays soft so the garment can move. This is a textile binder used as a cosmetic coating, not a medical adhesive and not a cleared cosmetic formula.

Spec · mix, apply, cure

MIX (WET)

100 PUD : 4 XL-732 : 0.4 GPTMS

PUD

40% solids, pH 8-8.5, MFFT <15C

APPLY

Print thin film, drop flake

CURE

24h room temp · optional 40C / 20 min · no 60C oven

FULL CDI

3–7 days at room temperature

WASH

Cold hand-wash after 3 days, expected. Perc sheds. Machine/hot: no.

What this page will not claim

Scout did not measure wear hours, sweat, or mucous-membrane contact — so we do not. Not hypoallergenic. Not dermatologist-tested. Patch-test. GPTMS is an epoxy silane. Avoid eyes and mucous membranes. Not BP-CA-1 (wicks, stiffens, blooms, yellows wool) and not BP-DA-1 (60 °C, MDI respiratory sensitizer). Perc dry-clean sheds the flake. Full wash hold is expected after three days, not after the first night. Backup kit BP-ACR-1 (DAAM/ADH) if PUD is unavailable.