
2025 Highlights

Crude steel production 2000 - 2025



Apparent steel use per capita




Globally, **209 kg of steel** was used in new products **per person in 2025.**

Crude steel production by process

Share of BOF steel in global production **69.4%**

Share of EAF steel in global production **30.3%**



Average BF-BOF GHG intensity	Average DRI-EAF EAF GHG intensity	Average scrap-EAF GHG intensity
2.66	1.66	0.71

Average global GHG intensity 2.18

In tonnes CO_2e per tonne of crude steel

Average BF-BOF CO_2 intensity	Average DRI-EAF CO_2 intensity	Average scrap-EAF CO_2 intensity
2.34	1.47	0.69

Average global CO_2 intensity 1.92

In tonnes CO_2 per tonne of crude steel

Based on 2024 activity data.

World crude steel production 1950 to 2025


million tonnes, crude steel production

Years	World
1950	189
1955	270
1960	347
1965	456
1970	595
1975	644
1980	717
1985	719
1990	770
1995	753

Years	World
2000	850
2005	1 148
2010	1 435
2011	1 540
2012	1 563
2013	1 654
2014	1 676
2015	1 626
2016	1 634

Years	World
2017	1 738
2018	1 831
2019	1 879
2020	1 883
2021	1 963
2022	1 889
2023	1 904
2024	1 887
2025	1 849

million tonnes, crude steel production



Average growth rates % per annum

Years	World
1950-55	7.4
1955-60	5.1
1960-65	5.6
1965-70	5.5
1970-75	1.6
1975-80	2.2
1980-85	0.1
1985-90	1.4
1990-95	-0.5
1995-00	2.5
2000-05	6.2
2005-10	4.6
2010-15	2.5
2015-20	3.0
2020-25	-0.4