



Application

It is mainly used in the discharge filtration of paint mist or industrial oil mist from painting systems or pre-filtration of general ventilation.

Feartures

- Step by step encryption of filter fibres and stratified filtration
- High dust holding and long service life
- Air outlet surface with film treatment, stable structure, not easy to drop chips
- Strong adsorptive power for paint mist and oil mist
- Excellent moisture-proof, elasticity, acid and alkali resistance, and high temperature resistance.

Technical Parameters

Main material	Fiberglass fiber	Flammability rating	Class 3/B1 (GB/T 17591-2006)
Filtration class	G2, G3, G4 (EN779)	Temperature resistance	250°C
Filter object	Paint mist, oil mist, dust particles	Temp. short peak	300°C
Final resistance	200Pa (Suggestion)	Humidity resistance	100%
Average weight efficiency	PA-50/60 ≥90%, PA-75 ≥95%, PA-100 ≥98%	Color	Green-white, Blue-white, Yellow-white, Pink-white and white

Specifications

Model	Filtration Class	Thickness (mm)	Weight (g/m²)	Dust holding capacity (g/m²)	Air velocity (m/s)	Rated air flow (m³/h)	I.N.P (Pa)	F.N.P (Pa)	Capture Rate
RT-PA30	G2	30-40	180	>3500	2	7200	15	200	85%
RT-PA50	G3	40-50	210	>3800	2	7200	18	200	90%
RT-PA60	G3	50-60	220	>4000	2	7200	20	200	90%
RT-PA70	G3	60-70	250	>4300	1,75	6300	23	200	95%
RT-PA80	G4	70-80	300	>4600	1,75	6300	28	200	95%
RT-PA100	G4	90-100	350	>5000	1,5	4500	35	200	98%
RT-PA120	G4	110-120	450	>6000	1,3	4200	55	200	98%
RT-PA130	G4	120-130	500	>6500	1,3	4200	60	300	98%