# Mill Plan

Milling sequence and setup instructions

## Board Specifications

Dimensions: 12.000" (12") × 18.000" (18") × 1.500" (1 1/2")
Style: checkerboard
Species: Walnut, Maple

## Milling Sequence

**1. Mill rough stock**

Joint one face and one edge on the jointer, then plane to final thickness plus 1/8" (3 mm). Rest overnight, then plane to final thickness. Take ~1/64" (0.4 mm) passes for the last two passes.

- Final pass depth: ~1/64" (0.4 mm)

**2. Rip strips**

Rip strips with the jointed edge against the fence. Measure from the fence face to the near side of a tooth set toward the fence.

- Fence to blade: strip width from cut list

**3. Glue up**

Glue the first edge-grain panel. Alternate clamps above and below the panel and check for flat with a straightedge.

- Clamp spacing: about 8" (200 mm)

**4. Flatten first panel**

Plane or sand the panel flat. It is still long grain, so the planer is allowed here if the panel is no wider than 12" (305 mm); a wider panel goes to the router sled or drum sander.

**5. Crosscut slices**

Crosscut the panel into slices of the final thickness on a crosscut sled with a stop block.

- Slice length: final board thickness from cut list

**6. Rotate slices**

Turn each slice end grain up.

**7. Flip alternate slices**

Flip every other slice end for end so the colours alternate into squares.

**8. Glue up**

Glue slices into the final panel, aligning the squares at every joint. Alternate clamps above and below the panel and check for flat with a straightedge.

- Clamp spacing: about 8" (200 mm)

**9. Flatten and sand**

Flatten with a router sled or drum sander, never the thickness planer. Sand 80, 120, 180 grit. Break edges (180 grit).

- Grits: 80 / 120 / 180

**10. Edge profile**

Rout the edge profile, default: 1/8" (3 mm) roundover. Optional finger grips: core box / round-nose bit 3/8-1/2" (9.5-12.7 mm).

- Bit: 1/8" (3 mm) roundover

**11. Finish**

Raise the grain with a damp cloth, sand 180 again, then flood with food-safe mineral oil and top with board butter.