



STONECHIP

DESCRIPTION	NOVAL STONCHIP is carefully formulated for the protection of sills, valances fenders, underbody, chassis and load box areas.		
CODE AND PACK SIZE	STC001, Stonechip Black – 1lt STC002, Stonechip White – 1lt STC003, Stonechip Grey – 1lt		
HEALTH & SAFETY DATA	Storage	: Should be stored at room temperature. : Equipment must be washed with water immediately after used	
	Protective Clothing	: Gloves & goggles should be worn	
GENERAL QUALITIES	<ul style="list-style-type: none">➤ Resistant to water, oil and petrol.➤ Stonechip is simple to apply and provides a durable surface with good elasticity➤ It will dry from the outer edges towards the centre within 2 – 3 hours➤ Accelerated drying can be achieved by baking at 80C.		
PHYSICAL PROPERTIES	Density	: Base Component	- 1.45 typical
		: Catalyst Component	- 1.00 typical
	Flash Point	: Base Component	- above 23 °C
		: Catalyst Component	- above 23 °C
	Solid Content	: Typically ± 65% by wt	
	Spreading Rate	: Depends upon contour of area to be repaired	
	Finish	: Dull matt	
	Colours Avail.	: Black, White and Grey	
	Viscosity	: Base Component	- ± 98 - 120 Ku's @ 25°C
	SG	: +/-1.250	
	Sag Resistant	: 350 micron – 1 coat no sag	
	Solids	: 48 – 52%	
RECOMMENDED SURFACE PREPARATION	Surface to be treated should be sanded or ground in order to remove all rust, grease, paint, dirt and wax.		
RECOMMENDED PRIMERS	Not applicable		
THINNER RECOMMENDED	N/A. Thinners should not be added to this product.		
OVERCOATABILITY	Can be overcoated with Vollux or Glaker top coats		
APPLICATION DETAILS	<ul style="list-style-type: none">➤ Stonechip sealer may be applied with a suction pistol or airless spray➤ Spraying pressures of 4 – 6 bar with a spraying distance of 25 – 30 cm➤ Overspray		

DISCLAIMER: The information given in this document is offered in good faith, but no warranty is implied or expressed. The onus is on the end user to ensure the suitability of this product to meet the end user requirements. It is also the end user's responsibility to follow health & safety procedures when using this product.