

STEEL GROUT RANGE





Features



Excellent Early Strengtheing



Non-shrink Grout



Self-compactable

SG 2 FLOWABLE

HIGH PERFORMANCE GROUT

AREAS OF APPLICATION


JSW Steel Grout SG 2 is a cementitious highly flow-able non shrink high strength grout for precision application like repair RCC Structures, heavy machinery foundations etc.



Turbine Generator Bearings



Boiler Foundations



Columns in precast crane

8 BENEFITS

- · High early strength and highly flow able
- Highly Durable
- Non Expansive
- Non Shrink
- · High Compressive, flexural & Tensile Strength
- Early loading
- Self-Compacting
- · High Bond Strength

BEST BEFORE

6 months from the date of manufacturing if stored in unopened original packing, under shaded area in dry and moisture free conditions.

COVERAGE & CLASS

- Yield about 11 litre per 25 kg bag
- 80 MPa Grout complying to ASTM C 1107/1107M: 20 & CRD-C-621-83

TECHNICAL SPECIFICATIONS

Properties	Results
Appearance	Free Flowing Powder
Color	Cementitious Grey
Water/ Powder Ratio	0.13 - 0.15
Flow on Table ⓐ 30°C in mm	Min. 260 mm
Fresh Wet Density, Kg/m3	2200 - 2400
Initial Setting Time, Minutes	> 200
Final Setting Time, Minutes	⟨ 600
Pot Life @ 30°C	45 - 60 minutes

Compressive Strength, MPa (IS 4031 Part 6)

1 Day	Minimum 25
3 Days	Minimum 50
7 Days	Minimum 65
28 Days	Minimum 80
Expansion	Nil

PACK SIZE 25 kg





World's No.1 Eco Friendly Cement Company



Babukhan Millenium Centre, 6-3-1099/1100, No. 702, Block-A, Somajiguda, Hyderabad, Telangana, India, Pincode - 500 082.



