




# **Role of Hypoxic Conditions in Cartilage Tissue Engineering**

Chan Cheuk Ka  
1155174356

Supervisor: Prof Li Zhong Alan  
Associate Examiner: Prof CHAN Pui Barbara





# Table of contents

**01**

## **Background**

Problem statement

**02**

## **Theory**

Experimental rationale

**03**

## **Materials & Methods**

Experimental protocols

**04**

## **Results & Discussion**


Experimental results



# 01

## Background

Problem statement



# Cartilage Damage

## Current situation

Cartilage damage is a very common ailment affecting many people worldwide



# Limited Regeneration Capacity <sup>[2]</sup>




## Avascular

Lacks direct oxygen supply



## Aneural

Lacks stimulation



## Alymphatic

Slow metabolism



## Lack Progenitors

Slow healing


[3]

[2] C. A. Vilela et al., *ACS biomaterials science & engineering*, 2015

[3] A. Lindahl et al., *Tissue Engineering*, 2023

# Hyaline Cartilage


- Smooth in nature
- Rich in type II collagen
- Exhibits low friction
- Aids joint articulation [4]



[4] J. C. Sherwood et al., *Drug Discovery Today*, 2014 [3] A. Lindahl et al., *Tissue Engineering*, 2023

[5] X. Li et al., *Advanced Healthcare Materials*, 2024

# Fibrocartilage Formation




- Form after injuries
- Rich in type I collagen
- Inferior biomechanical properties
- Unsuitable for joint articulation
- Degrades cartilage
- Can lead to osteoarthritis [7]


[6] Y. A. Pei et al., *Cellular and Molecular Life Sciences*, 2022

[7] J. Li et al., *Science Advances*, 2022

# Current Treatments



**Microfracture**




**Joint replacement**

[8] K. R. Stone, [www.stoneclinic.com](http://www.stoneclinic.com), 2020

[9] J. R. H. Foran et al., *Aaos.org*, 2016




# Autologous Chondrocyte Implantation




[1] M. Liu *et al.*, *Bone Research*, 2017

# Mesenchymal Stem Cells (MSCs)



[10]

# Chondrocyte Phenotypic Instability



[11] Z. Liu et al., *Human Cell*, 2023

# 02

## Theory

Experimental design rationale



# 2% – 7% O<sub>2</sub>

The native oxygen concentration of cartilage<sup>[12]</sup>

[12] H. Le et al., *Journal of Tissue Engineering*, 2020

# Hypoxia-Inducible Factor-1 $\alpha$



**5–10 mins half-life in O<sub>2</sub>** [13]

Normoxia:

Degraded via prolyl hydroxylation and  
proteasome degradation [14]

Hypoxia:

Hydroxylases are inhibited [15,16]

[13] S. Salceda *et al.*, *Journal of Biological Chemistry*, 1997

[14] R. Amarilio *et al.*, *Development*, 2007

[15] G. Teti *et al.*, *Stem Cells International*, 2018

[16] M. Y. Koh *et al.*, *Trends in Biochemical Sciences*, 2012

# Hypoxia-Inducible Factor-1 $\alpha$




## Regulates differentiation<sup>[17]</sup>

Upregulates related genes like *Sox9*



## Stabilises phenotype<sup>[18]</sup>


Epigenetic effects



[17] M. B. Goldring *et al.*, *Annals of the New York Academy of Sciences*, 2010

[18] D. K. Taheem *et al.*, *Tissue Engineering Part B: Reviews*, 2020

# Hypoxia mimetic agent $\text{CoCl}_2$





# 3D Culturing

## 3D

- Promote cell-cell & cell-ECM interactions [19]
- Natural cell morphology by allowing aggregation and micro-environments [19]
- Can induce more chondrogenic markers and proteins [20]

## 2D

- Convenient
- Easily reproducible
- Cannot mimic *in vivo* environments (mostly cell-plastic & cell-medium interactions) [20,21]

[19] D. Antoni *et al.*, *International Journal of Molecular Sciences*, 2015

[20] M. M. J. Caron *et al.*, *Osteoarthritis and Cartilage*, 2012

[21] J. C. Fontoura *et al.*, *Materials Science and Engineering: C*, 2020


# 03

## Materials & Methods

Experimental protocols



# Experimental Flow



# Chondrogenesis Evaluation

Gene (qPCR)	Chondrogenic Involvement	Expectation
<b><i>Hif1<math>\alpha</math></i></b>	Regulates chondrogenic differentiation	↑ in hypoxia
<b><i>Colla1</i></b>	Type I collagen	↓ in hypoxia
<b><i>Col2a1</i></b>	Type II collagen: major cartilage component	↑ in hypoxia
<b><i>Col10a1</i></b>	Type X collagen	↓ in hypoxia
<b><i>Acan</i></b>	Aggrecan: major cartilage component	↑ in hypoxia
<b><i>Sox9</i></b>	Maintains cartilage homeostasis	↑ in hypoxia
<b><i>Mmp13</i></b>	Degrades type II collagen	↓ in hypoxia

# 04

## Results & Discussion


Experimental results



# MSC Thawing


**Day 3**

**14-3-2025**




**Day 5**

**16-3-2025**




**Day 7**

**18-3-2025**



**Day 9**

**20-3-2025**




MSCs in T75 flask, 10× magnification

# MSC Culturing


**Day 1**

**20-3-2025**




**Day 3**

**22-3-2025**



**Day 5**

**24-3-2025**



MSCs in 12-well plate, 10× magnification

# MSC Chondrogenesis

**Day 1**

**24-3-2025**

**Day 5**

**28-3-2025**

**Day 9**

**1-4-2025**





**Day 11**

**3-4-2025**






**Day 14**

**6-4-2025**

**Control**



**CoCl<sub>2</sub>**



MSCs in 12-well plate, 10× magnification





# Alcian Blue Staining



4×

20×

Control



CoCl<sub>2</sub>




MSCs in 12-well plate (Alcian blue)

# RNA extraction

Sample	Concentration (ng/ $\mu$ L)	A260/A280	A260/A230
Norm-1	0.74	1.67	0.09
Norm-2	1.28	1.80	0.18
<b><u>Norm-3</u></b>	<b><u>1.92</u></b>	<b><u>2.09</u></b>	<b><u>3.30</u></b>
<b><u>Hypo-1</u></b>	<b><u>1.98</u></b>	<b><u>2.98</u></b>	<b><u>3.09</u></b>
Hypo-2	1.70	1.57	0.58
Hypo-3	1.58	3.37	0.01

# qPCR

qPCR (Trial 4)



$$\Delta\Delta Cq = -1.88$$

→ 3.69× higher in hypoxia

p=0.054

Gene	Normalised Cq						Mean		SD		P-value
	NORM		HYPO		NORM	HYPO	NORM	HYPO			
Hif1α	-1.46	-4.04	-1.31	-4.56	-4.02	-3.89	-2.27	-4.15	1.54	0.36	0.054
Col1a1	-0.40	-10.8	-10.2	-11.4	-10.8	-10.2	-7.14	-10.8	5.85	0.61	0.170
Col2a1	-	-	+6.87	+8.50	-	+6.59	+6.87	+7.54	1.35	1.35	-
Col10a1	+3.19	+3.22	+2.95	+0.96	+2.24	-0.46	+3.12	+0.91	0.15	1.35	0.024
Acan	+4.71	+5.68	+5.73	+6.06	+8.26	+6.32	+5.37	+6.88	0.57	1.2	0.061
Sox9	-0.30	+1.20	+0.41	+0.42	+0.71	+0.57	+0.44	+0.57	0.75	0.15	0.392
Mmp13	0.21	+0.32	-0.21	-0.62	-0.14	-0.26	+0.11	-0.34	0.28	0.25	0.053

# Discussion

## qPCR & Staining

To be reattempted in the future to acquire more conclusive results

## Implications

Based on literature...

Hypoxic culturing of cartilage tissue *in vitro* is viable

It is an effective and efficient method of phenotypic control, compared to the use of factor and hormone cocktails

# References

- [1] M. Liu *et al.*, "Injectable Hydrogels for Cartilage and Bone Tissue Engineering," *Bone Research*, vol. 5, no. 17014, p. 17014, May 2017, doi: <https://doi.org/10.1038/boneres.2017.14>.
- [2] C. A. Vilela, C. Correia, J. M. Oliveira, R. A. Sousa, J. Espregueira-Mendes, and R. L. Reis, "Cartilage Repair Using Hydrogels: A Critical Review of in Vivo Experimental Designs," *ACS biomaterials science & engineering*, vol. 1, no. 9, pp. 726–739, Aug. 2015, doi: <https://doi.org/10.1021/acsbiomaterials.5b00245>.
- [3] A. Lindahl *et al.*, "Cartilage and Bone Regeneration," in *Tissue Engineering (Third Edition)*, J. de Boer, C. A. van Blitterswijk, J. A. Uquillas, and N. Malik, Eds., Academic Press, 2023, pp. 533–583. doi: <https://doi.org/10.1016/b978-0-12-824459-3.00016-0>.
- [4] J. C. Sherwood, J. Bertrand, S. E. Eldridge, and F. Dell'Accio, "Cellular and Molecular Mechanisms of Cartilage Damage and Repair," *Drug Discovery Today*, vol. 19, no. 8, pp. 1172–1177, Aug. 2014, doi: <https://doi.org/10.1016/j.drudis.2014.05.014>.
- [5] X. Li *et al.*, "Research Progress in Hydrogels for Cartilage Organoids," *Advanced Healthcare Materials*, vol. 13, no. 22, May 2024, doi: <https://doi.org/10.1002/adhm.202400431>.
- [6] Y. A. Pei, S. Chen, and M. Pei, "The Essential anti-angiogenic Strategies in Cartilage Engineering and Osteoarthritic Cartilage Repair," *Cellular and Molecular Life Sciences*, vol. 79, no. 1, Jan. 2022, doi: <https://doi.org/10.1007/s00018-021-04105-0>.
- [7] J. Li *et al.*, "Articular fibrocartilage-targeted therapy by microtubule stabilization," *Science Advances*, vol. 8, no. 46, Nov. 2022, doi: <https://doi.org/10.1126/sciadv.abn8420>.
- [8] K. R. Stone, "Failed Microfracture," *www.stoneclinic.com*, Mar. 17, 2020. <https://www.stoneclinic.com/blog/failed-microfracture> (accessed May 20, 2024).
- [9] J. R. H. Foran and P. W. Manner, "Knee Replacement Implants – OrthoInfo – AAOS," *Aaos.org*, 2016. <https://orthoinfo.aaos.org/en/treatment/knee-replacement-implants/>
- [10] Proteintech Group, "Are Mesenchymal Stem Cells (MSCs) true stem cells?," *Ptglab.com*, 2018. <https://www.ptglab.com/news/blog/are-mesenchymal-stem-cells-mscs-true-stem-cells/>

# References

- [11] Z. Liu, T. Wang, X. Sun, and M. Nie, "Autophagy and apoptosis: Regulatory Factors of Chondrocyte Phenotype Transition in Osteoarthritis," *Human Cell*, vol. 36, no. 4, pp. 1326–1335, Jun. 2023, doi: <https://doi.org/10.1007/s13577-023-00926-2>.
- [12] H. Le, W. Xu, X. Zhuang, F. Chang, Y. Wang, and J. Ding, "Mesenchymal Stem Cells for Cartilage Regeneration," *Journal of Tissue Engineering*, vol. 11, p. 204173142094383, Jan. 2020, doi: <https://doi.org/10.1177/2041731420943839>.
- [13] S. Salceda and J. Caro, "Hypoxia-inducible Factor 1 $\alpha$  (HIF-1 $\alpha$ ) Protein Is Rapidly Degraded by the Ubiquitin-Proteasome System under Normoxic Conditions," *Journal of Biological Chemistry*, vol. 272, no. 36, pp. 22642–22647, Sep. 1997, doi: <https://doi.org/10.1074/jbc.272.36.22642>.
- [14] R. Amarilio, Sergey Viukov, Amnon Sharir, Idit Eshkar-Oren, R. S. Johnson, and Elazar Zelzer, "HIF1 $\alpha$  Regulation of Sox9 Is Necessary to Maintain Differentiation of Hypoxic Prechondrogenic Cells during Early Skeletogenesis," *Development*, vol. 134, no. 21, pp. 3917–3928, Nov. 2007, doi: <https://doi.org/10.1242/dev.008441>.
- [15] G. Teti et al., "The Hypoxia-Mimetic Agent Cobalt Chloride Differently Affects Human Mesenchymal Stem Cells in Their Chondrogenic Potential," *Stem cells international*, vol. 2018, pp. 1–9, Jan. 2018, doi: <https://doi.org/10.1155/2018/3237253>.
- [16] M. Y. Koh and G. Powis, "Passing the baton: the HIF switch," *Trends in Biochemical Sciences*, vol. 37, no. 9, pp. 364–372, Sep. 2012, doi: <https://doi.org/10.1016/j.tibs.2012.06.004>.
- [17] M. B. Goldring and S. R. Goldring, "Articular Cartilage and Subchondral Bone in the Pathogenesis of Osteoarthritis," *Annals of the New York Academy of Sciences*, vol. 1192, no. 1, pp. 230–237, Apr. 2010, doi: <https://doi.org/10.1111/j.1749-6632.2009.05240.x>.
- [18] D. K. Taheem, G. Jell, and E. Gentleman, "Hypoxia Inducible Factor-1 $\alpha$  in Osteochondral Tissue Engineering," *Tissue Engineering Part B: Reviews*, vol. 26, no. 2, Jan. 2020, doi: <https://doi.org/10.1089/ten.teb.2019.0283>.
- [19] D. Antoni, H. Burckel, E. Josset, and G. Noel, "Three-Dimensional Cell Culture: A Breakthrough in Vivo," *International Journal of Molecular Sciences*, vol. 16, no. 12, pp. 5517–5527, Mar. 2015, doi: <https://doi.org/10.3390/ijms16035517>.

# References

- [20] M. M. J. Caron *et al.*, "Redifferentiation of Dedifferentiated Human Articular chondrocytes: Comparison of 2D and 3D Cultures," *Osteoarthritis and Cartilage*, vol. 20, no. 10, pp. 1170–1178, Oct. 2012, doi: <https://doi.org/10.1016/j.joca.2012.06.016>.
- [21] J. C. Fontoura *et al.*, "Comparison of 2D and 3D Cell Culture Models for Cell growth, Gene Expression and Drug Resistance," *Materials Science and Engineering: C*, vol. 107, p. 110264, Feb. 2020, doi: <https://doi.org/10.1016/j.msec.2019.110264>.

# Thanks!

Guidance and assistance from PhD student CAI RunXuan are acknowledged  
Gratitude to Nelson SO for providing the teaching lab for use  
Gratitude to Priscilla YU for giving additional briefings

CREDITS: This presentation template was created by  
[Slidesgo](#), and includes icons by [Flaticon](#), and  
infographics & images by [Freepik](#)