



Stainless_Steel_310
Low Temperature Fit



High Temperature Fit



- BlummEtAl_2007
- CorsanEtAl_1991
- StutiusEtAl_1973
- 2.27, low: 1.52, hi: 2.41%