HiQ-CBR Series, COG Dielectric, Low ESR 6.3 – 500 VDC, 1 MHz – 50 GHz (RF & Microwave)



Overview

KEMET's CBR Series surface mount multilayer ceramic capacitors (MLCCs) in C0G dielectric feature a robust and exceptionally stable copper electrode dielectric system that offers excellent low loss performance (high Q). These devices provide extremely low ESR and high self-resonance characteristics, and are well-suited for resonant circuit applications or those where Q and stability of capacitance characteristics are required. CBR Series capacitors exhibit no change in capacitance with respect to time and voltage, and boast a negligible change in capacitance with




reference to ambient temperature. Capacitance change is limited to ±30 ppm/°C from -55°C to +125°C.

CBR Series devices are suitable for many circuit applications including RF power amplifiers, mixers, oscillators, low noise amplifiers, filter networks, antenna tuning, timing circuits, delay lines, and MRI imaging coils.

Benefits

- · High Q and low ESR
- · High SRF
- · High thermal stability
- 1 MHz to 50 GHz frequency range
- Operating temperature range of -55°C to +125°C
- Base metal electrode (BME) dielectric system
- · Pb-free and RoHS compliant
- 0201, 0402, 0603, and 0805 case sizes (inches)
- DC voltage ratings of 6.3 V, 10 V, 25 V, 50 V, 100 V, 200 V, 250 V, and 500 V
- · Capacitance offerings ranging from 0.1 pF up to 100 pF



Ordering Information

CBR	02	С	330	F	9	G	A	С	
Series	Case Size (L"x W")	Specification/ Series	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Dielectric	Termination Style	Termination Finish	Packaging/ Grade (C-Spec) ¹
CBR	02 = 0201 04 = 0402 06 = 0603 08 = 0805	C = Standard	Two significant digits and number of zeros Use 9 for 1.0 – 9.9 pF Use 8 for 0.1 – 0.99 pF e.g., 2.2 pF = 229 e.g., 0.5 pF = 508	A = ±0.05 pF B = ±0.1 pF C = ±0.25 pF D = ±0.5 pF F = ±1% G = ±2% J = ±5%	9 = 6.3 V 8 = 10 V 3 = 25 V 5 = 50 V 1 = 100 V 2 = 200 V A = 250 V C = 500 V	G = COG	A = N/A	C = 100% Matte Sn	Blank = 7" Reel Unmarked

¹ When ordering CBR Series devices, a "suffix" or "C-Spec" is not required to indicate a 7" reel packaging option. CBR devices are only available and shipped on 7" reels (paper tape). Bulk bag and cassette packaging options are not available. Please contact KEMET if you have a specific, non-standard packaging requirement.



Benefits cont.

- Available capacitance tolerances of ±0.05 pF, ±0.1 pF, ±0.25 pF, ±0.5 pF, ±1%, ±2%, and ±5%
- No piezoelectric noise
- No capacitance change with respect to applied rated DC voltage
- Negligible capacitance change with respect to temperature
- · No capacitance decay with time
- Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability

Applications

Typical applications include critical timing, tuning, bypass, coupling, feedback, filtering, impedance matching and DC blocking.

Field applications include wireless and cellular base stations, wireless LAN, subscriber-based wireless services, wireless broadcast equipment, satellite communications, RF power amplifier (PA) modules, filters, voltage-controlled oscillators (VCOs), PAs, matching networks, RF modules, satellite communications and medical electronics.

Qualification


RF and microwave products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

Environmental Compliance

Pb-free and RoHS compliant.



Dimensions - Millimeters (Inches)



Case Size (in.)	Case Size (mm)	L Length	W Width	T Thickness	B Bandwidth	Mounting Technique
0201	0603	0.60±0.03 (0.024±0.001)	0.30±0.03 (0.012±0.001)	0.30±0.03 (0.012±0.001)	0.15±0.05 (0.006±0.002)	Coldor Doflow Only
0402	1005	1.00±0.05 (0.040±0.002)	0.50±0.05 (0.020±0.002)	0.50±0.05 (0.020±0.002)	0.25+0.05/-0.10 (0.010+0.002/-0.004)	Solder Reflow Only
0603	1608	1.60±0.10 (0.063±0.004)	0.80±0.10 (0.031±0.004)	0.80±0.07 (0.031±0.003)	0.40±0.15 (0.016±0.006)	Solder Wave
0805	2012	2.00±0.20 (0.079±0.008)	1.25±0.20 (0.049±0.008)	0.85±0.10 (0.031±0.004)	0.50±0.20 (0.020±0.008)	or Solder Reflow

Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range:	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC):	0 ±30 ppm/°C (0 ±60 ppm/°C for 0201 case size product \geq 22 pF)
Aging Rate (Maximum % Capacitance Loss/Decade Hour):	0%
¹ Dielectric Withstanding Voltage (DWV):	See Dielectric Withstanding Voltage Table (5±1 seconds and charge/discharge not exceeding 50 mA)
² Quality Factor (Q):	≥ 1,000 for capacitance values ≥ 30 pF ≥ 400 + 20°C for capacitance values < 30 pF (C = Capacitance in pF)
³ Insulation Resistance (IR) Limit at 25°C:	10 GΩ minimum (rated voltage applied for 120±5 seconds)

¹ DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 & Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

 $^{^2}$ Capacitance and quality factor (Q) measured at 1 MHz \pm 100 kHz and 1.0 \pm 0.2 Vrms.

³ To obtain IR limit, divide $M\Omega$ - μ F value by the capacitance and compare to $G\Omega$ limit. Select the lower of the two limits.




Dielectric Withstanding Voltage Table

Rated Voltage (VDC)	≤100 V	200 V	250 V	500 V
DWV	250%	200%	200%	150%

Electrical Characteristics


SRF (MHz) vs. Cap (pF)






Electrical Characteristics cont.


ESR vs. Frequency 0402




Q vs. Frequency 0402




ESR vs. Frequency 0603



Q vs. Frequency 0603



ESR vs. Frequency 0805



Q vs. Frequency 0805






Table 1 - CBR Series, Capacitance Range Waterfall

Case Size -	Inches (mm)	(0201 ((0603))		0402	(1005)		06	03 (16	08)		0805	(2012)	
Length	mm (Inches)		0.60 :	± 0.03 ± 0.001)				± 0.05 ± 0.002)			1.60 ± 0.10 .063 ± 0.0		2.00 ± 0.20 (0.079 ± 0.008)			
Width	mm (Inches)		0.30 ± 0.03 (0.012 ± 0.001)						,	0.80 ± 0.10	0		1.25	± 0.20 ± 0.008)		
Thickness	mm (Inches)	0.30 ± 0.03 (0.012 ± 0.001) 0.15 ± 0.05 (0.006 ± 0.002)			0.50 ± 0.05 (0.020 ± 0.002)			,	0.80 ± 0.0 .031 ± 0.0	7	0.85 ± 0.10 (0.031 ± 0.004)					
Bandwidth	mm (Inches)					0.25 + 0	.05 / -0.10	4)	,	0.40 ± 0.1	5		0.50	± 0.20 ± 0.008)		
Rated Vol	tage (VDC)	(0.006 ± 0.002) (0.010 + 0.002 / -0.004 6.3 10 25 50 25 50 100					200	50	100	250	50	100	250	500		
Voltag	je Code	9	8	3	5	3	5	1	2	5	1	A	5	1	Α	С
Capacitance	Capacitance				,	Ca	pacitar	ice Cod	e (Avai	lable (Capacit	ance)		'	'	·
0.1 pF	Tolerance	108*	108*	108*	108*	108	108	108*	108*	<u> </u>	•		<u> </u>			
0.2 pF	A = ±0.05 pF	208	208	208	208	208	208	208	208							
0.3 pF	B = ±0.1 pF	308	308	308	308	308	308	308	308	308	308	308	308	308	308	308
0.4 pF		408	408	408	408	408	408	408	408	408	408	408	408	408	408	408
0.5 pF 0.6 pF		508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608	508 608
0.7 pF		708	708	708	708	708	708	708	708	708	708	708	708	708	708	708
0.8 pF		808	808	808	808	808	808	808	808	808	808	808	808	808	808	808
0.9 pF		908	908	908	908	908	908	908	908	908	908	908	908	908	908	908
1.0 pF		109	109	109	109	109	109	109	109	109	109	109	109	109	109	109
1.1 pF		119	119	119	119	119	119	119	119	119	119	119	119	119	119	119
1.2 pF		129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139	129 139
1.3 pF 1.4 pF		149	149	149	149	149	149	149	149	149	149	149	149	149	149	149
1.5 pF		159	159	159	159	159	159	159	159	159	159	159	159	159	159	159
1.6 pF		169	169	169	169	169	169	169	169	169	169	169	169	169	169	169
1.7 pF		179	179	179	179	179	179	179	179	179	179	179	179	179	179	179
1.8 pF		189	189	189	189	189	189	189	189	189	189	189	189	189	189	189
1.9 pF		199	199	199	199	199	199	199	199	199	199	199	199	199	199	199
2.0 pF 2.1 pF	-	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209 219	209
2.2 pF	_	229	229	229	229	229	229	229	229	229	229	229	229	229	229	229
2.3 pF		239	239	239	239	239	239	239	239	239	239	239	239	239	239	239
2.4 pF		249	249	249	249	249	249	249	249	249	249	249	249	249	249	249
2.5 pF		259	259	259	259	259	259	259	259	259	259	259	259	259	259	259
2.6 pF	A = ±0.05 pF	269	269	269	269	269	269	269	269	269	269	269	269	269	269	269
2.7 pF	B = ±0.1 pF	279	279	279	279	279	279	279	279	279	279	279	279	279	279	279
2.8 pF 2.9 pF	C = ±0.25 pF	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289 299	289
2.9 pF 3.0 pF		309	309	309	309	309	309	309	309	309	309	309	309	309	309	309
3.0 pF		319	319	319	319	319	319	319	319	319	319	319	319	319	319	319
3.2 pF		329	329	329	329	329	329	329	329	329	329	329	329	329	329	329
3.3 pF		339	339	339	339	339	339	339	339	339	339	339	339	339	339	339
3.4 pF		349	349	349	349	349	349	349	349	349	349	349	349	349	349	349
3.5 pF		359	359	359	359	359	359	359	359	359	359	359	359	359	359	359
3.6 pF 3.7 pF		369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379	369 379
3.7 pF 3.8 pF		389	389	389	389	389	389	389	389	389	389	389	389	389	389	389
3.9 pF		399	399	399	399	399	399	399	399	399	399	399	399	399	399	399
4.0 pF		409	409	409	409	409	409	409	409	409	409	409	409	409	409	409
4.1 pF		419	419	419	419	419	419	419	419	419	419	419	419	419	419	419
4.2 pF		429	429	429	429	429	429	429	429	429	429	429	429	429	429	429
4.3 pF		439 449	439 449	439 449	439	439	439	439	439	439 449	439	439	439	439	439 449	439
4.4 pF 4.5 pF	-	449	449	449	449 459	449 459	449 459	449 459	449 459	449	449 459	449 459	449 459	449 459	449	449 459
4.6 pF		469	469	469	469	469	469	469	469	469	469	469	469	469	469	469
4.7 pF		479	479	479	479	479	479	479	479	479	479	479	479	479	479	479
4.8 pF		489	489	489	489	489	489	489	489	489	489	489	489	489	489	489
4.9 pF		499	499	499	499	499	499	499	499	499	499	499	499	499	499	499
Rated Vol	tage (VDC)	6.3	10	25	50	25	50	100	200	50	100	250	50	100	250	500
														1	1	

^{*}Available only in "B" ($\pm 0.1 pF$) capacitance tolerance.



Table 1 - CBR Series, Capacitance Range Waterfall cont.

Case Size -	Inches (mm)		0201	(0603))		0402	(1005)		06	03 (16	08)		0805	(2012)	
Length	mm (Inches)			± 0.03 ± 0.001)				± 0.05 ± 0.002)			1.60 ± 0.1 063 ± 0.0				± 0.20 ± 0.008)	
Width	mm (Inches)			± 0.03 ± 0.001)				± 0.05 ± 0.002)			0.80 ± 0.1 031 ± 0.0				± 0.20 ± 0.008)	
Thickness	mm (Inches)		0.30 ± 0.03 (0.012 ± 0.001)				0.50	± 0.05 ± 0.002)		0.80 ± 0.07 (0.031 ± 0.003)			0.85 ± 0.10 (0.031 ± 0.004)			
Bandwidth	mm (Inches)		0.15	± 0.05 ± 0.002)			0.25 + 0	.05 / -0.10 002 / -0.00	14)	,	0.40 ± 0.1 016 ± 0.0	5		0.50	± 0.20 ± 0.008)	
Rated Volt	age (VDC)	6.3	10	25	50	25	50	100	200	50	100	250	50	100	250	500
Voltag	e Code	9	8	3	5	3	5	1	2	5	1	Α	5	1	Α	С
Capacitance	Capacitance Tolerance					Ca	pacitar	nce Cod	le (Avai	lable C	apacit	tance)	•	,	,	
						Π				l			<u> </u>			1
5.0 pF	A = ±0.05 pF B = ±0.1 pF C = ±0.25 pF	509	509	509	509	509	509	509	509	509	509	509	509	509	509	509
5.1 pF		519	519	519	519	519	519	519	519	519	519	519	519	519	519	519
5.2 pF 5.3 pF		529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539	529 539
5.4 pF		549	549	549	549	549	549	549	549	549	549	549	549	549	549	549
5.5 pF		559	559	559	559	559	559	559	559	559	559	559	559	559	559	559
5.6 pF		569	569	569	569	569	569	569	569	569	569	569	569	569	569	569
5.7 pF 5.8 pF		579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589	579 589
5.9 pF		599	599	599	599	599	599	599	599	599	599	599	599	599	599	599
6.0 pF		609	609	609	609	609	609	609	609	609	609	609	609	609	609	609
6.1 pF		619	619	619	619	619	619	619 629	619	619 629	619	619	619 629	619	619	619
6.2 pF 6.3 pF		629 639	629 639	629 639	629 639	629 639	629 639	639	629	639	629 639	629	639	629 639	629	629 639
6.4 pF		649	649	649	649	649	649	649	649	649	649	649	649	649	649	649
6.5 pF		659	659	659	659	659	659	659	659	659	659	659	659	659	659	659
6.6 pF		669	669	669	669	669	669	669	669	669	669	669	669	669	669	669
6.7 pF 6.8 pF		679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689	679 689
6.9 pF		699	699	699	699	699	699	699	699	699	699	699	699	699	699	699
7.0 pF		709	709	709	709	709	709	709	709	709	709	709	709	709	709	709
7.1 pF		719	719	719	719	719	719	719	719	719	719	719	719	719	719	719
7.2 pF	B = ±0.1 pF	729 739	729 739	729 739	729 739	729	729 739	729 739	729 739	729 739	729 739	729 739	729 739	729 739	729 739	729 739
7.3 pF 7.4 pF	$C = \pm 0.25 \text{ pF}$ $D = \pm 0.5 \text{ pF}$	749	749	749	749	739 749	739	739	739	739	739	739	749	739	739	749
7.5 pF	2 2000 p.	759	759	759	759	759	759	759	759	759	759	759	759	759	759	759
7.6 pF		769	769	769	769	769	769	769	769	769	769	769	769	769	769	769
7.7 pF		779	779	779	779	779	779	779	779	779	779	779	779	779	779	779
7.8 pF 7.9 pF		789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799	789 799
8.0 pF		809	809	809	809	809	809	809	809	809	809	809	809	809	809	809
8.1 pF		819	819	819	819	819	819	819	819	819	819	819	819	819	819	819
8.2 pF		829	829	829	829	829	829	829	829	829	829	829	829	829	829	829
8.3 pF 8.4 pF		839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849	839 849
8.5 pF		859	859	859	859	859	859	859	859	859	859	859	859	859	859	859
8.6 pF		869	869	869	869	869	869	869	869	869	869	869	869	869	869	869
8.7 pF		879	879	879	879	879	879	879	879	879	879	879	879	879	879	879
8.8 pF 8.9 pF		889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899	889 899
9.0 pF		909	909	909	909	909	909	909	909	909	909	909	909	909	909	909
9.1 pF		919	919	919	919	919	919	919	919	919	919	919	919	919	919	919
9.2 pF		929	929	929	929	929	929	929	929	929	929	929	929	929	929	929
9.3 pF		939	939	939	939	939	939	939 949	939	939	939	939	939	939	939	939
9.4 pF 9.5 pF		949 959	949 959	949 959	949 959	949 959	949 959	949	949 959	949 959	949 959	949 959	949 959	949 959	949 959	949 959
Rated Volt	tage (VDC)	6.3	10	25	50	25	50	100	200	50	100	250	50	100	250	500
	e Code	9	8	3	5	3	5	1	2	5	1	A	5	1	A	C
							_									



Table 1 - CBR Series, Capacitance Range Waterfall cont.

Case Size -	Inches (mm)		0201	(0603))		0402	(1005)		06	03 (16	08)		0805	(2012)	
Length	mm (Inches)		(0.024	± 0.03 ± 0.001)		1.00 ± 0.05 (0.040 ± 0.002)			(0.	1.60 ± 0.1 .063 ± 0.0	04)	2.00 ± 0.20 (0.079 ± 0.008)				
Width	mm (Inches)		0.30 ± 0.03 (0.012 ± 0.001)				(0.020	± 0.05 ± 0.002)		(0.	0.80 ± 0.1 .031 ± 0.0	04)		(0.049	± 0.20 ± 0.008)	
Thickness	mm (Inches)		(0.012	± 0.03 ± 0.001)			(0.020	± 0.05 ± 0.002)		(0.	0.80 ± 0.0 .031 ± 0.0	03)		(0.031	± 0.10 ± 0.004)	
Bandwidth	mm (Inches)		(0.006	± 0.05 ± 0.002)	1		(0.010 + 0.	0.05 / -0.10 002 / -0.00	04)		0.40 ± 0.1 .016 ± 0.0	06)		(0.020	± 0.20 ± 0.008)	
Rated Volt	age (VDC)	6.3	10	25	50	25	50	100	200	50	100	250	50	100	250	500
Voltag	e Code	9	8	3	5	3	5	1	2	5	1	Α	5	1	Α	С
Capacitance	Capacitance Tolerance					Ca	pacitar	ice Cod	le (Avai	lable C	Capacit	tance)		,	,	<u>'</u>
9.6 pF		969	969	969	969	969	969	969	969	969	969	969	969	969	969	969
9.7 pF	B = ±0.1 pF	979	979	979	979	979	979	979	979	979	979	979	979	979	979	979
9.8 pF	C = ±0.25 pF D = ±0.5 pF	989	989	989	989	989	989	989	989	989	989	989	989	989	989	989
9.9 pF	D - 10.5 pr	999	999	999	999	999	999	999	999	999	999	999	999	999	999	999
10 pF		100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
11 pF		110	110	110	110	110	110	110	110	110	110	110	110	110	110	110
12 pF		120	120	120	120	120	120	120	120	120	120	120	120	120	120	120
13 pF		130	130	130	130	130	130	130	130	130	130	130	130	130	130	130
15 pF		150	150	150	150	150	150	150	150	150	150	150	150	150	150	150
16 pF		160	160	160	160	160	160	160	160	160	160	160	160	160	160	160
18 pF		180	180	180	180	180	180	180	180	180	180	180	180	180	180	180
20 pF		200	200	200	200	200	200	200	200	200	200	200	200	200	200	200
22 pF		220	220	220		220	220	220	220	220	220	220	220	220	220	220
24 pF		240	240	240		240	240	240	240	240	240	240	240	240	240	240
27 pF		270	270	270		270	270	270	270	270	270	270	270	270	270	270
30 pF	F = ±1%	300	300	300		300	300	300	300	300	300	300	300	300	300	300
33 pF	G = ±2%	330	330	330		330	330	330	330	330	330	330	330	330	330	330
36 pF	J = ±5%					360	360 390	360 390		360	360	360	360	360 390	360 390	360 390
39 pF						390 430	430	430		390 430	390 430	390 430	390 430	430	430	430
43 pF						430	430	430		430	430	430	430	430	430	430
47 pF 51 pF						510	510	510		510	510	510	510	510	510	510
56 pF						560	560	560		560	560	560	560	560	560	560
62 pF						620	300	300		620	620	620	620	620	620	620
68 pF						680				680	680	680	680	680	680	680
75 pF						750				750	750	750	750	750	750	300
82 pF						820				820	820	820	820	820	820	
91 pF						910				910	910	910	910	910	910	
100 pF						101				101	101	101	101	101	101	
Rated Volt	age (VDC)	6.3	10	25	50	25	50	100	200	50	100	250	50	100	250	500
Voltage	e Code	9	8	3	5	3	5	1	2	5	1	Α	5	1	Α	С



Table 2 - Chip Thickness/Reeling Quantities

Chip Size	Chip Thickness	Reel Q	uantity			
Inches (mm)	(mm)	7" Paper	13" Paper			
0201 (0603)	0.30 ±0.03	15,000				
0402 (1005)	0.50 ±0.05	10,000	Contact KEMET			
0603 (1608)	0.80 ±0.07	4,000	for availability.			
0805 (2012)	0.85 ±0.10	4,000				


Table 3 - Chip Capacitor Land Pattern Design Recommendations per IPC-7351 (mm)

Case Size (Inches)	Case Size (mm)	Density Level A: Maximum (Most) Land Protrusion					Density Level B: Median (Nominal) Land Protrusion				N	/linimu	sity Level C: m (Least) Land rotrusion				
(mones)	(11111)	С	Y	X	V1	V2	С	Y	X	V1	V2	С	Y	X	V1	V2	
0201	0603	0.38	0.56	0.52	1.80	1.00	0.33	0.46	0.42	1.50	0.80	0.28	0.36	0.32	1.20	0.60	
0402	1005	0.50	0.72	0.72	2.20	1.20	0.45	0.62	0.62	1.90	1.00	0.40	0.52	0.52	1.60	0.80	
0603	1608	0.90	1.15	1.10	4.00	2.10	0.80	0.95	1.00	3.10	1.50	0.60	0.75	0.90	2.40	1.20	
0805	2012	1.00	1.35	1.55	4.40	2.60	0.90	1.15	1.45	3.50	2.00	0.75	0.95	1.35	2.80	1.70	

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of 0603(1608) and 0805 (2012) case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. **Density Level C:** For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC-7351).

Image below based on Density Level B for an EIA 1608 case size.





Soldering Process

Recommended Soldering Technique:

- Solder wave or solder reflow for 0603 and 0805 case sizes
- 0201 and 0402 case sizes are limited to solder reflow only

Recommended Soldering Profile:

• KEMET recommends following the guidelines outlined in IPC/JEDEC J-STD-020

Recommended Solder Alloys:

Alloy	Composition	Solidus	Liquidous
In50	50 ln, 50 Pb	180°C	209°C
In52	52 ln, 48 Sn	118°C	118°C
Sn62	62.5 Sn, 36.1 Pb, 1.4 Ag	179°C	179°C
Sn63	63 Sn, 37 Pb	183°C	183°C
Pb-Free	95.5 Sn, 3.8 Ag, 0.7 Cu	217°C	217°C
Hi-Temp	5 Sn, 93.5 Pb, 1.5 Ag	296°C	301°C
Sn5	5 Sn, 95 Pb	308°C	312°C



Table 4 – Performance & Reliability: Test Methods & Conditions

Stress		Test or Inspection Me	thod	Requirements
Terminal Strength	02 04 08	izing force: 201 case size: 2N 202 & 0603 case sizes: 5N 205 case size: 10N e: 10±1 second		No visible damage or separation of termination system.
Vibration Resistance	Total an Test tim	n frequency: 10 ~ 55 Hz/minin nplitude: 1.5 mm e: 6 hours (Two hours each in licular directions.)		No visible damage. Cap change and Q/DF: To meet initial specification
Solderability		emperature: 235±5°C time: 2±0.5 seconds		95% minimum coverage of termination finish.
Board Flex	means of deflection for 5±1 s Store at	or is mounted to a substrate wo of ram at a rate of 1 mm per se on becomes 1 mm. (Deflection second) room temperature for 24±2 ho ing electrical properties.	cond until the is maintained	No visible damage. Capacitance change: within ±5.0% or ±0.5 pF, whichever is larger. (Capacitance change is monitored during flexure.)
Resistance to Soldering Heat	Dipping Preheat the capa Store at	emperature: 260±5°C time: 10±1 second ing: 120 to 150°C for 1 minute acitor in a eutectic solder. room temperature for 24±2 ho ng electrical properties.		No visible damage. Capacitance change: within ±2.5% or ±0.25 pF, whichever is larger. Q/DF, IR and dielectric strength: To meet initial requirements. 25% maximum leaching on each edge.
	5 cycles	of steps 1 - 4:		
	Step	Temperature (°C)	Time (min.)	
	1	Minimum operating temperature +0/-3	30 ±3	No visible damage.
Temperature	2	Room temperature	2 ~ 3	Capacitance change: within ±2.5% or ±0.25 pF, whichever is larger.
Cycling	3	Maximum operating temperature +3/-0	30 ±3	Q/DF, IR and dielectric strength: To meet initial requirements.
	4	Room temperature (25°C)	2 ~ 3	
		room temperature for 24±2 hong electrical properties.		



Table 4 - Performance & Reliability: Test Methods & Conditions cont.


Stress	Test or Inspection Method	Requirements
Humidity (Damp Heat) Steady State	Test temperature: 40±2°C Humidity: 90 ~ 95% RH Test time: 500 +24/-0 hours Store at room temperature for 24±2 hours before measuring electrical properties.	No visible damage. Capacitance change: within $\pm 5.0\%$ or ± 0.5 pF, whichever is larger. Q/DF value: Capacitance ≥ 30 pF, Q ≥ 350 , $10 \text{ pF} \leq \text{Capacitance} < 30 \text{ pF}, \text{ Q} \geq 275 + 2.5 ^{\circ}\text{C}$ Capacitance $< 10 \text{ pF}; \text{ Q} \geq 200 + 10 ^{\circ}\text{C}$ IR: $\geq 1\text{G}\Omega$
Humidity (Damp Heat) Load	Test temperature: 40±2°C Humidity: 90 ~ 95% RH Test time: 500 +24/-0 hours Applied voltage: rated voltage Store at room temperature for 24±2 hours before measuring electrical properties.	No visible damage. Capacitance change: within $\pm 7.5\%$ or ± 0.75 pF, whichever is larger. Q/DF value: Capacitance ≥ 30 pF, Q ≥ 200 , Capacitance < 30 pF, Q $\geq 100+10/3$ °C IR: $\geq 500M\Omega$
High Temperature Life	Test temperature: 125±3°C Applied voltage: 200% of rated voltage (10 VDC – 250 VDC) 150% of rated voltage (6.3 VDC and 500 VDC) Test time: 1,000 +24/-0 hours Store at room temperature for 24±2 hours before measuring electrical properties.	No visible damage. Capacitance change: within $\pm 3.0\%$ or ± 0.3 pF, whichever is larger. Q/DF value: Capacitance ≥ 30 pF, Q ≥ 350 , $10 \text{ pF} \leq \text{Capacitance} < 30 \text{ pF}, \text{Q} \geq 275 + 2.5 ^{\circ}\text{C}$ Capacitance $< 10 \text{ pF}, \text{Q} \geq 200 + 10 ^{\circ}\text{C}$ IR: $\geq 1 \text{ G}\Omega$
ESR	The ESR should be measured at room temperature and tested at frequency 1±0.1 GHz.	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$
	The ESR should be measured at room temperature and tested at frequency 500±50 MHz.	0201 case size, 22pF ≤ Cap ≤ 33pF: < 300 mΩ



Storage and Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature—reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.

Construction



Marking

CBR series devices are supplied unmarked.

If you require marked product, please contact KEMET for availability of a laser-marked option.



Tape & Reel Packaging Information

KEMET offers RF and Microwave Multilayer Ceramic Chip Capacitors packaged in 8 mm tape on 7" reels. This packaging system is compatible with all tape-fed automatic pick and place systems.




Table 5 – Carrier Tape Configuration (mm)

EIA Case Size	Tape Size (W)*	Lead Space (P ₁)*
0201 - 0402	8	2
0603 - 1210	8	4

^{*}Refer to Figure 1 for W and P_1 carrier tape reference locations.

^{*}Refer to Table 6 for tolerance specifications.



Figure 1 - Punched (Paper) Carrier Tape Dimensions




Table 6 - Punched (Paper) Carrier Tape Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)								
Tape Size	D_0	E ₁	P ₀	P ₂	R Reference Note 2	K_0		
8 mm	1.55+0.05 (0.061+0.002)	1.55±0.05 (0.061±0.002)	4.0±0.10 (0.157±0.004)	2.0±0.05 (0.079±0.002)	25.0 (0.984)	-		
Variable Dimensions — Millimeters (Inches)								
Tape Size	Pitch	A_0	B ₀	F	P ₁	T	W	D_1
8 mm Half (2 mm)	Holf (2 mm)	0.37±0.03 (0.015±0.001)	0.67±0.03 (0.03±0.001)	3.5±0.05	2.0±0.05 (0.079±0.002)	0.42±0.03 (0.017±0.001)	8.0±0.10 (0.315±0.004)	-
	Hall (2 IIIII)	0.62±0.05 (0.025±0.002)	1.12±0.05 (0.04±0.002)			0.60±0.05 (0.024±0.002)		
8 mm Sing	Single (4 mm)	1.00±0.10 (0.040±0.004)	1.80±0.10 (0.07±0.004)	(0.138±0.002)	4.0±0.10 (0.157±0.004)	0.95±0.05 (0.037±0.002)		
	Siligle (4 IIIII)	1.50±0.10 (0.06±0.004)	2.30±0.10 (0.09±0.004)			0.95±0.05 (0.037±0.002)		

^{2.} The tape with or without components shall pass around R without damage (see Figure 3).



Packaging Information Performance Notes

- 1. Cover Tape Break Force: 1.0 Kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength	
8 mm	0.1 to 1.0 newton (10 to 100 gf)	
12 and 16 mm	0.1 to 1.3 newton (10 to 130 gf)	

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards 556 and 624*.

Figure 2 – Bending Radius




Figure 3 - Tape Leader & Trailer Dimensions






Figure 4 - Maximum Camber




Figure 5 - Reel Dimensions




Table 7 - Reel Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)							
Tape Size	Reel Size	A	С				
8 mm	7	178±0.10 (7.008±0.004)	13.0±0.20 (0.512±0.008)				
Variable Dimensions — Millimeters (Inches)							
Tape Size	N Minimum See Note 2, Table 6	W ₁					
8 mm	60±0.10 (2.4±0.04)	8.4+1.5/-0.0 (0.331+0.059/-0.0)					



KEMET Electronics Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed. All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

KEMET:

```
CBR02C109B3GACTU CBR02C209B3GACTU CBR02C279B3GACTU CBR02C309B3GACTU
CBR02C409B3GACTU CBR02C509C3GACTU CBR02C609C3GACTU CBR02C709C3GACTU
CBR02C809C3GACTU CBR02C909C3GACTU CBR04C209B5GACTU CBR04C309B5GACTU
CBR04C409B5GACTU CBR04C509B5GACTU CBR04C609C5GACTU CBR04C709C5GACTU
CBR04C809C5GACTU CBR04C909C5GACTU CBR06C109BAGACTU CBR06C129BAGACTU
CBR06C159BAGACTU CBR06C189BAGACTU CBR06C209BAGACTU CBR06C229BAGACTU
CBR06C279BAGACTU CBR06C309BAGACTU CBR06C339BAGACTU CBR06C399BAGACTU
CBR06C409BAGACTU CBR06C479BAGACTU CBR06C508BAGACTU CBR06C509CAGACTU
CBR06C569CAGACTU CBR06C608BAGACTU CBR06C609CAGACTU CBR06C689CAGACTU
CBR06C708BAGACTU CBR06C709CAGACTU CBR06C808BAGACTU CBR06C809CAGACTU
CBR06C829CAGACTU CBR06C908BAGACTU CBR06C909CAGACTU CBR08C509BAGACTU
CBR08C569BAGACTU CBR08C709BAGACTU CBR08C909BAGACTU CBR06C100JAGACTU
CBR06C470JAGACTU CBR08C100JAGACTU CBR08C229BAGACTU CBR08C390JAGACTU
CBR04C189B5GACTU CBR02C108B3GACTU CBR02C110J3GACTU CBR02C120J3GACTU CBR02C130J3GACTU
 CBR02C150J3GACTU CBR02C160J3GACTU CBR02C180J3GACTU CBR02C189B3GACTU
CBR02C208B3GACTU CBR02C220J8GACTU CBR02C270J8GACTU CBR02C308B3GACTU CBR02C330J8GACTU
 CBR02C339B3GACTU CBR02C399B3GACTU CBR02C408B3GACTU CBR02C479B3GACTU
CBR02C508B3GACTU CBR02C569C3GACTU CBR02C608B3GACTU CBR02C689C3GACTU
CBR02C708B3GACTU CBR02C808B3GACTU CBR02C829C3GACTU CBR02C908B3GACTU
CBR04C108B1GACTU CBR04C110J5GACTU CBR04C120J5GACTU CBR04C130J5GACTU CBR04C150J5GACTU
 CBR04C160J5GACTU CBR04C180J5GACTU CBR04C200J5GACTU CBR04C208B1GACTU
CBR04C220J5GACTU CBR04C308B1GACTU CBR04C408B1GACTU CBR04C569C1GACTU
CBR06C120JAGACTU CBR06C150JAGACTU CBR06C180JAGACTU CBR06C220JAGACTU
CBR06C270JAGACTU CBR06C308BAGACTU CBR06C330JAGACTU CBR06C390JAGACTU
CBR06C408BAGACTU
```