12500 TI Boulevard, MS 8640, Dallas, Texas 75243

PCN# 20260331003.2
Qualification of TI Philippines (PHI) as an additional Assembly & Test site for select package devices
Change Notification / Sample Request

Date: March 31, 2026
To: ADVANTECH TECHNOLOGY(CHINA)CO., LTD PCN

Dear Customer:

This is an announcement of a change to a device that is currently offered by Texas Instruments. The details of this change are on the following pages.

Texas Instruments requires acknowledgement of receipt of this notification within 60 days of the date of this notice. Lack of acknowledgement of this notice within 60 days constitutes acceptance and approval of this change. If samples or additional data are required, requests must be received within 60 days of this notification.

The changes discussed within this PCN will not take effect any earlier than the proposed first ship date on Page 3 of this notification, unless customer agreement has been reached on an earlier implementation of the change.

This notice does not change the end-of-life status of any product. Should product affected be on a previously issued product withdrawal/discontinuance notice, this notification does not extend the life of that product or change the life time buy offering/discontinuance plan.

For questions regarding this notice or to provide acknowledgement of this PCN, you may contact your local Field Sales Representative or the change management team.

For sample requests or sample related questions, contact your local Field Sales Representative.

TI values customer engagement and feedback related to TI changes. Customers should contact TI if there are questions or concerns regarding a change notification.

Sincerely,

Change Management Team
SC Business Services

20260331003.2
Change Notification / Sample Request
Attachments

Products Affected:

The devices listed on this page are a subset of the complete list of affected devices. According to our records, you have recently purchased these devices. The corresponding customer part number is also listed, if available.

DEVICE	CUSTOMER PART NUMBER
LM74700QDBVRQ1	NULL

Technical details of this Product Change follow on the next page(s).

PCN Number:	20260331003.2	**PCN Date:**	March 31, 2026
Title:	Qualification of TI Philippines (PHI) as an additional Assembly & Test site for select package devices		
Customer Contact:	Change Management team	**Dept:**	Quality Services
Proposed 1st Ship Date:	September 27, 2026	**Estimated Sample Availability:**	May 30, 2026

***Sample requests received after** May 30, 2026 **will not be supported.**

Change Type:

☒	Assembly Site	☐	Design	☐	Wafer Bump Material
☒	Assembly Process	☐	Data Sheet	☐	Wafer Bump Process
☒	Assembly Materials	☐	Part number change	☐	Wafer Fab Site
☐	Mechanical Specification	☒	Test Site	☐	Wafer Fab Material
☒	Packing/Shipping/Labeling	☐	Test Process	☐	Wafer Fab Process

PCN Details

Description of Change:

Texas Instruments is pleased to announce the Qualification of TI Philippines (PHI) as an additional Assembly & Test site for select package devices. Material differences between sites as follows.

	Current Site		**Additional Site**
Assembly/Test site	**UTAC**	**CDAT**	**PHI**
Wire diam/type	1.0mil Au	0.96mil Cu	0.96mil Cu
Mount compound	SID#PZ0068	4229877	4226215
Mold compound	SID#CZ0096	4222198	4222198
Lead finish	NiPdAu	Matte Sn	NiPdAu
Marking difference	Pin 1 stripe Backside marking Binary marking	Pin 1 dot Binary marking	Pin 1 dot Secondary/Binary marking

Qual details are provided in the Qual Data Section.
Test coverage, insertions, conditions will remain consistent with current testing.

Reason for Change:

Continuity of supply.

Anticipated impact on Form, Fit, Function, Quality or Reliability (positive / negative):

Review the SDP for full evaluation of the change based on the customer use case.

Impact on Environmental Ratings:

Checked boxes indicate the status of environmental ratings following implementation of this change. If below boxes are checked, there are no changes to the associated environmental ratings.

RoHS	REACH	Green Status	IEC 62474
☒ No Change	☒ No Change	☒ No Change	☒ No Change

Changes to product identification resulting from this PCN:

Assembly Site	Assembly Site Origin (22L)	Assembly Country Code (21L)	Assembly City
UTAC	NS2	THA	Bangpakomg
TI Chengdu	CDA	CHN	Chengdu

TI Philippines	PHI	PHL	Baguio City

Sample product shipping label (not actual product label)

Product Affected:

LM74700PQDBVRQ1	LM74700QDBVTQ1
LM74700QDBVRQ1	LM74700VQDBVRQ1

Qualification Data

Automotive New Product Qualification Summary
(As per AEC-Q100 Rev. J and JEDEC Guidelines)
Approve Date 05-March-2026

Product Attributes

Attributes	Qual Device: LM74700QDBVRQ1	QBS Process Reference: LM74700QDBVRQ1	QBS Package Reference: TMUX4051DYYRQ1	QBS Package Reference: TMUX4052DYYRQ1	QBS Package Reference: SN6505AQDBVRQ1	QBS Package Reference: LM74700QDDFRQ1
Automotive Grade Level	Grade 1	Grade 1	Grade 1	Grade 1	Grade 1	Grade 1
Operating Temp Range (C)	-40 to 125	-40 to 125	-40 to 125	-40 to 125	-40 to 125	-40 to 125
Product Function	Power Management	Power Management	Signal Chain	Signal Chain	Interface	Power Management
Wafer Fab Supplier	RFAB	RFAB	RFAB	RFAB	RFAB	RFAB
Assembly Site	PHI	UTL2	PHI	PHI	PHI	PHI
Package Group	SOT	SOT	SOT	SOT	SOT	SOT
Package Designator	DBV	DBV	DYY	DYY	DBV	DDF
Pin Count	6	6	16	16	6	8

QBS: Qual By Similarity, also known as Generic Data
Qual Device LM74700QDBVRQ1 is qualified at MSL2 260C
Note 1: Affected devices in PCN have justification to use Package QBS references for Group A and Group C tests based on AEC-100J Appendix 1 A1.3 assembly site and package attributes were qualified.
Note 2: Affected devices in PCN have justification to use Process QBS references for Group B tests based on AEC-Q100 Rev-J Appendix 1 A1.2, silicon wafer fab and die attributes were qualified.
Note 3: ED/HBM/CDM/LU QBS's LM74700QDDFQ1 which uses same die in a thinner SOT package.

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: LM74700QDBVRQ1	QBS Process Reference: LM74700QDBVRQ1	QBS Package Reference: TMUX4051DYYRQ1	QBS Package Reference: TMUX4052DYYRQ1	QBS Package Reference: SN6505AQDBVRQ1	QBS Package Reference: LM74700QDDFRQ1
Test Group A - Accelerated Environment Stress Tests													
PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL1 260C	-	-	-	1/77/0	2/154/0	1/77/0	-

PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL2 260C	-	Note 1	-	-	-	-	3/231/0
HAST	A2	JEDEC JESD22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	Note 1	-	1/77/0	2/154/0	1/77/0	3/231/0
AC/UHAST	A3	JEDEC JESD22-A102/JEDEC JESD22-A118	3	77	Autoclave	121C/15psig	96 Hours	Note 1	-	-	-	1/77/0	-
AC/UHAST	A3	JEDEC JESD22-A102/JEDEC JESD22-A118	3	77	Unbiased HAST	130C/85%RH	96 Hours	Note 1	-	1/77/0	2/154/0	-	3/231/0
TC	A4	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	Note 1	-	1/77/0	2/154/0	1/77/0	3/231/0
TC-BP	A4	MIL-STD883 Method 2011	1	5	Post Temp Cycle Bond Pull	-	-	Note 1	-	1/5/0	2/10/0	1/5/0	3/15/0
HTSL	A6	JEDEC JESD22-A103	1	45	High Temperature Storage Life	150C	1000 Hours	Note 1	-	1/45/0	2/90/0	1/45/0	3/135/0
Test Group B - Accelerated Lifetime Simulation Tests													
HTOL	B1	JEDEC JESD22-A108	3	77	Life Test	150C	408 Hours	Note 2	3/231/0	-	-	-	-
ELFR	B2	AEC Q100-008	3	800	Early Life Failure Rate	150C	24 Hours	Note 2	3/2400/0	-	-	-	-
Test Group C - Package Assembly Integrity Tests													
WBS	C1	AEC Q100-001	1	30	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	-	-	-	-	-
WBP	C2	MIL-STD883 Method 2011	1	30	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	-	-	-	-	-
SD	C3	JEDEC J-STD-002	1	15	PB Solderability	>95% Lead Coverage	-	Note 1	-	-	-	-	1/15/0
SD	C3	JEDEC J-STD-002	1	15	PB-Free Solderability	>95% Lead Coverage	-	Note 1	-	-	-	-	1/15/0
PD	C4	JEDEC JESD22-B100 and B108	1	10	Physical Dimensions	Cpk>1.67	-	1/10/0	-	-	-	1/10/0	-
Test Group D - Die Fabrication Reliability Tests													
EM	D1	JESD61	-	-	Electromigration	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
TDDB	D2	JESD35	-	-	Time Dependent Dielectric Breakdown	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
HCI	D3	JESD60 & 28	-	-	Hot Carrier Injection	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
BTI	D4	-	-	-	Bias Temperature Instability	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
SM	D5	-	-	-	Stress Migration	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
Test Group E - Electrical Verification Tests													
ESD	E2	AEC Q100-002	1	3	ESD HBM	-	2000 Volts	Note 3	-	-	-	-	3/9/0
ESD	E3	AEC Q100-011	1	3	ESD CDM	-	500 Volts	Note 3	-	-	-	-	1/3/0
LU	E4	AEC Q100-004	1	3	Latch-Up	Per AEC Q100-004	-	Note 3	-	-	-	-	1/3/0
ED	E5	AEC Q100-009	3	30	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	Note 3	-	-	-	-	1/30/0

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Ambient Operating Temperature by Automotive Grade Level:

Grade 0 (or E): -40C to +150C

Grade 1 (or Q): -40C to +125C

Grade 2 (or T): -40C to +105C

Grade 3 (or I) : -40C to +85C

E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):

Room/Hot/Cold : HTOL, ED
Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU
Room : AC/uHAST
Quality and Environmental data is available at TI's external Web site: http://www.ti.com/
TI Qualification ID: R-CHG-2510-037

Qualification Data

Automotive Qualification Summary
(As per AEC and JEDEC Guidelines)

Q006 SOT at PHI
Approve Date 05-March-2026

Product Attributes

Attributes	QBS Package Reference: TMUX4051DYYRQ1	QBS Package Reference: TMUX4052DYYRQ1	QBS Package Reference: LM74700QDDFRQ1
Automotive Grade Level	Grade 1	Grade 1	Grade 1
Operating Temp Range (C)	-40 to 125	-40 to 125	-40 to 125
Product Function	Signal Chain	Signal Chain	Power Management
Wafer Fab Supplier	RFAB	RFAB	RFAB
Assembly Site	PHI	PHI	PHI
Package Group	SOT	SOT	SOT
Package Designator	DYY	DYY	DDF
Pin Count	16	16	8

Qualification Results
Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	QBS Reference: TMUX4051DYYRQ1	QBS Reference: TMUX4052DYYRQ1	QBS Reference: LM74700QDDFRQ1
Test Group A - Accelerated Environment Stress Tests										
PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL1 260C	-	1/77/0	2/154/0	-
PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL2 260C	-	-	-	3/231/0
PC	A1.1	-	3	22	SAM Precon Pre	Review for delamination	-	1/22/0	2/44/0	3/66/0
PC	A1.2	-	3	22	SAM Precon Post	Review for delamination	-	1/22/0	2/44/0	3/66/0
HAST	A2.1	JEDEC JESD22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	1/77/0	2/154/0	3/231/0
HAST	A2.1.2	-	3	1	Cross Section, post bHAST, 1X	Post stress cross section	Completed	1/1/0	2/2/0	3/3/0
HAST	A2.1.3	-	3	3	Wire Bond Shear, post bHAST, 1X	Post stress	-	1/3/0	2/6/0	3/9/0
HAST	A2.1.4	-	3	3	Bond Pull over Stitch, post bHAST, 1X	Post stress	-	1/3/0	2/6/0	3/9/0
HAST	A2.1.5	-	3	3	Bond Pull over Ball, post bHAST, 1X	Post stress	-	1/3/0	2/6/0	3/9/0

HAST	A2.2	JEDEC JESD22-A110	3	70	Biased HAST	130C/85%RH	192 Hours	1/70/0	2/140/0	3/210/0
HAST	A2.2.1	-	3	22	SAM Analysis, post bHAST 2X	Review for delamination	Completed	1/22/0	2/44/0	3/66/0
HAST	A2.2.2	-	3	1	Cross Section, post bHAST, 2X	Post stress cross section	Completed	1/1/0	2/2/0	3/3/0
HAST	A2.2.3	-	3	3	Wire Bond Shear, post bHAST, 2X	Post stress	-	1/3/0	2/6/0	3/9/0
HAST	A2.2.4	-	3	3	Bond Pull over Stitch, post bHAST, 2X	Post stress	-	1/3/0	2/6/0	3/9/0
HAST	A2.2.5	-	3	3	Bond Pull over Ball, post bHAST, 2X	Post stress	-	1/3/0	2/6/0	3/9/0
TC	A4.1	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	1/77/0	2/154/0	3/231/0
TC	A4.1.1	-	3	22	SAM Analysis, post TC 1X	Review for delamination	Completed	1/22/0	2/44/0	3/66/0
TC	A4.1.2	-	3	1	Cross Section, post TC, 1X	Post stress cross section	Completed	1/1/0	2/2/0	3/3/0
TC	A4.1.3	-	3	3	Wire Bond Shear, post TC, 1X	Post stress	-	1/3/0	2/6/0	3/9/0
TC	A4.1.4	-	3	3	Bond Pull over Stitch, post TC, 1X	Post stress	-	1/3/0	2/6/0	3/9/0
TC	A4.1.5	-	3	3	Bond Pull over Ball, post TC, 1X	Post stress	-	1/3/0	2/6/0	3/9/0
TC	A4.2	JEDEC JESD22-A104 and Appendix 3	3	70	Temperature Cycle	-65C/150C	1000 Cycles	1/70/0	2/140/0	3/231/0
TC	A4.2.1	-	3	22	SAM Analysis, post TC, 2X	Review for delamination	Completed	1/22/0	2/44/0	3/66/0
TC	A4.2.2	-	3	1	Cross Section, post TC, 2X	Post stress cross section	Completed	1/1/0	2/2/0	3/3/0
TC	A4.2.3	-	3	3	Wire Bond Shear, post TC, 2X	Post stress	-	1/3/0	2/6/0	3/9/0
TC	A4.2.4	-	3	3	Bond Pull over Stitch, post TC, 2X	Post stress	-	1/3/0	2/6/0	3/9/0
TC	A4.2.5	-	3	3	Bond Pull over Ball, post TC, 2X	Post stress	-	1/3/0	2/6/0	3/9/0
HTSL	A6.1	JEDEC JESD22-A103	3	45	High Temperature Storage Life	150C	1000 Hours	1/45/0	2/90/0	3/135/0
HTSL	A6.1.1	-	3	1	Cross Section, post HTSL, 1X	Post stress cross section	Completed	1/1/0	2/2/0	3/3/0
HTSL	A6.2	JEDEC JESD22-A103	3	44	High Temperature Storage Life	150C	2000 Hours	1/44/0	2/88/0	3/132/0
HTSL	A6.2.1	-	3	1	Cross Section, post HTSL, 2X	Post stress cross section	Completed	1/1/0	2/2/0	3/3/0
Test Group C - Package Assembly Integrity Tests										
WBS	C1	AEC Q100-001	1	30	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	2/60/0	3/90/0
WBP	C2	MIL-STD883 Method 2011	1	30	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	2/60/0	3/90/0

QBS: Qual By Similarity, also known as Generic Data
Qual Device LM74700QDBVRQ1 is qualified at MSL2 260C
Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable
The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours
The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles
Ambient Operating Temperature by Automotive Grade Level:
Grade 0 (or E): -40C to +150C
Grade 1 (or Q): -40C to +125C
Grade 2 (or T): -40C to +105C
Grade 3 (or I) : -40C to +85C
E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):
Room/Hot/Cold : HTOL, ED
Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU
Room : AC/uHAST
Quality and Environmental data is available at TI's external Web site: http://www.ti.com/
TI Qualification ID: R-CHG-2510-037

In performing change qualifications, Texas Instruments follows integrated circuit industry standards in performing defect mechanism analysis and failure mechanism-based accelerated environmental testing to ensure wafer fab process, assembly process and product quality and reliability. As encouraged by these standards, TI uses both product-specific and generic (family) data in qualifying its changes. For devices to be categorized as a 'product qualification family' for generic data purposes, they must share similar product, wafer fab process and assembly process elements. The applicability of generic data (also known at TI as Qualification by Similarity (QBS)) is determined by the Reliability Engineering function following these industry standards. Generic data is shown in the qualification report in columns titled "QBS Process" (for wafer fab process), "QBS Package" (for assembly process) and "QBS Product" (for product family).

ZVEI ID: SEM-PA-18, SEM-PA-05, SEM-PA-08, SEM-PA-07, SEM-PA-11, SEM-PA-13, SEM-TF-01

For questions regarding this notice, e-mails can be sent to the Change Management team or your local Field Sales Representative.

IMPORTANT NOTICE AND DISCLAIMER

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES "AS IS" AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for, and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI's products are provided subject to TI's Terms of Sale (www.ti.com/legal/termsofsale.html) or other applicable terms available either on ti.com or provided in conjunction with such TI products. TI's provision of these resources does not expand or otherwise alter TI's applicable warranties or warranty disclaimers for TI products.