Eastern Environmental Inc.

203 Prospect St
Brockton, MA 02301
(617) 623-6678

May 9, 2023

LLC Clifton Avenue Development
Attn. Doug Schluter
63 Beach St
Marblehead, MA 01945

RE: Asbestos Inspection, 7 Ware Lane, Marblehead, MA

On April 28, 2023, Richard Alomar, Massachusetts licensed asbestos inspector AI900594, inspected the house at the above address for the presence of asbestos prior to demolition.

The following materials were suspected to contain asbestos and sampled:

Material	**Location**
Wall and ceiling materials	Throughout
Sheet floor and mastic	Bathrooms

The following materials were not suspected to contain asbestos:

Material	**Location**
Wood siding	**Exterior**
Wood floors	Throughout
Cement floor	Basement
Ceramic floor	Kitchen
Replacement asphalt roof	Exterior
Replacement windows	Exterior

The samples were delivered to Asbestos Identification Lab for analysis. The samples were analyzed by the EPA endorsed method of Polarized Light Microscopy with Dispersion Staining (PLM/DS) method. The PLM/DS is a qualitative and quantitative form of analysis that yields the type of asbestos in a sample, if any.

The following materials tested positive for the presence of asbestos:

Material	**Location**	**Approx Quantity**
None		

If any unknown materials are encountered during demolition, they must be tested by a Massachusetts licensed asbestos inspector. All asbestos containing materials must be removed by a licensed Massachusetts abatement contractor prior to demolition. See enclosed results.

If you should require more information on this matter, please do not hesitate to contact me at (617) 623-6678.

Sincerely,

Daniel Gomes Jr.

Daniel Gomes Jr
President

Asbestos Identification Laboratory.

165 New Boston St., Ste 227
Woburn, MA 01801
781-932-9600

Web: www.asbestosidentificationlab.com Email: mikemanning@asbestosidentificationlab.com

Testing
Lab Code: 200919-0

Batch: 96864

Daniel Gomes
Eastern Environmental Inc
203 Prospect St.
Brockton, MA 02301

Project Information

7 Ware Ln,
Marblehead

Method: BULK PLM ANALYSIS, EPA/600/R-93/116

Dear Daniel Gomes,

Asbestos Identification Laboratory has completed the analysis of the samples from your office for the above referenced project. The Analysis Method is BULK PLM ANALYSIS, EPA/600/R-93/116The information and analysis contained in this report have been generated using the EPA /600/R-93/116 Method for the Determination of Asbestos in Bulk Building Materials. Materials or products that contain more than 1% of any kind or combination of asbestos are considered an asbestos containing building material as determined by the EPA. This Polarized Light Microscope (PLM) technique may be performed either by visual estimation or point counting. Point counting provides a determination of the area percentage of asbestos in a sample. If the asbestos is estimated to be less than 10% by visual estimation of friable material, the determination may be repeated using the point counting technique. The results of the point counting supersede visual PLM results. Results in this report only relate to the items tested. This report may not be used by the customer to claim product endorsement by NVLAP or any other U.S. Government Agency.
Laboratory results represent the analysis of samples as submitted by the customer. Information regarding sample location, description, area, volume, etc., was provided by the customer. Asbestos Identification Laboratory is not responsible for sample collection activities or analytical method limitations. Unless notified in writing to return samples, Asbestos Identification Laboratory discards customer samples after 30 days. Samples containing subsamples or layers will be analyzed separately when applicable. Reports are kept at Asbestos Identification Laboratory for three years. This report shall not be reproduced, except in full, without the written consent of Asbestos Identification Laboratory.

- NVLAP Lab Code: 200919-0
- Massachusetts Certification License: AA000208
- State of Connecticut, Department of Public Health Approved Environmental Laboratory Registration Number: PH-0142
- State of Maine, Department of Environmental Protection Asbestos Analytical Laboratory License Number: LB-0078(Bulk) LA-0087(Air)
- State of Rhode Island and Providence Plantations. Department of Health Certification: AAL-121
- State of Vermont, Department of Health Environmental Health License AL934461

Thank you Daniel Gomes for your business.

Michael Manning

Michael Manning
Owner/Director

Daniel Gomes
Eastern Environmental Inc
203 Prospect St.
Brockton, MA 02301

Project Information

7 Ware Ln,
Marblehead

Method: BULK PLM ANALYSIS,
EPA/600/R-93/116

FieldID LabID	Material	Location	Color	Non-Asbestos %	Asbestos %
A 1062452	WSR	Kitchen	gray	Cellulose 2 Non-Fibrous 98	None Detected
B 1062453	WSR	2nd Fl Bath	gray	Cellulose 2 Non-Fibrous 98	None Detected
C 1062454	WSR	Master Bath	gray	Cellulose 2 Non-Fibrous 98	None Detected
D 1062455	CSR	Kitchen	gray	Cellulose 2 Non-Fibrous 98	None Detected
E 1062456	CSR	2nd Fl Bath	gray	Cellulose 2 Non-Fibrous 98	None Detected
F 1062457	CSR	Master Bath	gray	Cellulose 2 Non-Fibrous 98	None Detected
G 1062458	Sheet Fl	2nd Fl Bath	multi	Cellulose 10 Non-Fibrous 90	None Detected
H 1062459	Mastic	2nd Fl Bath			Not Analyzed
I 1062460	Sheet Fl	Master Bath	multi	Cellulose 10 Non-Fibrous 90	None Detected
J 1062461	Mastic	Master Bath			Not Analyzed

Sampled: April 28, 2023 **Received:** May 28, 2023 **Analyzed:** May 28, 2023

Monday 01 May 2023

Analyzed by: Erik Gorgas

Batch: 96864

CHAIN OF CUSTODY

EPA/600/R-93/116

Client: Eastern Environmental
Address: 203 Prospect St, Brockton
Project Site & #: 7 Ware lane, Marblehead
Phone / email address:

Contact: Danny Gomes
Relinquish by/date: Richard Alomar
Received by/date: Jonathan Chann 4/28/23
# of Samples Received: 10

Asbestos Identification Lab
165 New Boston St.
Suite 227
Woburn, MA 01801
(781)932-9600
www.asbestosidentificationlab.com

Date Sampled: ________

BATCH# 96864 Rev 06/16

Turnaround Time		Sample Method	
[ ]	Less 3 Hrs	[x]	Bulk
[ ]	Same Day	[ ]	Soil
[✓]	Next Day	[ ]	Wipe
[ ]	Two Day	[ ]	Point Count

Stop on 1st Positive? Yes/No
Notify Method: Mail/E-Mail/Verbal
Analyzed By: [signature]
Date: 4/28/2023

Temp in Celsius = 21

Lab ID# (Lab Use Only)	Field ID/ (Client Reference)	Material / Location	% of Asbestos	Color	Homogeneity	Texture	Friable	Asbestos Minerals	Asbestos %	Morphology	Extinction	Sign of Elongation	Birefringence	Pleochroism	∥	⊥	Fiberglass	Mineral Wool	Cellulose	Hair	Synthetic	Other	Non-Fibrous
	A	Material: WSR Location: Kitchen	0	gy	~ng	fry		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 2				98
	B	Material: WSR Location: 2nd fl Bath	0	gy	~ng	fry		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 2				98
	C	Material: WSR Location: Master Bath	0	gy	~ng	fry		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 2				98

Temp in Celcius = 21

Lab ID# (Lab Use Only)	Field ID/ (Client Reference)	Material / Location	Stereo Scope: % of Asbestos	Color	Homogeneity	Texture	Friable	Asbestos Minerals	Optical Properties: Asbestos %	Morphology	Extinction	Sign of Elongation	Birefringence	Pleochroism	RI: ‖	RI: ⊥	Non-Asbestos Percentage (%): Fiberglass	Mineral Wool	Cellulose	Hair	Synthetic	Other	Non-Fibrous
	D	Material: CSR Location: Kitchen	0	gry	n	[illegible]		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 2				98
	E	Material: CSR Location: 2nd Fl. Bath	0	gry	n	[illegible]		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 2				98
	F	Material: CSR Location: Master Bath	0	gry	n	[illegible]		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 2				98
	G	Material: Sheet Fl Location: 2nd Fl Bath	0	[illegible]	n	[illegible]		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R 10				90
	H	Material: Mastic Location: 2nd Fl Bath						Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite															

N.S

Page 3 of 3

Temp in Celcius = 21

Lab ID# (Lab Use Only)	Field ID/ (Client Reference)	Material / Location	% of Asbestos	Color	Homogeneity	Texture	Friable	Asbestos Minerals	Asbestos %	Morphology	Extinction	Sign of Elongation	Birefringence	Pleochroism	∥	⊥	Fiberglass	Mineral Wool	Cellulose	Hair	Synthetic	Other	Non-Fibrous
	1	Material: Sheet fl Location: Master Bath	0	NC		gry/brn		Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite											R W				aw
	J	Material: Mastic Location: Master Bath						Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite															
		Material: Location:						Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite															
		Material: Location:						Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite															
		Material: Location:						Chrysotile Amosite Crocidolite Tremolite Anthophyllite Actinolite															

N.S