

TECHNICAL DATA SHEET

AC-EAGLE(OH138-32M60)60%

Hydroxy acrylic 4.2% OH (calculated on non-volatiles)

Delivery form: 60% in Mixture of solvents



Specification:

Test	Standard	Unit	Method
Non-volatiles	58-62	%	ISO 3251
Viscosity, 25°C (Gardner-holdt)	Z1-Z3	-	ASTM D1545
Viscosity, 25°C (Brookfield)	Approx. 4500	[mPa.s] or cP	ISO 2555
Acid value	5-10	mg KOH/g	ASTM D1639
Color	50 max	APHA	ISO 6271

Performance:

- High build and gloss in two packs system
- Excellent mechanical properties
- Excellent outdoor durability and gloss retention

Application:

- Clear coats and solid colors for car repair 2K system
- Industrial top coats

Solubility:

• Xylene	Soluble	• Ethers	Soluble
• Esters	Soluble	• Solvesso 100	Soluble
• Alcohols	Soluble	• MEK	Soluble

Storage:

AC-EAGLE(OH138-32M60)60% should be stored indoor in the original, unopened and undamaged containers in a dry place at storage temperatures between 5°C to 30°C. Exposure to sunlight should be avoided

Stability:

Under the above mentioned storage condition the stability of AC-EAGLE(OH138-32M60)60% will be 24 months ex-work

Disclaimer: All recorded specifications, results and data mentioned in this document are based on Eagle Chemicals' instruments, ingredients and conditions. In case of not using Eagle Chemicals' products as a sole binder in your formulations and/or applications, you should do a ladder series of laboratory tests, to confirm the compatibility with other resins or ingredients in your formulation. This data is only recommended as a guideline for testing. This also applies in case we offer an alternative for your current product. If you have new/modified applications and/or solutions, it would be enriching to our R&D team if you share it with us.